

Lawrence Berkeley National Laboratory

Lawrence Berkeley National Laboratory

Title

COMMENTS ON ""EFFICIENCY OF THE SOLID-STATE ENGINE MADE WITH NITINOL MEMORY MATERIAL""

Permalink

<https://escholarship.org/uc/item/1x49249v>

Author

Mohamed, H.A

Publication Date

1978-11-01

ca

RECEIVED
LAWRENCE
BERKELEY LABORATORY


JUN 28 1979

LIBRARY AND
DOCUMENTS SECTION

TWO-WEEK LOAN COPY

This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 6782

Energy and Environment Division



Comments on "Efficiency of the Solid-State Engine Made with Nitinol Memory Material"

H. A. Mohamed and R. M. Banks

November 1978

Lawrence Berkeley Laboratory University of California/Berkeley

Prepared for the U.S. Department of Energy under Contract No. W-7405-ENG-48

LBL-8579ca

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

Comments on "Efficiency of the Solid-State Engine
Made with Nitinol Memory Material"

H. A. Mohamed and R. M. Banks

Energy and Environment Division
Lawrence Berkeley Laboratory
University of California
Berkeley, California 94720

ABSTRACT

A recent calculation of the thermal efficiency of a solid-state engine made with a Ni-Ti alloy (Nitinol) has been criticized with reference to the origin of the work output and the deformation behavior of the material.

In a recent publication, Golestaneh¹ has calculated the thermal conversion efficiency of a solid-state heat engine comprising the shape memory alloy Ni-Ti (Nitinol) as a working medium. The cycle considered by the author consists of deforming the material at a temperature T_0 below the transformation critical temperature T_c and then bringing the deformed material rapidly to a hot reservoir at a temperature $T > T_c$ (the stress-strain temperature path of the cycle has not been given) under constant applied load.

The analysis of the energetics of the cycle as presented, however, is misleading and suffers from serious difficulties that could lead to erroneous conclusions about the efficiency. This analysis and the conclusions reached by the author were based on the assumption that the useful work output can be expressed as:

$$W = \alpha m \Delta H - W_D \quad (1C)^1$$

where W_D is mechanical energy consumed in generating martensites of mass m at temperature T_0 , α is the volume fraction of martensites transformed to the parent phase at temperature T , and ΔH is the latent heat of the transformation.

In principal, this equation is incorrect as the enthalpy does not act as a potential for work in that system and it even contradicts the author's own assumptions, as shown below. Golestaneh¹ assumes that the latent heat of the $P \rightarrow M$ transformation at the temperature T_0 is equal to that of the $M \rightarrow P$ transformation at the higher temperature T . Since equal and opposite amounts of heat will be required to heat and cool the material between the temperatures T_0 and T , energy conservation leads to the conclusion that

$$W = - W_D$$

rather than to the incorrect equation 1C¹. In effect, the

author's cycle and assumptions lead to no net useful work output.

In addition to the above serious difficulty that negates the conclusions reached about the efficiency, the author has introduced physically unfounded parameters implied to be characteristic properties of the material. It was stated on page 1242 that "we define W_D as a fraction α' of the thermal energy $\alpha m \Delta H$ which is released during the shape recovery". There is no obvious justification, except in a purely algebraic sense, for the assumption that W_D can be expressed as a fraction of $\alpha m \Delta H$, therefore α' cannot be assumed constant. It has been observed experimentally² that in an initially partially-transformed Ti-50.3 at. pct. Ni alloy, a strain within the recoverable range is accommodated by reorientation and growth of the most favorably oriented martensite variants with respect to the applied stress. This occurs by stress-induced migration of twin boundaries. Therefore, the mechanical energy W_D is consumed in overcoming the internal frictional forces which oppose motion of twin boundaries. Accordingly, the parameter β defined by the author as $\beta = 1 - \alpha'$ (β was assigned a value of 0.90 - 0.95) is physically unfounded and thus cannot be considered as a characteristic property of the material. The author also did not show how β was estimated. Furthermore, general observations concerning the relative merits of the type of deformation (linear, flexural) cited by the author in reference (2) do not support the quantities assigned to the parameter β and the derivation of this parameter developed in the presented argument.

It should be realized that the feasibility of converting heat into mechanical energy in that system is essentially based on the effect of martensite transformation on the stress-strain-temperature behavior of the material as illustrated in the following: It is well known that there exists a one-to-one correspondence between shape recovery and the $M \rightarrow P$ transformation which occurs upon heating. For the purpose of this

discussion we assume that the shape memory element is fully transformed to martensite (thermally induced martensite) at the temperature of the cold reservoir T_0 . The stress required to induce a given strain within the recoverable range at T_0 where the martensite phase is thermodynamically stable is smaller than that at a higher temperature T within the $M \rightarrow P$ transformation temperature range. This behavior which gives rise to a net work output originates from two factors:

(1) reversability of the deformation modes that accommodate a strain within the recoverable range,² and (2) increasing thermodynamic instability of the martensite phase as the temperature increases. Thus, the recovery stress developed gradually by the material as it recovers its shape originates from the driving force of the $M \rightarrow P$. This force arises from the free energy difference between the two phases. Therefore, it is free energy, namely Helmholtz free energy of the phase change that acts as a potential for work in that system.

Finally, we would like to point out that the data used by Golestaneh to calculate the efficiency are not based on experimental measurements of a particular alloy, but rather seem to have been chosen arbitrarily.

This work has been supported partially by the Division of Fossil Fuel Utilization, Office of Energy Technology and partially by the Solar Heating and Cooling Research & Development Branch, Office of Conservation and Solar Applications, U.S. Department of Energy under contract No.W-7405-ENG-48.

1. A. A. Golestaneh, J. Appl. Phys. 49, 1241 (1978).
2. H. A. Mohamed and J. Washburn, J. Mater. Scien. 12, 469 (1977).

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720