

# Lawrence Berkeley National Laboratory

## LBL Publications

### Title

ZERO FIELD SPLITTINGS OF  $\text{Am}^{2+}$  AND  $\text{Cm}^{3+}$  IN CUBIC SYMMETRY SITES IN  $\text{CaF}_2$

### Permalink

<https://escholarship.org/uc/item/0nt1g5h2>

### Authors

Edelstein, N.  
Easley, W.

### Publication Date

1967-09-01

*C.2*

# University of California

## Ernest O. Lawrence Radiation Laboratory

ZERO FIELD SPLITTINGS OF  $\text{Am}^{2+}$  AND  $\text{Cm}^{3+}$   
IN CUBIC SYMMETRY SITES IN  $\text{CaF}_2$

N. Edelstein and W. Easley

September 1967

RECEIVED  
LAWRENCE  
RADIATION  
LIBRARY  
DOCUMENTS

**TWO-WEEK LOAN COPY**

This is a Library Circulating Copy  
which may be borrowed for two weeks.  
For a personal retention copy, call  
Tech. Info. Division, Ext. 5545

*Cy. 2*  
UCRL-17855

## **DISCLAIMER**

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

to be submitted to J. Chem. Phys.

UCRL-17855

Preprint

UNIVERSITY OF CALIFORNIA

Lawrence Radiation Laboratory  
Berkeley, California

AEC Contract No. W-7405-eng-48

ZERO FIELD SPLITTINGS OF  $\text{Am}^{2+}$  AND  $\text{Cm}^{3+}$  IN CUBIC SYMMETRY SITES IN  $\text{CaF}_2$

N. Edelstein and W. Easley

September 1967

ZERO FIELD SPLITTINGS OF  $\text{Am}^{2+}$  AND  $\text{Cm}^{3+}$  IN CUBIC SYMMETRY SITES IN  $\text{CaF}_2^*$

N. Edelstein and W. Easley

Lawrence Radiation Laboratory  
University of California  
Berkeley, California

September 1967

ABSTRACT

The g value anisotropies of the ground crystal field states of the nominally  $8S_{7/2}$  ions,  $\text{Am}^{2+}$  and  $\text{Cm}^{3+}$ , have been measured in cubic symmetry in  $\text{CaF}_2$  at 35 Gc and magnetic fields of approximately 5500 gauss by epr spectroscopy. From the magnitude of these anisotropies the  $\Gamma_6 - \Gamma_8$  zero field splittings of  $13.4 \pm 0.5 \text{ cm}^{-1}$  and  $18.6 \pm 0.5 \text{ cm}^{-1}$  have been deduced for  $\text{Cm}^{3+}$  and  $\text{Am}^{2+}$  respectively. These splittings are about 250 times greater than for the corresponding lanthanides,  $\text{Gd}^{3+}$  and  $\text{Eu}^{2+}$ . It is shown that the large intermediate coupling effects in the actinide ions can account qualitatively for these differences.

## I. INTRODUCTION

The lanthanide series has been extensively investigated in crystals of the fluorite type by electron paramagnetic resonance (epr) and optical spectroscopy. The trivalent ions in these crystals may be found in various symmetry sites depending upon the conditions under which the crystals were grown.<sup>1</sup> The divalent ions are found in sites of cubic symmetry. Two of the most studied lanthanide ions are  $Gd^{3+}$  and  $Eu^{2+}$ , the half-filled shell ( $4f^7$ ,  $^8S_{7/2}$ ) configuration. For these ions in cubic symmetry the crystal field splittings are readily measured although the mechanisms causing these splittings are not well understood.<sup>2</sup>

We have previously reported the spin Hamiltonian parameters for  $Am^{2+}$  and  $Cm^{3+}$ , the  $5f^7$  actinide analogs for  $Eu^{2+}$  and  $Gd^{3+}$ .<sup>3</sup> The earlier epr measurements were done at 9.2 Gc and temperatures of  $4^\circ$  K and  $1^\circ$  K, and were obtained for these actinide ions doped in  $CaF_2$  in sites of cubic symmetry. For  $Cm^{3+}$ , spin Hamiltonian parameters for two different trigonal sites were also measured.<sup>4</sup> No resonance lines due to actinide ions were seen at  $77^\circ$  K. In this paper we report epr measurements made at 35 Gc on  $Am^{2+}$  and  $Cm^{3+}$  in cubic crystal field sites in the  $CaF_2$  lattice. The larger magnetic field mixes into the ground crystal field state ( $\Gamma_6$ ) the next highest crystal field state ( $\Gamma_8$ ) which causes the measured g values to be anisotropic. From the anisotropy of the g value we have determined the zero field splitting in these two ions. We also show that the simple point charge model qualitatively explains the magnitude of the effects.

## II. EXPERIMENTAL

Single crystals of actinide doped  $\text{CaF}_2$  were grown as oriented cylinders by the Bridgman-Stockbarger technique. Optical quality pure  $\text{CaF}_2$  was used for all experiments.<sup>5</sup> A 4 mm cylinder of single-crystal  $\text{CaF}_2$  in a known orientation (for example, the cylinder axis parallel to the 110 direction) was placed in the bottom of a carbon crucible. Powdered  $\text{CaF}_2$  to which had been added 2 wt percent  $\text{PbF}_2$ , was placed on top of the crystal and an acid solution of the actinide ion in minimum volume (10-50  $\lambda$ ) was pipeted onto the powder. The crucible was then placed in an evacuated tube furnace and raised into the hot zone such that the powder and the top part of the oriented cylinder melted. After soaking for about an hour or so, the crucible was slowly lowered from this hot region down to a region near room temperature. A disk of the oriented cylinder containing the actinide ions was cleaved from the main crystal and placed in a thin-walled teflon cylinder which was plugged with polystyrene foam. The teflon cylinder was glued with stopcock grease to the bottom of a  $\text{TE}_{01n}$  cylindrical cavity such that the cylinder axis of the crystal was parallel to the axis of rotation of the D.C. magnetic field. It is estimated that the orientation of the crystal is known to about  $\pm 2^\circ$ . In this way, the magnetic field could be rotated in a particular plane of  $\text{CaF}_2$ .

For the experiments described in this paper we used approximately equimolar amounts of  $\text{Am}^{243}$  (nuclear spin  $I = 5/2$ ) and  $\text{Cm}^{244}$  ( $I = 0$ ) in one crystal. When the crystals were initially grown or annealed, the actinide ions were in the trivalent state. However, due to the high level of radioactivity caused mainly by the alpha emission from the  $\text{Cm}^{244}$  nucleus ( $t_{1/2} = 18.1$  yr) part of the  $\text{Am}^{3+}$  was reduced to the divalent state and part of the  $\text{Cm}^{3+}$

was oxidized to  $\text{Cm}^{4+}$ . At the time the measurements were done, the ratio of  $\text{Am}^{2+}$  to  $\text{Cm}^{3+}$  in cubic sites was approximately 10:1.

The epr measurements were made at 1° K with a conventional superheterodyne spectrometer operating at approximately 34.5 Gc. The magnetic field was produced by a 12-inch rotating magnet and measured with an nmr gaussmeter whose frequency was monitored by a frequency counter. A small piece of  $\text{Tm}^{2+}$  in  $\text{CaF}_2$  was placed in the cavity and the isotropic resonance from the  $\Gamma_7$  state was used as an internal reference.<sup>6</sup> The frequency of the signal klystron was measured with a high-Q wavemeter.

### III. PRELIMINARY DISCUSSION AND RESULTS

A free ion placed in a crystalline electric field undergoes a splitting of its total angular momentum  $J$  which is dependent upon the symmetry of the electrostatic field. We are interested in the case of a  $J = 7/2$  state placed in a cubic symmetry site in the  $\text{CaF}_2$  lattice. From group theoretical arguments, the  $J = 7/2$  state in zero magnetic field will split into two doubly degenerate states,  $\Gamma_6$  and  $\Gamma_7$ , and one quartet state,  $\Gamma_8$ . The Hamiltonian for this problem including the Zeeman effect caused by an external magnetic field may be written

$$H = g_J \beta \vec{H} \cdot \vec{J} + B_4 (O_4^0 + 5 O_4^4) + B_6 (O_6^0 - 21 O_6^4) \quad (1)$$

The first term represents the Zeeman interaction where  $g_J$  is the Landé  $g$  value for the lowest free ion level,  $\beta$  is the Bohr magneton, and  $\vec{H}$  is the



external magnetic field. The last two terms represent the effect of the cubic crystalline field on the  $J = 7/2$  manifold, where we consider  $B_4$  and  $B_6$  as adjustable parameters related to the strength of the crystalline field. The  $O_n^m$  terms are angular momentum operators of the appropriate symmetry.<sup>7</sup>

For the zero magnetic field case we find an exact solution for this Hamiltonian applied to the  $J = 7/2$  manifold, the energies of the levels being given in terms of  $b_4 = 60B_4$  and  $b_6 = 1260B_6$ . The energy level diagram is shown in Fig. 1. If we choose the energy of the  $\Gamma_6$  state to equal zero, the second column in Fig. 1 shows the relative energies. If the crystal field splitting is much greater than the Zeeman interaction, then the zero field wavefunctions will be an accurate representation and can be used to calculate  $g$  values of the crystal field energy levels.<sup>7</sup> For the cases under consideration here we have neglected  $J$  mixing by the crystal field because the next free ion level is on the order of  $17,000 \text{ cm}^{-1}$  higher in energy.<sup>8</sup> We have used the zero field wavefunctions to calculate  $g$  values and interpret our epr results at X band, 9.2 Gc and approximately 1500 gauss, and have shown that the  $\Gamma_6$  state has the lowest energy for  $\text{Am}^{2+}$  and  $\text{Cm}^{3+}$  in cubic symmetry and is isotropic to within our experimental error.<sup>3</sup> Our earlier results are given in Table I.

At higher magnetic fields the Zeeman term will become important and will cause an anisotropy in the epr spectrum of the  $\Gamma_6$  state since this interaction will mix the  $\Gamma_8$  with the  $\Gamma_6$  state. From the magnitude of the anisotropy we can determine the splitting of the  $\Gamma_6 - \Gamma_8$  levels. The experimental data are shown as circles in Fig. 2. We have plotted the  $g$  value of the  $\Gamma_6$  state for both  $\text{Cm}^{3+}$  and  $\text{Am}^{2+}$  as a function of the angle of the magnetic field with respect to the unit cell axis of the  $\text{CaF}_2$  lattice. The magnetic field was

rotated in the [110] plane of  $\text{CaF}_2$ . The hyperfine coupling constant of  $\text{Am}^{243}$  was isotropic to within our experimental error of  $\sim 1\%$  on this particular measurement. In order to determine the values of the parameters  $b_4$ ,  $b_6$ , and  $g_J$  which would reproduce the experimental data, the Hamiltonian (Eq. 1) was applied to the  $J = 7/2$  manifold which resulted in an  $8 \times 8$  matrix with elements in terms of the above parameters, the magnetic field  $H$ , and the direction cosines of  $H$  relative to the cubic axes of  $\text{CaF}_2$ . A computer program was written which diagonalized the  $8 \times 8$  matrix and calculated the  $g$  value for the ground Kramers doublet state. The values of  $b_4$ ,  $b_6$ , and  $g_J$  were varied until the best fit to the experimental data was found.<sup>9</sup> The calculated fits for  $\text{Am}^{2+}$  and  $\text{Cm}^{3+}$  are shown in Fig. 2 along with the values for the parameters. The solid line is the calculated  $g$  value for  $\text{Am}^{2+}$ , the dotted line is for  $\text{Cm}^{3+}$ .

Unique values of  $b_4$  and  $b_6$  could not be determined from this analysis as the anisotropy depended only on the  $\Gamma_6 - \Gamma_8$  splitting. Therefore, there are any number of values of  $b_4$  and  $b_6$  which can give the same splitting. The  $\Gamma_7$  level is so relatively high in energy that our data are not sensitive to its position. We have determined the magnitude of the  $\Gamma_6 - \Gamma_8$  splitting as  $13.4 \pm 0.5 \text{ cm}^{-1}$  for  $\text{Cm}^{3+}:\text{CaF}_2$  and  $18.6 \pm 0.5 \text{ cm}^{-1}$  for  $\text{Am}^{2+}:\text{CaF}_2$ . The  $g_J$  values were found to be  $1.9261 \pm 0.001$  and  $1.9258 \pm 0.001$  for  $\text{Cm}^{3+}$  and  $\text{Am}^{2+}$ , respectively. The absolute values of  $g_J$  are measured to the accuracy shown; however, the relative measurement of the two  $g_J$  values is about one order of magnitude better.

In the lanthanide series a recent survey has shown that for trivalent rare earth ions in cubic sites in the  $\text{CaF}_2$  lattice, the fourth order term  $b_4$  is about an order of magnitude larger than the sixth order term  $b_6$ .<sup>1</sup> This

ratio is also true for  $\text{Eu}^{2+}$  in the  $\text{CaF}_2$  lattice. We have made this assumption,  $b_6 < b_4$ , for  $\text{Cm}^{3+}$  and  $\text{Am}^{2+}$  and show in Fig. 3 the energy level diagrams for the crystal field levels with the values of  $b_6 = 0$ , and  $-.1 \text{ cm}^{-1}$ . For the purpose of comparison, we show the energy diagram of  $\text{Gd}^{3+}$  and  $\text{Eu}^{2+}$  doped in  $\text{CaF}_2$  in Fig. 4. It is instructive to see how the Zeeman interaction mixes the crystal field levels for  $\text{Cm}^{3+}$ . Fig. 5 shows the energies of the crystal field levels as a function of magnetic field applied in the [100] direction.

#### IV. DISCUSSION

Our experimental results show that the crystal field splittings of the nominally  $^8\text{S}_{7/2}$  actinide ions are approximately 250 times larger than the corresponding lanthanides. Clearly such a large effect must arise from the differences of the electronic structures of the two sets of ions. Such differences are quite significant and arise because of the intermediate coupling effects induced by the relatively large spin orbit coupling energies of the actinide ions. The spin orbit interaction matrix elements are diagonal in J but are not diagonal in L and S, so states of the same J but different L and S will be mixed.<sup>10</sup> For example, the leading terms of the ground state wavefunction of  $\text{Gd}^{3+}$  have been given by Wybourne as<sup>11</sup>

$$\psi(\text{Gd}^{3+}, J=7/2) = 0.987|^8\text{S}\rangle + 0.162|^6\text{P}\rangle - 0.012|^6\text{D}\rangle + \dots \quad (2)$$

which shows that for  $\text{Gd}^{3+}$  the ground state is approximately 98% pure  $^8\text{S}_{7/2}$ . Recent work on the optical spectra of  $\text{Cm}^{3+}$  has shown that the leading terms

for the  $\text{Cm}^{3+}$  ground state wavefunction are<sup>8</sup>

$$\psi(\text{Cm}^{3+}, J=7/2) = 0.891|{}^8S\rangle + 0.414|{}^6P\rangle - 0.090|{}^6D\rangle + \dots \quad (3)$$

so that it is only 79% pure  ${}^8S_{7/2}$ . However, the fourth order crystal field operator will not split any of the three terms listed above nor will there be any non-zero matrix elements between any combination of them. Therefore, the contribution to the zero field splitting from the intermediate coupled wavefunction will come from a large number of small terms. We will now calculate the zero field splitting caused by these terms using the electrostatic point charge model.

The theoretical expression for  $B_4$  in the approximation of the electrostatic model may be written<sup>12</sup>

$$B_4 = A_4^0 \langle r^4 \rangle (1 - \sigma_4) \langle \psi_J || \beta || \psi_J' \rangle \quad (3)$$

where  $A_4^0$  represents the sum of all the charges in the lattice at a particular point,  $\langle r^4 \rangle$  is the expectation value for the magnetic electrons,  $\langle \psi_J || \beta || \psi_J' \rangle$  is the fourth degree operator equivalent factor. The expression  $(1 - \sigma_4)$  takes into account shielding effects, where  $\sigma_4$  is the fourth degree shielding parameter. Since we have a good wave function for  $\text{Cm}^{3+}$ , we will carry out the above calculation for the ions  $\text{Cm}^{3+}$  and  $\text{Gd}^{3+}$ . We will assume  $\sigma_4 = 0$  (no shielding effects).

Bleaney<sup>12</sup> has performed the lattice summation for the  $\text{CaF}_2$  lattice considering the first four shells of ions surrounding the trivalent ion. He has

also estimated the polarization effects of a trivalent ion occupying a  $\text{Ca}^{2+}$  position. He gives the formula for trivalent ions (in  $\text{cm}^{-1}$ ).

$$B_4 = -659 \langle r^4 \rangle \langle \psi_J \| \beta_J \| \psi_J \rangle \quad (4)$$

where  $r$  is expressed in Ångströms. Dr. M. Wilson<sup>13</sup> from Argonne National Laboratory has performed a Hartree-Fock calculation and provided us with the value  $\langle r^4 \rangle = 3.69$  a.u. for the trivalent Cm ion. The matrix element remaining  $\langle \psi_J \| \beta_J \| \psi_J \rangle$  may be written as the summation of terms of the type<sup>10,14</sup>

$$16 \left[ \frac{14(2J-4)!}{11(2J+5)!} \right]^{1/2} (-1)^{S+L'+J+k} (2J+1) \begin{Bmatrix} J & JK \\ L' & LS \end{Bmatrix} \langle f^n \alpha SL \| U^{(k)} \| f^n \alpha' SL' \rangle \quad (5)$$

where  $k = 4$ . The values of the reduced matrix elements for  $k = 2, 3, 4, 5$ , and 6 have been tabulated for all  $f^n$  configurations by Nielson and Koster.<sup>15</sup> A computer program has been written<sup>9</sup> which will calculate operator equivalent factors for intermediate coupled wavefunctions. The values of the operator equivalent factors,  $\alpha, \beta, \gamma$  for the 50-term  $\text{Cm}^{3+}$  wavefunction are given in Table II. A similar calculation for  $\text{Cm}^{3+}$  but with a wavefunction which was derived from extrapolated parameters has been performed by Dr. S. Feneuille.<sup>16</sup> We have checked the relevant parts of his calculation with ours. We also list in Table II the operator equivalent factors for  $\text{Gd}^{3+}$  calculated from an intermediate coupled wavefunction which was obtained from electrostatic and spin orbit coupling parameters which best reproduced the spectra and intensities of this ion in solution.<sup>17</sup>

We now calculate

$$b_4 (\text{Cm}^{3+}) = 60B_4 (\text{Cm}^{3+}) = -0.24 \text{ cm}^{-1} \quad (6)$$

and similarly

$$b_4 (\text{Gd}^{3+}) = 60B_4 (\text{Gd}^{3+}) = -4.7 \times 10^{-4} \text{ cm}^{-1} \quad (7)$$

where we have used for  $\text{Gd}^{3+}$ ,  $\langle r^4 \rangle = 1.52$  a.u. obtained from the work of Freeman and Watson.<sup>18</sup> These numbers can be compared to the experimental values

$$b_4 (\text{Cm}^{3+})_{\text{exp}} \approx -1.12 \text{ cm}^{-1} \quad (8a)$$

$$b_4 (\text{Gd}^{3+})_{\text{exp}} = -46 \times 10^{-4} \text{ cm}^{-1} \quad (8b)$$

We may also take the ratio of the calculated parameters and compare them with the ratio of the experimental parameters. We find

$$\frac{b_4 (\text{Cm}^{3+})_{\text{exp}}}{b_4 (\text{Gd}^{3+})_{\text{exp}}} = 243 \quad (9)$$

and

$$\frac{b_4 (\text{Cm}^{3+})_{\text{calc}}}{b_4 (\text{Gd}^{3+})_{\text{calc}}} = \frac{\langle r^4 \rangle_{\text{Cm}^{3+}} \langle \psi_J \| \beta_J \| \psi_J \rangle_{\text{Cm}^{3+}}}{\langle r^4 \rangle_{\text{Gd}^{3+}} \langle \psi_J \| \beta_J \| \psi_J \rangle_{\text{Gd}^{3+}}} = 511 \quad (10)$$

The signs of the calculated  $b_4$  parameters agree with experiment but the magnitudes are off. However it has been shown that the lattice summation term ( $A_4^0$ ) in the simple point charge model is not a good approximation and one must consider the extended nature of the induced moments.<sup>19</sup> For this reason the comparison of the ratio of the calculated  $b_4$  terms to the ratio of the experimental  $b_4$  terms is a more valid criterion. We find that these ratios differ by approximately a factor of two. Considering the uncertainties in the parameters used, this agreement shows the intermediate coupling mechanism accounts qualitatively in a very satisfactory manner for the difference in the crystal field splittings between the half-filled shell configurations of the lanthanide and actinide ions.

For the case of  $Gd^{3+}$  in  $La(C_2H_5SO_4)_3 \cdot 9H_2O$ , Wybourne<sup>11</sup> has pointed out that the intermediate coupling mechanism gives rise to a contribution of the wrong sign to the value of  $b_2^0$  (relative to the experimental value) because the Stark levels of the  $^6P_{7/2}$  state are ordered oppositely to those of the  $^8S_{7/2}$  ground state. Apparently the sign of  $b_2^0$  is determined by another mechanism. Kim and Moos<sup>20</sup> have recently measured  $b_2^0$  for  $Eu^{2+}$  in  $LaCl_3$  and have found that it is approximately fifty times larger than that for  $Gd^{3+}$  in  $LaCl_3$ . They have attributed this ratio to the difference in electronic properties of  $Eu^{2+}$  and  $Gd^{3+}$ ; specifically to the lowering in energy of the excited configurations in  $Eu^{2+}$ . They show that their results are in accord with the assumption that configuration interaction and intermediate coupling are the dominant mechanisms for the observed splittings but suggest that the relative importance of these two mechanisms are different for the ground and excited states. Accordingly, they suggest that Wybourne did not completely

account for the effects of configuration interaction. It has been shown that configuration interaction effects for rare earth ions are, for the most part, linear and can be accounted for in terms of a shielding factor which for  $b_2^0$  is written as  $\sigma_2$ .<sup>21</sup> It has also been shown that  $\sigma_2 > \sigma_4 > \sigma_6$ .<sup>22,23</sup> The result of our calculation for the value of  $b_4$  ( $Gd^{3+}$  in  $CaF_2$ ) is qualitatively consistent with the arguments of Kim and Moos,<sup>20</sup> in that we would expect the configuration interaction mechanism to be less important for  $b_4$ , and, therefore, the intermediate coupling mechanism might dominate. We have shown that the intermediate coupling mechanism gives at least the correct sign. This qualitative argument is supported by the fact that  $b_4(Gd^{3+}) \approx b_4(Eu^{2+})$  for cubic sites in  $CaF_2$ .

The  $g_J$  values mentioned earlier are in quite good agreement with the earlier values of  $g_J$  for  $Cm^{3+}$  measured by Abraham, Judd, and Wickman<sup>24</sup> and by Conway et al.<sup>8</sup> However, it is rather surprising that the relative values of  $g_J$  found for  $Am^{2+}$  and  $Cm^{3+}$  are to within experimental error ( $\pm 0.0002$ ) the same. From the arguments of Judd et al.<sup>24</sup> we would expect the  $g_J$  value of  $Cm^{3+}$  to be less than that of  $Am^{2+}$ . The reason for this is that the spin orbit coupling constant for trivalent Cm is larger than for divalent Am and so intermediate coupling effects should be more important for  $Cm^{3+}$ . We list for comparison in Table III the  $g_J$  values for Am I<sup>25</sup> (spectroscopic notation) and Am III and a number of lanthanide atom-divalent ions, the electronic configurations differing only by a filled s shell. The  $g_J$  values for the ions were calculated from epr data using zero field crystal field wavefunctions.<sup>7,12,28</sup> We see the difference between  $g_J$  for Am I - Am III ( $5f^7 7s^2 - 5f^7$ ) is as large as the largest lanthanide atom-ion shift,



Ho I - Ho III ( $4f^{11} 6s^2 - 4f^{11}$ ). These shifts and also the Cm IV, Am III shift might be ascribed to covalent bonding, but an orbit-lattice interaction of the type described by Inoue<sup>29</sup> and Birgeneau<sup>30</sup> produces the same sort of experimental results. It is interesting to note that Am III which is approximately 80% pure  $^8S$  has a  $g_J$  shift relative to the atom that is as large as that found in Ho III,  $4f^{11}$ .

#### V. CONCLUSION

In this paper we have described measurements which give the zero field field splittings of the  $5f^7$  ions,  $Am^{2+}$  and  $Cm^{3+}$ , in cubic symmetry in  $CaF_2$ . The parameters deduced from these experiments have been calculated using the point charge approximation. It has been shown that intermediate coupling, that is the mixing of states of the same J into the ground state by spin orbit coupling, can account qualitatively for the large difference in zero field splittings between the lanthanide and actinide ions of nominally  $^8S$  character.

#### ACKNOWLEDGMENTS

We wish to thank Drs. K. Rajnak, J. Conway, R. McLaughlin, and Professors B. B. Cunningham, B. R. Judd, and D. A. Shirley for many helpful discussions.

REFERENCES AND NOTES

- \* This work was done under the auspices of the U. S. Atomic Energy Commission.
1. M. J. Weber and R. W. Bierig, Phys. Rev. 134, A1492 (1964), and references contained therein.
  2. M. M. Abraham, L. A. Boatner, C. B. Finch, E. J. Lee, and R. A. Weeks, J. Phys. Chem. Solids 28, 81 (1967), and references contained therein.
  3. N. Edelstein, W. Easley, and R. McLaughlin, J. Chem. Phys. 44, 3130 (1966).
  4. N. Edelstein, W. Easley, and R. McLaughlin, "Symposium on Lanthanide and Actinide Elements," Advances in Chemistry Series, American Chemical Society, Washington, in press .
  5. The powdered  $\text{CaF}_2$  and the seed crystals used in these experiments were obtained from Optovac, Inc., North Brookfield, Massachusetts.
  6. W. Hayes and J. W. Twidell, J. Chem. Phys. 35, 152 (1961).
  7. K. R. Lea, M. J. M. Leask, and W. P. Wolf, J. Phys. Chem. Solids 23, 1381 (1962).
  8. J. B. Gruber, W. R. Cochran, J. G. Conway, and A. J. Nicol, J. Chem. Phys. 45, 1423 (1966).
  9. We are indebted to Miss Ruth Hinkins of the Lawrence Radiation Laboratory Mathematics and Computing Group for writing this program.
  10. B. G. Wybourne, "Spectroscopic Properties of Rare Earths," Interscience Publishers, New York, 1965.
  11. B. G. Wybourne, Phys. Rev. 148, 317 (1966).
  12. B. Eleaney, Proc. Roy. Soc. (London) A277, 289 (1964).

13. We wish to thank Dr. M. Wilson for providing us with the results of his calculations.
14. J. P. Elliott, B. R. Judd, and W. A. Runciman, Proc. Roy. Soc. (London) A240, 509 (1957).
15. C. W. Nielson and G. F. Koster, "Spectroscopic Coefficients for the  $p^n$ ,  $d^n$ , and  $f^n$  Configurations," Massachusetts Institute of Technology Press, Cambridge, Massachusetts, 1963.
16. Dr. S. Feneuille, CNRS, Bellevue, France. We wish to thank Dr. Feneuille for providing us with the details of his calculations.
17. K. Rajnak and W. Carnall, private communication.
18. A. Freeman and R. E. Watson, Phys. Rev. 127, 2058 (1962).
19. G. Burns, J. Chem. Phys. 42, 377 (1965).
20. B. F. Kim and H. W. Moos, Phys. Rev. 161, 869 (1967).
21. K. Rajnak and B. G. Wybourne, J. Chem. Phys. 41, 565 (1964).
22. A. Freeman and R. Watson, Phys. Rev. 139, A1606 (1965).
23. C. J. Lenander and E. Y. Wong, J. Chem. Phys. 38, 2750 (1963).
24. M. Abraham, B. R. Judd, and H. H. Wickman, Phys. Rev. 130, 611 (1963).
25. L. Armstrong, Jr. and R. Marrus, Phys. Rev. 144, 994 (1966).
26. B. R. Judd and I. Lindgren, Phys. Rev. 122, 1802 (1961).
27. J. M. Baker and F. I. B. Williams, Proc. Roy. Soc. (London) A267, 283 (1962).
28. E. S. Sabisky, Phys. Rev. 141, 352 (1966).
29. M. Inoue, Phys. Rev. Letters 11, 196 (1963).
30. R. J. Birgeneau, Phys. Rev. Letters 19, 160 (1967).

Table I. Spin Hamiltonian Parameters for  $\text{Am}^{2+}$  and  $\text{Cm}^{3+}$  in Cubic Sites in  $\text{CaF}_2$ .  $I$  is the nuclear spin and  $A$  is the hyperfine coupling constant.

<u>Ion</u>	<u>g</u>	<u>I</u>	<u> A  (cm<sup>-1</sup>)</u>
$^{244}\text{Cm}^{3+}$	4.492 ± .002	0	
$^{241}\text{Am}^{2+}$	4.490 ± .002	5/2	.01837 ± .00002
$^{243}\text{Am}^{2+}$	4.490 ± .002	5/2	.01821 ± .00002

Table II. Calculated Operator Equivalent Factors for  $\text{Cm}^{3+}$  and  $\text{Gd}^{3+}$ .

<u>Ion</u>	<u><math>\langle \psi_J    \alpha_J    \psi_J' \rangle</math></u>	<u><math>\langle \psi_J    \beta_J    \psi_J' \rangle</math></u>	<u><math>\langle \psi_J    \gamma_J    \psi_J' \rangle</math></u>
$\text{Cm}^{3+}$	$-3.397 \times 10^{-3}$	$2.109 \times 10^{-5}$	$-8.933 \times 10^{-7}$
$\text{Gd}^{3+}$	$-5.460 \times 10^{-5}$	$9.885 \times 10^{-8}$	$-6.010 \times 10^{-10}$

Table III. The  $g_J$  Values for Am I - Am III and Various Lanthanide Atoms-Ions. The numbers in parentheses are the errors in the last significant figures.

	$g_J$	$\Delta g_J(I - III)$	Configuration	Term	Reference
Am I	1.937884(67)		$5f^7 7s^2$	$8S_{7/2}$	25
		.012			
Am III	1.926(1)		$5f^7$	$8S_{7/2}$	This Work
Eu I	1.99337(7)		$4f^7 6s^2$	$8S_{7/2}$	26
		.0008			
Eu III	1.9926(3)		$4f^7$	$8S_{7/2}$	27
Ho I	1.19516(10)		$4f^7 6s^2$	$4I_{15/2}$	26
		.013			
Ho III	1.182(1)		$4f^7$	$4I_{15/2}$	28
Tm I	1.14122(15)		$4f^{13} 6s^2$	$2F_{7/2}$	26
		.007			
Tm III	1.134(1)		$4f^{13}$	$2F_{7/2}$	12

FIGURE CAPTIONS

- Fig. 1. The zero field splittings of a  $J = 7/2$  manifold in cubic symmetry.
- Fig. 2. The measured  $g$  value as a function of the rotation of the D.C. magnetic field in the  $110$  plane of  $\text{CaF}_2$ . The angle  $0^\circ$  corresponds to the  $100$  direction.
- Fig. 3. The zero field splittings for the ions  $\text{Cm}^{3+}$  and  $\text{Am}^{2+}$  for the values of the fourth and sixth degree parameters shown.
- Fig. 4. The zero field splittings for the lanthanide ions  $\text{Gd}^{3+}$  and  $\text{Eu}^{2+}$  in cubic symmetry. The data are taken from Table 2 in Reference 2.
- Fig. 5. Calculated energy level diagram for the ground  $J = 7/2$  state of  $\text{Cm}^{3+}$  in cubic symmetry as a function of magnetic field. The direction of the magnetic field is along a cube axis ( $100$ ).

$$\begin{array}{l} \Gamma_7 \text{ ————— } -18b_4 - 12b_6, \quad -32b_4 + 8b_6 \\ \Gamma_8 \text{ ————— } 2b_4 + 16b_6, \quad -12b_4 + 36b_6 \\ \Gamma_6 \text{ ————— } 14b_4 - 20b_6, \quad 0 \end{array}$$

$$b_4 = 60B_4; \quad b_6 = 1260B_6$$

Fig. 1

XBL674-2665-A




Fig. 2

XBL674-2667



$\text{Cm}^{3+}$  in  $\text{CaF}_2$

$$b_4 = -1.433 \text{ cm}^{-1}$$

$$b_6 = -0.1 \text{ cm}^{-1}$$

$$g_J = 1.9261$$

$$\text{————— } \text{cm}^{-1} \\ \text{————— } (45.1)$$

$$\text{————— } 13.4 \pm 0.5 \\ \text{————— } 0$$

$$b_4 = -1.115 \text{ cm}^{-1}$$

$$b_6 = 0$$

$$g_J = 1.9261$$

$$\text{————— } (35.7)$$

$$\text{————— } 13.4 \pm 0.5 \\ \text{————— } 0$$

$\text{Am}^{2+}$  in  $\text{CaF}_2$

$$b_4 = -1.849 \text{ cm}^{-1}$$

$$b_6 = -0.1 \text{ cm}^{-1}$$

$$g_J = 1.9258$$

$$\text{————— } \text{cm}^{-1} \\ \text{————— } (58.4)$$

$$\text{————— } 18.6 \pm 0.5 \\ \text{————— } 0$$

$$b_4 = -1.549 \text{ cm}^{-1}$$

$$b_6 = 0$$

$$g_J = 1.9258$$

$$\text{————— } (49.6)$$

$$\text{————— } 18.6 \pm 0.5 \\ \text{————— } 0$$

Fig. 3

XBL674-2664-A

Gd<sup>3+</sup> in CaF<sub>2</sub>

$$b_4 = -46.3 \times 10^{-4} \text{ cm}^{-1}$$

$$b_6 = +1.0 \times 10^{-4} \text{ cm}^{-1}$$

$$\Gamma_7 \text{ ————— } 0.149 \text{ cm}^{-1}$$

$$\Gamma_8 \text{ ————— } 0.059$$

$$\Gamma_6 \text{ ————— } 0$$

Eu<sup>2+</sup> in CaF<sub>2</sub>

$$b_4 = -57.9 \times 10^{-4} \text{ cm}^{-1}$$

$$b_6 = +0.50 \times 10^{-4} \text{ cm}^{-1}$$

$$\Gamma_7 \text{ ————— } 0.186 \text{ cm}^{-1}$$

$$\Gamma_8 \text{ ————— } 0.071$$

$$\Gamma_6 \text{ ————— } 0$$

Fig. 4

XBL 678-4807




Fig. 5

XBL674-2666

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

