

Lawrence Berkeley National Laboratory

LBL Publications

Title

RADIOTRACER AND THERMAL DESORPTION STUDIES OF DEHYDROGENATION AND ATMOSPHERIC HYDROGENATION OF ORGANIC FRAGMENTS OBTAINED FROM ^{14}C -ETHYLENE CHEMISORBED OVER Pt(111) SURFACES

Permalink

<https://escholarship.org/uc/item/19s991ns>

Author

Davis, S.M.

Publication Date

1984-06-01



Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

BERKELEY LABORATORY

AUG 20 1984

Materials & Molecular Research Division

LIBRARY AND
DOCUMENTS SECTION

Submitted to the Journal of Catalysis


RADIOTRACER AND THERMAL DESORPTION STUDIES OF
DEHYDROGENATION AND ATMOSPHERIC HYDROGENATION OF
ORGANIC FRAGMENTS OBTAINED FROM ^{14}C -ETHYLENE
CHEMISORBED OVER Pt(111) SURFACES

S.M. Davis, F. Zaera, B.E. Gordon,
and G.A. Somorjai

June 1984

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.*



LBL-17902
c2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

LBL-17902

RADIOTRACER AND THERMAL DESORPTION STUDIES OF DEHYDROGENATION AND
ATMOSPHERIC HYDROGENATION OF ORGANIC FRAGMENTS OBTAINED FROM
¹⁴C-ETHYLENE CHEMISORBED OVER Pt(111) SURFACES

S.M. Davis,* F. Zaera, B.E. Gordon, and G.A. Somorjai

Materials and Molecular Research and Chemical Biodynamics Divisions,
Lawrence Berkeley Laboratory, and Department of Chemistry
University of California, Berkeley
Berkeley, California 94720

* Present Address: Exxon Research and Development Laboratory, P.O. Box 2226
Baton Rouge, LA 70821.

RADIOTRACER AND THERMAL DESORPTION STUDIES OF DEHYDROGENATION AND
ATMOSPHERIC HYDROGENATION OF ORGANIC FRAGMENTS OBTAINED FROM
¹⁴C-ETHYLENE CHEMISORBED OVER Pt(111) SURFACES

S.M. Davis, F. Zaera, B.E. Gordon, and G.A. Somorjai

Materials and Molecular Research and Chemical Biodynamics Divisions,
Lawrence Berkeley Laboratory, and Department of Chemistry
University of California, Berkeley
Berkeley, California 94720

ABSTRACT

The energetics and reversibility of ethylene sequential dehydrogenation on the (111) platinum single crystal surface has been investigated at 300 - 600K using thermal desorption spectroscopy and a carbon-¹⁴ radiotracer technique. Ethylidyne species produced by ¹⁴C-C₂H₄ chemisorption at 300 - 400K were stable with respect to hydrogenation at room temperature. However, at atmospheric hydrogen pressure and temperatures above 350K, ethylidyne species were easily eliminated from the platinum surface by hydrogenation. For ¹⁴C-C₂H₄ adsorption temperatures above 450K, radiotracer studies revealed the presence of both "active" and "inactive" forms of partially dehydrogenated carbonaceous deposits on the platinum surface which differ greatly in their reactivity for hydrogenation and hydrogen transfer with unlabelled hydrocarbons. The inactive fraction increased with increasing adsorption temperature as the surface species became more hydrogen deficient. Removal of the active ¹⁴C-containing species by hydrogen transfer occurred readily.

Introduction

The formation of stable alkylidyne surface species with well defined atomic structure has now been carefully demonstrated for the hexagonal (111) crystal faces of rhodium¹, palladium², and platinum³⁻⁶. In the case of platinum, recent reaction studies in our laboratory⁷ have provided direct evidence for an olefin hydrogenation mechanism wherein the alkylidyne surface species function as an important and unique co-catalyst in the hydrogenation pathway. Specifically, during ethylene hydrogenation at atmospheric pressures and 300 - 370K, an ordered ethylidyne ($\text{Pt}_3\equiv\text{CCH}_3$) overlayer is formed immediately as the reaction commences. High resolution electron energy loss spectroscopy (HREELS)⁸ and a radiotracer technique (reported here), have both shown that this ethylidyne is stable towards rehydrogenation and desorption under the conditions where ethylene hydrogenation occurs (300K, 1atm H_2). Hydrogen-deuterium exchange of the methyl group in ethylidyne is also a slow process in comparison to the high pressure hydrogenation^{5,7,8,9}. It now appears very likely that the hydrogenation reaction actually takes place on top of this ordered metal-organic layer, which acts as a transfer agent for hydrogen atoms from the metallic surface to the reactant ethylene. Furthermore, it appears that the "structure insensitivity" of ethylene hydrogenation over platinum catalysts^{10,11}, originates at least in part from the presence of this active ethylidyne layer which effectively masks the underlying platinum structure.

At higher temperatures of (450 - 800K), the chemistry of all hydrocarbons adsorbed on platinum is dominated by dissociative chemisorption involving the scission of one or more C-H bonds¹². Detailed understanding of these elementary C-H bond breaking processes is essential for establishing

reaction mechanisms for important hydrocarbon skeletal rearrangement such as isomerization and aromatization. These reactions are catalyzed directly at metal sites^{13,14}, and only at high temperatures ($> 500\text{K}$), where C-H bond breaking occurs easily. Of particular importance are the energetics and reversibility of the sequential C-H bond breaking processes.

Hydrogen thermal desorption (TDS) and carbon-14 radiotracer studies have been applied here to investigate the energetics and reversibility of ethylene sequential dehydrogenation on the flat (111) platinum single crystal surface. The evolution of hydrogen under UHV conditions was monitored as a function of adsorption temperature to determine the activation energies for sequential C-H bond breaking and the average (H/C) composition of the adsorbed species. Simultaneous radiotracer studies were employed to explore the adsorption reversibility. Reactivity studies carried out near atmospheric pressure revealed two distinct types of carbonaceous species on the platinum surfaces:

- (1) an active form consisting of ethylidyne species and fragments which undergo hydrogenation and hydrogen transfer under mild conditions, and
- (2) an inactive form that displays little reactivity over the entire range of temperature (300 - 700K) and pressure (10^{-10} - 1 atm) investigated.

Removal of the active ^{14}C -containing species by hydrogen transfer reactions with unlabelled hydrocarbons was also studied, and significant reaction rates at 520 - 570K for such processes were found. The proportion of the total surface carbon which exists in the active form decreased with increasing adsorption temperature as the surface species became more hydrogen deficient.

Experimental

Experiments were carried out in an ultra high vacuum (UHV) system, described previously¹⁴, that was equipped with facilities for low energy electron diffraction, Auger electron spectroscopy, thermal desorption, radiotracer analysis, and in situ sample treatment at atmospheric pressures. The counting system for ¹⁴C-radiotracer studies was detailed in a separate report¹⁵, and is shown schematically in Figure 1. It consisted of a solid state surface barrier detector which was mounted on a rotatable feedthrough in the center of the UHV chamber. The detector could be reproducibly positioned directly in front of the single crystal surface (within 1 cm) for counting adsorbed species, or rotated away for background corrections, high pressure reactions, or LEED and AES studies. It was interfaced to conventional counting electronics and to a pulse height analyzer where N(E) spectra of the beta emission from ¹⁴C could be stored and integrated to obtain the total radioactivity present on the surface. The absolute detection efficiency (in the range 2.4 - 3.2%) was calibrated for the experimental counting geometry by depositing thin films of ¹⁴C-polymethylmethacrylate onto the single crystals and by monitoring the ¹⁴C-count rate as a function of the amount deposited¹⁵. Using this system ¹⁴C-containing species could be easily detected at surface concentrations of $10^{12} - 10^{13}$ molec/cm². Counting times were in the range of 3 - 10 minutes, and count rates for adsorbed species and background were in the ranges 200 - 1600 and 2 - 5 counts per minute (cpm), respectively.

The (111) single crystal sample used in these investigations was deliberately cut very thin so that the polycrystalline edges would constitute less than about 15% of the total platinum surface area. The crystal was

cleaned by repeated cycles of 1.0 keV Ar⁺ bombardment at 1000K, O₂-treatment at 10⁻⁷ Torr and 900 - 1200K, and annealing to 1300K. The crystal temperature was continuously regulated to ±2K with a precision temperature controller referenced to a chromel-alumel thermocouple spotwelded to the edge of the crystal. Heating rates in the range of 12 - 90K/sec were employed for all thermal desorption measurements.

Unlabelled hydrocarbon reagents were of the highest obtainable research purity. The liquid hydrocarbons were outgassed by repeated freeze-pumping cycles at 77K prior to use. Carbon-14 labelled ethylene (Amersham, 128 mc/mole, radiochemical purity > 99.5%) was used as supplied after brief freeze pumping at 77K.

Results and Discussion

A. ¹⁴C-Ethylene Chemisorption and Dehydrogenation on Pt(111)

Isotherms obtained for ¹⁴C-ethylene chemisorption on Pt(111) at 330 - 570K are shown in Figure 2. For temperatures below about 450K, the initial sticking coefficient S₀ and the saturation coverage C_s were constant. At higher temperatures a second and slower adsorption process was apparent, which continued for exposures above 20L (1L = 10⁻⁶ Torr · sec, uncorrected for ion gauge sensitivity). As demonstrated below, the slow adsorption process was accompanied by extensive dehydrogenation and rearrangement of the surface species.

Ethylene chemisorption on Pt(111) at 300 - 430K leads to the formation of surface ethylidyne species which display a 2x2 overlayer structure. Dynamical LEED intensity analysis^{3,6}, HREELS^{3,4}, and TDS^{4,5} studies have

revealed that they occupy 3-fold hollow adsorption sites with the C-C internuclear axis directed normal to the platinum surface and with C-C and Pt-C bond distances of 1.5 and 2.0Å, respectively. The radiotracer uptake curve (Figure 2) show that this specie forms according to 1st-order Langmuir kinetics, i.e.

$$\frac{d\theta}{d\varepsilon} = \frac{S_0}{C_S (2\pi mkT)^{1/2}} (1 - \theta) \quad (1)$$

where ε is the gas exposure, C_S is the ethylidyne saturation coverage ($C_S = 3.8 \times 10^{14}$ molec/cm²), and S_0 was constant at 0.9 ± 0.2 over the temperature range 330 - 420K.

Hydrogen thermal desorption spectra representing the sequential dehydrogenation of ethylene chemisorbed on Pt(111) at 110 - 570K are shown in Figure 3. As discussed in detail by Salmeron⁵, ethylene dehydrogenation following adsorption at about 110K is characterized by 3 sets of H₂-desorption peaks. The initial C-H bond activation produces a sharp peak at 295K which corresponds to ethylidyne formation. The second dehydrogenation reaction occurs at about 470K and corresponds to the loss of 2 hydrogen atoms per ethylidyne^{4,5}. A final series of dehydrogenation of the carbonaceous residue at higher temperatures leads to the formation of graphite on the surface.

Activation energies for the C-H bond breaking processes that produced the different hydrogen desorption peaks were estimated by assuming that all are unimolecular reactions. Kinetic analysis of the dehydrogenation steps is then identical to that for first order molecular desorption

which may be conveniently treated with the Redhead formula¹⁶,

$$E_a = RT_p^2 (\nu/\beta) \exp(-E_a/RT_p) \quad (2)$$

where β is the sample heating rate, ν is surface reaction pre-exponential factor, and T_p is the temperature of the desorption peak maximum.

The assumption of first order reaction kinetics was justified by the fact that the desorption peak temperatures were invariant to changes in initial surface coverage. Assuming $\nu = 10^{13} \text{ sec}^{-1}$, the activation energies for ethylene dehydrogenation were found to vary widely from about 18 kcal/mole for ethylidyne formation to 35 - 43 kcal/mole for complete dehydrogenation.

The average (H/C) stoichiometry of the adsorbed species, expressed as hydrogen atoms per surface carbon atom, was determined as a function of adsorption temperature from the total areas under the hydrogen thermal desorption spectra. The desorption peak area was assumed to be proportional to the amount of hydrogen originally retained by the adsorbed species. Comparison of this peak area with the C_{273}/Pt_{237} AES peak-to-peak height ratio provided a measure of the initial (H/C) composition, as described in detail previously¹³.

The composition of the strongly bound species resulting from ethylene chemisorption is temperature dependent in the 300 - 670K range, as shown in Figure 4. The hydrogen content of the surface species decreased with increasing adsorption temperature and approached zero at temperatures higher than 670K.

B. Reversibility of Sequential Dehydrogenation: Radiotracer Studies of Ethylene Rehydrogenation and Hydrogen Transfer Reactions

Radiotracer decay curves representing the rehydrogenation of ethylidyne chemisorbed on the (111) platinum surface are shown in Figure 5. These species were prepared by chemisorbing ^{14}C -ethylene at 335 - 345K and 10^{-7} Torr using a constant exposure of 6L. The rehydrogenation reactions were carried out at 300 - 470K in the presence of 1 atm of flowing hydrogen. The reactions were interrupted at intervals of 1 - 10 minutes so that the residual coverage ($\theta(t)/\theta(t=0) = \theta/\theta_0$, in cpm/cpm₀) of the radioactive surface species could be determined as a function of total reaction time. Two observations are significant: (1) the ethylidyne species became highly reactive only at temperatures higher than about 340K, and (2) the rehydrogenation was not a first-order process. At 300K only about 25% of the surface moieties were removed by rehydrogenation in 30 minutes of reaction time. By contrast, at 370K or higher temperatures, the same surface species underwent essentially complete rehydrogenation in just 2 - 5 minutes. From the initial slopes of the decay curves the activation energy for ethylidyne hydrogenation can be very roughly estimated to be 5 - 10 kcal/mole.

These results are in excellent agreement with those obtained using HREELS, where the stability of ethylidyne was inferred from the observation that no changes occur in the vibrational spectra after 1 atm H_2 exposure at temperatures up to about 330K⁸. Hydrogenation of ethylene occurs readily under these conditions with turnover frequencies of 1 - 100 molecules/Pt \cdot sec⁷, implying therefore that hydrogenation reactions proceed in the presence of an ethylidyne saturated surface.

A similar series of rehydrogenation reactions was carried out following the chemisorption of ^{14}C -ethylene on Pt(111) at 473 and 600K. Ethylene adsorption at these temperatures produced surface species with average compositions " C_2H " (473K) and " C " (600K). Representative results are shown in Figure 6. Rehydrogenation of these more strongly adsorbed species at 370 - 640K proceeded in at least two distinct stages. A very rapid initial reaction which was complete within about 2 minutes was always followed by a very slow rehydrogenation process ($R_{\text{H}} < 10^{-5}$ molec/Pt atom \cdot sec), which continued for hours without reaching completion. The rapid initial reaction appears to represent the hydrogenation of small C, C_2 , CH and/or C_2H fragments that are reportedly present following ethylene chemisorption at 470 - 650K^{4,5}. The second process, on the other hand, appears to represent the gasification of polymer carbon islands with very low hydrogen content. Similar catalytic behavior characterized by a two stage rehydrogenation reaction was reported by Krebs and Bonzel¹⁷ for the hydrogenation of surface carbon deposited on iron foils at 560K.

These results show that for temperatures higher than about 470K, ethylene chemisorption on Pt(111) is always partially irreversible. The proportion of the total surface carbon which exists in the inactive form increases with increasing adsorption temperature. In Figure 4 the irreversibly adsorbed fraction is shown as a function of temperature along with the (H/C) stoichiometry of the adsorbed layer as determined from thermal desorption studies. The irreversibly adsorbed fraction was defined as the proportion of preadsorbed ^{14}C -ethylene which could not be removed by rehydrogenation (40 - 80 minute reaction time) at the same temperature at which the initial adsorption was carried out. The (H/C) ratio displayed

a striking correlation with the adsorption reversibility. Sequential dehydrogenation of ethylidyne to " C_2H " like species at 450 - 470K was accompanied by a corresponding decrease in reversibility from 95 - 100% to about 50 - 70%. The reversibility approached zero as the hydrogen content decreased further at higher adsorption temperatures.

The fact that the amount of inactive carbon deposited at 473K was dependent upon the temperature of subsequent rehydrogenation reactions suggests that the process that causes the formation of the inactive carbon involves two independent pathways. The initial formation of inactive carbon responsible for the overall shape of Figure 6 appears to occur during adsorption. Further polymerization, which competes with direct hydrogenation, appears to occur during the initial stages of the rehydrogenation reactions. Provided that the activation energy for inactive carbon formation is smaller than that for hydrogenation, the irreversibly adsorbed fraction should decrease with increasing reaction temperature as observed experimentally. Further studies are in progress to better clarify the inactive carbon formation process.

The formation of inactive metal-organic surface species derived from ^{14}C -ethylene on alumina supported Ni^{18} , Pd^{18} , $Rh^{18,19}$, Ir^{20} , and Pt^{18} catalysts was previously investigated by Thomson and Webb and co-workers. Inactive carbonaceous species were detected under all conditions of direct hydrogenation and hydrogen transfer with unlabelled ethylene and acetylene at 290 - 470K. At 290K, the irreversibly adsorbed fraction decreased in the sequence $Pd (63\%) > Ni (20\%) > Ir (6-13\%) > Pt (4-7\%)$. The inactive fraction retained by the platinum catalyst increased to 40 - 60% at 470K. These results appear to be in excellent agreement with those reported here for the small area (111) platinum single crystal surface.

The strongly adsorbed " C_2H " fragments resulting from ^{14}C -ethylene chemisorption on Pt(111) at 470K were also active for intermolecular hydrogen transfer reactions with unlabelled hydrocarbons. Radiotracer decay curves illustrating hydrogen transfer between " C_2H " and n-hexane or cyclohexene at 523 - 573K are shown in Figure 7. An interesting feature of the hydrogen transfer reactions is the ease with which they occurred. Initial disappearance rates for the active ^{14}C -containing species by hydrogen transfer with 20 Torr of n-hexane or cyclohexene appear to be within an order of magnitude of those for direct hydrogenation in 1 atm of hydrogen. Hexenes and benzene were detected as byproducts of the hydrogen transfer reactions. Cyclohexene (a good hydrogen donor) underwent hydrogen transfer to " C_2H " more rapidly than n-hexane (a poor hydrogen donor). In the absence of hydrogen, the hydrogen transfer reactions were accompanied by the formation of high concentrations of carbonaceous deposit on the platinum surface ($C_{273}/Pt_{237} = 5 - 8$), as measured by AES. The pathway by which hydrogen transfer takes place remains uncertain at this time. While a direct transfer mechanism cannot be ruled out, it appears more likely that this reaction is mediated by dehydrogenation of unlabelled hydrocarbon molecules on the metal surface followed by addition of chemisorbed hydrogen to the ^{14}C -containing species.

It should be noted that neither hydrogenation nor hydrogen transfer could be detected at low reactant pressures ($10^{-8} - 10^{-6}$ Torr). Weakly adsorbed species that can be produced at atmospheric pressures appears to be an essential requirement for activity in these chemical reactions.

The radiotracer studies clearly demonstrate that hydrogen transfer reactions take place readily between hydrocarbon species strongly

chemisorbed on the (111) platinum single crystal surface. Previous studies of cyclohexene hydrogenation and disproportionation catalyzed at 425K over Pt(322) revealed that direct hydrogenation was ten times faster than hydrogen transfer^{12,20}. Because the activation energy for disproportionation (~16 kcal/mole) was larger than that for direct hydrogenation (5 - 6 kcal/mole), the importance of the hydrogen transfer pathway is expected to increase with increasing reaction temperature.

The notion that hydrogen transfer reactions may be important in hydrocarbon catalysis is not new. Thomson and Webb²² have argued that a hydrogen transfer mechanism provides a general explanation for the patterns of catalytic activity displayed by metal catalysts in olefin hydrogenation reactions. Gardner and Hansen²³ reached a similar conclusion in connection with studies of ethylene hydrogenation over tungsten catalysts. Our results⁷ certainly tend to confirm that hydrogen transfer reactions are important. More detailed kinetic studies of the hydrogen transfer pathway would be very valuable to determine the relevance of these processes.

ACKNOWLEDGEMENT

This work was supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Sciences Division of the U.S. Department of Energy under Contract DE-AC03-76SF00098. We are grateful to the Shell Development Company for supplying the ¹⁴C-ethylene.


REFERENCES

1. R.J. Koestner, M.A. Van Hove and G.A. Somorjai, *J. Phys. Chem.* 87, 203 (1983).
2. L.L. Kesmodel and J.A. Gates, *Surf. Sci.* 111, L747 (1981).
3. L.L. Kesmodel, L.H. Dubois and G.A. Somorjai, *J. Chem. Phys.* 70, 2180 (1979).
4. A.M. Baro and H. Ibach, *J. Chem. Phys.* 74, 4194 (1981) and references therein.
5. M. Salmeron and G.A. Somorjai, *J. Phys. Chem.* 86, 341 (1982).
6. R.J. Keostner, J.C. Frost, P.C. Stair, M.A. Van Hove and G.A. Somorjai, *Surf. Sci.* 116, 85 (1982).
7. F. Zaera and G.A. Somorjai, *J. Am. Chem. Soc.* 106, 2288 (1984).
8. B.E. Bent, B. Koel, F. Zaera and G.A. Somorjai, to be published.
9. J.R. Creighton, K.M. Ogle and J.M. White, *Surf. Sci.* 138, L137 (1984).
10. J.C. Schlatter and M. Boudart, *J. Catal.* 24, 482 (1972).
11. G.C. Bond, J.J. Phillipson, P.B. Wells and J.M. Winterbottom, *Trans. Faraday Soc.* 60, 1847 (1964).
12. See for example S.M. Davis and G.A. Somorjai, Hydrocarbon Conversion over Metal Catalysts, in The Chemical Physics of Solid Surfaces and Heterogeneous Catalysis (D.A. King and D.P. Woodruff, eds.) Elsevier, Amsterdam, 1982.
13. S.M. Davis, F. Zaera and G.A. Somorjai, *J. Catal.* 77, 439 (1982).
14. S.M. Davis, F. Zaera and G.A. Somorjai, *J. Catal.* 85, 206 (1984).
15. S.M. Davis, B.E. Gordon, M. Press and G.A. Somorjai, *J. Vac. Sci. & Techn.* 19, 231 (1981).
16. P.A. Redhead, *Vacuum* 12, 203 (1962).
17. H.J. Krebs and H.P. Bonzel, *Surf. Sci.* 99, 570 (1980).
18. G.F. Taylor, J.J. Thomson and G. Webb, *J. Catal.* 12, 191 (1968).
19. J.U. Reid, S.J. Thomson and G. Webb, *J. Catal.* 30, 372 (1973).
20. S.V. Norval, S.J. Thomson and G. Webb, *Appl. Surf. Sci.* 4, 51 (1980).
21. S.M. Davis, Ph.D. Thesis, University of California, Berkeley, 1981.
22. S.J. Thomson and G. Webb, *J.C.S. Chem. Comm.*, 526 (1976).
23. H.C. Gardner and R.J. Hansen, *J. Phys. Chem.* 74, 3298 (1970).

FIGURE CAPTIONS

- Figure 1 Schematic diagram of the radiotracer counting system for adsorption and catalysis studies using small area surfaces in ultra-high vacuum.
- Figure 2 Adsorption isotherms for $^{14}\text{C}-\text{C}_2\text{H}_4$ chemisorption on Pt(111) at 330 - 570K (left frame). The adsorption behavior at 330 - 420K is well described by a first-order Langmuir model (right frame).
- Figure 3 Hydrogen thermal desorption spectra representing the sequential dehydrogenation of C_2H_4 chemisorbed on Pt(111) at 110 - 565K. The heating rate was 88K/sec except for the top curve reproduced from ref. 5 where it was 12K/sec.
- Figure 4 Composition and reactivity of ^{14}C -ethylene chemisorbed on Pt(111) at 320 - 670K. The irreversibly adsorbed fraction determined by radiotracer analysis displays an excellent correlation with the average hydrogen content (H/C) of the strongly bound surface species.
- Figure 5 Radiotracer decay curves illustrating the rehydrogenation of ^{14}C -ethylidyne species chemisorbed on Pt(111).
- Figure 6 Radiotracer decay curves illustrating the partial rehydrogenation of ethylene decomposition products with average composition " C_2H " (left frame) and " C " (right frame). These species were prepared by chemisorbing $^{14}\text{C}-\text{C}_2\text{H}_4$ on Pt(111) at 470 and 600K.
- Figure 7 Radiotracer decay curves illustrating hydrogen transfer reactions between n-hexane (left frame) or cyclohexene (right frame) with " C_2H " surface species that were produced from ^{14}C -ethylene chemisorption on Pt(111) at 470K.


^{14}C - Radiotracer Studies of Carbonaceous Layers on Platinum



XBL 801-4637


Figure 1

$^{14}\text{C}_2\text{H}_4$ adsorption Pt(III)




XBL 818-1105

Figure 2



XBL 846 - 7050

Figure 3




XBL 812-5151A

Figure 4

>C-CH_3 Rehydrogenation Pt(III)


1 atm H₂



XBL813-5385

Figure 5


Rehydrogenation of Ethylene Decomposition Products -Pt(III)



XBL 817-6083A

Figure 6

HYDROGEN TRANSFER TO $^{14}\text{C}_2\text{H}^*$



XBL 815-5660A

Figure 7.

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720