

# Lawrence Berkeley National Laboratory

## Recent Work

### Title

HEAT CAPACITY OF THE SUPERCONDUCTING KDND0 SYSTEM (LaCe)Al<sub>2</sub>

### Permalink

<https://escholarship.org/uc/item/1tb222t7>

### Authors

Bader, S.D.

Fogle, W.E.

Phillips, Norman E.

et al.

### Publication Date

1975-03-01

0 0 0 0 4 3 0 2 8 9 3

To be presented at the 4th International  
Conference on Chemical Thermodynamics,  
Montpellier, France, August 26 - 30, 1975

LBL-3755

c1

HEAT CAPACITY OF THE SUPERCONDUCTING  
KONDO SYSTEM (La Ce)A<sub>12</sub>


S. D. Bader, W. E. Fogle, Norman E. Phillips,  
M. B. Maple, and C. A. Luengo

March 1975

Prepared for the U. S. Atomic Energy Commission  
under Contract W-7405-ENG-48

**For Reference**

Not to be taken from this room



LBL-3755

c1

## **DISCLAIMER**

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

HEAT CAPACITY OF THE SUPERCONDUCTING  
KONDO SYSTEM  $(\text{LaCe})\text{Al}_2^*$

S. D. Bader,<sup>+</sup> W. E. Fogle, and Norman E. Phillips

Inorganic Materials Research Division of the  
Lawrence Berkeley Laboratory and Department of Chemistry  
University of California, Berkeley, California 94720 U.S.A.

and

M. B. Maple and C. A. Luengo

Institute for Pure and Applied Physical Sciences,  
University of California, San Diego, La Jolla, California 92037

The addition of magnetic impurities to a superconducting host introduces a "pair-breaking mechanism", i.e. the impurities interfere with the formation of Cooper pairs. In general, magnetic impurities tend to suppress the transition to the superconducting state, but the detailed behavior depends on the impurity concentration, on the relative strengths of the conduction electron-impurity exchange interaction and the net attractive interaction between electrons in the pure host, and on the sign of  $J$ , the conduction electron-impurity exchange parameter (1). When  $J < 0$ , the Kondo effect occurs in the normal state with a characteristic temperature  $T_K$ . For  $T_K \ll T_{C0}$ , where  $T_{C0}$  is the critical temperature for superconductivity in the pure host, "reentrant" behavior has been predicted (2) over a limited range of impurity concentration - as the temperature is reduced an alloy with an impurity concentration within this range should first become superconducting at  $T_{C1}$ , normal again at  $T_{C2}$ , and finally superconducting at  $T_{C3}$ . Solutions of  $\text{CeAl}_2$  (in which localized magnetic moments are associated with the Ce ions) in the superconductor  $\text{LaAl}_2$  have been identified as showing this type of behavior; several properties indicate (3-9) that  $J < 0$ , and a return to the normal state with decreasing temperature has been observed (10,11) at  $T_{C2}$  [although no evidence has been found for a transition back to the superconducting state at  $T_{C3}$  to temperatures as low as

6 mK (11)]. To obtain more information on this system, we have made heat capacity measurements on several  $(\text{LaCe})\text{Al}_2$  alloys with Ce concentration varying from zero to above the turning point concentration of the reentrant  $T_c$  vs. Ce concentration curve. The measurements extend below the temperature of the maximum in  $C_N$ , the normal-state heat capacity, and, for the one sample that shows reentrant superconducting behavior, below  $T_{c2}$ .

Measurements were made on samples with 0, 0.193, 0.640, and 0.906 at. % Ce substituted for La, in the temperature range 0.07 to 20 K, and in magnetic fields from 0 to 38 kOe. The 0.640 at. % Ce sample showed reentrant superconductive behavior with  $T_{c1} = 1.1$  K and  $T_{c2} = 0.25$  K, as determined by ac mutual inductance measurements [see Figure 1(a)]. The 0.906 at. % Ce sample showed no transition to the superconducting state at temperatures above 0.3 K, consistent with a turning point concentration of 0.67 at. % Ce. The samples were prepared as described in connection with other work except that the 0.906 at. % Ce sample was annealed at 800°C for one week (rather than 16 h). Between 0.5 and 4.2 K, the results are similar to those obtained in earlier heat capacity measurements (5) that covered only that interval.

A complete analysis of the data on all samples shows that the lattice and normal state electronic heat capacities of the alloy samples are the same as those of pure  $\text{LaAl}_2$ . [The high-temperature tail of the Kondo anomaly (Figure 2) appeared as an apparent enhancement of  $\gamma$  in the earlier measurements (5)]. In magnetic fields high enough to quench superconductivity, the magnetic impurity contribution to the heat capacity is approximately proportional to the Ce impurity concentration  $c$  and approaches the temperature dependence associated with the Kondo effect in the low field limit. This is illustrated in Figure 2, where  $\Delta C$ , the heat capacity in excess of that of the pure host, is plotted as  $\Delta C/c$  vs.  $\log T$  for the 0.640 at. % Ce sample. Curves a and b represent the 38 and 20 kOe data respectively for all the alloy samples to within experimental error, and correspond to an entropy of  $R \ln 2$  per mole Ce. This shows unambiguously that the Ce ground state has an effective spin of  $1/2$ , in accord with magnetic susceptibility measurements which suggest that the cubic crystal field splits the  $\text{Ce}^{3+}$   $J = 5/2$

multiplet into an excited-state quartet and a ground-state doublet with a splitting of 100 K (7,8). Curve d represents the heat capacity associated with the formation of the Kondo spin-compensated state in zero-magnetic field. It was originally drawn to represent data (12) on  $\text{CuCr}$ , a typical and well-established Kondo system, in the single-impurity limit. It is also consistent with the calculations of Bloomfield and Hamann (13). As redrawn in Figure 2, shifted in temperature and scaled by a factor of 1/2 to correspond to an entropy of  $R \ln 2$  per mole Ce, it also fits the zero field data for the 0.906 at. % Ce sample. It is a good approximation to the 0.5 kOe

FIGURE 1

- (a) Magnetically determined transitions in the 0.640 at. % Ce sample  
 (b) Zero field and 0.5 kOe heat capacity data for the 0.640 at. % Ce sample, relative to the zero-field normal-state heat capacity. The error bars represent the effect of a 1 % error in the total measured heat capacity.





FIGURE 2

Heat capacity of the 0.64 at. % Ce sample.  
 (See text for complete explanation).




normal state data for the 0.640 at. % Ce sample (and also to the zero field data for that sample for which it might be expected that the normal-state and superconducting-state electronic heat capacities do not differ much). The good agreement of curve d with the  $(\text{LaCe})\text{Al}_2$  data provides confirmation of the Kondo effect in this system. Comparison with the Bloomfield-Hamann theory also gives  $T_K = 0.42$  K, in reasonable agreement with other estimates (3-9) of  $T_K$ , which range from 0.1 to 1 K.

In order to display the heat capacity anomalies associated with the superconducting transitions, the zero-field and 0.5 kOe heat capacities for the 0.640 at. % Ce sample are shown on an expanded scale and compared with the magnetically determined transitions in Figure 1. In Figure 1(b),  $\Delta C$  represents the heat capacity relative to a smooth reference curve that was chosen to approximate the zero-

FIGURE 3

Sum of the magnetic and electronic heat capacities of the 0.193 at. % Ce sample in zero-field. (See text for complete explanation).



field normal-state heat capacity. The 0.5 kOe points therefore represent the field dependence of the normal-state heat capacity and the zero-field points represent  $C_S - C_N$  ( $H = 0$ ). Since the zero-field normal-state heat capacity is not determined unambiguously by our measurements, this interpretation of either set of points in Figure 1(b) by itself is somewhat uncertain, but the difference between the zero-field and 0.5 kOe data is, of course, represented exactly. The precision of the data in the region 0.3 to 0.5 K is relatively poor because this is the region of overlap of two separate sets of measurements. Nevertheless, both the zero-field and 0.5 kOe data show a peak or shoulder in this region. The fact that it occurs in both fields shows that it reflects a systematic error (e.g., an error in the temperature scale or an irregularity in the reference curve) and that it has no significance for  $C_S - C_N$  ( $H = 0$ ). Relative to the 0.5 kOe data, however, there are two well-defined peaks in the zero-field data. They occur in the outer regions of the magnetically determined transitions [see Figure 1(a)],



but, given the breadth of the transitions and the different nature of the two measurements, the agreement in temperature is quite reasonable. The anomaly at  $T_{C1}$  has a shape consistent with a slightly broadened second-order transition. It is similar to that observed by Steglich and Armbrüster (14) who have shown that its size is consistent with a bulk superconducting transition. In Figure 1(b) a similar anomaly appears just below  $T_{C2}$ , and the negative values of  $C_s - C_n$  ( $H = 0$ ) required by the equality of the free energies at  $T_{C1}$  occur at intermediate temperatures. The shapes of the anomaly at  $T_{C2}$  and of  $C_s - C_n$  ( $H = 0$ ), at intermediate temperatures depend on the assumptions made in deriving  $C_n$  ( $H = 0$ ), but the existence of the anomaly is clear in any precise comparison of the zero-field and 0.5 kOe data. The anomaly at  $T_{C2}$  appears to be smaller than that at  $T_{C1}$ , but that would be quite reasonable in view of the lower temperature, and we believe it is evidence for a bulk second-order transition.

The zero field normal- and superconducting-state heat capacities of the 0.193 at. % Ce sample are compared in Figure 3. The points represent zero field data for  $C - C_L$ , where  $C_L$  is the lattice heat capacity; the horizontal line represents the normal state electronic heat capacity; the dashed and dash-dot curves represent, respectively, the sum of the normal state electronic and impurity heat capacities, and the normal state impurity heat capacity. Below 0.54 K the total superconducting state heat capacity is less than the normal state impurity heat capacity alone. This shows clearly the modification of the Kondo effect by the formation of Cooper pairs. At temperatures from 0.3 K to the lowest temperature reached, 0.08 K, the superconducting state heat capacity increases with decreasing temperature. Unfortunately, the measurements do not extend to low enough temperatures to reveal the maximum in  $C_s$  below 0.08 K which is required by the equality of the normal and superconducting state entropies at 0 K and  $T_c$ . Although the theory has not been developed to the point of permitting a quantitative comparison, this increase is qualitatively consistent with the predicted (15) impurity band at low energies in the gap.

\* Work at Berkeley supported by the U. S. Energy Research and Development Authority. Work at La Jolla supported by the Air Force Office of Scientific Research under Grant No. AF-AFOSR-71-2073.

+ Present address: Material Science Division, Argonne National Laboratory, Argonne, Illinois 60439.

1. For references to experimental and theoretical results, see M. BRIAN MAPLE, in "MAGNETISM: A Treatise on Modern Theory and Materials," edited by H. Suhl (Academic Press, New York, 1973) Vol. 5, Chap. 10.
2. E. MÜLLER-HARTMANN and J. ZITTARTZ, Phys. Rev. Lett. 26, 428 (1971).
3. M. B. MAPLE and Z. FISK, Proceedings of the Eleventh International Conference on Low Temperature Physics, St. Andrews, 1968, J. F. Allen, D. M. Finlayson, and D. M. McCall, Eds. University of St. Andrews Printing Department, 1968, Vol. 2, p. 1288.
4. M. B. MAPLE, Solid State Commun. 8, 1915 (1970).
5. C. A. LUENGO, M. B. MAPLE, and W. A. FERTIG, Solid State Commun. 11, 1445 (1972).
6. H. ARMBRÜSTER, H. v. LÖHNEYSSEN, G. RIBLET, and F. STEGLICH, Solid State Commun. 14, 55 (1974).
7. A. BENOIT, J. FLOUQUET, and J. SANCHEZ, Solid State Commun., 13, 1581 (1973).
8. J. H. MOESER, F. STEGLICH, and G. v. MINNERGERODE, to be published.
9. W. FELSCH and K. WINZER, Solid State Commun. 13, 569 (1973).
10. G. RIBLET and K. WINZER, Solid State Commun. 9, 1663 (1971).
11. M. B. MAPLE, W. A. FERTIG, A. C. MOTA, L. E. DeLONG, D. WOHLLEBEN and R. FITZGERALD, Solid State Commun. 11, 829 (1972).
12. B. B. TRIPLETT and NORMAN E. PHILLIPS, Phys. Rev. Lett. 27, 1001 (1971).
13. P. E. BLOOMFIELD and D. R. HAMANN, Phys. Rev. 164, 856 (1967).
14. F. STEGLICH and H. ARMBRÜSTER, to be published.
15. J. ZITTARTZ, A. BRINGER, and E. MÜLLER-HARTMANN, Solid State Commun. 10, 513 (1972).

## LEGAL NOTICE

*This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.*

TECHNICAL INFORMATION DIVISION  
LAWRENCE BERKELEY LABORATORY  
UNIVERSITY OF CALIFORNIA  
BERKELEY, CALIFORNIA 94720