

Lawrence Berkeley National Laboratory

LBL Publications

Title

Hybrid Spin-Filter / Magnetic Tunnel Junction Heterostructures with Room Temperature Ferrimagnetic Barrier Layers

Permalink

<https://escholarship.org/uc/item/2ch8d981>

Authors

Nelson-Cheeseman, B. B.

Wong, F. J.

Chopdekar, R. V.

et al.

Publication Date

2009-03-16

Hybrid Spin-Filter / Magnetic Tunnel Junction Heterostructures with Room Temperature Ferrimagnetic Barrier Layers.

*B. B. Nelson-Cheeseman*¹; *F. J. Wong*¹; *R. V. Chopdekar*¹; *E. Arenholz*²; *Y. Suzuki*¹

1. Dept of Materials Science and Engineering, University of California, Berkeley, Berkeley, CA, USA.

2. Advanced Light Source, Lawrence Berkeley National Laboratory, Berkeley, CA, USA.

Magnetic tunnel junctions (MTJ) with ferrimagnetic barrier layers exhibit both spin filtering and MTJ device characteristics, providing a promising means to enhance spin transport over conventional MTJs. In such all-magnetic devices, the magnetic coupling behavior at the electrode-barrier interfaces is crucial to successful device operation. We have investigated the interfacial magnetism of this novel device architecture in the presence of a barrier layer with long-range magnetic order at room temperature. Heterostructures of highly spin polarized $\text{La}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$ (LSMO) and Fe_3O_4 electrodes sandwiching an insulating NiFe_2O_4 (NFO) ($T_C = 850$ K) barrier layer were grown by pulsed laser deposition on (110) SrTiO_3 substrates. This heterostructure incorporates an isostructural spinel-spinel (NFO- Fe_3O_4) interface and a non-isostructural perovskite-spinel (LSMO-NFO) interface. X-ray diffraction in the 2θ - θ geometry shows only (110)-oriented peaks for both the perovskite and spinel crystal structures, indicating that the films grow epitaxially on one another with high crystallinity. Bulk-sensitive hysteresis loops taken at both 300K and 5K show sharp, independent magnetic switching of both the LSMO and Fe_3O_4 electrodes, creating well-defined parallel and antiparallel states despite the presence of a robust ferrimagnetic barrier layer between them. X-ray magnetic circular dichroism (XMCD) was used to probe the magnetic structure at each electrode-barrier interface with elemental specificity and surface sensitivity by total electron yield. Using various truncated heterostructures to probe the two different electrode-barrier interfaces separately, we have found independent magnetic switching between the Mn in LSMO and the Ni and Fe in NFO at the non-isostructural perovskite-spinel interface. However, we have found strong magnetic coupling and coincident switching of the magnetic cations across the isostructural spinel-spinel interface. The decoupled perovskite-spinel interface is crucial for independent electrode switching as observed in magnetotransport, while the isostructural spinel interface helps preserve interfacial spin polarization of Fe_3O_4 , which has shown to be less robust when using non-isostructural barrier layers. The combination of a magnetically-coupled isostructural interface and a magnetically-decoupled non-isostructural interface is a key feature of this new hybrid device architecture whose room temperature operation is possible with NiFe_2O_4 barrier layers.

The Advanced Light Source is supported by the Director, Office of Science, Office of Basic Energy Sciences, of the U.S. Department of Energy under Contract No. DE-AC02-05CH11231.