UC Irvine UC Irvine Previously Published Works

Title

Field induced quasi-particles in the heavy-fermion superconductor CeCoIn5

Permalink https://escholar<u>ship.org/uc/item/4hr348gb</u>

Journal Journal of Magnetism and Magnetic Materials, 310(2)

ISSN 0304-8853

Authors

Deguchi, K Yonezawa, S Nakatsuji, S <u>et al.</u>

Publication Date

2007-03-01

DOI

10.1016/j.jmmm.2006.10.231

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at https://creativecommons.org/licenses/by/4.0/

Peer reviewed



Available online at www.sciencedirect.com





Journal of Magnetism and Magnetic Materials 310 (2007) 587-589

www.elsevier.com/locate/jmmm

Field induced quasi-particles in the heavy-fermion superconductor CeCoIn₅

K. Deguchi^{a,b,*}, S. Yonezawa^b, S. Nakatsuji^{b,1}, Z. Fisk^{c,2}, Y. Maeno^{b,d}

^aDepartment of Physics, Graduate School of Science, Nagoya University, Nagoya 464-8602, Japan

^bDepartment of Physics, Graduate School of Science, Kyoto University, Kyoto 606-8502, Japan

^cDepartment of Physics, University of California, Davis, CA 95616, USA

^dKyoto University International Innovation Center, Kyoto 606-8501, Japan

Available online 3 November 2006

Abstract

Heavy-fermion superconductor $CeCoIn_5$ has two energy scales for quasiparticle excitation mechanisms in the vortex state: Zeeman shift for the paramagnetic depairing and Doppler shift for the diamagnetic depairing. We have found the two energy-scales description of the specific heat in magnetic fields, which indicates the crossover of the quasiparticle excitation mechanisms from the diamagnetic depairing to the paramagnetic depairing. This result recalls careful interpretations about the field angle resolved specific heat experiment for identification of the superconducting gap structure.

© 2006 Elsevier B.V. All rights reserved.

PACS: 74.20.Rp; 74.25.Bt; 74.25.Op; 74.70.Tx

Keywords: CeCoIn5; Unconventional superconductivity; Gap symmetry; Specific heat

Since the discovery of its superconductivity, the heavyfermion superconductor CeCoIn₅ ($T_c = 2.3$ K) has generated extensive research activities [1]. Its superconductivity exhibits pronounced unconventional features. CeCoIn₅ exhibits the superconducting (SC) transition is of the first order at low temperatures, indicating a fieldinduced destruction of the SC state by Pauli paramagnetism [2,3]. The emergence of a Fulde–Ferrel–Larkin–Ovchinnikov SC state has also been reported in the vicinity of the upper critical field H_{c2} [4,5]. For its SC symmetry, a number of experimental studies of the SC state in CeCoIn₅ have revealed the existence of line nodes in the SC gap [6–8]. However, its pairing symmetry is still controversial. The four-fold anisotropy of the thermal conductivity and of the specific heat in magnetic fields suggests an order parameter with $d_{x^2-y^2}$ and d_{xy} symmetry, respectively [2,9]. This contradiction comes from the interpretation of the origin of the four-fold anisotropy in both quantities.

In order to identify the pairing symmetry, the intensive study of the quasiparticle (QP) excitation mechanisms by magnetic fields in the vortex state is currently of prime importance by specific heat measurements. Experimental results require two energy scales for the QP excitation mechanisms: the Zeeman shift for the paramagnetic depairing and the diamagnetic (orbital) depairing energy associated with the Doppler shift. In the heavy-fermion superconductor CeCoIn₅, the role of the Zeeman shift cannot be neglected. In this paper, we present the two energy-scales description of the specific heat in magnetic fields, which indicates the crossover of the QP excitation mechanisms from the diamagnetic depairing to the paramagnetic depairing.

Single crystals were prepared using an In self-flux method [1]. The sample was cut into a thin plate ($\sim 2.5 \times 2.3 \times 0.08 \text{ mm}^3$) with 2.6 mg and the largest plane oriented perpendicular to the *c*-axis. The directions of the tetragonal crystallographic axes of the sample were

^{*}Corresponding author. Department of Physics, Graduate School of Science, Nagoya University, Nagoya 464-8602, Japan.

E-mail address: deguchi@edu3.phys.nagoya-u.ac.jp (K. Deguchi).

¹Present address: Institute for Solid State Physics, University of Tokyo, Chiba 277-8581, Japan.

²Present address: University of California, Irvine, California 92697-4573, USA.

^{0304-8853/\$ -} see front matter © 2006 Elsevier B.V. All rights reserved. doi:10.1016/j.jmmm.2006.10.231

determined by X-ray Laue method. The field dependence of the specific heat was measured by a relaxation method with a dilution refrigerator [10].

Fig. 1 shows the field dependence of the electronic specific heat divided by temperature C_e/T at T = 0.14 K for $H \parallel [100]$. The electronic specific heat $C_e = C - C_{\rm sch}$ in magnetic fields was obtained after subtracting the nuclear Schottky contribution from the measured specific heat.

For $T/T_c < H/H_{c2}$ and $T/T_c, H/H_{c2} \ll 1$ ($T_c = 2.2$ K, $\mu_0 H_{c2} = 11.6 \text{ T}$ for $H \parallel [100]$ [5]), the QPs induced by magnetic field are dominant. The QPs induced by magnetic fields have two origins: (i) diamagnetic depairing and (ii) paramagnetic depairing. For case (i), the QP energy spectrum E_k is affected and becomes $E'_k = E_k + \varepsilon_D$ by the Doppler shift $\varepsilon_{\rm D} = \hbar \mathbf{k} \cdot \mathbf{v}_{rms}$ (diamagnetic depairing) in the mixed state, where v_s is the superfluid velocity around the vortices and $\hbar k$ is the QP momentum. In the case of $\varepsilon_{\rm D} \ge \Delta(\mathbf{k})$, this energy shift gives rise to a finite DOS at the Fermi level. This leads to the field dependence of $C_{\rm e}/T \propto$ DOS being proportional to \sqrt{H} at low temperature for the SC gap with line nodes [11]: $C_e/\gamma_N T \propto \underline{\varepsilon_D}/\underline{\Delta_0}$ at zero temperature, where $\varepsilon_D/\Delta_0 = (\pi\sqrt{2}/4)\sqrt{H/H_{orb}} \equiv$ $b\sqrt{H/H_{c2}}$ is the energy scale associated with the Doppler shift [12]. H_{orb} is the orbital limiting field.

In magnetic field, for case (ii), the QP energy spectrum E_k splits and becomes $E'_k = E_k \pm \varepsilon_P$ by the Zeeman shift $\varepsilon_P = \mu H$ (paramagnetic depairing). The Zeeman shift destroys superconductivity over parts of the Fermi surface, where the ε_P exceeds the local gap $\Delta(\mathbf{k})$, and induces a spin polarization of the normal electrons: $C_e/\gamma_N T \propto \varepsilon_P/\Delta_0$ at low temperature for line node gap, where $\varepsilon_P/\Delta_0 = \sqrt{2}H/H_P \equiv cH/H_{c2}$ is the energy scale associated with the Zeeman shift [12–14]. H_P is the Pauli paramagnetic limiting field. The paramagnetic depairing in higher field leads to corrections of order H^2 to the average



Fig. 1. Field dependence of C_e/T at T = 0.14 K for $H \parallel [100]$. The line is a fit with the function in the text. Both dotted and dashed lines represent the limits of $\varepsilon_D \gg \varepsilon_P$ and $\varepsilon_D \ll \varepsilon_P$, respectively. The inset shows the field dependence of C_e/T at 0.14 K, which extrapolate to the upper critical field H_{c2} with high field experiment [5].

DOS. Now we modify the energy scale of the paramagnetic depairing to $\varepsilon_{\rm P}/\Delta_0 = c\{H/H_{\rm c2} + d(H/H_{\rm c2})^2\}$. The field dependence of two energy scales $\varepsilon_{\rm D}$ and $\varepsilon_{\rm P}$ indicates that the diamagnetic and the paramagnetic depairings are dominant at low and relatively high fields, respectively.

Recently, it has been shown that the field induced QP DOS at zero temperature should yield a relation with two energy scales [14]. To focus on the QP excitation only by magnetic field, we define $C_{\text{QP}}(T, H)/T \equiv C_{\text{e}}(T, H)/T - \gamma_0$. The scaling function has been explicitly calculated for the specific heat.

$$\frac{C_{\rm QP}(0,H)}{C_{\rm QP}(0,H_{c2})} = \frac{\varepsilon_{\rm D}}{\Delta_0} f\left(\frac{\varepsilon_{\rm D}}{\varepsilon_{\rm P}}\right),\tag{1}$$

$$f(s) = \begin{cases} s + \frac{1}{2s} & (s \ge 1), \\ \frac{2}{\pi} \left(s + \frac{1}{2s} \right) \arcsin s + \frac{3}{\pi} \sqrt{1 - s^2} \, (s \le 1), \end{cases}$$
(2)

where we estimate residual electronic-specific heat coefficient $\gamma_0 = 0.039 \,\text{J/K}^2 \,\text{mol}$ and deduce $C_e(0, H_{c2})/T =$ 1.3 J/K^2 mol in the inset of Fig. 1. The data at 0.14 K is chosen as the limit of $T/T_c \rightarrow 0$ because field induced QPs become dominant and C_e/T has little temperature dependence below 0.2 K: $C_{\text{OP}}(0, H)/T \simeq \{C_{\text{e}}(0.14, H) C_{\rm e}(0.14,0)$ / T. $C_{\rm OP}$ is well fitted by two magnetic energy scales with (b, c, d) = (0.065, 0.13, 2.4) in Fig. 1. We estimate the crossover field $H^* = 2.0 \text{ T}$ from $\varepsilon_D = \varepsilon_P$. Thus, unusual field dependence of specific heat of CeCoIn₅ is naturally explained with the crossover between the diamagnetic and the paramagnetic depairings [14,15]. Note that since the paramagnetic depairing has no field orientation dependence, the anisotropic DOS in magnetic fields by Doppler shift is weakened above H^* [14,12]. To identify the SC gap structure of CeCoIn₅, an intensive study by the field angle resolved specific heat experiment below H^* at low temperatures will be of importance.

In summary, we have found the two energy-scales description of the specific heat in magnetic fields, which reveals the crossover of the QP excitation mechanisms between the diamagnetic and the paramagnetic depairings. We also point out an influence on the field angle resolved specific heat experiment for determination of the SC gap structure.

This work has been supported by the Grants-in-Aid for Scientific Research from JSPS and MEXT of Japan, and the 21COE program "Center for Diversity and Universality in Physics" from MEXT of Japan.

References

- [1] C. Petrovic, et al., J. Phys. Condens. Matter 13 (2001) L337.
- [2] K. Izawa, et al., Phys. Rev. Lett. 87 (2001) 057002.
- [3] A. Bianchi, et al., Phys. Rev. Lett. 89 (2002) 137002.
- [4] H. Radovan, et al., Nature (London) 425 (2003) 51.
- [5] A. Bianchi, et al., Phys. Rev. Lett. 91 (2003) 187004.
- [6] R. Movshovich, et al., Phys. Rev. Lett. 86 (2001) 5152.
- [7] Y. Kohori, et al., Phys. Rev. B 64 (2001) 134526.

- [8] N.J. Curro, et al., Phys. Rev. B 64 (2001) 180514.
- [9] H. Aoki, et al., J. Phys. Condens. Matter 16 (2004) L13.
- [10] K. Deguchi, T. Ishiguro, Y. Maeno, Rev. Sci. Instrum. 75 (2004) 1188.
- [11] G.E. Volovik, JETP Lett. 58 (1993) 469.

- [12] I. Vekhter, P.J. Hirschfeld, E.J. Nicol, Phys. Rev. B 64 (2001) 064513.
- [13] K. Yang, S. Sondhi, Phys. Rev. B 57 (1998) 8566.
- [14] N.D. Whelan, J.P. Carbotte Phys. Rev. B 62 (2000) 14511.
- [15] H. Adachi, M. Ichioka, K. Machida, J. Phys. Soc. Japan 74 (2005) 2181.