

Lawrence Berkeley National Laboratory

Recent Work

Title

ELECTROCHEMICAL STUDIES IN GLASS. I: THE SYSTEM $\text{Na}_2\text{O} \cdot 2\text{SiO}_2 \cdot x\text{NiO}$.

Permalink

<https://escholarship.org/uc/item/4z79w619>

Authors

Lacy, Alton M.
Pask, Joseph A.

Publication Date

1969-02-01

c. 2

RECEIVED
LAWRENCE
RADIATION LABORATORY

MAY 15 1970

LIBRARY AND
DOCUMENTS SECTION

ELECTROCHEMICAL STUDIES IN GLASS
I: THE SYSTEM $\text{NiO-Na}_2\text{Si}_2\text{O}_5$

Alton M. Lacy and Joseph A. Pask

March 1970

AEC Contract No. W-7405-eng-48

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

LAWRENCE RADIATION LABORATORY
UNIVERSITY of CALIFORNIA BERKELEY

25

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

ELECTROCHEMICAL STUDIES IN GLASS
I: THE SYSTEM NiO-Na₂Si₂O₅

Alton M. Lacy and Joseph A. Pask

Inorganic Materials Research Division, Lawrence Radiation Laboratory,
and Department of Materials Science and Engineering,
College of Engineering, University of California,
Berkeley, California

March 1970

ABSTRACT

A solid electrolyte electrochemical cell of the type
 $\text{Pt}|\text{Ni}:\text{NiO}_{a=1}||\text{ZrO}_2 + 7.5\% \text{CaO}|\text{Ni}:\text{NiO}_{a<1} + \text{glass}|\text{Pt}$ has been utilized to
measure the activities of NiO in sodium disilicate glass over the
temperature interval from 750 to 1100°C. The data indicates a solu-
bility varying from 11 mole percent (5.0 wt%) at 800° to 20 mole percent
(9.3 wt%) at 1100°C. From the variation in NiO activity, the activity
of sodium disilicate in glass solution has been estimated; and from
these combined data partial molar free energies and entropies of solution
of NiO and Na₂Si₂O₅, and free energies and entropies of mixing have been
calculated. A partial phase diagram for the system NiO-Na₂Si₂O₅ is pro-
posed from solubility data indicating a eutectic at approximately 12 mole
percent (5.3 wt%) NiO at 830°C.

This work was done under the auspices of the U. S. Atomic Energy
Commission.

At the time this work was done the writers were, respectively, graduate
research assistant and professor of ceramic engineering.

Based on part of the thesis submitted by Alton M. Lacy for the Ph.D. degree
in ceramic science at the University of California, Berkeley, Sept. 1969.

I. INTRODUCTION

The ability to predict and understand reactions occurring between materials of any system requires a knowledge of the thermodynamic properties of the constituents. In the development of a chemical bond between glass and metal, Pask and co-workers¹⁻³ have shown that a necessary criterion for maximum bond strength is the establishment of a condition of saturation of the glass by the oxide of the metallic substrate. Equilibrium compositions can also develop at the interface by redox reactions between dissolved oxides in the glass and the metal substrate. The extent to which any reaction will occur is dependent upon the imbalance of chemical potentials of the constituents in the reacting phases. The stability of glasses in oxidizing or reducing atmospheres, as well as the kinetics of diffusion-controlled reactions are dependent upon the activities of constituents in glasses relative to activities of the same components elsewhere in the system of interest. This work has been undertaken to establish quantitatively the compositional dependence of activities of some "adherence oxides" in sodium disilicate glass (NS₂) in order that we may improve our understanding of this glass as a reactive constituent in bonding and wetting studies.

Those activity measurements on molten silicates reported in the literature have been made principally on binary metal oxide-silica systems and on multicomponent slags. Most of these have been carried out by gas equilibration techniques. An electrochemical method is often preferable because of the wider range of oxygen potentials capable of being measured accurately. The number of electrochemical studies of glasses reported is, however, relatively small.

Herring⁴ and Didtshenko and Rochow⁵ have used cells of the type $O_2(Pt)/liq\ I::liq\ II/O_2(Pt)$ in order to determine the activities of Na_2O in soda-silica glasses and of Na_2O , K_2O and Li_2O in $PbO-SiO_2$ glasses respectively. This type of cell is not generally suitable for quantitative measurements because of the inherent possibilities for error arising from undefined thermoelectric emf's, liquid junction potentials, poorly defined cell reactions and indeterminate transference numbers of the conducting species. Esin⁶ has utilized a simple formation cell of the type M/MO (in glass sol'n)/ O_2 to measure activities of FeO in complex silicate melts. Unknown transference numbers and questionable reversibility also present problems in these measurements. Matsushita and Goto⁷ and Charette and Flangas⁸ have carried out studies of the oxide activities in the $PbO-SiO_2$ system between $900-1100^\circ C$ using a solid electrolyte cell of the type $Ni/NiO//CSZ^\dagger//Pb/PbO + SiO_2$. Their data corresponds well with that of Richardson and Webb⁹ obtained by other methods.

We are presenting here the first part of a current series of electrochemical studies of the activities of the transition metal oxides NiO , $Fe_{0.47}$ and CoO in sodium disilicate glass.

II. EXPERIMENTAL

A schematic diagram of the experimental set-up is illustrated in Fig. 1. The cell arrangement was constructed by positioning a 6" calcia-stabilized zirconia tube^{*} in a Coors CN-5 alumina crucible containing a tightly packed Ni/NiO mixture. The Ni powder was certified chemically

[†] CSZ refers to $0.15 CaO \cdot 0.85 ZrO_2$

^{*} Obtained from Zirconium Corporation of America, Solon, Ohio.

pure by A. D. Mackay Co. Inc., and the NiO was a Baker's analyzed reagent. The electrodes were 20 mil Pt wire--the outer wire doubly wound around the lower portion of the zirconia electrolyte tube and twisted tightly to secure it, and the inner electrode was coiled on one end and pushed to the bottom of the tube. Approximately 1-1/2 grams of $x\text{NiO}\cdot\text{Na}_2\text{O}\cdot 2\text{SiO}_2$ glass was put into the tube with a small quantity of powdered Ni metal. A boron nitride plug with a 25 mil hole was placed over the upper end of the tube to prevent the Pt electrode from touching the tube walls at any point above the glass surface. In the latter stages of the experimental program, the outer electrode was contained in a short piece of mullite thermocouple protection tubing which penetrated the surface of the Ni/NiO mixture. The remaining exposed surface of the Ni/NiO powder was sealed off from the ambient atmosphere by covering it with a powdered sodium disilicate glass containing 7.55% NiO plus excess Ni metal. It was found that the e.m.f. output of a cell was not altered but that the cells were stabilized for longer periods of time, increasing the precision of the measurements.

The assembly shown in Fig. 1 was then seated in a Pt basket and suspended on a push rod containing a thermocouple and the electrodes leading to the recorder. After sealing in a resistance wound furnace, the system was pumped out to approximately 10^{-5} mm Hg. ($\sim 2 \times 10^{-8}$ atm O_2) and the cell was lowered in vacuo into the hot zone of the furnace. After one minute, argon was introduced into the furnace and the ambient pressure was brought up to 1 atm. After one hour, measurements of the generated e.m.f. were taken. Although a tendency existed for some of the residual oxygen in the system to be picked up by the Ni metal in the glass, this

presented no significant problem, since the quantity of oxygen was not large enough after evacuation to significantly alter the composition of the glass even if it were primarily absorbed into the glass; and secondly, the quantity of Ni metal exposed to the ambient atmosphere was substantially greater in the outer electrode compartment than inside the tube. Quantitative electron microprobe analysis after operation of the cell indicated no change in the glass composition due to Ni oxidation and subsequent solution.


The e.m.f. output was recorded by a Honeywell Elektronik 19 high impedance potentiometric recorder. All cells were run for a minimum of 2 days. Over this time, the temperature was varied between 750-1100°C.

The reversibility of the cell was inferred from the reproducible behavior of several cells containing the same glass, and also by the tendency for the cell to return to the same e.m.f. value when disturbed by a temporary short circuit or by impressing a small voltage via a potentiometer.

III. RESULTS AND DISCUSSION

(1) Thermodynamic Data

Since measurements were made by using a cell of the type Ni/NiO//CSZ//Ni/NiO_{a<1} + NS₂, the overall cell reaction may be expressed as



At equilibrium in a reversible cell, the free energy of this reaction may be related to the cell potential by the expression

$$\Delta F = -nFE = RT(2.303)\log(a_{\text{NiO}}). \quad (2)$$

The activity of NiO in the glass (relative to pure solid NiO) may therefore be directly calculated from (2) as

$$a_{\text{NiO}} = \exp(-nFE/2.303RT), \quad (3)$$

where F = Faraday's constant (23,061 cal/volt), E = the cell output in volts, R = the gas constant (1.987 cal/°C), T = absolute temperature, and n = the number of electrons transferred in the cell reaction (in this case, two).

The isocompositional cell output vs. temperature is shown in Fig. 2. Each line represents the average of a minimum of two experimental determinations for each glass composition. The uncertainty is ± 2 mv. The variation of a_{NiO} with temperature for each composition is shown in Fig. 3, and the activity-composition curves are given in Fig. 4 for several temperatures.

The activity of NS_2 in the glass relative to pure liquid NS_2 may be found by calculating the activity coefficient, γ_{NS_2} (where $\gamma_{\text{NS}_2} = a_{\text{NS}_2}/N_{\text{NS}_2}$), from integration of the Gibbs-Duhem equation

$$\ln \gamma_{\text{NS}_2} = \int_{N_{\text{NS}_2}=1}^{N_{\text{NS}_2}} \frac{N_{\text{NiO}}}{N_{\text{NS}_2}} d \ln \gamma_{\text{NiO}} \quad (4)$$

The calculated activities of NS_2 are shown in Fig. 5. Over this small concentration range, the experimental uncertainty is too large to distinguish precisely the temperature variation of the activity of NS_2 , hence a single line is drawn with an estimated uncertainty for all temperatures of 2%.

The partial molar quantities for the solution of pure solid NiO and pure liquid NS_2 in glass may be calculated from the following expressions:

$$\Delta\bar{F}_{\text{oxide}} = -RT \ln a_{\text{oxide}}, \quad (5)$$

$$\Delta\bar{S}_{\text{oxide}} = -\left(\frac{\partial\Delta\bar{F}}{\partial T}\right)_p, \text{ and} \quad (6)$$

$$\Delta\bar{H}_{\text{oxide}} = \Delta\bar{F}_{\text{oxide}} + T\Delta\bar{S}_{\text{oxide}} = -nF \left[E - T \left(\frac{\partial E}{\partial T} \right)_p \right] \quad (7)$$

where E is the cell output in volts. The partial molar data for the glass studied here is presented in Table I. Free energies, entropies and enthalpies of mixing of pure NiO and NS_2 may be calculated from the general expression

$$N_1\bar{X}_1 + N_2\bar{X}_2 = \Delta X_{\text{mix}},$$

where N_1, N_2 are the mole fractions of each component, and X is the thermodynamic property of interest. Mixing data are presented in Table II.

(2) Solubility Limits

For any temperature, the composition in which the activity of NiO equals unity represents the saturation solubility of NiO . By extension of the isothermal activity-composition curves (Fig. 4) to $a_{\text{NiO}} = 1$, the

equilibrium solubility limits can be estimated. Similarly, extension of e.m.f.-temperature curves (Fig. 2) to $E=0$ will produce the same information.

The NS_2 liquidus was determined by the intersection of the experimentally calculated a_{NS_2} vs temperature plots, with the plot of the activity of pure solid NS_2 relative to the pure liquid standard state. The data for this determination was taken from the compilations of Kelley.¹⁰ The graphical analysis is shown in Fig. 6.

Since no compounds along the join NiO-NS_2 are known to the authors, the solubility data determined from these data are presented in the tentative phase diagram of Fig. 7. Intersection of these two liquiduses indicates a eutectic at $N_{\text{NiO}} = 0.12$ (5.28 wt%) at a temperature of approximately 830°C . The broken curves in Fig. 7 are interpolated.

IV. SUMMARY

The solid electrolyte electrochemical method has been shown to be adaptable to studies on the solution of nickel oxide in sodium disilicate glass, providing numerical thermodynamic data as well as information concerning the phase diagram, in the absence of direct observation of crystalline products.

ACKNOWLEDGMENTS

The authors wish to express their appreciation to Dr. Prodyot Roy, Dr. Leo Brewer and Dr. John Chipman for their helpful comments.

REFERENCES

1. J. A. Pask and R. M. Fulrath, "Fundamentals of Glass to Metal Bonding: VIII, Nature of Wetting and Adherence," *J. Am. Ceram. Soc.* 45 (12) 592-96 (1962).
2. F. D. Gaidos and J. A. Pask, "Effect of Glass Composition on the Glass-Iron Interface," *Advances in Glass Technology*, pp. 548-65, (Plenum Press, New York, 1962).
3. M. P. Borom, J. A. Longwell, and J. A. Pask, "Role of 'Adherence Oxides' in the Development of Chemical Bonding at Glass-Metal Interfaces," *J. Am. Ceram. Soc.* 50 (2) 61-66 (1967).
4. A. P. Herring, "Electrochemical Determination of Activities in Sodium Oxide-Silica Melts," given at the 68th annual meeting of the Glass Division of the American Ceramic Society, Washington, D.C. (1966).
5. R. Didtshenko and E. G. Rochow, "Electrode Potentials in Molten Silicates," *J. Am. Chem. Soc.* 76 3291 (1954).
6. Esin and Lepinskikh, *Izv. Akad. Nauk, S.S.S.R., Otd. Tekh. Nauk*, 60 (1954); see - J. W. Tomlinson, "Electrochemical Measurements," *Physicochemical Measurements at High Temperatures*, Sec. 4, Ch. 11, p. 268.
7. Y. Matsushita and K. Goto, "The Application of Oxygen Concentration Cells with the Solid Electrolyte $ZrO_2 \cdot CaO$ to Thermodynamic Research," *Thermodynamics, IAEA Symposium, Vienna*, pp. 111-129, Vol. 1 (1965).
8. G. G. Charette and S. N. Flengas, "Thermodynamic Properties of $PbO-SiO_2$ Slags by emf Measurements," *Canadian Metallurgical Quarterly*, 7 (4) 191-200 (1968).

9. F. D. Richardson and L. E. Webb, "Oxygen in Molten Lead and Thermodynamics of Lead Oxide-Silica Melts," *Trans. Inst. Mining and Metallurgy*, 64 529 (1955).
10. K. K. Kelley, U. S. Bureau of Mines Bulletin 584, "Contributions to the Data on Theoretical Metallurgy, XIII: High Temperature Heat Content, Heat Capacity, and Entropy Data for the Elements and Inorganic Compounds," (1960).

Table I. Activity and partial molar free energy data for the solution of NiO in sodium disilicate glass

| N_{NiO} | a_{NiO} | | | | $\overline{\Delta F}_{NiO}$ (cal/mole) | | | | N_{NS_2} | a_{NS_2} | $\overline{\Delta F}_{NS_2}$ (cal/mole) | | | | $\overline{\Delta S}_{NiO}$ | $\overline{\Delta S}_{NS_2}$ |
|-----------|-----------|-------|-------|-------|--|-------|-------|-------|------------|------------|---|-------|-------|-------|-----------------------------|------------------------------|
| | 800° | 900° | 1000° | 1100° | 800° | 900° | 1000° | 1100° | | | 800° | 900° | 1000° | 1100° | | |
| .015 | .17 | .11 | .075 | .050 | -3780 | -5150 | -6550 | -8170 | .985 | .99 | -20 | -20 | -25 | -30 | 15.2 | .03 |
| .027 | .27 | .17 | .12 | .080 | -2790 | -4130 | -5360 | -6890 | .973 | .98 | -40 | -50 | -55 | -60 | 13.3 | .07 |
| .053 | .45 | .29 | .20 | .14 | -1700 | -2890 | -4070 | -5360 | .947 | .96 | -60 | -70 | -80 | -90 | 10.8 | .10 |
| .076 | .63 | .42 | .31 | .22 | -990 | -2020 | -2960 | -4130 | .924 | .93 | -150 | -170 | -180 | -200 | 9.7 | .15 |
| .099 | .86 | .59 | .43 | .32 | -320 | -1230 | -2130 | -3110 | .901 | .90 | -220 | -250 | -270 | -290 | 9.0 | .22 |
| .109 | 1.00 | .68 | .50 | .38 | 0 | -900 | -1750 | -2640 | .891 | .88 | -270 | -300 | -320 | -340 | 8.8 | .25 |
| .116 | ---- | .74 | .54 | .42 | ----- | -700 | -1560 | -2370 | .884 | .87 | ----- | -330 | -350 | -380 | 8.5 | .30 |
| .127 | ----- | .86 | .62 | .48 | ----- | -350 | -1210 | -2000 | .873 | .85 | ----- | -380 | -410 | -440 | 8.2 | .40 |
| .139 | ----- | 1.00 | ----- | ----- | ----- | 0 | ----- | ----- | .861 | .83 | ----- | -430 | ----- | ----- | ----- | ----- |
| .149 | ----- | ----- | .80 | .62 | ----- | ----- | -560 | -1300 | .851 | .82 | ----- | ----- | -470 | -510 | ----- | ----- |
| .170 | ----- | ----- | 1.00 | ----- | ----- | ----- | 0 | ----- | .830 | .77 | ----- | ----- | -500 | ----- | ----- | ----- |
| .200 | ----- | ----- | ----- | 1.00 | ----- | ----- | ----- | 0 | .800 | --- | ----- | ----- | ----- | -710 | ----- | ----- |

* Entropy data given in (cal/mole.°K).


Table II. Mixing data for the NiO-Na₂Si₂O₅ system

| N _{NiO} | N _{NS₂} | ΔF_{mix} (cal/mole) | | | | ΔS_{mix}^* |
|------------------|-----------------------------|------------------------------------|------|-------|-------|---------------------------|
| | | 800° | 900° | 1000° | 1100° | |
| .015 | .985 | - 76 | - 97 | -123 | -152 | .26 |
| .027 | .973 | -114 | -160 | -198 | -244 | .43 |
| .053 | .947 | -147 | -219 | -291 | -369 | .67 |
| .076 | .924 | -214 | -311 | -391 | -499 | .95 |
| .099 | .901 | -230 | -347 | -454 | -569 | 1.10 |
| .109 | .891 | -241 | -365 | -476 | -591 | 1.19 |
| .116 | .884 | ---- | -373 | -490 | -611 | 1.25 |
| .127 | .873 | ---- | -376 | -512 | -638 | 1.39 |
| .139 | .861 | ---- | -370 | ---- | ---- | ---- |
| .149 | .851 | ---- | ---- | -483 | -628 | ---- |
| .170 | .830 | ---- | ---- | -415 | ---- | ---- |
| .200 | .800 | ---- | ---- | ---- | -568 | ---- |

* Entropy data given in (cal/mole·°K).


FIGURE CAPTIONS

- Figure 1. Schematic diagram of the experimental cell assembly
- Figure 2. Isocomposition cell output for NiO-NS₂ glasses as a function of temperature (± 2 mv).
- Figure 3. Variation in the activity of NiO (referred to the pure solid standard state) with temperature for each composition studied.
- Figure 4. Isothermal dependence of NiO activity (referred to the pure solid standard state) on composition.
- Figure 5. Activity of NS₂ (referred to the liquid standard state) calculated from integration of the modified Gibbs-Duhem equation. (One curve is drawn to represent all temperatures between 800° and 1100°C. Over this small range of concentration, the experimental uncertainty is too large to distinguish precisely the temperature variation on activity of NS₂). The estimated uncertainty in these data is 2%.
- Figure 6. Isocompositional activity plots for NS₂ for determination of the NS₂ liquidus in the NiO-NS₂ system.
- Figure 7. Proposed phase diagram for the NiO-NS₂ system.




XBL 692-225

Fig. 1




XBL 699-1432

Fig. 2.




LBL 695-1471

Fig. 3




NBL 699-1422

Fig. 4




XBL 699-1425

Fig. 5



XBL 667-1410

Fig. 6



XBL 689-1431

Fig. 7

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or*
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.*

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

TECHNICAL INFORMATION DIVISION
LAWRENCE RADIATION LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720