

# Lawrence Berkeley National Laboratory

## Recent Work

### Title

A COMPARISON OF TOE MISSING-ROW MODEL AND SEVERAL NEWER MODELS FOR THE RECONSTRUCTED Ir (110)-(1X2) SURFACE

### Permalink

<https://escholarship.org/uc/item/5bz7f705>

### Authors

Chan, CM.

Hove, M.A. Van

### Publication Date

1984-11-01



# Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

## Materials & Molecular Research Division

RECEIVED  
LAWRENCE  
BERKELEY LABORATORY

JAN 7 1985

LIBRARY AND  
DOCUMENTS SECTION

Submitted to Surface Science

A COMPARISON OF THE MISSING-ROW MODEL AND  
SEVERAL NEWER MODELS FOR THE RECONSTRUCTED  
Ir (110)-(1x2) SURFACE

C.-M. Chan and M.A. Van Hove

November 1984

**For Reference**

Not to be taken from this room



LBL-18667  
c.1

## **DISCLAIMER**

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

A Comparison of the Missing-Row Model  
and Several Newer Models for the  
Reconstructed Ir (110)-(1X2) Surface

by

C.-M. Chan  
Corporate Technology  
Raychem Corporation  
300 Constitution Drive  
Menlo Park, CA 94025

and

M. A. Van Hove  
Materials and Molecular Research Division  
Lawrence Berkeley Laboratory  
and  
Department of Chemistry  
University of California  
Berkeley, CA 94720

Submitted to Letters in Surface Science  
November, 1984

Abstract

The structure of reconstructed Ir(110)-(1X2) is reanalyzed by Low-Energy Electron Diffraction. In addition to wider variations of the missing-row model, the Bonzel-Ferrer (sawtooth) model and related structures are examined. The missing-row model remains the favorite, virtually unchanged in all respects from an earlier LEED study. But the sawtooth model cannot be excluded as a possible structure.

Much work has been performed on the structure of the (1X2) reconstructions of the clean Ir, Pt and Au(110) surfaces, which are believed to be mutually similar. Several models have been discussed, foremost of which is the missing-row model, cf. Figure 1. Also prominent is the "sawtooth" model of Bonzel and Ferrer (1), cf. Figure 2. Early LEED work on Ir(110) (2, 3) clearly favored the missing-row model over several other models, but did not consider the sawtooth model, which was proposed later. LEED analyses of the (1X2) reconstructions of Pt(110) (4, 5) and Au(110) (6, 7) were, however, inconclusive; some of these analyses included the sawtooth model (5, 7). The missing-row model has been clearly favored by a number of other techniques; namely, for Ir(110), Field Ion Microscopy (8), and for Au(110), X-ray diffraction (9), Scanning Tunneling Microscopy (10), High-Resolution Electron Microscopy (11) and High-Energy Ion Scattering (12). Atom diffraction done on Pt(110) cannot easily distinguish between the missing-row and the sawtooth models, but rules out many other models (13, 15). Total-energy calculations do strongly favor the missing-row model over the sawtooth model for Ir(110) (16), Pt(110) (16) and Au(110) (16, 17).

The theory-experiment agreement in the previous LEED study (2, 3) for Ir(110)-(1X2) was far superior to the case of Pt(110) (4, 5) and Au(110) (6, 7). Also, good theory-experiment agreement was obtained (18) for Ir(110)-c(2X2)0. Therefore, the Ir(110) surface presents the most favorable case for solving the structure by LEED. Since our previous work (2, 3) did not consider the sawtooth model or large relaxations within the missing-row model (large expansions are suggested by results on Au(110) (9, 11, 12)), we here extend the LEED study for Ir(110) to these structures. At the same time, we consider a few alternate models inspired by the sawtooth model; namely, the "hollow-on-facet" and "ridge" models, defined below.

In the missing-row model shown in Figure 1, we vary the two topmost layer spacings and the lateral position of the second-layer atoms (while maintaining two mirror planes perpendicular to the surface). In the sawtooth model shown by position A in Figure 2, the geometrical position of the top-layer atom is varied in two different schemes as indicated by  $A_1$  and  $A_2$  in Table 1. In the  $A_1$ -sawtooth model, the top-layer atom is moved perpendicularly to the (110) surface while remaining directly over a third-layer atom. In the  $A_2$ -sawtooth model, the top-layer atom is moved perpendicularly to the (111) facet over a hollow site formed by two second-layer atoms and one third-layer atom. The hollow-on-facet model, as indicated by position B in Figure 2, is similar to the  $A_2$ -sawtooth model, but uses a different hollow site on the (111) facets: the top-layer atom moves perpendicularly to the (111) facet over a hollow site formed by one second-layer atom and two third-layer atoms. In the ridge model, as indicated by

position C in Figure 2, the top-layer atom is located on a bridged site of the ridge. A detailed summary of the geometrical parameters used in the different models is presented in Table 1.

We have used the same set of experimental LEED I-V curves, theoretical methods and non-structural parameters as in our previous work (2, 3). However, this time, five R-factors and their average are used, which include the Zanazzi-Jona R-factor used previously and the Pendry R-factor. These are the R-factors ROS, R1, R2, RRZJ and RPE which were already applied in a number of LEED analyses (19). Our structural selection is based on minimizing the average over the five R-factors.

The best five R-factor averages for each model are summarized in Table 2. The missing-row model with a topmost interlayer spacing of  $1.20 \pm 0.10$  Å and a bulk-like second layer (and an inner potential of 9 eV) is the best model among all those we have considered (this spacing corresponds to a  $12 \pm 5\%$  contraction relative to the bulk interlayer spacing of 1.3585 Å). These optimum parameter values are nearly identical to our previous published results (2, 3). However, there remains considerable room for improvement. On the other hand, the sawtooth model of Bonzel and Ferrer performs nearly as well and thus we are not able to rule out this model. The Zanazzi-Jona, Pendry and 5-R-factor-average values are 0.30, 0.66 and 0.29 for our best missing-row model, and 0.32, 0.56 and 0.31 for our best sawtooth model, respectively. By contrast, the hollow-on-facet and ridge models are much worse. Averaged R-factor contour plots are presented in Figures 3 and 4 for the missing-row and sawtooth models, respectively, to illustrate the sensitivity to the main structural parameters.

In conclusion, the missing-row model remains the most likely for Ir(110)-(1X2) based on LEED. But we cannot exclude the sawtooth model for Ir(110). Also, we see no evidence for a large top-layer expansion ( $\sim 0.5\text{\AA}$ ) in the missing-row model for Ir(110), contrary to such conclusions for Au(110) obtained with other techniques (9, 11, 12). In addition, parallel displacement greater than  $0.2\text{\AA}$  in the second layer is not observed.



REFERENCES

1. H. P. Bonzel and S. Ferrer, Surface Sci. 118, L263 (1982).
2. C.-M. Chan, M. A. Van Hove, W. H. Weinberg, and E. D. Williams, Solid State Commun. 30, 47 (1979).
3. C.-M. Chan, M. A. Van Hove, W. H. Weinberg, and E. D. Williams, Surface Sci. 91, 440 (1980).
4. D. L. Adams, H. B. Nielsen, M.A. Van Hove and A. Ignatiev, Surface Sci. 104, 47 (1981).
5. K. Müller, private communication.
6. W. Moritz and D. Wolf, Surface Sci. 88, L29 (1979); J. R. Noonan and H. L. Davis, J. Vac. Sci. Technol. 16, 587 (1979).
7. H. L. Davis, private communication.
8. J. D. Wrigley and G. Ehrlich, Phys. Rev. Letters 44, 661 (1980).
9. I. K. Robinson, Phys. Rev. Letters 50, 1145 (1983).
10. G. Binnig, H. Rohrer, Ch. Gerber, and E. Weibel, Surface Sci. 131, L379 (1983).
11. L. D. Marks, Phys. Rev. Letters 51, 1000 (1983).
12. S. H. Overbury, W. Heiland, D. M. Zehner, S. Datz and R. S. Thoe, Surface Sci. 109, 238 (1981); Y. Kuk, L. C. Feldman and I. K. Robinson, Surface Sci. 138, L168 (1984).
13. K. H. Rieder, T. Engel and N. Garcia, Proc. 4th ICSS - 3rd ECOSS, Suppl. "Le Vide Les Couches Minces" No. 201, p. 861 (1980).
14. M. Manninen, J. K. Norskov and C. Omrigar, Surface Sci. 119, L393 (1982).
15. A. M. Lahee, W. Allison, R. F. Willis, K. H. Rieder, Surface Sci. 126, 654 (1983).
16. D. Tomanek, H. J. Brocksch and K. H. Bennemann, Surface Sci. 138, L129 (1984); H. J. Brocksch and K. H. Bennemann, in Proc. First International Conference on the Structure of Surfaces, "The Structure of Surfaces" eds. S. Y. Tong and M. A. Van Hove, Springer Series in Chem. Phys. Vol XX (1985), p. xxx.
17. T. Takai, T. Halicioglu and W. A. Tiller, First International Conference on the Structure of Surfaces, University of California, Berkeley, L6 (1984).

REFERENCES (continued)

18. C.-M. Chan, K. L. Luke, M. A. Van Hove, W. H. Weinberg and S. P. Withrow, *Surface Sci.* 78, 386 (1978).
19. M. A. Van Hove and R. J. Koestner, *Proc. Conf. on Determination of Surface Structure by LEED*, Plenum Press (New York) 1984; R. J. Koestner, M. A. Van Hove and G. A. Somorjai, *Surface Sci.* 107, 439 (1981).

Table 1: Summary of the Geometrical Parameters Used in Different Models

<u>Model*</u>	<u>Range of Geometrical Variables, Å</u>	<u>Increment in the Variables, Å</u>
Missing-row	$d_1 = 0.6585$ to $1.9885$	0.07
Missing-row with row pairing	$d_1 = 0.8585$ to $1.7585$	0.1
	$d_2 = 0.8585$ to $1.7585$	0.1
	$\frac{\beta}{2} = 1.5212$ to $2.7212$	0.2
$A_1$ Sawtooth	$d_1 = 1.1485$ to $1.4985$	0.07
	$d_2 = 1.0788$ to $1.6385$	0.07
$A_2$ Sawtooth	$\ell = 2.3094$ to $3.1925$	0.07
	$d_2 = 1.0788$ to $1.6385$	0.07
B Hollow-on-Facet	$\ell = 2.3094$ to $3.1925$	0.07
C Ridge	$d_1 = 0.6585$ to $1.9885$	0.07

$A_1$  = The top-layer atom is sitting on top of a third-layer atom.

$A_2$  = The top-layer atom is sitting in a hollow site perpendicularly to the (111) facet formed by two second-layer atoms and one third-layer atom.

B = The top-layer atom is sitting in a hollow site perpendicularly to the (111) facet formed by one second-layer atom and two third-layer atoms.

C = The top-layer atom is sitting on the short-bridged site of the ridge.

$d_1$  = The spacing between the first and second layers of atoms.

$d_2$  = The spacing between the second and third layers of atoms.

$\beta$  = The change in inter-row spacing in the second layer of atoms, referred to the bulk.

$\ell$  = The bond length between atoms in the top layer and atoms in the nearest (111) facet.

\*(See Figures 1 and 2)

Table 2: A Summary of the R-Factor Analysis

<u>Model</u>	<u>Geometrical Parameters, Å</u>	<u><math>V_0</math>, eV</u>	<u>Averaged R-Factor</u>
Missing-row	$d_1 = 1.2007$	9	0.2829
Missing-row with row pairing	$d_1 = 1.1772$ $d_2 = 1.3585$ $\frac{\beta}{2} = 1.9212$	10	0.2872 (see Figure 3)
$A_1$ Sawtooth	$d_1 = 1.1485$ $d_2 = 1.4285$	10	0.3125
$A_2$ Sawtooth	$d_1 = 1.1505$ $y = 0.0000$ $z = 1.7740$ $d_2 = 1.4285$	10	0.3069 (see Figure 4)
B Hollow-on-Facet	$d_1 = 1.1060$ $y = 0.0000$ $z = 2.7033$	4	0.3768
C Ridge	$d_1 = 1.4285$	6	0.3920

FIGURE CAPTIONS

Figure 1 (a), (b) Top and side views of a hard-sphere representation of the missing-row model.

(c) The geometrical parameters used in the missing-row model where  $a = 3.84\text{\AA}$  is the bulk-like spacing between rows of atoms in the [001] crystallographic direction.

Figure 2 (a) Top view of a hard-sphere representation of several models. Site A is the sawtooth model; Site B is the hollow-on-facet model; and Site C is the ridged model.


(b) The corresponding <sup>side</sup> view of (a).

Figure 3 Contour plot of the average of five R-factors as a function of  $d_1$  and  $d_2$  for the missing-row model with  $\beta = 3.8424\text{\AA}$ .

Figure 4 Contour plot of the average of five R-factors as a function of  $\lambda$  and  $d_2$  for the  $A_2$ -sawtooth model.



(a)

**TOP VIEW**

(b)


**SIDE VIEW**

Figure 2




Figure 3






Figure 4

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT  
LAWRENCE BERKELEY LABORATORY  
UNIVERSITY OF CALIFORNIA  
BERKELEY, CALIFORNIA 94720