

Lawrence Berkeley National Laboratory

LBL Publications

Title

Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench: I. Ag/Bi₂Sr₂CaCu₂O_x multifilament round wires

Permalink

<https://escholarship.org/uc/item/6xw8d1w2>

Journal

Superconductor Science and Technology, 30(2)

ISSN

0953-2048

Authors

Ye, Liyang
Li, Pei
Jaroszynski, Jan
[et al.](#)

Publication Date

2017-02-01

DOI

10.1088/0953-2048/30/2/025005

Peer reviewed

PAPER

Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench: I. Ag/Bi₂Sr₂CaCu₂O_x multifilament round wires

To cite this article: Liyang Ye *et al* 2017 *Supercond. Sci. Technol.* **30** 025005

Manuscript version: Accepted Manuscript

Accepted Manuscript is “the version of the article accepted for publication including all changes made as a result of the peer review process, and which may also include the addition to the article by IOP Publishing of a header, an article ID, a cover sheet and/or an ‘Accepted Manuscript’ watermark, but excluding any other editing, typesetting or other changes made by IOP Publishing and/or its licensors”

This Accepted Manuscript is © © 2016 IOP Publishing Ltd.

During the embargo period (the 12 month period from the publication of the Version of Record of this article), the Accepted Manuscript is fully protected by copyright and cannot be reused or reposted elsewhere.

As the Version of Record of this article is going to be / has been published on a subscription basis, this Accepted Manuscript is available for reuse under a CC BY-NC-ND 3.0 licence after the 12 month embargo period.

After the embargo period, everyone is permitted to use copy and redistribute this article for non-commercial purposes only, provided that they adhere to all the terms of the licence <https://creativecommons.org/licenses/by-nc-nd/3.0>

Although reasonable endeavours have been taken to obtain all necessary permissions from third parties to include their copyrighted content within this article, their full citation and copyright line may not be present in this Accepted Manuscript version. Before using any content from this article, please refer to the Version of Record on IOPscience once published for full citation and copyright details, as permissions will likely be required. All third party content is fully copyright protected, unless specifically stated otherwise in the figure caption in the Version of Record.

View the [article online](#) for updates and enhancements.

Strain control of composite superconductors to prevent degradation of superconducting magnets due to a quench. I. Ag/Bi₂Sr₂CaCu₂O_x multifilament round wires

Liyang Ye^{1,2,3}, Pei Li¹, Jan Jaroszynski⁴, Justin Schwartz³, Tengming Shen^{1,2,*}

¹ Fermi National Accelerator Laboratory, Batavia, IL 60510, USA

² Lawrence Berkeley National Laboratory, Berkeley, CA 94720, USA

³ Department of Materials Science and Engineering, North Carolina State University, Raleigh, NC 27695, USA

⁴ National High Magnetic Field Laboratory, Florida State University, Tallahassee FL 32310, USA

*Email: tshen@lbl.gov

Abstract

The critical current of many practical superconductors is sensitive to strain, and this sensitivity is exacerbated during a quench that induces a peak local strain which can be fatal to superconducting magnets. Here, a new method is introduced to quantify the influence of the conductor stress and strain state during normal operation on the margin to degradation during a quench, as measured by the maximum allowable hot spot temperature $T_{\text{allowable}}$, for composite wires within superconducting magnets. The first conductor examined is Ag-sheathed Bi₂Sr₂CaCu₂O_x round wire carrying high engineering critical current density, J_E , of 550 A/mm² at 4.2 K and 15 T. The critical axial tensile stress of this conductor is determined to be 150 MPa and, in the absence of Lorentz forces, $T_{\text{allowable}}$ is greater than 450 K. With increasing axial tensile stress, σ_a , however, $T_{\text{allowable}}$ decreases nonlinearly, dropping to 280 K for $\sigma_a = 120$ MPa and to 160 K for $\sigma_a = 145$ MPa. $T_{\text{allowable}}(\sigma_a)$ is shown to be nonlinear and independent of magnetic field from 15 T to 30 T. $T_{\text{allowable}}(\sigma_a)$ dictates the balance between magnetic field generation, which increases with the magnet operating current and stress, and the safety margin, which decreases with decreasing $T_{\text{allowable}}$, and therefore has important engineering value. It is also shown that $T_{\text{allowable}}(\sigma_a)$ can be predicted accurately by a general strain model, showing that strain control is the key to preventing degradation of superconductors during a quench.

Introduction

In the last two decades, several superconductors including Cu/N₃Sn wires, Ag/Bi₂Sr₂CaCu₂O_x (Bi-2212) wires, Ag/Bi₂Sr₂Ca₂Cu₃O_x (Bi-2223) tapes, MgB₂ tapes and wires, and REBCO coated conductors have seen significant advances in terms of record critical current density and lengths produced. These advances have fueled many research activities to build powerful superconducting magnets, such as a 3 T, 20 K cryocooled MRI magnet [1], a 28 T solenoid magnet with an insert made using high-temperature superconductors [2], a 26 T all REBCO magnet [3], and a 32 T all superconducting magnet system [4]. With several of these record-achieving systems having been degraded due to quenches, it has become increasingly clear that quench protection is a central issue [5].

A central strategy to building magnets safe from quenches using these conductors is to obtain a fundamental understanding of failure mechanisms of superconductors during a quench. An important practical question along this line is whether quench-induced critical current degradation is driven by strain. Each of these conductors (Nb₃Sn, Bi-2212, Bi-2223, MgB₂, and REBCO) is known to be strain sensitive, and therefore if quench degradation is due to strain, then there is an intrinsic design trade-off between the operating strain, which is due to Lorentz forces and strain associated with magnet manufacturing and cool-down, and the temperature margin during a quench. The question becomes particularly important for high field superconducting magnets, for which the Lorentz forces are particularly large.

Here we introduce a new method to quantify the influence of the conductor stress and strain state during normal operation on the margin to degradation during a quench for composite superconducting wires and apply it to a high current Bi-2212 wire. This method utilizes spiral wound coils on mandrels to determine the critical current of a superconducting wire as well as measure its critical axial tensile stress and simulate a quench with a large current in high magnetic field and an axial stress on the conductor approaching to the critical stress.

Methods

Sample preparation and critical current measurement

Samples are commercial powder-in-tube Ag/Bi-2212 round wires (diameter = 0.8 mm, 37 x 18 filaments (18 bundles, each of which has 37 filaments) (Figure 1), filament diameter ≈ 20 μm, the

1
2
3 area ratio Ag:Ag-0.2 wt.% Mg:Bi-2212 = 0.5:0.25:0.25 in which Ag-0.2 wt.% Mg is an oxide-dispersion
4 strengthened alloy) that are available in a single piece of 2.5 km from industry (e.g. the Oxford
5 Superconducting Technology, New Jersey) [6]. High critical current density (J_c) was obtained using a
6 recently developed overpressure partial melt processing (4% oxygen and balance argon, total
7 pressure = 25 bar, oxygen partial pressure = 1 bar) [7,8]. High gas pressure during the heat
8 treatment densifies wires through silver creep and increases the Bi-2212 filament density from ~75%
9 to >92% [9]. A 1 m of such wire is wound on an alumina barrel with spiral grooves (32 mm diameter,
10 3.175 mm pitch length). The barrel design is similar to those used for measuring critical current (I_c)
11 of ITER Nb-Ti and ITER Nb₃Sn strands [10]. The spiral coil was heat treated and after the heat
12 treatment, the sample was transferred to a G-10 barrel with matching grooves for I_c measurements
13 and quench experiments. The critical current was determined using a standard four-point resistive
14 measurement technique with an electric field criterion of 1 $\mu\text{V}/\text{cm}$ at 4.2 K and in magnetic fields up
15 to 31 T. The n -value, the resistive transition index, was obtained by fitting the electrical field –
16 current (E - I) curve around $E=0.1$ - $1 \mu\text{V}/\text{cm}$. The magnetic field was applied parallel to the central axis
17 of the barrel and thus perpendicular to the wire. During I_c measurements, the transport current is
18 oriented such that the Lorentz force pushes the wire inward so that it is supported by the G-10
19 barrel and experiences zero hoop stress.
20
21
22
23
24
25
26
27
28
29
30
31
32

33 *Determining the critical axial tensile stress using hoop stress*

34
35 The critical axial stress at which I_c degrades irreversibly is an important engineering parameter and
36 was determined using the spiral coil as follows. A hoop stress σ_h was induced using a transport
37 current oriented such that the Lorentz force was outward away from the G-10 barrel ($\sigma_h = B Jr$,
38 where J is the current density averaged over the entire wire cross-section and r the radius of the
39 spiral.). The transport critical current was re-measured after applying the hoop stress.
40
41
42
43
44

45 *Determining the maximum allowable temperature during a quench, $T_{\text{allowable}}$, with increasing axial* 46 *stress σ_a*

47
48 The spiral coil geometry lends itself well to simulating a quench with a large current in high magnetic
49 field and thus large Lorentz forces. This is accomplished by applying a controlled hoop stress and
50 initiating a quench using a heater, similar to previous studies on short straight samples [11] and coils
51 [12]. The heater is an epoxy spot heater (Ecobond 60L) designed for triggering small normal zones
52 and it is also easy to mount onto the sample. The normal zone evolution was monitored via
53 thermocouples (E-type, AWG32) and voltage taps around the hot zone. The hot spot temperature
54
55
56
57
58
59
60

was obtained by cross-examining the measured resistivity of the hot zone with the temperature dependence of Bi-2212 wire resistivity [13] and verified by thermocouples. Samples were quenched with raising hot spot temperature incrementally, beginning around 50 K, and after each quench, the I_c of the sample was re-measured with zero hoop stress. The safety margin was measured using the maximum allowable hot spot temperature $T_{\text{allowable}}$ during a quench, which is defined as the hot spot temperature at which I_c of the wire degrades by 5%. The simplification of quench degradation limit to $T_{\text{allowable}}$ is warranted by our earlier findings that the maximum hot spot temperature T_{max} correlates well with J_c degradation induced by a quench for a large pool of Bi-2212 wires and that the degradation is strain driven [11]. This experiment is representative of quenches in high-field magnets whereas prior quench experiments were performed either without electromagnetic stresses [11] or unknown (and well below 80 MPa) stresses in an epoxy impregnated coil [12,14].

Results

$J_c(B)$ and tensile axial stress limit

Figure 1 shows the 4.2 K engineering current density (J_E) and n -value as a function of magnetic field up to 30 T for our sample. The sample carries an exceptional J_E of 550 A/mm² at 4.2 K and 15 T. Figure 2 depicts the results of a critical axial stress measurement at 4.2 K and 15 T. I_c is constant with increasing the hoop stress till 150 MPa, at which irreversible reductions in both I_c (5%) and n -value are observed. The decrease in n -value indicates that irreversible damages is mechanical and likely caused by filament cracking. The results are consistent with the axial strain dependence of J_c for Ag-Ag-alloy/Bi-2212 wires shown in the Figure 1 inset: J_c is reversible with increasing tensile strain to an irreversible strain limit (ε_{irr}) ranging from 0.45% to 0.6% [15-19], where J_c starts to degrade irreversibly likely because filament breakage becomes significant. This hoop stress technique was used to determine the stress limit of the high-strength Ag/Bi-2223 tape manufactured by Sumitomo Electric and was shown to produce trustable results [20,21].

$T_{\text{allowable}}(\sigma_a)$ in magnetic field up to 30 T

Figure 3 shows how I_c of the Bi-2212 coil evolves due to a series of quenches with increasing T_{max} . Note that at 4.2 K, self field, when $\sigma_h = 0$, the $T_{\text{allowable}}$ is greater than 450 K (Figure 3). The dependence of I_c on the T_{max} at a constant axial tensile stress σ_a (hoop stress) is determined; one example is presented in Figure 4. The wire carries an I_c of 262 A at 4.2 K, 15 T and survives a quench with $T_{\text{max}} = 330$ K with the Lorentz force pointing inward. The next nine quenches were conducted

with a hoop stress of 120 MPa applied and $T_{\text{allowable}}$ drops to 280 K. The hoop stress is then increased to 145 MPa and $T_{\text{allowable}}$ decreases further to 160 K.

We perform experiments similar to that presented in Figure 4 in magnetic fields ranging from 20 T to 30 T using a 31 T high-field resistive magnet facility at the National High Magnetic Field Laboratory (NHMFL). These experiments generate a coherent relationship between $T_{\text{allowable}}$ and the applied axial tensile stress, graphed in Figure 5, which is independent of magnetic field. The relationship is highly nonlinear; $T_{\text{allowable}}$ decreases only from 450 K to 280 K with increasing the stress from zero to 120 MPa, but then decreases quickly to below 160 K for a stress of 145 MPa.

Analysis and discussion

Now we attempt to provide a mathematical description of $T_{\text{allowable}}$ as a function of only σ_a . Fundamental to our analysis is the assumption that quench induced I_c degradation is strain driven. In composite superconducting wires the total strain of superconductor filaments in a composite superconductors, ϵ_t , during a quench can be described as

$$\epsilon_t = \epsilon_0 + \epsilon_s + \epsilon_q \quad (1)$$

where ϵ_0 is the strain on the superconductor filaments due to bending and cool-down, ϵ_s the strain from Lorentz forces, and ϵ_q the axial tensile strain from differential thermal expansion between the entire wire and the superconductor filaments during the temperature rise during the quench. ϵ_s results from the operational axial stress σ_a , an important parameter used for magnet design, through $\epsilon_s = f(\sigma_a)$, the inverted stress - strain relationship of the wires [18,22]. We assume that ϵ_q relates to T_{max} only and does not relate to either dT_{max}/dt or dT_{max}/dx . In the case of Ag/Bi-2212 wires, ϵ_q in the Bi2212 filaments can be appropriated by

$$\epsilon_q|_{\text{Bi2212 filaments}} = \Delta L/L_{T_{\text{max}}-4.2K}|_{\text{wire}} - \Delta L/L_{T_{\text{max}}-4.2K}|_{\text{Bi2212 filaments}} \quad (2)$$

where $\Delta L/L_{T_{\text{max}}-4.2K}|_{\text{wire}}$ and $\Delta L/L_{T_{\text{max}}-4.2K}|_{\text{Bi2212 filaments}}$ the total linear expansion from 4.2 K to T_{max} for the entire wire and the Bi2212 filaments, respectively. Combining equation (1), $\epsilon_s = f(\sigma_a)$, and $\epsilon_q = g(T_{\text{max}})$ and assuming the total strain ϵ_t is equal to the irreversible strain limit ϵ_{irr} , $T_{\text{allowable}}$ is expressed as a single-variable function of σ_a ($T_{\text{allowable}}(\sigma_a)$). For Ag/Bi-2212 wires, the detailed shape of $T_{\text{allowable}}(\sigma_a)$ does not depend on magnetic field because neither their strength nor their $I_c(\epsilon)$ depend on magnetic field. ϵ_t for all experimental cases in Figure 5 were calculated, using the stress and strain data in [22,23] and the $\Delta L/L_{T_{\text{max}}-4.2K}|_{\text{wire}}$ data in [19], and it varies from 0.42%

1
2
3 to 0.55% (Figure 6), consistent with the ε_{irr} of 0.4-0.6% obtained by measurements of the strain
4 dependence of I_c and further validating the strain model.
5
6

7 The decrease of $T_{allowable}$ with increasing σ_a is intuitively not surprising. The detailed shape of
8 $T_{allowable}(\sigma_a)$ is important, however, because it dictates the balance between the field generation
9 efficiency of a magnet, which increases with increasing operating current and stress, and the safety
10 of the magnet, which decreases with decreasing $T_{allowable}$. It is apparent from Figure 5 that if a Bi-
11 2212 magnet is designed to operate at a σ_a of 120 MPa, 80% of the stress limit, with a T_{max} during a
12 quench designed at 300 K, following the conventional wisdoms, the magnet will likely fail during the
13 first quench. Designing a Bi-2212 magnet to work at a stress of >120 MPa (the yielding stress of Bi-
14 2212 wires is about 110 MPa.) will be a significant risk because during the quench protection the hot
15 spot temperature needs to be kept well below 280 K, which is not an easy task considering that the
16 quench detection is not easy due to the slow normal zone propagation and that the hot spot
17 temperature may exceed 100 K before detection [12,14]. Yet this does not rule out operating a Bi-
18 2212 magnet in the stress range from 120 MPa to 150 MPa because upon quench detection, the
19 magnet current is forced to go to zero, thereby reducing σ_a and effectively raising $T_{allowable}$. The fate
20 of the magnets will therefore reside on the competition between the increase of the hot spot
21 temperature and the increase of the $T_{allowable}$. If the hot spot temperature as a function of time,
22 $T_{max}(t)$, exceeds the maximum allowable temperature $T_{allowable}(\sigma_a(t))$, the magnet will degrade like
23 that in [24].
24
25
26
27
28
29
30
31
32
33
34
35
36

37 Note that the detailed shape of $T_{allowable}(\sigma_a)$ depends on the strength of the composite
38 superconductor and the strain dependence of its critical current. The fast decrease of $T_{allowable}$ with
39 increasing σ_a above 120 MPa is a result of the wire starting to plastically deform. Therefore, to
40 increase $T_{allowable}$, one can increase either ε_{irr} or the Young's modulus and/or the yielding stress of the
41 Bi-2212 wire by, for example, using an alternative sheath material such as Ag-Al [25,26].
42
43
44
45

46 Together with our earlier investigation [11], this work confirms that the quench induced I_c
47 degradation in Bi-2212 round wires is driven by axial strain. This conclusion seems to be valid for
48 other strain sensitive, multifilamentary wires including Cu/Nb₃Sn wires, Ag/Bi-2223 tapes with or
49 without metal cladding, and MgB₂ tapes and wires (note that REBCO coated conductor has a
50 multilayered thin film structure that more likely fails due to delamination), and thus provides a
51 simple method for estimating the margin to degradation during a quench for superconductors
52 within high-field magnets quantitatively.
53
54
55
56
57
58
59
60

Conclusions

This work provides an understanding for avoiding catastrophic degradation of composite superconductors within superconducting magnets due to a quench. $T_{\text{allowable}}(\sigma_a)$ has a clear physical significance and engineering values for magnet design. We introduce a method for measuring $T_{\text{allowable}}(\sigma_a)$ and demonstrate its use using high current density Bi-2212 round wires. We further show that $T_{\text{allowable}}(\sigma_a)$ can be estimated using a strain model from the strain dependence of I_c and the stress-strain data of composite superconductors. While the results shown here are derived from Bi-2212 magnets, the insights and the approach developed are generally applicable for other strain-sensitive technical superconductors including Nb₃Sn, MgB₂, Bi-2223, and REBCO coated conductors.

Acknowledgements

This work was funded by the Office of High Energy Physics of the U.S. Department of Energy (DOE) through a US DOE Early Career Award. The work at Fermilab is supported by U.S. DOE through Fermi Research Alliance (DE-AC02-07CH11359), and at the NHMFL by the National Science Foundation (DMR-1157490) and the State of Florida. We greatly appreciated Daniel Assell, Ryan Mahoney, and NHMFL staff for technical support.

REFERENCES

- 1 Terao Y *et al.* 2013 Newly designed 3 T MRI magnet wound with Bi-2223 tape conductors *IEEE Trans. Appl. Supercond.* **23** 4400904-4400904.
- 2 Kajita K *et al.* 2016 Degradation of a REBCO Coil due to cleavage and peeling originating from an electromagnetic force *IEEE Trans. Appl. Supercond.* **26** 1-6.
- 3 Yoon S, Kim J, Lee H, Hahn S and Moon S-H 2016 26 T 35 mm all-GdBa₂Cu₃O_{7-x} multi-width no-insulation superconducting magnet *Supercond. Sci. and Technol.* **29** 04LT04.
- 4 Markiewicz W D *et al.* 2012 Design of a superconducting 32 T magnet with REBCO high field coils *IEEE Trans. Appl. Supercond.* **22** 4300704-4300704.
- 5 Schwartz J *et al.* 2008 High field superconducting solenoids via high temperature superconductors *IEEE Trans. Appl. Supercond.* **18** 70-81.
- 6 Miao H, Marken K R, Meinesz M, Czabaj B and Hong S 2005 Development of round multifilament Bi-2212/Ag wires for high field magnet applications *IEEE Trans. Appl. Supercond.* **15** 2554-2557.
- 7 Larbalestier D *et al.* 2014 Isotropic round-wire multifilament cuprate superconductor for generation of magnetic fields above 30 T *Nat. Mater.* **13** 375.
- 8 Heine K, Tenbrink J and Thoner M 1989 High-field critical current densities in Bi₂Sr₂CaCu₂O_{8+x}/Ag wires *Appl. Phys. Lett.* **55** 2441-2443.
- 9 Shen T, Ghosh A, Cooley L and Jiang J 2013 Role of internal gases and creep of Ag in controlling the critical current density of Ag-sheathed Bi₂Sr₂CaCu₂O_x wires *J. Appl. Phys.* **113** 213901.
- 10 Pong I *et al.* 2012 Worldwide benchmarking of ITER internal tin and NbTi strands test facilities *IEEE Trans. Appl. Supercond.* **22** 4802606-4802606.
- 11 Ye L, Li P, Shen T and Schwartz J 2016 Quench degradation limit of multifilamentary Ag/Bi₂Sr₂CaCu₂O_x round wires *Supercond. Sci. and Technol.* **29** 035010.

- 1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
- 12 Shen T, Ye L, Turrioni D and Li P 2015 High-field quench behavior and dependence of hot spot temperature on quench detection voltage threshold in a $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$ coil *Supercond. Sci. and Technol.* **28** 075014.
- 13 Li P, Ye L, Jiang J and Shen T 2015 RRR and thermal conductivity of Ag and Ag-0.2 wt.% Mg alloy in Ag/Bi-2212 wires *IOP Conf. Ser.: Mater. Sci. Eng.* **102** 012027.
- 14 Shen T, Ye L and Li P 2016 Feasible voltage-tap based quench detection in a Ag/Bi-2212 coil enabled by fast 3D normal zone propagation *Supercond. Sci. and Technol.* **29** 08LT01.
- 15 Cheggour N, Lu X, Holesinger T, Stauffer T, Jiang J and Goodrich L 2012 Reversible effect of strain on transport critical current in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ superconducting wires: a modified descriptive strain model *Supercond. Sci. and Technol.* **25** 015001.
- 16 Godeke A, Hartman M, Mentink M, Jiang J, Matras M, Hellstrom E and Larbalestier D 2015 Critical current of dense Bi-2212 round wires as a function of axial strain *Supercond. Sci. and Technol.* **28** 032001.
- 17 Ten Haken B, Godeke A, Schuver H-J and Ten Kate H H 1996 Descriptive model for the critical current as a function of axial strain in Bi-2212/Ag wires *IEEE Trans. Magn.* **32** 2720-2723.
- 18 Bjoerstad R *et al.* 2015 Strain induced irreversible critical current degradation in highly dense Bi-2212 round wire *Supercond. Sci. and Technol.* **28** 062002.
- 19 Sugano M, Itoh K and Kiyoshi T 2006 Strain dependence of critical current in Bi2212 W&R wires under magnetic field up to 30 T *IEEE Trans. Appl. Supercond.* **16** 1039-1042.
- 20 Miyoshi Y, Kitaguchi H, Chaud X, Debray F, Nishijima G and Tsuchiya Y 2013 Homogeneous performance and strain tolerance of long Bi-2223 HTS conductors under hoop stress *Supercond. Sci. and Technol.* **27** 025003.
- 21 Miyoshi Y, Nishijima G, Kitaguchi H and Chaud X 2015 Hoop stress test on new high strength alloy laminated Bi-2223 conductor *Supercond. Sci. and Technol.* **28** 075013.
- 22 Dai C, Liu B, Qin J, Liu F, Wu Y and Zhou C 2015 The axial tensile stress-strain characterization of Ag-sheathed Bi 2212 round wire *IEEE Trans. Appl. Supercond.* **25** 1-4.
- 23 Wesche R, Fuchs A, Jakob B and Pasztor G 1996 Axial and bending strain effects in Ag and AgNiMg/Bi-2212 wires *Cryogenics* **36** 419-426.
- 24 Terao Y, Ozaki O, Kawashima S, Saito K, Hase T, Kitaguchi H, Sato K-i, Urayama S-i and Fukuyama H 2014 Analysis of an abnormal event in a 3-T MRI magnet wound with Bi-2223 tape conductors *IEEE Trans. Appl. Supercond.* **24** 1-5.
- 25 Kajbafvala A, Nachtrab W, Kumar R, Hunte F, Wong T and Schwartz J 2013 High strength oxide dispersion strengthened silver aluminum alloys optimized for $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ round wire *Supercond. Sci. and Technol.* **26** 125012.
- 26 Kajbafvala A, Nachtrab W, Wong T and Schwartz J 2014 $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ round wires with Ag/Al oxide dispersion strengthened sheaths: microstructure properties relationships, enhanced mechanical behavior and reduced Cu depletion *Supercond. Sci. and Technol.* **27** 095001.

List of Figures

Figure 1: $J_E(B)$ and n -value of the Bi-2212 sample at 4.2 K. The inset shows an optical cross-section of the wire and the strain dependence of I_c of a sister wire (data from [15]).

Figure 2: Dependence of J_E and n -value on the axial tensile stress applied to the Bi-2212 wire determined using the hoop stress test of the spiral coil. The inset depicts the method of applying the axial tensile stress.

Figure 3: Typical quench-induced I_c degradation behavior at 4.2 K, self-field for the spiral coil sample and a straight sample [11], which show similar temperature onset for degradation. The insets show the sample and the instrumentation (heater, voltage taps, and thermocouples) used for initiating a quench and monitoring the normal zone propagation and hot spot temperature.

Figure 4: An example of quench degradation results at 4.2 K, 15 T. Thirteen quenches were performed with this example.

Figure 5: The dependence of maximum allowable temperature limit $T_{\text{allowable}}$ on the axial tensile stresses σ_a . Within the dashed area, $T_{\text{allowable}}$ is less than 280 K and it marks a dangerous area for magnets to operate within.

Figure 6: The total strain of the conductor seen ranges from 0.42% to 0.55%. ϵ_0 is 0.05%. ϵ_q was obtained using the thermal expansion data for Ag/Ag-Cu-Mg/Bi-2212 wire in [19] and the electromagnetic strain was estimated using the 4.2 K stress – strain data for a Ag/Ag-Mg/Bi-2212 wire in [22] and for a Ag/Ag-Ni-Mg/Bi-2212 wire in [23]. The uncertainty with estimating ϵ_s is small at $\sigma_a < \sim 120$ MPa and is significant at $\sigma_a > \sim 120$ MPa where the wire yields.

Figure 1:




Figure 2




Figure 3




Figure 4





Figure 5



1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Figure 6:

