

Lawrence Berkeley National Laboratory

LBL Publications

Title

D7H-Test Results

Permalink

<https://escholarship.org/uc/item/77z1v8dt>

Author

Caspi, S

Publication Date

1982-07-01

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at <https://creativecommons.org/licenses/by/4.0/>



Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

Accelerator & Fusion Research Division

RECEIVED
LAWRENCE
BERKELEY LABORATORY

SEP 30 1982

LIBRARY AND
DOCUMENTS SECTION


D7H-TEST RESULTS

S. Caspi

July 1982

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 6782.*



LBL-14796
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

SUMAG-70
LBL-14796

D7H-Test Results*

S. Caspi

Accelerator and Fusion Research Division
Lawrence Berkeley Laboratory
University of California
Berkeley, California 94720

July 30, 1982

*This work was supported by the Director, Office of Energy Research, Office of High Energy and Nuclear Physics, High Energy Physics Div., U.S. Dept. of Energy, under Contract No. DE-AC03-76SF00098.

D7H-Test Results*

S. Caspi

Data was reduced from the voltage-time relations stored in files D7H001 to D7H090 on HP1000. The I-B calibration curve is included in Fig. 1. The data base is shown in Table 1 and can be used by the 9845B. The data include the quench location, Q₂ layer 1 top, Q₃ layer 1 bottom and the quench current and its normalized value with respect to short sample, I_c = 4920A at 4.4 K, I_c = 6710 A at 1.8 K. The resistance (Ω/cm) was calculated using the propagation time according to the voltage change across the measured sections. The conductor potential length are L_{5,9} = 48.6 cm, L_{6,10} = 17.9 cm, L_{7,11} = 40.6 cm (Fig. 8). The turn to turn velocity V_t was calculated dividing the nominal turn to turn distance (58 mil) by the propagation time (Trans. Time). The quench time T_q was measured from the time the resistive rise starts until the energy extraction system fires. Figures 2-6 are plots of the data base. The time to energy extracton can be estimated as:

$$T_q = \frac{V_0}{2IR'V} \quad (1)$$

where:

V₀ = trip voltage

R' = resistance per unit length

V = velocity

I = current

For a propagation which is axial only. The discontinuity in T_q (Fig. 4) is due to a drop in the propagation velocity when the temperature was

*This work was supported by the Director, Office of Energy Research, Office of High Energy and Nuclear Physics, High Energy Physics Div., U.S. Dept. of Energy, under Contract No. DE-AC03-76SF00098.

lowered from 4.4 K to 1.8 K. Assuming $V_0 = .25$ volt and using I , R , V values from the data base, equation 1 is plotted in Fig 5.

Resistivity

The resistance per unit length at the normal state is plotted in Fig. 6. The values at the magnet ends vary from .9 to $1.3 \mu\Omega/\text{cm}$ between 4000A and 7000 A and the straight section values are about 15 percent higher. For a 23 strand cable at 27 mil strand diameter and 1.8/1 S.C/copper ratio the total copper cross section area is $5.46 \times 10^{-2} \text{ cm}^2$. Assuming all the current had been switched to the copper the resistivity is $4.9 \times 10^{-8} - 7.1 \times 10^{-8} (\Omega \text{ cm})$ and the corresponding resistivity ratio is therefore $\text{RRR} = 35$ to 20.

The alteration of the quench location between the halves of the inner shell is plotted in Fig.7 and the quench origin around the first inner turn is plotted in Fig. 8. All quenches occurred around the first turn! (The only exceptions were very fast ramp rates).

Temperature Rise

After the normal zone propagates through a measured section, its resistance keeps increasing due to a temperature increase. The resistance rise with respect to time is observed to be linear (Fig. 9) in the time scale before the energy extraction. Converting this values to a resistivity rise the results are given in Table 2. A simplified energy balance result in an approximate temperature-time relation.

$$MC \frac{dT}{dt} = I^2 R \quad (2)$$

$$M = \rho_d l A \quad (\rho_d = \text{density, } l = \text{length, } A = \text{crosssection area})$$

$$R = \rho_r l/A \quad (\rho_r = \text{resistivity})$$

The total mass assumes copper only (e.g. no liquid participation).

Equation (2) reduces to

$$c \frac{dT}{dt} = \frac{\rho_r}{\rho_d} \frac{I^2}{A^2}$$

$$\int C dT = \frac{I^2}{A^2} \frac{1}{\rho_d} \int \rho_r dt$$

The experiment shows that $\rho_r = \rho_r(t) = \alpha t$

therefore,

$$\int C dT = \frac{\alpha}{2\rho_d} \left(\frac{It}{A} \right)^2 \quad (3)$$

Equation (3) was solved for 2 nominal cases using $A = 5.46 \times 10^{-10} \text{ cm}^2$;

$$\rho_d = 8.94 \text{ (gr/cm}^3\text{)}$$

1. File = D7H008 (4.4 K)

$$I = 4220 \text{ A};$$

$$\alpha = 1.1 \times 10^{-6} \text{ } \Omega\text{-cm/sec}$$

$$\int C dT = 3.675 \times 10^{-4} \cdot t^2 \text{ (t = msec)}$$

2. File = D7H061 (2.0 K)

$$I = 6340 \text{ A};$$

$$\alpha = 2.46 \times 10^{-6} \text{ } \Omega\text{-cm/sec}$$

$$\int C dT = 1.855 \times 10^{-3} \cdot t^2 \text{ (t = msec)}$$

The result from the two cases using integral values of specific heat for copper are shown in Fig. 10.

Magnet Rate Dependence and Losses

The magnet was ramped at various rates and the quench field recorded. Repeating the test both in the He I and He II result in the relations shown in Fig. 11. The normalized field data were then fitted to a parabolic relation and plotted in Fig. 12.

Using our standard procedure in He II to determine energy losses the average heat flux generated during a cycle is plotted in Fig. 13 for a number of different field rates.

7/22/82 JBR

D-7H
FIELD VS CURRENT

$$B_0 = 0.000915469(A) = 0.012636$$

AMPERES
GEARHEAD CORPORATION
MADE IN U.S.A.




Fig. 1
Field as a function of current







Fig. 2 Axial Velocity



I/I_c

A



Time to Q (ms)

I/I_c

B

Fig. 3: A) Turn to turn velocity; B) Time from initial resistive rise to energy extraction as a function of normalized current.




Fig. 4 Measured time from detection to extraction as a function of current.




Fig. 5 Calculated time to extraction based on Equation 1 using the same data points.





Fig. 6 Resistance per unit length during the transition from the S.C. state to the normal state.




Fig. 7 Quench location variation per half inner shell as a function of storage file.




Fig. 8 Quench location in upper and lower inner shell.




Fig. 9 Normal zone propagation and resistive rise prior to energy extraction.




Fig. 10 Temperature history prior to energy extraction based on equation 3.




Fig. 11 Maximum field as a function of ramp rate.




Fig. 12 Normalized maximum field as a function of ramp rate. The lines are a least fit to the data.




Fig. 13 Magnet loss during cycling around 0-3.85 (T).

FILE NAME	LOCATION	I _q (A)	T _q (ms)	T (K)	I _q /I _c	MICROHM/CM (end)	MICROHM/CM (straight)	V ₅ (m/s)	V ₆ (m/s)	V ₇ (m/s)	V ₉ (m/s)	V ₁₀ (m/s)	V ₁₁ (m/s)	V _t (m/s)	TRANS. TIME (ms)
D7H001		0	0.0	0.00	0.000	0.00	0.00	0.0	0.0	0.0	0.0	0.0	0.0	0.000	0.0
D7H002	03	3444	48.0	4.40	.700	0.00	0.00	0.0	0.0	0.0	0.0	0.0	0.0	.030	38.0
D7H003	03	3603	44.0	4.40	.732	0.00	0.00	0.0	0.0	0.0	0.0	0.0	0.0	.042	35.0
D7H005	02	3021	46.0	4.40	.776	.95	0.00	0.0	9.2	0.0	0.0	0.0	0.0	.077	19.0
D7H006	02	3959	36.0	4.40	.804	.90	0.00	0.0	12.3	0.0	0.0	0.0	0.0	.113	13.0
D7H007	02	4100	34.0	4.40	.833	.80	0.00	0.0	13.4	0.0	0.0	0.0	0.0	.113	13.0
D7H008	02	4220	30.5	4.40	.857	.89	0.00	15.2	12.6	10.6	0.0	0.0	0.0	.122	12.0
D7H009	02	4351	31.0	4.40	.884	.96	0.00	18.2	19.9	20.3	0.0	0.0	0.0	1.470	1.0
D7H010	02	4453	33.5	4.40	.905	.92	0.00	21.0	15.2	24.6	0.0	0.0	0.0	.105	14.0
D7H011	02	4561	31.5	4.40	.927	.96	0.00	25.0	16.7	28.0	0.0	0.0	0.0	.105	14.0
D7H012	02	4650	26.3	4.40	.947	0.00	0.00	27.2	35.0	30.0	0.0	0.0	0.0	.147	10.0
D7H013	02	4742	27.2	4.40	.964	.90	0.00	30.0	21.0	33.3	0.0	0.0	0.0	.117	12.5
D7H014	02	4833	26.0	4.40	.982	.85	0.00	35.2	26.3	34.7	0.0	0.0	0.0	.140	10.5
D7H015	03	4913	14.6	4.40	.998	1.06	0.00	0.0	0.0	0.0	46.0	35.0	45.0	1.130	1.3
D7H016	03	4000	15.0	4.40	.991	1.07	0.00	0.0	0.0	0.0	43.0	47.7	41.0	3.000	.5
D7H017	03	4091	15.0	4.40	.994	1.09	0.00	0.0	0.0	0.0	42.0	30.9	41.4	3.000	.5
D7H018	03	4005	19.0	4.40	.992	.99	0.00	0.0	0.0	0.0	60.7	35.0	59.7	.147	10.0
D7H019	03	4057	19.4	4.40	.987	1.00	0.00	0.0	0.0	0.0	40.0	47.0	0.0	.267	5.5
D7H020	03	4650	22.5	4.40	.945	0.00	0.00	0.0	0.0	0.0	36.0	42.6	0.0	.100	0.0
D7H021	03	4559	24.5	4.40	.926	.82	0.00	0.0	0.0	0.0	36.0	39.7	0.0	.154	9.5
D7H022	03	4564	21.5	4.40	.927	0.00	0.00	0.0	0.0	0.0	34.4	30.0	0.0	.196	7.5
D7H023	03	4370	24.0	4.40	.880	.91	0.00	0.0	0.0	0.0	29.6	33.1	0.0	.173	8.5
D7H040	03	4900	33.3	1.05	.743	1.19	0.00	0.0	0.0	0.0	0.0	11.4	0.0	.004	17.5
D7H042	02	5102	33.0	1.05	.761	0.00	0.00	16.0	0.0	0.0	0.0	0.0	0.0	.090	15.0
D7H043	03	5240	29.5	1.07	.703	0.00	0.00	0.0	0.0	0.0	22.6	0.0	0.0	.109	13.5
D7H044	02	5300	29.5	1.90	.810	0.00	0.00	10.3	0.0	0.0	0.0	0.0	0.0	.122	12.0
D7H045	02	5484	25.7	1.90	.828	1.14	0.00	0.0	16.2	0.0	0.0	0.0	0.0	.140	10.5
D7H046	02	5507	26.7	1.90	.844	1.02	0.00	0.0	10.0	0.0	0.0	0.0	0.0	.163	9.0
D7H047	02	5602	23.0	1.90	.850	1.14	0.00	0.0	59.6	0.0	0.0	0.0	0.0	.210	7.0
D7H048	02	5769	26.5	1.95	.874	0.00	0.00	0.0	15.1	0.0	0.0	0.0	0.0	.122	12.0
D7H049	02	5047	21.3	1.05	.877	1.30	0.00	0.0	32.0	0.0	0.0	0.0	0.0	.267	5.5
D7H050	02	5917	10.7	1.09	.892	0.00	0.00	0.0	99.0	0.0	0.0	0.0	0.0	.267	5.5
D7H052	02	5973	19.3	1.91	.900	1.07	0.00	0.0	20.3	0.0	0.0	0.0	0.0	.470	3.1
D7H053	02	6051	21.7	1.03	.904	1.25	0.00	0.0	17.2	0.0	0.0	0.0	0.0	.137	10.7
D7H054	02	6122	20.5	1.09	.923	1.21	0.00	0.0	10.6	27.0	0.0	0.0	0.0	.147	10.0
D7H055	02	6194	19.1	1.99	.942	1.31	0.00	0.0	19.9	29.0	0.0	0.0	0.0	.163	9.0
D7H050	02	6236	15.0	2.00	.952	1.25	0.00	0.0	24.0	34.7	0.0	0.0	0.0	.204	7.2
D7H060	02	6279	15.0	1.00	.950	0.00	0.00	0.0	24.5	0.0	0.0	0.0	0.0	.590	2.5
D7H061	02	6340	17.0	2.00	.960	1.17	0.00	0.0	22.1	32.5	0.0	0.0	0.0	.173	0.5
D7H062	02	6395	17.2	1.90	.966	1.20	0.00	0.0	21.5	32.5	0.0	0.0	0.0	.173	0.5
D7H063	02	6453	15.0	2.04	.980	1.11	0.00	0.0	24.5	36.9	0.0	0.0	0.0	.210	7.0
D7H064	02	6495	16.0	1.05	.974	1.10	0.00	0.0	23.5	36.2	0.0	0.0	0.0	.173	0.5
D7H065	02	6558	14.5	1.00	.984	1.06	0.00	0.0	27.0	45.0	0.0	0.0	0.0	.226	6.5
D7H066	03	6507	11.0	2.03	.990	1.32	0.00	0.0	0.0	0.0	0.0	29.0	67.0	3.000	.5
D7H067	03	6417	10.5	2.14	.990	1.00	0.00	0.0	0.0	0.0	0.0	32.5	62.5	3.000	.5
D7H068	03	6652	15.0	1.07	.990	1.30	0.00	0.0	0.0	0.0	0.0	20.0	60.0	.196	7.5
D7H069	03	6564	10.5	2.05	.990	1.00	0.00	0.0	0.0	0.0	0.0	35.0	65.0	3.000	.5
D7H070	03	6709	15.0	1.01	.990	0.00	0.00	0.0	0.0	0.0	0.0	0.0	54.0	.196	7.5
D7H071	03	6675	10.3	1.09	.990	1.10	0.00	0.0	0.0	0.0	0.0	36.0	62.0	3.000	.5
D7H072	03	6670	15.5	0.00	.990	0.00	0.00	0.0	0.0	0.0	0.0	0.0	0.0	.210	7.0
D7H073	03	6320	10.5	0.00	.990	0.00	0.00	0.0	0.0	0.0	0.0	0.0	0.0	.103	0.0

Table I. Data base on the 9845B desktop; I_q = quench current; T_q = time from quench detection to energy extraction; I_q/I_c = normalized quench current; Microhm/cm = resistive rise from S.C. state to normal state per unit length; V_i = propagation velocity for section i; V_t = turn to turn velocity; Trans. time = turn to turn propagation time.

File name	Resistivity rise micro_ohm-cm/s	
	end	straight
----- He I -----		
D7H005	1.00	-
D7H006	1.2	-
D7H007	0.97	-
D7H008	1.06	1.13
D7H009	1.21	0.99
D7H010	1.40	1.13
D7H011	1.27	1.23
D7H012	1.40	1.18
D7H013	1.31	1.36
D7H014	1.40	1.33
D7H015	1.34	-
D7H016	1.13	-
D7H017	1.21	1.04
D7H018	1.10	1.15
----- He-II -----		
D7H040	1.43	-
D7H045	1.52	-
D7H046	2.12	-
D7H047	2.12	-
D7H048	2.65	-
D7H049	2.31	-
D7H050	2.13	-
D7H052	1.67	-
D7H053	2.53	-
D7H054	2.71	-
D7H055	2.56	-
D7H058	2.02	-
D7H060	2.34	-
D7H061	2.46	-
D7H062	2.78	-
D7H063	3.11	-
D7H064	3.05	-
D7H065	2.65	-

Table 2 Resistivity per second prior to energy extraction due to temperature rise only.

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720