

Lawrence Berkeley National Laboratory

Recent Work

Title

COAL LIQUEFACTION RESEARCH SEMI ANNUM, REPORT. OCT. 1, 1930 TO MARCH 30, 1981.

Permalink

<https://escholarship.org/uc/item/7m4010h3>

Author

Heinemann, H.

Publication Date

1981-03-01



Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

Materials & Molecular Research Division

COAL LIQUEFACTION RESEARCH
SEMI ANNUAL REPORT
October 1, 1980 to March 30, 1981

Heinz Heinemann

March 1981

RECEIVED
LAWRENCE
BERKELEY LABORATORY

AUG 18 1981

LIBRARY
DOCUMENTS

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 6782*



LBL-12920
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

SEMI ANNUAL REPORT

October 1, 1980, to March 30, 1981

COAL LIQUEFACTION RESEARCH

Principal Investigator: Heinz Heinemann

Lawrence Berkeley Laboratory

University of California

Berkeley, CA 94720

This work was supported by the Assistant Secretary for Fossil Energy, Office of Coal Research, Liquefaction Division of the U. S. Department of Energy under Contract W-7405-Eng-48 through the Pittsburgh Energy Technology Center, Pittsburgh, PA.

This manuscript was printed from originals provided by the author.

PROGRESS REPORT - OCTOBER 1, 1980, to MARCH 30, 1981

Principal Investigator: Heinz Heinemann

Lawrence Berkeley Laboratory

University of California

Berkeley, CA 94720

This project is aimed at examining the differences between Fischer-Tropsch reactions carried out in a slurry reactor on the one hand and in a fixed bed reactor on the other hand. As outlined in our previous report, there are two differences between slurries and fixed beds: 1) in a slurry reactor, less catalyst deactivation is observed, even at low H_2/CO ratios. 2) The product distributions are different: Higher relative amounts of heavy products are produced in the slurry. Both of these differences have been confirmed experimentally. An earlier phase of this project was concerned with temperature control in the reactors. (See report of July 10, 1981). The present phase centers on an investigation of mass transport phenomena. We are engaged in research on two levels: experimental and computational.

A. Experimental work

The experiments have been aimed at measuring mass transfer coefficients and reaction kinetics, which will be used in a model of the slurry reactor. Obtaining data has been difficult, for two mechanical reasons. First, the flow controllers have not been functioning properly, and second, the catalyst tends to cake, and sometimes plug the reactor. Experiments with a glass column, the geometry of which is similar to that of the pressure slurry reactor have led to the design of baffles that break up clumps of catalyst.

The data we have taken allow us to draw some conclusions about the Fischer-Tropsch slurry system. Using the apparatus described in the report of September 26, 1980, the rates of production of CO_2 and hydrocarbons through C_{10} were measured as a function of H_2/CO ratio and temperature. The catalyst was subjected to six days of reduction under 10 atm of hydrogen at a space velocity of 80 $CM^3/min-g$ catalyst. The catalyst loading was .125 of catalyst/g slurry liquid. The data discussed here were taken over a ten-day period. A schedule of the run is shown in Table 1. After the first 50 hours, no deactivation was observed. The data shown were all taken during steady state operation. Table 2 shows rates of production of CO_2 and hydrocarbons through C_{10} as a function of temperature, at $H_2/CO = .96$ and $P = 10$ Atm. If no water is produced, the rate at which carbon is incorporated into hydrocarbons will be equal to the rate of CO_2 production. The total rate of carbon incorporation through C_{10} is shown in the last column in Table 2. If this rate is lower than the rate of CO_2 production, some of the

CO is consumed to make other products. The fate of this CO is not known. It may form surface carbon; it may react with the iron to make iron carbide; it may react with the slurry liquid; or it could make alcohols, which were present in small amounts. It is also possible that the CO is converted to heavier hydrocarbons, which stay in the slurry liquid. If the rate of carbon incorporation into hydrocarbons is greater than the rate of CO₂ production, hydrogen must react on the catalyst surface to produce water. From the numbers in Table 2, it can be seen that at low temperature, water is produced. This is consistent with the equilibrium behavior of the water gas shift reaction: low temperature favors the production of water. (1). As temperature increases, the rate of consumption of CO for other products increases. This is consistent with McKee's (2) data on fixed bed reactors, which showed that carbon formation increased with temperature.

In Figure 1, activation energy plots are shown for CO₂, CH₄, and C₂H₄. All of the curves show activation energies that decrease as temperature increases, although they remain relatively high. (31 K cal for CO₂) This is an indication that mass transfer is starting to affect the rate of reaction. The mass transfer resistance appears to be at the gas-liquid interface: Calculations based on published correlations for k₁a (3) and the measured rate of reaction at 300°C predict a slight concentration difference between the gas-liquid interface and the catalyst surface. Further, calculations based on the measured rate, using the correlation presented by Satterfield (4), show that under the conditions used, the reaction is far from an internal diffusion limited regime.

Figure 2 shows the product distribution as a function of temperature. The changes in product distribution, while not large, are consistent with other work in fixed beds. $\frac{C_n}{C_1}$ for a given n, decreases as temper-

ature increases; light products are favored at high temperature.

Rates of reaction as a function of H₂/CO ratio are shown in Table 3. Again, the total rate of carbon consumption is shown. In every case, a significant amount of CO is reacting to produce something other than C₁ through C₁₀ hydrocarbons. The fraction f of CO that goes to other products is given by $f = 1 - \frac{\sum nR_{cn}}{R_{CO_2}}$

f is not a strong function of H₂/CO; however, as we might expect, f increases as the H₂/CO ratio decreases.

The product distribution as a function of H₂/CO ratio is also shown in Figure 3. As the H₂/CO ratio increases, the curve $\frac{C_n}{C_1}$ vs. n becomes steeper; lighter products are favored.

Note that the rates of reaction at 300°C and H₂/CO = .88 are significantly different from those at H₂/CO = .96 and 300°C. This is believed to result from a higher degree of carburization at H₂/CO = .96. As shown in Table 1, the data at H₂/CO = .88 was taken after a long period of

running at high H_2/CO ratio. The higher value for f at $H_2/CO = .88$ supports this hypothesis: since the catalyst is less carbided, the rate of carbon consumption for carbiding increases.

B. Computational Work

A model for the slurry reactor has been developed, assuming plug flow in the gas, and a well-stirred liquid phase. Such a model gives rise to a differential mass balance equation for each component in the gas phase, an overall balance for the gas phase, and an integral balance for each component in the liquid phase. In the equations presented, all variables are defined in the nomenclature section on page 9.

The gas phase balance is:

$$-\frac{d}{dz} UC_i = k_L a_i \left(\frac{C_i}{H_i} - C_{iL} \right) \quad (1)$$

The overall balance comes from summing equation (1) over all components:

$$-\frac{du}{dz} = \frac{1}{C_{TOT}} \sum_{i=1}^n \frac{k_L a_i}{H_i} (C_i - C_{Li}) \quad (2)$$

The liquid phase balance can be written:

$$Q_L C_{iL} + \int_0^{V_R} R_L a_i \left(\frac{C_i}{H_i} - C_{iL} \right) dV_R - R_i V_R = 0 \quad (3)$$

Rearranging the integral yields:

$$-Q_L C_{iL} + \frac{V_R k_L a_i}{H_i} (\bar{C}_i - C_{iL} H_i) - R_i V_R = 0 \quad (4)$$

where $\bar{C}_i = \frac{1}{L} \int_0^L C_i dz$

these equations are solved in the following manner:

- 1) Guess C_{iL}
- 2) Solve the gas phase mass balances
- 3) Evaluate \bar{C}_i
- 4) Check to see if the liquid balance is satisfied.

5) If not, go to 1) and guess a new C_{iL}

A Fortran program has been written to find this solution, and has been tested on the simple case: $2\text{CO} + 2\text{H}_2 \longrightarrow \text{CO}_2 + \text{CH}_4$, where the reaction is assumed to be first order in H_2 and zero order in CO . The differential equation solvers on file at U.C. is used to solve the gas phase balances, and the regula falsi method is used to iterate C_{iL} . The regula falsi method has been found to converge.

The work proposed in the immediate future remains, for the most part, unchanged. We will continue to look at mass transfer effects, and the extent to which recombination occurs: both can have an effect on deactivation and product distribution. However, the work presented here may indicate that deactivation is different in the slurry reactor, regardless of heat or mass transfer. The presence of the slurry liquid may change the course of the reaction on the catalyst surface.

Table 1

Schedule of the Run Reported Here

<u>Time, Hours</u>	<u>Conditions</u>
0-57	H ₂ /CO = 1.0 T = 300 ^o C
57-76	H ₂ /CO = 1.0 T = 270 ^o C
76-95	H ₂ /CO = 1.0 T = 285 ^o C
95-100	H ₂ /CO = 1.0 T = 320 ^o C
100-121	H ₂ /CO = 1.0 T = 300 ^o C
121-165	H ₂ /CO = 3.0 T = 300 ^o C
165-200	H ₂ /CO = 2.0 T = 300 ^o C
200-213	H ₂ /CO = .88 T = 300 ^o C
213-235	H ₂ /CO = .374 T = 300 ^o C
235-240	H ₂ /CO = 1.0 T = 300 ^o C

TABLE 2

H₂/CO = .96

Rates in moles/min-g catalyst

T	R _{CO₂} x10 ⁴	R _{CH₄} x10 ⁵	R _{C₂} ⁼ x10 ⁵	R _{C₂} x10 ⁶	R _{C₃} ⁼ x10 ⁶	R _{C₃} x10 ⁷	R _{C₄} ⁼ x10 ⁶	R _{C₄} x10 ⁷	R _{C₅} ⁼ x10 ⁶	R _{C₅} x10 ⁷	R _{C₆} ⁼ x10 ⁶	R _{C₆} x10 ⁶	R _{C₇} ⁼ x10 ⁶	R _{C₇} x10 ⁷	R _{C₈} ⁼ x10 ⁶	R _{C₈} x10 ⁷	R _{C₉} ⁼ x10 ⁶	R _{C₉} x10 ⁷	R _{C₁₀} ⁼ x10 ⁶	R _{C₁₀} x10 ⁷	ΣR _n x10 ⁴
270°C	.144	.297	.106	.179	.67	2.15	.51	.787	.357	1.006	.286*	.153	.433	.203	.443	.175	.390	.131	.318	.213	
285°C	.462	.657	.229	.343	-	-	1.275	1.41	.790	1.82	.597*	.427	.827	.427	.820	.399	.907	.302	.663	-	
300°C	.833	1.32	.343	.770	2.53	3.53	2.20	3.09	1.45	2.84	.867*	.774	1.31	.674	1.17	.568	1.12	.414	.812	.780	
320°C	1.70	2.38	.577	1.17	4.53	5.23	2.98	4.06	2.18	3.95	1.15*	1.49	3.07	1.40	2.54	1.12	2.09	.667	1.16	1.28	

*(R₆ + R₆⁼) x 10⁶ R⁼ Denotes Rates of Olefin Formation
 R Denotes Rates of Paraffin Formation

TABLE 3

T = 300°C; Rates in Moles/Min. g Catalyst

H ₂ /CO	R _{CO₂}	R _{CH₄}	R _{C₂} ⁼	R _{C₂}	R _{C₃} ⁼	R _{C₃}	R _{C₄} ⁼	R _{C₄}	R _{C₅} ⁼	R _{C₅}	R _{C₆} ⁼	R _{C₆}	R _{C₇} ⁼	R _{C₇}	R _{C₈} ⁼	R _{C₈}	R _{C₉} ⁼	R _{C₉}	R _{C₁₀} ⁼	R _{C₁₀}	ΣnR _n
	x10 ⁴	x10 ⁵	x10 ⁵	x10 ⁶	x10 ⁶	x10 ⁶	x10 ⁶	x10 ⁶	x10 ⁶	x10 ⁷	x10 ⁶	x10 ⁷	x10 ⁷	x10 ⁷	x10 ⁷	x10 ⁷	x10 ⁷	x10 ⁸	x10 ⁸	x10 ⁸	x10 ⁴
2.953	2.410	3.54	1.00	2.61	9.2	1.45	4.9	1.00	2.75	6.8	1.43	3.38	9.60	2.27	5.57	1.30	2.90	7.43	8.33	1.88	1.62
2.00	2.79	2.84	1.04	2.31	9.17	1.64	4.87	.795	2.94	8.37	1.64	4.38	12.3	2.41	8.03	1.69	5.67	12.90	12.02	2.32	1.66
.881	1.54	1.31	.507	.84	3.60	.577	2.73	.399	2.02	4.33	*1.55		9.10	1.57	6.57	1.10	3.99	7.90	15.7	2.79	.913
.374	.697	.597	.259	.246	1.73	.105	1.44	.125	.930	2.43	*.524		4.10	.620	2.72	.457	1.70	2.79	3.42	.426	.403

*(R_C + R₆⁼)

- (1) Newsome, D. S., Catalysis Reviews - Sci. Eng., 21, 275-318 (1980)
- (2) McKee, W. G., M. S. Thesis, University of California, Berkeley, Department of Chemical Engineering. (1980)
- (3) Kolbel, H., and Ralek, M., Cat. Rev., 21, 225 (1980)
- (4) Satterfield, C., Mass Transfer in Heterogeneous Catalysis, MIT Press, 1970.
- (5) Cannella, W., and Bell, A. T., Unpublished Results.
- (6) Calderbank, P. H., Evans, F., Farley, R., Jepson, G., and Poll, A., Catalysis in Practice, London, Instn. Chem. Engrs. (1963).

NOMENCLATURE

- a Bubble area per reactor volume, cm^{-1}
- C_i Gas phase concentration of component i, moles/cm^3
- C_{iL} Liquid phase concentration of component i, moles/cm^3
- C_T Total gas phase concentration, moles/cm^3
- H_i Henry's law constant for component i, $\frac{(\text{moles}/\text{cm}^3)_{\text{gas}}}{(\text{moles}/\text{cm}^3)_{\text{liquid}}}$
- k_{Li} Mass transfer coefficient for component i
from gas-liquid interface to bulk liquid, cm/sec
- L Height of the reactor, cm
- R_i Rate of consumption of component i per reactor volume, $\text{moles}/\text{sec}\text{-cm}^3$
- Q_L Volumetric flow rate of liquid, cm^3/sec
- V_R Volume of the reactor
- k_i rate constant, $\frac{\text{moles } i}{\text{cm}^3 \text{ sec}} \frac{(\text{moles } \text{H}_2)^{-1}}{\text{cm}^3}$
- z Position in the reactor, cm

ACTIVATION ENERGY PLOT




FIGURE 1

EFFECT OF TEMPERATURE ON PRODUCT DISTRIBUTION




FIGURE 2

XBL 814 - 3770

EFFECT OF H₂/CO RATIO ON PRODUCT DISTRIBUTION




FIGURE 3

XBL 814-3767

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720