Lawrence Berkeley National Laboratory

Recent Work

Title

COMMENT ON VOID FORMATION IN NICKEL AND SILVER DURING CREEP

Permalink

<https://escholarship.org/uc/item/06p8f7h7>

Author

Langdon, T.G.

Publication Date

1967-09-01

cy. I

University of California

Ernest O. Lawrence Radiation Laboratory

COMMENT ON VOID FORMATION
IN NICKEL AND SILVER
DURING CREEP

T. G. Langdon

September 1967

RECEIVED
LAWRENCE
RADIATION LABORATORY

LIBRARY AND
DOCUMENTS SECTION

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

Berkeley, California

UCRL-17821
cy. I

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

UCRL-17821
Preprint

To be submitted to Acta Met.

UNIVERSITY OF CALIFORNIA
Lawrence Radiation Laboratory
Berkeley, California
AEC Contract No. W-7405-eng-48

COMMENT ON VOID FORMATION
IN NICKEL AND SILVER
DURING CREEP

T. G. Langdon

September 1967

COMMENT ON VOID FORMATION IN NICKEL AND SILVER DURING CREEP

In two recent papers, dealing with void formation in nickel¹ and silver² respectively, Price has reached conclusions concerning the role of grain boundary sliding in creep. In nickel,¹ voids were first observed at the start of the secondary stage and it was suggested that primary creep was due to deformation within the grains, and that the transition to secondary creep marked the onset of general grain boundary sliding. However, an examination of the extensive literature on grain boundary sliding suggests that both this view and the contrary suggestion,^{3,4} that sliding accounts for all of the initial deformation until some "critical" strain when slip first occurs, are untenable.

In a number of investigations of the occurrence of grain boundary sliding during creep, measurements have been taken to determine the average displacement ($\bar{v}$) due to sliding, perpendicular to the surface, between adjacent grains, and these values have been plotted against the total creep strain, ϵ_t . If deformation within the grains accounts for all of the strain until the onset of secondary creep, then it follows that these plots should reveal zero displacement throughout the primary stage. In fact, a considerable volume of work on a large number of materials (Al,^{5,6,7} Al alloys,^{5,8} β -brass,⁹ Cd,⁵ Cu,¹⁰ Cu - 0.37%Be,⁵ Fe,⁵ Fe - 30% Ni,¹¹ Mg,¹² Mg - 0.78% Al,^{13,14} Ni,^{15,16,17,18} Pb,¹⁹ Pb - 2.2% Tl,^{19,20} Sn,⁵ and Zn⁵) has shown that, at least initially in primary and the early stages of secondary creep, there is a linear relationship between the average sliding displacement and the creep strain. In some cases a deviation from linearity has been reported, such that the sliding thereafter increases at a slower rate than the total strain, but this

usually occurs towards the end of the secondary stage. Typical results for specimens of a Mg - 0.78% Al alloy are shown in Fig. 1. Four specimens, of different grain size, were tested at 200°C under an initial stress of 6000 psi; full details of the experimental procedure are given elsewhere.¹³ In each case, the transition to secondary creep occurred at a total strain of ~2%. Whilst these results refer to measurements taken on the surface, Graeme-Barber¹⁴ has recently used internal oxide markers to show that similar trends pertain in the interior.

Price¹ attempted to determine the total strain due to grain boundary sliding by considering that the primary deformation, which followed the Andrade $t^{1/3}$ law, represented the deformation due to grain strain, and that the same mode of deformation continued throughout secondary creep. By extrapolation, the grain deformation was determined through the secondary stage, and, knowing the total creep strain, the sliding contribution was calculated by difference. The result suggested that, by the start of tertiary creep, the sliding contribution accounted for almost 50% of the total strain. Unfortunately, an accurate assessment of the sliding contribution is not easy, and a detailed analysis of the methods by which this may be calculated is given elsewhere.²¹ However, the trend deduced by Price is contrary to results reported on a Mg - 0.78% Al alloy,¹³ where a decrease in the importance of grain boundary sliding with increasing strain was inferred from the formation internally of extremely corrugated boundaries during creep. Furthermore, recent results using internal markers have tended to confirm this decrease.¹⁴

This work was supported through the Inorganic Materials Research Division of the Lawrence Radiation Laboratory by the United States Atomic Energy Commission.

REFERENCES

1. C. E. Price, Acta Met. 15, 1249 (1967).
2. C. E. Price, Acta Met. 14, 1781 (1966).
3. V. S. Ivanova, Dokl. Akad. Nauk SSSR 94, (2), 217 (1954).
4. Ya. R. Rauzin and A. R. Zhelezniakova, Fiz. met. metallov. 3, 146 (1956); Metallovedenie i Obrabotka Metallov. (12), 41, (1957).
5. D. McLean and M. H. Farmer, J. Inst. Metals 85, 41 (1956-57).
6. D. McLean, J. Inst. Metals 81, 293 (1952-53).
7. S. S. Gorelik, S. M. Kal'yanova and V. M. Rozenberg, Fiz. met. metallov, 10, (2), 251 (1960).
8. D. McLean and M. H. Farmer, J. Inst. Metals 83, 1 (1954-55).
9. A. Gittins, Ph.D. Thesis, Univ. of Melbourne (1964).
10. D. McLean, N. P. L. Symposium on Creep and Fracture, pp. 73-87, H. M. S. O., London (1956).
11. V. M. Rozenberg, Izvest. Akad. Nauk SSSR, Met. i Topl. (1), 105 (1960).
12. A. Gittins, M. Eng. Sc. Thesis, Univ. of Melbourne (1962).
13. R. L. Bell and T. G. Langdon, J. Materials Science 2, 313 (1967).
14. C. Graeme-Barber, Ph.D. Thesis, Univ. of London (1967).
15. G. Ya. Kozyrsky, V. A. Kononenko and P. N. Okrainets, Ukrain. Fiz. Zhur. 3, (3), 391 (1958).
16. E. A. Minkina, N. V. Preobrazhenskaya and V. M. Rozenberg, Izvest. Akad. Nauk SSSR, Met. i Topl. (2), 48 (1959).
17. V. M. Rozenberg, Fiz. met. metallov. 15, (3), 397 (1963).
18. V. M. Rozenberg, Fiz. met. metallov. 11, (6), 899 (1961).
19. R. C. Gifkins, J. Aust. Inst. Metals 8, 148 (1963).

20. R. C. Gifkins, Properties of Reactor Materials and the Effects of Radiation Damage, (D. J. Littler, ed.), pp. 335-342, Butterworths, London (1961).
21. R. L. Bell, C. Graeme-Barber and T. G. Langdon, Trans Am. Inst. Min. Metall. Engrs. (in press).

FIG 1

Variation of grain boundary sliding with strain
for four different grain sizes

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.