Lawrence Berkeley National Laboratory

Recent Work

Title

ON THE NEED FOR HIGHER GAS PRESSURES TO OBTAIN SURFACE STRUCTURES IN LOW ENERGY ELECTRON DIFFRACTION STUDIES

Permalink

<https://escholarship.org/uc/item/0fv888dx>

Authors

French, T.M.
Morgan, A.E.
Somorjai, G. A.

Publication Date

1970-05-01

c.2

RECEIVED
LAWRENCE
RADIATION LABORATORY

AUG 12 1970

LIBRARY AND
DOCUMENTS SECTION

ON THE NEED FOR HIGHER GAS PRESSURES
TO OBTAIN SURFACE STRUCTURES IN
LOW ENERGY ELECTRON DIFFRACTION STUDIES

T. M. French, A. E. Morgan, and G. A. Somorjai

May 1970

AEC Contract No. W-7405-eng-48

TWO-WEEK LOAN COPY

This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545

25 LAWRENCE RADIATION LABORATORY
UNIVERSITY of CALIFORNIA BERKELEY

UCRL-19642

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

ON THE NEED FOR HIGHER GAS PRESSURES TO OBTAIN
SURFACE STRUCTURES IN LOW ENERGY ELECTRON DIFFRACTION STUDIES

T. M. French, A. E. Morgan and G. A. Somorjai

Department of Chemistry, University of California, and
Inorganic Materials Research Division,
Lawrence Radiation Laboratory,
Berkeley, California 94720

Low energy electron diffraction (LEED) experiments have shown^(1,2) that ordered structures result from the chemisorption of gases on the surfaces of most solids studied so far. These structures are attributable either to an ordered arrangement of the adsorbed species or to a rearrangement of the substrate atoms during chemisorption⁽²⁾. In these experiments, the pressure of the gas, whose chemisorption is a necessary condition for producing the surface structure, is usually in the range of 10^{-9} - 10^{-5} torr. If a lengthy exposure of the surface to the adsorbing gas molecules is required [on account of low sticking probabilities or other chemical considerations] the time of exposure is usually varied rather than increasing the gas pressure. There are several reasons for restricting chemical reaction studies to low pressures in LEED experiments; 1) steady state gas flow conditions can be easily established and maintained by continuous pumping only at low gas fluxes, 2) the purity of the ambient can be better maintained since at higher

pressures there is a substantial backstreaming of unwanted gases from the ion-pump and 3) contamination and subsequent deterioration of the electron gun optics can be minimized.

Oxygen on the (0001) face of $\alpha\text{-Al}_2\text{O}_3$

The structure of the hexagonal (0001) face of aluminum oxide has been studied in several laboratories.^(3,4,5,6,) After heating in vacuum (by electron bombardment or by radiation) at temperatures $\geq 1250^\circ\text{C}$, the surface exhibits a complex structure which indicates a mesh with a unit cell larger by $\sqrt{3}l$ and rotated 9° with respect to the projection of the bulk unit cell to the (0001) surface [Al_2O_3 (0001) - $(\sqrt{3}l \times \sqrt{3}l)R \pm 9^\circ$]. The structure may also be indexed by the transformation matrices for the two equivalent orientations of the unit mesh: $\begin{pmatrix} 11/2 & \sqrt{3}/2 \\ -\sqrt{3}/2 & 11/2 \end{pmatrix}$, $\begin{pmatrix} 11/2 & -\sqrt{3}/2 \\ \sqrt{3}/2 & 11/2 \end{pmatrix}$. It has been reported⁽⁴⁾ that oxygen at pressures $\leq 10^{-5}$ torr has no effect on this surface and produces no new surface structures in the temperature range $25^\circ - 1800^\circ\text{C}$. We have found⁽⁷⁾ that heating the rotated Al_2O_3 (0001) - $(\sqrt{3}l \times \sqrt{3}l)$ surface structure in an ambient of 2×10^{-4} torr oxygen at $1000^\circ\text{C} - 1200^\circ\text{C}$ generates the (1x1) structure, which is the stable low temperature structure in vacuum. The transformation Al_2O_3 (0001) - (1x1) $\rightleftharpoons (\sqrt{3}l \times \sqrt{3}l)R \pm 9^\circ$ is completely reversible. The complex surface structure is stable at high temperatures and can always be produced by heat treatment in vacuum, while the (1x1) surface structure can be regenerated at will in oxygen as long as the oxygen partial pressure is $\geq 2 \times 10^{-4}$ torr.

Hydrogen on the (100) Face of Platinum

The (100) face of platinum exhibits a stable (5x1) surface structure.⁽⁸⁾ Hydrogen, at gas pressures in the range of 10^{-9} - 10^{-6} torr, does not appear to affect the Pt(100) - (5x1) surface in any detectable way over a wide temperature range (25° - 1400°C).⁽⁹⁾ However, if the crystal is heated between 500° - 1000°C in a hydrogen partial pressure greater than 10^{-5} torr, the (5x1) structure is removed and a (2x2) surface structure formed⁽⁹⁾ [Pt(100) - (2x2) - H]. Heating the sample to these temperatures prevents the adsorption of ambient carbon monoxide which would compete with hydrogen for the adsorption sites. The (2x2) surface structure is stable in vacuum. Heating the platinum crystal at 1200°C in vacuo (for a few minutes) is necessary to remove this structure and to restore the (5x1) surface structure. However, heating the crystal at only 500°C in 2×10^{-8} torr of oxygen is sufficient to remove the (2x2) surface structure.

It is apparent that high gas pressures are often necessary to form surface structures of different kinds for several reasons;

a) frequently there is a competition between two adsorbing gases for surface sites and changes in the partial pressures can markedly affect the relative adsorption rates and therefore the subsequent formation of ordered surface structures. For example, carbon monoxide has a great affinity for platinum surfaces and the adsorption of most gases on platinum takes place in competition with the carbon monoxide always present in the ambient of an ultra-high vacuum system.^(8,9) b) The dissociation of a diatomic molecule (H_2 , O_2 , N_2 , etc.) on the solid surface may well be the rate-limiting step in the formation of ordered surface structures.

Increased gas pressures should certainly increase the rate of dissociation.

c) There is evidence that gases dissolved in the bulk of the crystal may play an important role in surface reactions.⁽¹⁰⁾ The formation of certain surface structures (especially during oxidation) may require the presence of gas atoms which have diffused below the surface. Both the solubility and diffusion rate of gases in solids increase with increasing ambient gas pressures.

The question often arises as to how applicable the results of low pressure LEED studies are to industrially important surface reactions which take place at higher pressures. It is apparent that the application of higher pressures in LEED experiments may lead to the formation of new surface structures. Therefore higher pressure LEED experiments should be carried out in order to utilize the obtained structural information in the analysis of the mechanisms of high pressure surface reactions.

Acknowledgement. This work was supported by the United States Atomic Energy Commission.

References

- 1) J. J. Lander, "Advances in Solid State Chemistry," Vol. 2 (MacMillan Co., New York, 1965).
- 2) G. A. Somorjai and H. H. Farrell, Advances in Chemical Physics (to be published).
- 3) J. M. Charig, App. Phys. Letters 10, 139 (1967).
- 4) C. C. Chang, J. App. Phys. 39, 5570 (1968).
- 5) J. M. Charig and D. K. Skinner, Proc. Conf., "The Structure and Chemistry of Solid Surfaces" ed. G. A. Somorjai, pg. 34-1 (Wiley Publ., New York 1969).
- 6) C. C. Chang, Proc. Conf., "The Structure and Chemistry of Solid Surfaces" ed. G. A. Somorjai, pg. 77-1 (Wiley Publ., New York 1969).
- 7) T. M. French and G. A. Somorjai, J. Phys. Chem. (to be published).
- 8) A. E. Morgan and G. A. Somorjai, J. Chem. Phys. 51, 3309 (1969).
- 9) A. E. Morgan and G. A. Somorjai, Surface Science 12, 405 (1968).
- 10) G. E. Moore and F. C. Unterwald, J. Chem. Phys. 48, 5409 (1968).

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or*
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.*

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

TECHNICAL INFORMATION DIVISION
LAWRENCE RADIATION LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720