UC Berkeley

UC Berkeley Previously Published Works

Title

Aromaticity as a Guide to Planarity in Conjugated Molecules and Polymers

Permalink

<https://escholarship.org/uc/item/0hr407z9>

Journal

Journal of Physical Chemistry C, 124(10)

ISSN

1932-7447

Authors

Wood, BM

Forse, AC

Persson, KA

Publication Date

2020-03-12

DOI

10.1021/acs.jpcc.0c01064

Peer reviewed

Aromaticity as a Guide to Planarity in Conjugated Molecules and Polymers

Brandon M. Wood,^{†,‡} Alexander C. Forse,[¶] and Kristin A. Persson^{*,§,‡}

[†]*Graduate Group of Applied Science and Technology, University of California, Berkeley*

[‡]*Energy Technologies Area, Lawrence Berkeley National Lab*

[¶]*Department of Chemistry, University of California, Berkeley*

[§]*Department of Materials Science and Engineering, University of California, Berkeley*

E-mail: kapersson@lbl.gov

Abstract

Conjugated molecules and polymers have the ability to be transformative semiconducting materials; however, to reach their full potential a detailed understanding of the factors governing molecular structure is crucial for establishing design principles for improved materials. Creating planar or “locking” structures is of particular interest for tuning electronic properties. While noncovalent locks are an effective strategy for increasing planarity, the precise interactions leading to these planar structures are often unknown or mischaracterized. In this study, we demonstrate that aromaticity can be used to investigate, interpret, and modify the complex physical interactions which lead to planarity. Furthermore, we clearly illustrate the important role aromaticity has in determining structure through torsional preferences and find that modern noncovalent locks utilize hyperconjugation to alter aromaticity and increase planarity. We envision that our approach and our explanation of prevalent noncovalent locks will assist in the design of improved materials for organic electronics.

Introduction

Organic semiconductors offer unique blends of physical and electronic properties along with the processability and fabrication potential of polymers and small molecules.^{1,2} This combination opens up countless opportunities for new functional materials that can be tailored for specific applications.^{3–6} One successful strategy for tuning molecular properties is adding pendant groups to the conjugated backbone; these “noncovalent locks” control molecular structure by inducing nonbonded interactions.^{7–10} The goal is to create structures that prefer coplanar torsional configurations that maximize electron delocalization across the molecule or polymer (i.e. conjugation),¹¹ and as a result improve electronic properties such as carrier mobility.

While noncovalent locks have proven to be effective at creating planar structures, the exact nature of the interactions leading to planarity remain difficult to disentangle. A few

reports have attempted to isolate and identify the fundamental interactions behind non-covalent locking systems. For instance, Jackson et al. demonstrated that nontraditional hydrogen bonding (i.e. hydrogen bonding that involves less electronegative atoms such as C, S, and Cl) can play a predominant role in stabilizing planar configurations.⁷ Nevertheless, many locking molecules such as 3,4-ethylenedioxythiophene (EDOT) and fluorinated thiophenes—which are utilized in state-of-the-art conjugated molecules and polymers^{12–18}—do not involve nontraditional hydrogen bonding. Conboy et al. confirmed the importance of heteroatom interactions in poly-EDOT (PEDOT) and similar molecules, but stated that a precise description of torsional energetics was unclear and speculated that electrostatics were responsible for the observed planarity.⁹

Aromaticity is a common chemical descriptor that can be used to simplify some of the underlying physics and provide novel insights into torsional energetics. A key objective of this communication is to highlight how the competition between aromaticity and conjugation^{10,19,20} influences planarity in organic electronic materials. We show that the introduction of popular noncovalent locks modifies aromaticity and drives structures towards planarity. Finally, we identify the specific hyperconjugation interaction that alters aromaticity and determines planarity.

Results and Discussion

An illustrative example of the balance between ring aromaticity and conjugation is the torsion potential of bithiophene (BT) (Fig. 1). Dimers provide a computationally efficient and accurate representation of the torsion potential and trends in aromaticity observed in larger conjugated polymers (See SI Section 1)²¹ and hence are used throughout this work. The aromaticity of individual rings is quantified using the multicenter bonding index (MCI),^{22,23} and the nucleus-independent chemical shift (NICS)^{24,25} (see SI Section 2), with both methods producing very similar results. We represent conjugation semi-quantitatively as the

Figure 1: Ring aromaticity, molecular conjugation, and relative energies are plotted as a function of torsion angle for bithiophene (BT) and hydrogenated bithiophene (hBT). Both BT and hBT structures are represented in the 180° (trans) configuration. Aromaticity and conjugation are directly opposed in BT at 180° and the balance between the two driving forces results in a nonplanar torsional minimum around 150°. This key region is highlighted with gray shading. Hydrogenation of the terminal C-C double bonds essentially reduces aromaticity to zero, while preserving conjugation across the two rings. With aromaticity removed in hBT, torsional energetics mirror conjugation and there is a planar minimum at 180°. Aromaticity is defined as the multicenter bonding index (MCI $\times 10^3$) for one C-C-S-C-C thiophene ring. Only one ring is displayed because both BT and hBT are symmetric molecules. Conjugation is quantified as the normalized relative bridge C-C bond length. A value of 1 represents the shortest bond length and the highest conjugation, whereas 0 represents the longest bond and lowest amount of conjugation.

normalized relative bond length of the bridge C-C bond between rings; the rationale being configurations with shorter bridge bonds are more conjugated.^{26,27} Figure 1 (left side) clearly shows that the stabilizing effects of aromaticity and conjugation are in direct competition with one another. This agrees with a simple description based on atomic orbitals, where planar structures (0° cis and 180° trans) exhibit the most p_z -orbital overlap (π -bonding) and afford the most electron delocalization across the molecule. In contrast, the torsioned structure at 90° will exhibit the least electron sharing between rings, and it possesses the highest ring aromaticity or electron delocalization within a ring. The nonplanar global minimum at 150° in the torsion potential appears to reflect the balance between these two driving forces.

To test this hypothesis we removed aromaticity by hydrogenating the terminal C=C

double bonds, leaving intact the conjugation across the rings (right side of Fig. 1). Once aromaticity was removed the torsional energetics essentially mirrored conjugation, and most importantly the global minimum in the torsion potential shifted to the planar 180° configuration. It is noteworthy that the inter-ring $\text{H}\cdots\text{S}$ distance is reduced in hydrogenated bithiophene (hBT) ($2.78\text{\AA}$ in the 180° configuration) compared to BT ($2.93\text{\AA}$ in the 180° configuration), which reduces concern that the 150° torsional minimum in BT is due to steric repulsion between $\text{H}\cdots\text{S}$. This conclusion is supported with through-space calculations (Fig. S8) and noncovalent interaction (NCI) analysis (Fig. S12).^{28,29} Establishing aromaticity as a driving force in torsional energetics is fundamental for understanding structure; additionally, if aromaticity can be modified or controlled it may represent a design opportunity.

Having demonstrated the important role of aromaticity in directing torsion angles, we were motivated to explore the role of aromaticity in known planar systems with noncovalent locks. We discovered that a number of reported noncovalent locks modify aromaticity. As observed in the top of Fig. 2 both 3,3'-difluorobithiophene (F2-BT) and bis-EDOT (BEDOT) exhibit a coplanar torsional minimum at 180° accompanied by a reduction in the aromaticity change between 90° and 180° compared to BT. As expected, conjugation is minimized at 90° and is maximized at 180° , it has been omitted from Fig. 2 for clarity. For torsional energetics the magnitude of aromaticity is less important than the change in aromaticity. For example, if aromaticity is constant across all torsion angles there is no torsional driving force. As a result, we are primarily interested in the change of aromaticity between 90° and 180° because they represent the extrema which generate the torsional driving force that has the largest influence on planarity.

To further investigate the modification of ring aromaticity and its impact on planarity we systematically added fluorine at different positions on one thiophene ring, termed ring 1, within the BT molecule (bottom of Fig. 2) and examined the torsional dependence. We find that ring aromaticity is only altered in a manner that encourages planarity when the F atom is in position 3 near the S atom of the adjacent ring, which we denote as ring 2. The

Figure 2: (Top) Torsional relative energies and aromaticity are plotted for F2-BT and BEDOT. In both systems, the change in aromaticity between 90 and 180° is reduced compared to BT and this corresponds to an energetic minimum near 180°. (Bottom) Ring 1 and ring 2 aromaticities are plotted against torsion angles for BT, 3F-BT, and 4F-BT. Both rings are plotted because 3F-BT and 4F-BT molecules are no longer symmetric. For ring 1 the addition of F—regardless of the position—reduces the magnitude of aromaticity by a constant, but preserves the shape of the BT curve. The ring 2 curves are similar for 4F-BT and BT, however, ring 2 of 3F-BT deviates in shape and aromaticity is altered near 180° similar to the plots in the top of the figure.

aromaticity of ring 1, where F is covalently bonded, is reduced by a constant across all torsion angles regardless of the F atom position. This is consistent with earlier reports that adding halogen substituents to an aromatic ring reduces the overall aromaticity.^{30,31} However, there remains a torsional driving force due to the constant reduction in the aromaticity of ring 1. Clearly, the F atom position is important, as 4F-BT retains a nonplanar energetic minimum around 150°, whereas 3F-BT has a planar minimum at 180°. Together these results indicate that there is an advantageous noncovalent inter-ring interaction between F...S causing a change in aromaticity and promoting planarity.

Using Natural Bonding Orbital (NBO) analysis we identify the key interaction responsible for the modification of aromaticity and for stabilizing the planar 180° configuration (Fig. 3). Our through-space calculations for F···S and O···S indicate that both would be repulsive at the respective relaxed separation distance present in the 180° configuration of F2-BT and BEDOT (see SI Section 3). Thus, it is clear that some other interaction involving X···S is stabilizing the repulsive effects in order for the 180° configuration to be energetically favorable. For both F2-BT and BEDOT, NBO perturbation analyses revealed a 3-center-2-electron interaction between a heteroatom lone pair and a C-S antibonding orbital (σ_{C-S}^*) pictured in the top of Fig. 3. Details on stabilization energies are provided in Section 5 of the SI. Similar interactions have been reported for the association of supramolecules.³² Conboy et al. mentioned this type of interaction as a possible source of attraction in BEDOT-like molecules, but dismissed it due to a lack of bond length correlations across a series of related molecules.⁹

Figure 3: (Top) Isosurface plots of the overlap between C-S antibonding (σ_{C-S}^*) and F or O lone pair (LP) natural bonding orbitals in F2-BT and BEDOT (isovalues ≈ 0.03). The orbital overlap leads to a stabilizing hyperconjugation interaction depicted in between the isosurface plots. (Bottom) The torsion potentials of F2-BT and BEDOT are displayed for ω B97x-D, RHF, and RHF with the σ_{C-S}^* orbital removed. RHF and ω B97x-D are qualitatively similar, both having a minimum at 180°. When the σ_{C-S}^* orbital is deleted from the Fock matrix (using NBO6) the hyperconjugative stabilization is no longer present and without that interaction the molecules are no longer planar.

In order to confirm the importance of the 3-center-2-electron interaction we utilized the NBO deletion method,³³ which has been used previously to deconvolute torsional energetics.³⁴ Because the NBO deletion method necessitates the use of restricted Hartree-Fock (RHF) we recalculated the torsion potentials with RHF to ensure qualitatively similar behavior to the higher level of theory (ω B97x-D). Then using the RHF deletion method, we removed the C-S antibonding orbitals (σ_{C-S}^*) on both rings, which eliminates hyperconjugation. Remarkably, removing hyperconjugation altered the torsional energetics in both F2-BT and BEDOT such that the planar 180° configurations are no longer favorable (as shown in Fig. 3), most likely due to the repulsion that exists. We characterize these as hyperconjugation interactions because they result in electron delocalization across the molecule and there is a history of hyperconjugation impacting torsional energetics.^{34,35} This result, which we found by observing changes in ring aromaticity, provides strong evidence that hyperconjugation is the critical interaction responsible for the locking behavior in these molecules and associated polymers.

Conclusions

Using a novel combination of quantum chemistry techniques, we have demonstrated the power of employing aromaticity as a guide to understanding the complex interactions that give rise to the atomic structure of conjugated molecules and polymers. In general, both aromaticity and conjugation are stabilizing and energetically favorable, yet we have shown that ring aromaticity favors torsioned or nonplanar configurations because it confines delocalized electrons within a ring instead of delocalizing them across the molecule or polymer as preferred by conjugation. We directly quantified the competition between aromaticity and conjugation in an ideal bithiophene system which results in a nonplanar minimum energy structure. Further, we found that the torsional driving force from aromaticity can indeed be beneficially altered through pendant group additions, such as those in state-of-the-art

noncovalent locks F2-BT and BEDOT. To probe the exact nature of this interaction we identified and removed hyperconjugation between a heteroatom (i.e. F and O) lone pair and the C-S antibonding orbital on the adjacent ring, concluding that hyperconjugation is key for the changes in aromaticity and the resulting planarity, contrary to previous work that suggested electrostatic interactions dominate. Our findings, therefore, indicate that aromaticity can serve as a new handle or screen for tuning the structure and the resulting electronic properties of conjugated materials. We anticipate that the structural insights and methods presented here are applicable to a wide range of conjugated molecules and polymers and will open the door to new and unforeseen advances in our ability to design functional organic electronic materials.

Computational Details

All quantum chemistry calculations were performed with Gaussian 16 unless otherwise noted.³⁶ The default level of theory was ω B97x-D with the def2-TZVPP basis set.^{37,38} The general procedure for calculating torsion potentials started with an unconstrained geometry relaxation followed by a frequency calculation to ensure no substantial imaginary frequencies existed. Then the relaxed geometry was rotated around the central C-C bond, fixing the C-C-C-C torsion every 10° for a constrained geometry optimization. An additional torsional constraint was used for hydrogenated calculations (See SI Subsection 6.1). MCI aromaticities were computed with the natural atomic orbital basis from NBO6 for all 5 member (C-C-S-C-C) rings at each torsional geometry using Multiwfn.³⁹ NBO analysis was performed using NBO6.³³ All RHF and RHF NBO orbital deletions were done with Gaussian 09⁴⁰ and NBO6 again using the def2-TZVPP basis set. RHF NBO orbital deletions were single point calculations utilizing relaxed RHF geometries. Isosurface images were made with VMD,⁴¹ and all plotting utilized Matplotlib and cubic spline interpolation via SciPy.⁴²

Supporting Information

- Examination of Different Length Polymer Chains
- Comparison of MCI and NICS Aromaticity Values
- Through-space Calculations
- Noncovalent Interaction Analysis
- NBO Perturbation Analysis
- Expanded Methods
- Tabular Data

Acknowledgement

This work was funded by the U.S. Department of Energy, Office of Science, Office of Basic Energy Sciences, Materials Sciences and Engineering Division under Contract No. DE-AC02-05CH11231 (Materials Project program KC23MP). Additionally, we acknowledge the Molecular Graphics and Computation Facility at the University of California Berkeley Chemistry Department for providing high-performance computational resources (NIH S10OD023532).

References

- (1) Kuei, B.; Gomez, E. D. Chain conformations and phase behavior of conjugated polymers. *Soft Matter* **2017**, *13*, 49–67.
- (2) Swager, T. M. 50th Anniversary Perspective: Conducting/Semiconducting Conjugated Polymers. A Personal Perspective on the Past and the Future. *Macromolecules* **2017**, *50*, 4867–4886.
- (3) Mei, J.; Diao, Y.; Appleton, A. L.; Fang, L.; Bao, Z. Integrated materials design of organic semiconductors for field-effect transistors. *Journal of the American Chemical Society* **2013**, *135*, 6724–6746.

- (4) Muench, S.; Wild, A.; Friebe, C.; Häupler, B.; Janoschka, T.; Schubert, U. S. Polymer-Based Organic Batteries. *Chemical Reviews* **2016**, *116*, 9438–9484.
- (5) Someya, T.; Bao, Z.; Malliaras, G. G. The rise of plastic bioelectronics. *Nature* **2016**, *540*, 379–385.
- (6) Van De Burgt, Y.; Melianas, A.; Keene, S. T.; Malliaras, G.; Salleo, A. Organic electronics for neuromorphic computing. *Nature Electronics* **2018**, *1*, 386–397.
- (7) Jackson, N. E.; Savoie, B. M.; Kohlstedt, K. L.; Olvera de la Cruz, M.; Schatz, G. C.; Chen, L. X.; Ratner, M. A. Controlling Conformations of Conjugated Polymers and Small Molecules: The Role of Nonbonding Interactions. *Journal of the American Chemical Society* **2013**, *135*, 10475–10483.
- (8) Cheng, Y.; Qi, Y.; Tang, Y.; Zheng, C.; Wan, Y.; Huang, W.; Chen, R. Controlling Intramolecular Conformation through Nonbonding Interaction for Soft-Conjugated Materials: Molecular Design and Optoelectronic Properties. *Journal of Physical Chemistry Letters* **2016**, *7*, 3609–3615.
- (9) Conboy, G.; Spencer, H. J.; Angioni, E.; Kanibolotsky, A. L.; Findlay, N. J.; Coles, S. J.; Wilson, C.; Pitak, M. B.; Risko, C. To bend or not to bend - are heteroatom interactions within conjugated molecules effective in dictating conformation and planarity? *Material Horizons* **2016**, *3*, 333–339.
- (10) Huang, H.; Yang, L.; Facchetti, A.; Marks, T. J. Organic and Polymeric Semiconductors Enhanced by Noncovalent Conformational Locks. *Chemical Reviews* **2017**, *117*, 10291–10318.
- (11) Brédas, J. L.; Street, G. B.; Thémans, B.; André, J. M. Organic polymers based on aromatic rings (polyparaphenylene, polypyrrole, polythiophene): Evolution of the electronic properties as a function of the torsion angle between adjacent rings. *The Journal of Chemical Physics* **1985**, *83*, 1323–1329.

- (12) Yum, S.; An, T. K.; Wang, X.; Lee, W.; Uddin, M. A.; Kim, Y. J.; Nguyen, T. L.; Xu, S.; Hwang, S.; Park, C. E. et al. Benzotriazole-containing planar conjugated polymers with noncovalent conformational locks for thermally stable and efficient polymer field-effect transistors. *Chemistry of Materials* **2014**, *26*, 2147–2154.
- (13) Granstrom, M.; Berggren, M.; Inganas, O. Micrometer- and Nanometer-Sized Polymeric Light-Emitting Diodes. *Science* **1995**, *267*, 1479–1481.
- (14) Wijsboom, Y. H.; Sheynin, Y.; Patra, A.; Zamoshchik, N.; Vardimon, R.; Leitun, G.; Bendikov, M. Tuning of electronic properties and rigidity in PEDOT analogs. *Journal of Materials Chemistry* **2011**, *21*, 1368–1372.
- (15) Gao, Y.; Zhang, X.; Tian, H.; Zhang, J.; Yan, D.; Geng, Y.; Wang, F. High Mobility Ambipolar Diketopyrrolopyrrole-Based Conjugated Polymer Synthesized Via Direct Arylation Polycondensation. *Advanced Materials* **2015**, *27*, 6753–6759.
- (16) Gao, Y.; Bai, J.; Sui, Y.; Han, Y.; Deng, Y.; Tian, H.; Geng, Y.; Wang, F. High Mobility Ambipolar Diketopyrrolopyrrole-Based Conjugated Polymers Synthesized via Direct Arylation Polycondensation: Influence of Thiophene Moieties and Side Chains. *Macromolecules* **2018**, *51*, 8752–8760.
- (17) Jo, J. W.; Jung, J. W.; Wang, H. W.; Kim, P.; Russell, T. P.; Jo, W. H. Fluorination of polythiophene derivatives for high performance organic photovoltaics. *Chemistry of Materials* **2014**, *26*, 4214–4220.
- (18) Li, Z.; Lin, H.; Jiang, K.; Carpenter, J.; Li, Y.; Liu, Y.; Hu, H.; Zhao, J.; Ma, W.; Ade, H. et al. Dramatic performance enhancement for large bandgap thick-film polymer solar cells introduced by a difluorinated donor unit. *Nano Energy* **2015**, *15*, 607–615.
- (19) Hernandez, V.; Castiglioni, C.; Del Zoppo, M.; Zerbi, G. Confinement potential and π -electron delocalization in polyconjugated organic materials. *Physical Review B* **1994**, *50*, 9815–9823.

- (20) Kertesz, M.; Choi, C. H.; Yang, S. Conjugated polymers and aromaticity. *Chemical Reviews* **2005**, *105*, 3448–3481.
- (21) Dubay, K. H.; Hall, M. L.; Hughes, T. F.; Wu, C.; Reichman, D. R.; Friesner, R. A. Accurate Force Field Development for Modeling Conjugated Polymers. *Journal of Chemical Theory and Computation* **2012**, *8*, 4556–4569.
- (22) Giambiagi, M.; de Giambiagi, M. S.; Mundim, K. C. Definition of a multicenter bond index. *Structural Chemistry* **1990**, *1*, 423–427.
- (23) Giambiagi, M.; De Giambiagi, M. S.; Dos Santos Silva, C. D.; De Figueiredo, A. P. Multicenter bond indices as a measure of aromaticity. *Physical Chemistry Chemical Physics* **2000**, *2*, 3381–3392.
- (24) Schleyer, P. V. R.; Maerker, C.; Dransfeld, A.; Jiao, H.; Van Eikema Hommes, N. J. Nucleus-Independent Chemical Shifts: A Simple and Efficient Aromaticity Probe. *Journal of the American Chemical Society* **1996**, *118*, 6317–6318.
- (25) Chen, Z.; Wannere, C. S.; Corminboeuf, C.; Puchta, R.; Schleyer, P. V. R. Nucleus-Independent Chemical Shifts (NICS) as an Aromaticity Criterion. *Chemical Reviews* **2005**, *105*, 3842–3888.
- (26) Daudey, J. P.; Trinquier, G.; Barthelat, J.; Malrieu, J. Decisive role of π conjugation in the central bond length shortening of butadiene. *Tetrahedron* **1980**, *36*, 3399–3401.
- (27) Fernández, I.; Frenking, G. Direct estimate of the strength of conjugation and hyperconjugation by the energy decomposition analysis method. *Chemistry - A European Journal* **2006**, *12*, 3617–3629.
- (28) Johnson, E. R.; Keinan, S.; Mori-Sánchez, P.; Contreras-García, J.; Cohen, A. J.; Yang, W. Revealing Noncovalent Interactions. *Journal of the American Chemical Society* **2010**, *132*, 6498–6506.

- (29) Contreras-García, J.; Johnson, E. R.; Keinan, S.; Chaudret, R.; Piquemal, J. P.; Beratan, D. N.; Yang, W. NCIPLOT: A program for plotting noncovalent interaction regions. *Journal of Chemical Theory and Computation* **2011**, *7*, 625–632.
- (30) Krygowski, T. M.; Ejsmont, K.; Stepień, B. T.; Cyrański, M. K.; Poater, J.; Solà, M. Relation between the substituent effect and aromaticity. *Journal of Organic Chemistry* **2004**, *69*, 6634–6640.
- (31) Shishkin, O. V.; Omelchenko, I. V.; Krasovska, M. V.; Zubatyuk, R. I.; Gorb, L.; Leszczynski, J. Aromaticity of monosubstituted derivatives of benzene. The application of out-of-plane ring deformation energy for a quantitative description of aromaticity. *Journal of Molecular Structure* **2006**, *791*, 158–164.
- (32) Cozzolino, A. F.; Vargas-Baca, I.; Mansour, S.; Mahmoudkhani, A. H. The nature of the supramolecular association of 1,2,5-chalcogenadiazoles. *Journal of the American Chemical Society* **2005**, *127*, 3184–3190.
- (33) Glendening, E. D.; Badenhoop, J. K.; Reed, A. E.; Carpenter, J. E.; Bohmann, J. A.; Morales, C. M.; Landis, C. R.; Weinhold, F. NBO 6.0. 2013; <http://nbo6.chem.wisc.edu/>, Theoretical Chemistry Institute, University of Wisconsin, Madison, WI.
- (34) Pophristic, V.; Goodman, L. Hyperconjugation not steric repulsion leads to the staggered structure of ethane. *Nature* **2001**, *411*, 565–568.
- (35) Rablen, P. R.; Hoffmann, R. W.; Hrovat, D. A.; Borden, W. T. Is hyperconjugation responsible for the "gauche effect" in 1-fluoropropane and other 2-substituted-1-fluoroethanes? *J. Chem. Soc., Perkin Trans. 2* **1999**, 1719–1726.
- (36) Frisch, M. J.; Trucks, G. W.; Schlegel, H. B.; Scuseria, G. E.; Robb, M. A.; Cheeseman, J. R.; Scalmani, G.; Barone, V.; Petersson, G. A.; Nakatsuji, H. et al. Gaussian16 Revision A.03. 2016; Gaussian Inc. Wallingford CT.

- (37) Chai, J.-D.; Head-Gordon, M. Long-range corrected hybrid density functionals with damped atom-atom dispersion corrections. *Physical Chemistry Chemical Physics* **2008**, *10*, 6615.
- (38) Weigend, F.; Ahlrichs, R. Balanced basis sets of split valence, triple zeta valence and quadruple zeta valence quality for H to Rn: Design and assessment of accuracy. *Phys. Chem. Chem. Phys.* **2005**, *7*, 3297–3305.
- (39) Lu, T.; Chen, F. Multiwfn: A multifunctional wavefunction analyzer. *Journal of Computational Chemistry* **2012**, *33*, 580–592.
- (40) Frisch, M. J.; Trucks, G. W.; Schlegel, H. B.; Scuseria, G. E.; Robb, M. A.; Cheeseman, J. R.; Scalmani, G.; Barone, V.; Mennucci, B.; Petersson, G. A. et al. Gaussian09 Revision D.01. 2009; Gaussian Inc. Wallingford CT.
- (41) Humphrey, W.; Dalke, A.; Schulten, K. VMD – Visual Molecular Dynamics. *Journal of Molecular Graphics* **1996**, *14*, 33–38.
- (42) Jones, E.; Oliphant, T.; Peterson, P.; Others, SciPy: Open source scientific tools for Python. 2001–; <http://www.scipy.org/>.

Graphical TOC Entry