Lawrence Berkeley National Laboratory

Recent Work

Title

THE CATALYZED PHOTODISSOCIATION OF WATER

Permalink

<https://escholarship.org/uc/item/0kg5f5f7>

Authors

Somorjai, G.A.
Hendewerk, M.
Turner, J.E.

Publication Date

1984

2

Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

RECEIVED
LAWRENCE
BERKELEY LABORATORY

MAY 30 1984

LIBRARY AND
DOCUMENTS SECTION

Materials & Molecular Research Division

Presented at the 2nd Berkeley Catalysis and
Surface Science Conference, Lawrence Berkeley
Laboratory, Berkeley, CA, January 11-13, 1984

THE CATALYZED PHOTODISSOCIATION OF WATER

G.A. Somorjai, M. Hendewerk, and J.E. Turner

January 1984

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 6782.*

LBL-17623
2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

THE CATALYZED PHOTODISSOCIATION OF WATER

G.A. Somorjai, M. Hendewerk and J.E. Turner

Materials and Molecular Research Division,
Lawrence Berkeley Laboratory, and
Department of Chemistry
University of California, Berkeley
Berkeley, California, 94720

THE CATALYZED PHOTODISSOCIATION OF WATER

G.A. Somorjai, M. Hendewerk and J.E. Turner

Materials and Molecular Research Division,
Lawrence Berkeley Laboratory, and
Department of Chemistry,
University of California, Berkeley
Berkeley, California, 94720

ABSTRACT

The dissociation of water to hydrogen and oxygen requires energy of $\Delta G_{298} = 228$ kJ/mole. By irradiating a semiconductor with light of energy greater than this amount, one may produce electrons in the excited state and electron vacancies at the surface that can perform the photochemical reduction ($2H^+ + 2e^- \rightarrow 2H \rightarrow H_2$) and oxidation ($2OH^- + 2h^+ \rightarrow H_2O_2 \rightarrow H_2O + (1/2)O_2$).

There are several semiconductors, $SrTiO_3$, TiO_2 , CdS , and Fe_2O_3 among them, that can photodissociate water. Some possess sites for both reduction and oxidation, while others carry out the two processes at different surfaces. A reversible solid state reaction that involves changes in the transition metal and ion oxidation state must accompany the splitting of water. Platinum, rhodium, and ruthenium oxide, when deposited on the semiconductor, serve as catalysts that accelerate the water photodissociation. These additives accelerate the recombination of hydrogen and oxygen atoms, shift the semiconductor Fermi level to a more favorable position that improves the thermodynamic feasibility for the process, accelerate electron transport, and inhibit side reactions like the photoreduction of oxygen. Many of the elementary reaction steps leading to photoproduction of hydrogen and oxygen over $SrTiO_3$ and Fe_2O_3 have been identified and will be discussed.

I. Introduction

Chemical interactions between molecules in excited electronic, vibrational, or rotational states and surfaces is a new field of catalytic science. Until recently, catalysis of chemical reactions has only been considered for molecules in their thermodynamic ground states. Most of the surface reactions to be catalyzed were exothermic or thermodynamically downhill. In carrying out endothermic reactions, the only source of energy considered has been the addition of heat. This also assured that the molecules maintained an equilibrium energy distribution throughout the reaction.

There is growing evidence from fields other than catalysis that when molecules are allowed to react from excited electronic or vibrational states, they often take different reaction paths than would be available from a ground state configuration. Some examples of this are the deposition of materials from low energy plasmas, the formation of compounds under bombardment by high energy particles, or the application of explosions to induce bonding. Such techniques can lead to the formation of unique coatings, improved adhesion, or better electrical contact between materials.

Photoassisted thermodynamically uphill reactions such as the photodissociation of water to hydrogen and oxygen are one class of these excited state reactions. Figure 1 shows free energies for the dissociation of both H_2O and CO_2 . Both of these molecules are reactants in photosynthesis to produce hydrocarbons and oxygen. If light could be used to dissociate either H_2O and CO_2 , all subsequent reactions of hydrogen with carbon dioxide or carbon monoxide with water are thermodynamically downhill. These reactions can readily be catalyzed by a large number of transition metals or

transition metal compounds to produce small organic molecules. Thus, in the photodissociation of water for example, one produces oxygen, and the subsequent catalytic reactions of hydrogen with carbon dioxide might yield small organic molecules from inorganic photosynthesis even more efficiently than the chlorophyll-catalyzed process of photosynthesis. It is possible that inorganic photosynthesis was an important path in the formation of organic molecules in the pre-chlorophyll era of this planet.

The process of using photons to dissociate stable and abundant molecules like water and carbon dioxide could, if successful, provide for chemicals or for fuel. It is somewhat surprising how little catalytic chemistry has been published using carbon dioxide or methane as carbon sources, or using water for a source of hydrogen or oxygen.

The catalyzed photodissociation of water has been receiving increased attention since the early 70's, when the first experiments on the photoelectrochemical dissociation of water were reported.¹ When a strontium titanate (SrTiO_3) anode was illuminated with light of greater than bandgap energy in a basic solution using a Pt counterelectrode, hydrogen and oxygen evolution occurred at the cathode and anode respectively without the use of any external potential.² The reaction was catalytic and the electrodes showed no sign of deactivation.

The electronic state of an n-type semiconductor such as SrTiO_3 immersed in solution is well understood (Figure 2). Water photodissociation may also be observed when the platinum cathode is substituted with a p-type semiconductor such as gallium phosphide. In this circumstance, both the semiconductor anode and cathode must be illuminated with light of energy greater than their respective bandgaps. While both configurations

may photodissociate water, these two types of photoelectrochemical cells have one essential difference. The n-type semiconductor/metal cell requires illumination of only the semiconductor anode, while the n-type/p-type semiconductor cell requires the illumination of both electrodes simultaneously to induce water photodissociation.

The thermodynamic conditions necessary to carry out this photochemical reaction have been investigated³ and give restrictions on the location of semiconductor band edges in solution. The conduction band edge must be anodic with respect to the H^+/H_2 half reaction, while the valence band edge must be cathodic with respect to the O_2/OH^- redox couple. This way, electrons at the cathode can produce hydrogen atoms, while electron transfer from OH^- to hole states in the valence band will produce OH radicals, which can then be dimerized to H_2O_2 , that splits up to produce oxygen.

Figure 3 shows the conduction and valence band edges for a number of oxides. In order to qualify as a suitable electrode, a material must satisfy three basic criteria. It must have a bandgap larger than 1.23 eV (ΔG for the reaction $H_2O \rightarrow OH^- + H^+$). In addition, band edges must be appropriately positioned with respect to the redox couples as described above. Finally, the material must be chemically stable under the reaction conditions.

As seen in Figure 3, $SrTiO_3$ satisfies the thermodynamic conditions remarkably well, while Fe_2O_3 does not. In fact, $SrTiO_3$ has been found to photodissociate water with about 5% efficiency (calculated as hydrogen energy produced divided by the total photon energy) even in the short circuit configuration as shown in Figure 4. Thus when small particles or single crystal surfaces of $SrTiO_3$ are platinized and illuminated with

light of energy greater than the bandgap of 3.1 eV, the steady state evolution of hydrogen and oxygen can readily be observed. The rate of gas evolution is greater if the SrTiO_3 is pre-reduced in a hydrogen furnace and the electrolyte solution has a pH of 14 or greater. These findings indicate that this is not only an electrochemical process, but that water photodissociation over this material involves both photoelectrochemical and photocatalytic reactions.

Carrier generation and electron transfer at the semiconductor surface are the first of several elementary steps in the photodissociation of water. Electrons and holes are usually generated near the surface in close proximity to the solution. Thus single crystals with high charge mobilities in the bulk are not necessarily needed. Alternatively, small particles or colloids may be utilized in a short circuit configuration to maximize the active surface area of the device. Indeed colloidal platinized TiO_2 and SrTiO_3 systems have been found effective for water photodissociation.⁴

In this paper, we review what is known about the photoelectrochemical dissociation of water in two different configurations - the $\text{SrTiO}_3/\text{Pt}/\text{KOH}$ semiconductor metal system and the n-type/p-type iron oxide photoelectrochemical diode. Both have been shown to drive the water splitting photochemical reaction without an external potential. The SrTiO_3 based system requires illumination by light in the near UV region ($h\nu > 3.1$ eV), while the iron oxide system can operate with light in the visible region ($h\nu > 2.3$ eV). Through the discussion of these two systems for water dissociation, we will demonstrate the accomplishments and difficulties of research in this field of inorganic photosynthesis.

The SrTiO₃/Pt/KOH System:

Figure 5 shows the steady state evolution of hydrogen from a strontium titanate single crystal which had been pre-reduced in a hydrogen furnace, platinized and immersed in 1N KOH solution. The reaction appeared to continue indefinitely with no signs of deactivation, and from the hydrogen yield, this photoinduced process appeared to utilize about 5% of the incident photon energy that is absorbed by the solid. Upon turning off the light, the hydrogen evolution stops. In fact, some of the hydrogen and oxygen disappears due to the favorable back reaction of recombination in the dark. When bandgap radiation illuminates the surface again, the evolution of hydrogen recommences. Heating the electrolyte solution increases the rate somewhat, since the activation energy for this process is about 8 kcal/mole.

A variety of surface science techniques have been used to study the elementary steps in this photochemical surface reaction. Some of these are shown in Figure 6. Auger electron spectroscopy yields the surface composition of the stoichiometric or hydrogen furnace reduced strontium titanate. Photoelectron spectroscopy reveals the presence of Ti³⁺ formal oxidation state metal ion along with Ti⁴⁺ ions, while ultraviolet photoelectron spectroscopy shows a small peak near the Fermi level also associated with the presence of a Ti³⁺ ion. It is apparent that Ti³⁺ ions at the strontium titanate surface play an important role during the photodissociation reaction. Figure 7 shows the intensity of the Ti³⁺ signal as water is adsorbed on the surface in the form of D₂O and the surface is illuminated. Upon illumination, deuterium gas evolves and the Ti³⁺ signal diminishes, indicating that surface ions are being oxidized

to Ti^{4+} . In the dark, oxygen desorption occurs and the surface returns to its reduced state. Upon illumination in the presence of adsorbed water, the process repeats. Thus, it appears that the photon interaction with the surface results in an oxidation/reduction reaction, involving a charge transfer for the transition metal ion from the T^{3+} to the Ti^{4+} oxidation state, which is subsequently returned to its reduced state.

Figure 8 gives direct evidence of the solid state reaction between water and the oxide surface. When H_2^{18}O is adsorbed on the surface and a thermal desorption experiment is carried out, part of the water desorbs as H_2^{18}O . In addition, a substantial amount of the water desorbs in the form of H_2^{16}O . This indicates an exchange of oxygen in the water with the oxygen in the oxide surface. Further information on this solid state reaction is provided by Figure 9, showing a thermal desorption spectrum from SrTiO_3 after adsorption of D_2O or D_2 on the surface. In both cases, the D_2 desorbs in addition to D_2O , indicating that the deuterium is a reducing agent which removes oxygen from the oxide lattice. From these results, one can conclude that the photodissociation of water over SrTiO_3 is a solid state surface reaction similar to the photographic process except that instead of a gross, irreversible photodecomposition of the solid itself, molecules near the surface undergo a reversible photodecomposition. The oxidation/reduction cycle of the transition metal ions on the surface is an integral part of this process.

In Figure 10, the importance of the presence of alkali hydroxide in this process is demonstrated. As one increases the hydroxyl ion concentration in the electrolyte solution, there is an increased rate of hydrogen evolution. Photoelectron spectroscopy indicates that the surface

is completely hydroxylated. In Figure 11, the top curve shows the UPS spectrum from sodium hydroxide. The three electronic transitions are the fingerprints of the presence of OH^- ions. It is clearly seen that the strontium titanate surface in the presence of hydrogen or water shows the same fingerprint. Thus we can infer that a strontium titanate surface which is active towards water photodissociation is completely hydroxylated.

The hydroxylation of the oxide surface does not occur readily at room temperature, and the presence of potassium hydroxide or other alkali hydroxides seems to catalyze this process. This is the reason that alkali hydroxide plays such an important role when the reaction is carried out at 300K. However, if we carry out the reaction at 450-500K in the presence of steam, alkali hydroxides are not needed. Under these circumstances, the surface is readily hydroxylated and hydrogen evolution commences without the presence of alkali hydroxides.⁵

Next, we investigate the importance of the presence of platinum or other metals on the surface in accelerating this reaction. Table I indicates that the reaction occurs faster in the presence of metals on the surface. Platinum seems to be more active than gold, while gold is more active than strontium titanate without any metal. Hydrogen atom recombination is one of the elementary reaction steps leading to the formation of hydrogen gas after the photodissociation of water. Strontium titanate does not carry out hydrogen atom recombination well; however, platinum is an excellent catalyst for this process. Thus, the best water splitting system would involve strontium titanate that carries out the photodissociation process, alkali hydroxides that keep the surface continuously hydroxylated, and metal that is needed for hydrogen atom recombination.

Let us summarize these important findings that indicate the complexity of this process:

- (1) Irradiation by energy $h\nu > 3.1$ eV is needed to induce water photodissociation over SrTiO_3 .
- (2) Alkali hydroxides such as KOH catalyze the hydroxylation of the strontium titanate surface and facilitate water dissociation.
- (3) Oxygen vacancies and the presence of Ti^{3+} at the surface are critical in the dissociation.
- (4) Transition metals such as Pt at the strontium titanate surface accelerate water photodissociation by catalyzing the formation of hydrogen molecules from atoms.

These observations provide information on many of the elementary reaction steps, so one can propose a simple reaction mechanism for the photodissociation of water on strontium titanate surfaces. This mechanism is shown schematically in Figure 12.⁶ In the dark, strontium titanate consists of titanium atoms in the Ti^{4+} oxidation state. Upon illumination, a photoelectron that is generated by bandgap or higher energy radiation reduces the Ti^{4+} to Ti^{3+} . The electron vacancy takes the charge from the OH^- ion and converts it into a peroxide molecule that splits up oxygen. The surface is left in a reduced state that is ready to adsorb another molecule of water which reoxidizes the surface to Ti^{4+} and produces hydrogen in the process. Then, the reaction will repeat itself in a catalytic manner. This mechanism is consistent with all experimental information available on the photodissociation process over strontium titanate at present.

The difficulty with strontium titanate for the photodissociation of water is the necessity for ultraviolet radiation. Since this process works poorly with solar radiation, hydrogen generation using SrTiO_3 is not an economical possibility. A continued search for materials that

would carry out this reaction in the solar range led us to the study of iron oxide surfaces.

III. The N-type Iron Oxide / P-type Iron Oxide Photochemical Diode:

Undoped iron oxide is an intrinsic n-type semiconductor with a bandgap of approximately 2.3 eV. Early work by Hackerman et al⁷ demonstrated some of the desirable properties of iron oxide for water photodissociation. When Fe₂O₃ is used against a Pt counterelectrode, photocurrents corresponding to oxygen production are generated for an applied bias of $V_a > 700$ mV, RHE. It has been found in our laboratory that doping with Si reduces the magnitude of the bias that must be employed and increases the magnitude of the anodic photocurrents. This result motivated a systematic study of various dopants in Fe₂O₃, which showed that the introduction of Mg could yield iron oxide electrodes with p-type behavior. In preparing these p-type samples we followed a well-defined procedure that included heating the mixed oxide powders to 1400°C and then rapidly quenching them in water. The resulting material was a highly heterogeneous Mg doped iron oxide, also containing phases of magnesium ferrate (MgFe₂O₄) and magnesium oxide (MgO).

Individual photocurrent versus voltage characteristics for the n-type (Si doped) and p-type (Mg doped) electrodes are shown in Figure 13. For the n-type (Si doped) electrodes, anodic photocurrents due to oxygen evolution appear for $V_a > 400$ mV, RHE, while the p-type (Mg doped) electrodes yielded cathodic photocurrents corresponding to H₂ evolution of $V_a < 900$ mV, RHE. Individually, these electrodes require an external bias to sustain oxygen or hydrogen evolution under illumination when employed against a platinum counterelectrode. However, when connected in

a short circuit configuration as shown in Figure 14, the p/n assembly assumes an intermediate operating bias of approximately 750 mV, RHE so that O_2 and H_2 production will occur simultaneously without external bias.

The iron oxide based assembly has a photoresponse more closely matched to the solar spectrum than $SrTiO_3$. Figure 15 shows the quantum efficiency (defined as the number of chemically active electron/hole pairs produced per incident photon) plotted versus wavelength for three different iron oxide electrodes. For the undoped Fe_2O_3 electrode, the quantum efficiency was a maximum of 0.03 at a wavelength of 3800Å. Doping with Si (Figure 15b) produced photocurrents about an order of magnitude larger than undoped Fe_2O_3 , due to enhanced electronic mobility. Figure 15c shows the effect of doping with Mg. In this case, the photocurrents are cathodic, while features of the spectral response curves are very similar to both the undoped and Si doped electrodes.

By examining photocurrents in the near bandgap region, one can determine the bandgap. In Figure 16, we have replotted the photocurrents from the Si doped and Mg doped electrodes as $(I_{ph}hv)^{1/2}$ versus photon energy hv . The linearity of these plots tells us that both n-type and p-type materials are indirect bandgap semiconductors with a bandgap of approximately 2.3 eV. These results indicate that the photoelectrochemically active component in both electrodes is most likely Fe_2O_3 .

The locations of conduction and valence band edges with respect to redox couples in solution are of critical importance. To determine the location of these edges on the electrochemical scale, we performed Mott Schottky measurements in which the capacitance of the space charge layer was determined for the Si doped and Mg doped electrodes separately using

a phase shift technique. In Figure 17, we use the Mott Schottky relation and plot the inverse square space charge capacitance ($1/C_{sc}^2$) versus applied potential to obtain the flatband potential from the intercept for the n-type and p-type iron oxides. In addition, one can obtain carrier types and concentrations from the slopes of these plots.

For heavily doped semiconductors such as these iron oxides, the flatband potential is nearly coincident with the band carrying the majority carriers. Thus for the n-type electrode, the measured flatband potential corresponds to the conduction band edge ($E_c = 200$ mV, RHE); in the p-type the flatband potential gives the valence band edge ($E_v = 2300$ mV, RHE). Information on flatband potentials can therefore be used to generate an energy level diagram as shown in Figure 18. This shows the interfaces between the electrolyte and the n-type or p-type surfaces. We have determined band edges from Mott Schottky plots as described above and extrapolated using the measured bandgap (2.3 eV) to find the alternate band edges. The Fermi level was determined by connecting an operating assembly through a high impedance voltmeter to a reference electrode.

From this diagram, one can easily see how the p/n assembly operates. Upon illumination in solution, electron hole pairs are produced in both the p-type and n-type iron oxides. In the p-type electrode, electrons are driven through the depletion layer towards the interface where they convert hydronium ions in solution to hydrogen gas. Conversely, vacancies driven to the n-type interface convert hydroxyl species to oxygen gas. In both electrodes, the majority carriers migrate away from the surface to produce the observed photocurrents. Thus hydrogen evolution occurs at the p-type electrode and oxygen evolution takes place at the n-type electrode.

Hydrogen generation over undoped Fe_2O_3 was shown to be energetically unfeasible. However, in this p/n assembly, H_2 evolution now occurs readily at the p-type electrode. It appears that doping the iron oxide with Mg has shifted the p-type band edges cathodically by several hundred millivolts so that hydrogen evolution is thermodynamically feasible.

To establish that the iron oxide assembly operates as a true p/n diode with a depletion layer at both interfaces, experiments were performed using a CW Kr^+ laser. Both p-type and n-type electrodes were illuminated with the laser at a wavelength of 411 nm or 544 nm. Figure 19 shows the open circuit voltage generated between the p-type and n-type electrodes in solution as a function of illumination intensity at both wavelengths. The most important result from this plot is that open circuit voltage increases 118 mV per decade increase in light intensity. For a single depletion layer, it is known that V_{oc} will increase 59 mV for every tenfold increase in the intensity of illumination as the semiconductor is driven toward flatband conditions. Since we obtained twice this value in our experiments, it is clear that Schottky barriers exist at both the p-type and n-type electrode surfaces.

In separate experiments, oxygen evolution has been observed from an unbiased p/n cell. An $\text{NaOH}/\text{H}_2\text{O}$ solution containing isotopically labelled water (H_2^{18}O) was used as the electrolyte and the production of $^{34}\text{O}_2$ was monitored as a function of time with a mass spectrometer. Figure 20 clearly shows that oxygen was evolved when the p-type and n-type iron oxide electrodes were connected and illuminated in solution, but that no oxygen was produced when the electrodes were disconnected.

Another important consideration for the viability of this process for solar energy conversion is the long term stability of these oxides in solution. Figure 21 shows the photocurrents generated by an illuminated p-type/n-type iron oxide assembly as a function of time after the first immersion in solution. Initially, photocurrents and the corresponding gas production rates were low. However these photocurrents gradually increased over an 80 hour period to approximately $15\mu\text{A}$, where they remained for the duration of the test. The stability of the photocurrents as well as Auger analysis of the electrodes before and after testing indicate that there is no appreciable dissolution of the iron oxide electrodes.

At present, the efficiency of the iron oxide p/n assembly is low, approximately 0.1%. This efficiency is lower than strontium titanate under ultraviolet illumination, but the iron oxide assembly operates with visible light in the solar range. In addition, iron oxide is an excellent catalyst. Thus, once hydrogen is created, it might be reacted in situ with carbon dioxide or nitrogen to form organic molecules or ammonia, respectively.

It is interesting to note that the olivins which comprise over 50% of the mantle of the earth have chemical compositions very similar to the doped iron oxides we have prepared. These materials are primarily iron silicates and magnesium iron silicates, which in various compounds are known to display either n-type or p-type behavior. One can speculate that some of these minerals could form p/n diode configurations, leading to the formation of hydrogen and oxygen from water in the presence of sunlight. Subsequent chemical reactions involving hydrogen might have produced organic molecules in a thermodynamically downhill process.

ACKNOWLEDGEMENT

This work was supported by the Director, Office of Energy Research,
Office of Basic Energy Sciences, Chemical Sciences Division of the U.S.
Department of Energy under contract No. DE-AC03-76SF00098.

FIGURE CAPTIONS

- Figure 1 Free energies for the dissociation of H_2O and CO_2 related to the electrochemical energy scale (RHE).
- Figure 2 Solid state models of band bending for n-type and p-type semiconductor electrodes immersed in aqueous solution. a) n-type semiconductor electrode short circuited to a Pt electrode, b) n-type (TiO_2) electrode in electrical contact with a p-type (GaP) electrode.
- Figure 3 Location of conduction and valence band edges of oxide semiconductors relative to the hydrogen and oxygen redox couples.
- Figure 4 Photoelectrolysis with suspensions of catalyst coated semiconductor particles.
- Figure 5 Steady state hydrogen evolution from a platinized strontium titanium (reduced) crystal immersed in 1N KOH.
- Figure 6 Surface analyses of reduced $SrTiO_3:Ti:O$ ratios determined by Auger electron spectroscopy, and the presence of Ti^{3+} and Ti^{4+} ions determined by X-ray photoelectron spectroscopy and ultraviolet photoelectron spectroscopy.
- Figure 7 Simultaneous evolution of D_2 gas and the oxidation of Ti^{3+} to Ti^{4+} after water (D_2O) adsorption is shown by monitoring the D_2 gas by mass spectrometry and the intensity of the Ti^{3+} signal with ELS.
- Figure 8 Thermal desorption of water following adsorption of isotopically labelled water ($H_2^{18}O$) on a $SrTiO_3$ crystal.
- Figure 9 Thermal desorption from $SrTiO_3$ following adsorption of D_2O or D_2 .
- Figure 10 Hydrogen evolution from a $SrTiO_3/Pt$. Dependence on hydroxyl concentration in the electrolyte solution.
- Figure 11 The same characteristic features are seen by comparison of the UPS spectra of hydroxyl ions and $SrTiO_3$ exposed to hydrogen or water.
- Figure 12 A simple reaction mechanism for the photodissociation of water on strontium titanate surfaces.
- Figure 13 Photocurrents for n-type (Si-doped) and p-type (Mg-doped) iron oxide electrodes under biased conditions.
- Figure 14 Schematic illustration of p/n assembly for the photodissociation of water using doped iron oxide electrodes.
- Figure 15 Measured quantum efficiencies as a function of wavelength for doped and pure iron oxide.
- Figure 16 Bandgap determinations of doped iron oxide electrodes from photocurrent dependence on wavelength.

- Figure 17 Mott-Schottky plots of the inverse square of space charge capacitance versus applied potential for n-type and p-type iron oxide electrodes.
- Figure 18 Energy level diagram depicting band edge locations of doped iron oxide electrodes relative to hydrogen/oxygen redox couples.
- Figure 19 Open circuit voltage generated between p-type and n-type electrodes immersed in solution as a function of illumination intensity at 411nm and 544nm.
- Figure 20 Oxygen evolution from a p/n assembly with doped iron oxide electrodes.
- Figure 21 Photocurrent as a function of time for a p/n assembly during the first immersion.
- Table I A summary of hydrogen evolution rates from stoichiometric and pre-reduced SrTiO_3 crystals in varied NaOH environments and with metal catalysts deposited on the surface.

REFERENCES

1. A. Fujishima and K. Honda, Bull. Chem. Soc. Japan 44 (1971) 1148; Nature (London) 238 (1972) 37.
2. F.T. Wagner and G.A. Somorjai, J. Amer. Chem. Soc. 102 (1980) 5494.
3. H. Gerischer in Solar Energy Conversion, Topics in Applied Physics, v. 31, B.O. Seraphin, editor, Springer-Verlag, 1979.
4. T. Kawai and T. Sakata, J. Chem. Soc. Chem. Comm. (1980) 694.
5. R.G. Carr and G.A. Somorjai, Nature 290 (1981) 576.
6. H. Van Damme and W.K. Hall, J. Amer. Chem. Soc. 101 (1979) 4373.
7. J.M. Wilhelm, K.S. Yun, L.W. Ballenger and N. Hackerman, J. Electrochem. Soc. 126 (1979) 419.

XBL 828-6302

Fig.1

Semiconductor - Conductor Cell

Semiconductor - Semiconductor Cell

XBL 7610-7610

Fig.2

XBL 825-5829

Fig. 3

PHOTOELECTROLYSIS WITH SUSPENSIONS OF CATALYST COATED SEMICONDUCTOR PARTICLES

Fig. 4

XBL 799-7067

Fig.5

Fig.6

XB L 8010-6050

Fig. 7

XBL 803-4762

Fig. 8

XBL 803-4761

Fig.9

XBL799-7068

Fig.10

XBL 799-7042

Fig. 11

Van Damme and Hall, JACS 101 4373

XBL 822-7816

Fig.12

XBL 832-5322

Fig.13

XBL 835-5725

Fig.14

Fig.15

XBL 838-5791A

Fig.16

XBL 831-5155

Fig.17

ENERGETICS OF CONNECTED P-TYPE AND N-TYPE IRON OXIDES

XBL 832-5181A

Fig.18

XBL 838-6241

Fig.19

XBL 835-9804

Fig.20

-39-

Fig.21

XBL 833-8744

A. Hydrogen production from SrTiO_3 crystals covered by thick ($>30\mu$) NaOH films saturated with water vapor

Crystal	Monolayers* H_2/hr
Pre-reduced, platinized	1580
Pre-reduced, metal-free	100
Stoichiometric, metal-free	30

B. Hydrogen production from SrTiO_3 crystals in 20 M NaOH

Crystal	Monolayers* H_2/hr
Pre-reduced, platinized	4500
Stoichiometric, platinized	120
Pre-reduced, metal-free	30
Stoichiometric, metal-free	50
Pre-reduced, gold coated	200

* 1 monolayer $\equiv 1 \times 10^{15}$ molecules/cm² illuminated surface

Table I

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720