UC Irvine

UC Irvine Previously Published Works

Title

Spin-Peierls state versus Néel state in doped CuGeO₃.

Permalink

<https://escholarship.org/uc/item/0td3j3m8>

Journal

Physical review letters, 74(8)

ISSN

0031-9007

Authors

Oseroff, SB
Cheong, SW
Aktas, B
et al.

Publication Date

1995-02-01

DOI

10.1103/physrevlett.74.1450

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at <https://creativecommons.org/licenses/by/4.0/>

Peer reviewed

Spin-Peierls State versus Néel State in Doped CuGeO_3

S. B. Oseroff,¹ S-W. Cheong,² B. Aktas,³ M. F. Hundley,⁴ Z. Fisk,⁴ and L. W. Rupp, Jr.²

¹*San Diego State University, San Diego, California 92182*

²*AT&T Bell Laboratories, Murray Hill, New Jersey 07974*

³*University of California San Diego, San Diego, California 92093*

⁴*Los Alamos National Laboratory, Los Alamos, New Mexico 87545*

(Received 13 April 1994)

The competition between nonmagnetic spin-Peierls (SP) and magnetic Néel ground states has been investigated in CuGeO_3 doped with Zn, Ni, Mn, and Si. The analysis of specific heat, C_p , data in CuGeO_3 , measured as a function of magnetic field, supports a SP transition at $T_{\text{SP}} = 14$ K. The replacement of Cu^{2+} by Zn^{2+} , Ni^{2+} , or Mn^{2+} reduces T_{SP} and stabilizes a Néel state, not a spin-glass phase as previously suggested. No significant difference in C_p was observed for Zn- and Ni-doped samples. We suggest that the Néel state depends on $|S' - S|$, where S' is the spin of the dopant and $S = \frac{1}{2}$.

PACS numbers: 75.10.Jm, 75.40.Cx, 75.50.Ee

Quantum magnetism in low-dimensional (D) and low-spin (S) Heisenberg systems is a perennially attractive subject. Particularly, doping in quantum magnets has drawn great attention in recent years [1]. The linear structure of CuGeO_3 suggests that it is a good realization of a 1D $S = \frac{1}{2}$ antiferromagnet (AF). Furthermore, the inorganic nature of this compound allows different spin substitutions. From the isotropic and rapid drop of the magnetic susceptibility (χ), Hase, Terasaki, and Uchinokura concluded that the compound undergoes a spin-Peierls (SP) transition at 14 K [2]. The SP transition can be described as a progressive dimerization of $S = \frac{1}{2}$ AF chains coupled to the 3D lattice. As the temperature (T) is lowered, the assembly of uniform AF chains undergoes a second-order phase transition at $T = T_{\text{SP}}$ to a system of alternating-bond-length AF chains. The main feature of this state is the appearance of an energy gap between the new ground state, a spin singlet, and a band of spin-triplet states. Such a transition has been reported in a few organic compounds, such as TTF-Cu(Au)BDT and [MEM(TCNQ)₂], where the unpaired electrons are localized on the TTF⁺ and TCNQ⁻ units of the structure, respectively [3]. In CuGeO_3 , the $S = \frac{1}{2}$ spin is localized on the Cu^{2+} ion. CuGeO_3 forms in an orthorhombic structure with a Cu-Cu distance of 4.793, 4.251, and 2.942 Å along the **a**, **b**, and **c** axes, respectively [4]. AF chains of Cu^{2+} along the **c** axis are coupled through O^{2-} ions and separated by Ge-O chains. This structure suggests 1D AF magnetic coupling. Recent neutron scattering data [5] have been interpreted as due to a continuous twisting of the oxygens connecting the Cu atoms to the *a-b* plane between room temperature and $T \sim T_{\text{SP}}$. This structural distortion was claimed to abruptly end at T_{SP} , suggesting that it drives the SP transition, i.e., the motion of the oxygens modulates the spin-spin interaction along the **c** axis, and they are responsible for the coupling between the singlet spin

pairs and phonons. A model proposed by Imada [6], using the concept of the resonating valence bond (RVB) introduced by Anderson [7], may describe the SP phase in CuGeO_3 . In his model, the spin gap is not a consequence of a static lattice dimerization, but the result of dynamic SP fluctuations. Nevertheless, two-magnon scattering data are not in agreement with the SP interpretation [8], but agree with a strong interchain ferromagnetic (FM) interaction in CuGeO_3 , contrary to the negligible interchain interaction expected for SP systems.

CuGeO_3 is interesting because it can be used in order to address the problem of doping in one-dimensional magnetic systems. This is a subject of current interest where little experimental work is available [9], primarily because of the difficulty of finding chain magnets that can be doped without large changes in their symmetry and magnetic interactions. CuGeO_3 is a unique system because it allows us to study the effects of partial replacement of Cu by $S \neq \frac{1}{2}$ ions. The effect of doping has not been investigated in organic SP systems because of the low solubility of dopants. Hase *et al.* recently reported [10] a rapid decrease of T_{SP} in CuGeO_3 upon doping with Zn and the appearance of a new magnetic state for concentrations of $\text{Zn} \geq 0.02$. From their χ data, they concluded that the new state is a spin-glass (SG) phase. On the other hand, Lu, Su, and Yu [11] suggested that Zn doping results in the collapse of the spin gap, and predicted the existence of a gapless SP state for $\text{Zn} \sim 0.03$.

In this Letter we present specific heat, C_p , data measured as a function of magnetic field (H) in pure CuGeO_3 and the effects of Zn, Ni, Mn, and Si doping. Magnetic specific heat has been useful in understanding organic SP systems [12]. The data are analyzed in terms of a mean-field model and compared with χ and EPR measurements on the same samples [13]. Polycrystalline materials were prepared by the standard solid-state reac-

tion in air. Large single crystals were grown by the slow cooling of stoichiometric melts. The specific heat was measured between 1.4 and 20 K using a small-sample relaxation calorimeter [14].

Data for C_p/T vs T for several compounds are shown in Fig. 1. A λ -type anomaly is observed in every case. C_p is similar for 4% Ni or Zn doping. A more rapid reduction of T_{SP} was found for Mn than for Ni or Zn doping. In contrast, Si which substitutes for Ge has little effect on T_{SP} . Applied fields of up to 10 T shift T_{SP} by ~ 1.7 K. As seen in the inset of Fig. 1, $\text{Cu}_{0.98}\text{Zn}_{0.02}\text{GeO}_3$ exhibits anomalies at ~ 3 and ~ 10 K. In order to separate the lattice contribution, C_L , from the magnetic contribution, C_m , we have assumed that the magnetic transition, the applied magnetic field, and the doping have only minor effects on C_L . It is a reasonable assumption because independent fits for the different samples provide comparable values for C_L . This is clear from a simple inspection of the curves shown in Fig. 1 which remain essentially parallel everywhere except close to the anomalies. The data for $T \ll T_{SP}$ have been fitted by

$$C_p = \beta_1 T^3 + c \exp(-bT_{SP}/T), \quad (1)$$

where the first term accounts for C_L . A better fit for $T > 4$ K is obtained by adding a term $\beta_2 T^5$. The data can then be represented above and below T_{SP} by means of the same C_L . A mean-field analysis of an SP system is analogous to a BCS analysis for the superconducting state; thus we fit the magnetic specific heat data below T_{SP} using a BCS-like exponential gap function [15]. The data above T_{SP} were fitted by

$$C_p = \beta_1 T^3 + \beta_2 T^5 + \gamma T, \quad (2)$$

FIG. 1. Total specific heat, C_p/T , for pure CuGeO_3 measured at 0, 5, and 10 T, and for 4% Zn and 4% Ni doping, measured in $H = 0$. The inset shows data for $\text{Cu}_{0.98}\text{Zn}_{0.02}\text{GeO}_3$, where two anomalies are seen. The full lines are the best fits by Eqs. (1) and (2) for CuGeO_3 and $\text{Cu}_{0.96}\text{Zn}_{0.04}\text{GeO}_3$ data, respectively.

where the linear term γT is characteristic of 1D homogeneous AF systems with $\gamma = 2Nk_B^2/3J$ [3,12]. More weight was given to the parameters obtained for Eq. (1) using CuGeO_3 data. A larger T range is covered when $T < T_{SP}$ for the undoped sample; consequently, the errors are smaller. Using the same argument, the parameters obtained from fitting the 4% Zn and Ni data by Eq. (2) were given more weight for $T > T_{SP}$. These parameters were determined independently for each compound and fell within experimental error of each other. The best fits were obtained with $\beta_1 = 0.66 \pm 0.05 \text{ mJ/mol K}^4$, $\beta_2 = -0.00077 \pm 10^{-5} \text{ mJ/mol K}^6$, and $\gamma = 45 \pm 5 \text{ mJ/mol K}^2$. β_1 corresponds to a Debye temperature $\Theta_D \sim 240$ K. In Fig. 1 we display the fit by Eq. (1) of the CuGeO_3 , and by Eq. (2) of $\text{Cu}_{0.96}\text{Zn}_{0.04}\text{GeO}_3$ data, with $H = 0$. For the sake of clarity, fits to the other samples are not given. If $\gamma = 45 \pm 5 \text{ mJ/mol K}^2$ is substituted in the expression $\gamma = 2Nk_B^2/3J$, a value of $J/k_B \sim 123$ K is obtained that is in agreement with the value of ~ 125 K derived from high magnetic field data [16]. The discrepancy with $J/k_B = 88$ K, obtained from χ data [2], may be associated with the poor agreement between the χ data and the model used to fit them [17].

In order to study the region of the transition in more detail we analyze it within the mean-field model, as in the case for the organic SP compounds [12]. In Fig. 2 we present $C_m = C_p - C_L$ for CuGeO_3 . The λ -shaped anomaly is approximated by means of a triangular function, with the same entropy gain under this function as under the measured anomaly. The baseline of the triangle, represented by the term γT for the 4% Zn and Ni specimens, shows the entropy gain as compared to the case where no transition occurs. The mean-field

FIG. 2. Magnetic specific heat, C_m ($\circ$), of CuGeO_3 . The triangular function approximates the mean-field character of the transition leaving the entropy gain unaltered. The baseline of the triangle is defined by C_m of $\text{Cu}_{0.96}\text{Zn}_{0.04}\text{GeO}_3$ ($\triangle$) and $\text{Cu}_{0.96}\text{Ni}_{0.04}\text{GeO}_3$ ($\times$) for $T > T_c$. The temperatures discussed in the text, T_{SP}^{MF} and T_p , are shown. The inset shows the best fit by $c \exp(-bT_{SP}/T)$ for CuGeO_3 measured in different fields.

transition temperature, T_{SP}^{MF} , is found to be ~ 14 K, in excellent agreement with T_{SP} obtained from χ and EPR data [2,13]. The temperature of the peak, T_p , is ~ 13.3 K, i.e., indicating a transition width of ~ 0.7 K. The jump in the triangular function, $\sim 920 \pm 100$ mJ/mol K, can be compared with the jump predicted by the BCS model, $\Delta C_m = 1.43\gamma T_{SP}$. This expression yields a value of $\gamma \sim 46 \pm 5$ mJ/mol K², in excellent agreement with the value of γ obtained by extrapolation above T_{SP} . Below T_{SP} , the magnetic term C_m was fitted by $c \exp(-bT_{SP}/T)$. The fit yields $c \sim 20$ J/mol K and $b \sim 2.6$. These values can be compared with those expected for a BCS model, $c \sim 10\gamma T_{SP}$ and $b \sim 1.5$ [15]. For CuGeO_3 , values of $c \sim 6$ J/mol K and $b \sim 1.5$ are obtained by using $\gamma \sim 45$ mJ/mol K² and $T_{SP}^{MF} \sim 14$ K, these values are smaller than the experimental ones. Similar discrepancies were found in organic SP systems [12].

A test for the SP model is to study the change of T_{SP} with magnetic field. The behavior in a field can help in discriminating between a simple structural transition and a SP transition. A large difference in the decrease of T_{SP} is expected between the two cases, $\Delta T \sim (H/J)^2$ for a structural transition and $\Delta T_{SP} \sim (H/T_{SP})^2$ for a SP transition [18]. In the inset of Fig. 2 we present the fits of the C_m data measured at 0, 5, and 10 T by $c \exp(-bT_{SP}/T)$. The best fits are obtained with $c = 20 \pm 2$, 16 ± 2 , and 9 ± 2 ; and $bT_{SP} = 37 \pm 1$, 32 ± 1 , and 25 ± 1 K for $H = 0, 5$, and 10 T, respectively. When analyzing the data within the mean-field model, values of $T_{SP}^{MF} = 13.6$ and 12.3 K and $T_p = 12.8$ and 11.5 K were found for $H = 5$ and 10 T, respectively. A decrease of bT_{SP} with H is expected because of the increase of the Zeeman energy and the reduction of the energy gap in the spin-wave spectrum. For fields with $\mu_B H < 0.5k_B T_{SP}$, a decrease of T_{SP} by $\Delta T_{SP}/T_{SP} = \alpha x(1 + x + \dots)$, where $x = (g\mu_B H/2k_B T_{SP})^2$ and g (gyromagnetic factor for Cu^{2+}) is ~ 2.17 for a powder sample [13], has been predicted [18–20]. The expression reduces to the first term for $\mu_B H \ll k_B T$. Using the T_{SP}^{MF} and T_p given above, values of $\alpha = 0.41$ and 0.40 for 5 and 10 T are obtained, respectively. They agree well with those derived from a Hartree-Fock approximation, which yields $\alpha = 0.44$ [18,19] and the calculation by Cross which predicts $\alpha = 0.38$ [20]. For fields larger than 5 T, the agreement is possibly fortuitous. A similar agreement was found in the organic SP systems when measuring at high fields [21]. Our data analysis supports a SP transition, in disagreement with the two-magnon scattering conclusions [8]. A strong FM interaction between chains, as suggested in Ref. [8], should produce large g shifts of the Cu^{2+} EPR line as a function of T , but they were not observed [13].

The influence of doping upon the magnetic specific heat can be observed in Fig. 3, in which C_m/T ratios are plotted as a function of temperature. The anomaly associated with the SP transition shifts to lower T with doping. As previously suggested by Hase *et al.* [10], and

FIG. 3. Magnetic specific heat, C_m/T , as determined from the subtraction of the lattice contribution, C_L . For pure CuGeO_3 measured at 0 ($\circ$), 5 ($\blacktriangledown$), and 10 ($\diamond$) T, and at $H = 0$, for 2% ($\bullet$) and 4% ($\triangle$) Zn and 4% ($\times$) Ni doping. Inset (a) shows C_m ($\triangle$), and the zero-field-cooled (ZFC) ($\circ$) and field-cooled (FC) ($\blacktriangle$) χ for $\text{Cu}_{0.96}\text{Zn}_{0.04}\text{GeO}_3$, measured in 50 Oe. Inset (b) shows C_m ($\times$) and χ ($\triangle$) for $\text{Cu}_{0.96}\text{Ni}_{0.04}\text{GeO}_3$ measured in 50 Oe.

seen in Figs. 1 and 3, there is a second anomaly at ~ 3 K for $\text{Cu}_{0.98}\text{Zn}_{0.02}\text{GeO}_3$. For larger concentrations of Zn or Ni, the temperature of the second anomaly increases to ~ 4 K with the complete disappearance of the SP anomaly. There is no significant difference between the specific heat for 4% Zn and Ni materials. We calculated the excess entropies for 4% Zn and Ni with $|S' - S| = \frac{1}{2}$. The fit yields $\Delta S \sim 0.15$ J/mol K, which accounts for $\sim 4\%$ of $R \ln(2|S' - S| + 1) = 5.76$ J/mol K. One would expect that replacing Cu by Zn would result in an increase of χ due to Cu ions that do not dimerize in a singlet ground state. However, only a small increase in χ , that weakly depends on doping, is measured. This can be understood as follows: Zn can be thought of as an on-site spin vacancy that introduces a localized magnetic moment which is “polarized” by the staggered magnetization. As it sees the local field due to the staggered order, no Curie term appears [9]. The consequence of doping with nonmagnetic Zn^{2+} or magnetic Ni^{2+} , $S = 1$, is almost the same. The increase in χ due to Ni doping is small compared with the contribution expected from Ni^{2+} free ions. The effect of doping with Mn^{2+} , $S = \frac{5}{2}$, was studied by EPR. The EPR data can be explained as Mn^{2+} doping depresses T_{SP} about twice as rapidly as Zn and Ni. From these observations we may infer that the difference

between the spin value of the doping impurity and the $S = \frac{1}{2}$ spin of Cu^{2+} is an important parameter in determining the properties of the system. Furthermore, the size of the ion substituting for $\text{Cu}^{2+} = 0.73 \text{ \AA}$ ($\text{Zn}^{2+} = 0.74 \text{ \AA}$, $\text{Ni}^{2+} = 0.69 \text{ \AA}$) does not seem to play a significant role. Replacing Ge^{4+} by up to 10% of Si^{4+} reduces T_{SP} by just $\sim 1 \text{ K}$.

Our data analysis does not agree with the speculation of Ref. [10] that a SG phase resulted from Zn doping. As seen in the insets of Fig. 3 for 4% of Zn or Ni, a peak in C_m is found at the same T , within the experimental error, where χ shows a maximum. It is well known that the magnetic specific heat of a SG system shows no indication of a cooperative peak, discontinuity, or any broad anomaly close to the freezing temperature, T_{SG} , where χ displays its characteristic sharp peak [22]. For a SG system, C_m increases linearly with T showing only a rounded maximum at T well above T_{SG} . Furthermore, contrary to Ref. [10], and as can be seen in inset (a) of Fig. 3, our low field χ measured in $H = 50 \text{ Oe}$ for $\text{Cu}_{0.96}\text{Zn}_{0.04}\text{GeO}_3$ does not display a difference between zero-field cooling and field cooling below the χ cusp, as would be expected for a SG compound [22]. Another argument against the SG description is that frustration is required for its occurrence, which is not possible within 1D chains, unless a strong interchain interaction is induced by doping [10]. The peak in C_m and the drop in the χ below its maximum are strong indications of a Néel state, rather than a SG. The presence of two peaks in the C_p of $\text{Cu}_{0.98}\text{Zn}_{0.02}\text{GeO}_3$ suggests the coexistence of a SP and a Néel state, for which we do not have an explanation. In addition, the existence of the two peaks appears to be inconsistent with the gapless SP state proposed by Lu, Su, and Yu [11].

As mentioned above, neutron scattering data [5] indicate that the SP transition in CuGeO_3 is not a consequence of a static lattice dimerization, but is due to dynamic fluctuations of the oxygens, a possibility proposed earlier by Imada [6] using the concept of RVB [7]. Doping could destroy the fluctuations by pinning the impurities, which could explain the rapid decrease of T_{SP} with Cu-site substitution. Inagaki and Fukuyama [23] studied the possibility of having a magnetic Néel or a SP as a ground state for a quasi-1D Heisenberg AF. They obtained a phase diagram where either the SP or the Néel state is the ground state depending on the ratio between the interchain and intrachain exchange interaction. As Cu substitution modifies the chain length, it changes the spin-phonon interaction, and possibly increases the intrachain-interchain ratio, then a Néel state ground state could be stabilized. For CuGeO_3 the boundary between the SP state and the Néel state is $\sim 3\%$ for Zn or Ni and $\sim 1\%$ for Mn.

New x-rays and neutron studies on CuGeO_3 were reported after the completion of this work [24]. Their authors postulate the existence of oxygen displacements

in the a - b plane and critical fluctuations above T_{SP} for CuGeO_3 . Their data analysis supports a SP transition [24].

In summary, the analysis of the field dependent specific heat data of CuGeO_3 indicates the occurrence of a SP transition, and the specific heat data suggest that the second magnetic anomaly observed for doped samples is associated to a Néel and not a SG ground state.

This research was sponsored at San Diego State University by NSF Grant No. DMR-91-17212 and at Los Alamos National Laboratory under the auspices of the United States Department of Energy. One of us (B.A.) was supported by TUBITAK. We wish to thank D. Arovas, B. Batlogg, and J. Templin for their enlightening discussions.

-
- [1] L. J. de Jongh, in *Magnetic Phase Transitions*, edited by R. J. Elliot and M. Ausloos (Springer-Verlag, New York, 1983); F. D. M. Haldane, *Phys. Rev. Lett.* **50**, 1153 (1983).
 - [2] M. Hase, I. Terasaki, and K. Uchinokura, *Phys. Rev. Lett.* **70**, 3651 (1993).
 - [3] I. S. Jacobs *et al.*, *Phys. Rev. B* **14**, 3036 (1976).
 - [4] H. Vollenke, A. Wittman, and H. Nowotny, *Monatsh. Chem.* **98**, 1352 (1967).
 - [5] M. Arai *et al.*, *J. Phys. Soc. Jpn.* **63**, 1661 (1994).
 - [6] M. Imada, *J. Phys. Soc. Jpn.* **60**, 1877 (1991); **61**, 423 (1992).
 - [7] P. W. Anderson, *Mater. Res. Bull.* **8**, 153 (1973).
 - [8] S. Sugai, *J. Phys. Soc. Jpn.* **62**, 3829 (1993).
 - [9] M. Azzouz, *Phys. Rev. B* **48**, 6136 (1993); D. G. Clarke, T. Giamarchi, and B. Shraiman, *ibid.* **48**, 7070 (1993); K. S. Narayan *et al.*, *ibid.* **46**, 6195 (1992).
 - [10] M. Hase *et al.*, *Phys. Rev. Lett.* **71**, 4059 (1993).
 - [11] Z. Y. Lu, Z. B. Su, and L. Yu, *Phys. Rev. Lett.* **72**, 1276 (1994).
 - [12] T. Wei *et al.*, *Solid State Commun.* **21**, 595 (1977); S. Huisinga *et al.*, *Phys. Rev. B* **19**, 4723 (1979); R. A. Craven *et al.*, *Phys. Rev. Lett.* **32**, 769 (1974).
 - [13] S. Oseroff *et al.*, *J. Appl. Phys.* **75**, 6819 (1994).
 - [14] R. Bachman *et al.*, *Rev. Sci. Instrum.* **43**, 205 (1972).
 - [15] M. Tinkham, in *Low Temperature Physics*, edited by C. De Witt *et al.* (Gordon and Breach, New York, 1962), p. 147.
 - [16] H. Hori *et al.*, *J. Phys. Soc. Jpn.* **63**, 18 (1994).
 - [17] J. C. Bonner and M. E. Fisher, *Phys. Rev.* **135**, A640 (1964).
 - [18] L. N. Bulaeviskii, A. I. Buzdin, and D. I. Khomskii, *Solid State Commun.* **27**, 5 (1978).
 - [19] J. W. Bray, *Solid State Commun.* **26**, 771 (1978).
 - [20] M. C. Cross, *Phys. Rev. B* **20**, 4606 (1979).
 - [21] J. C. Bonner *et al.*, *Phys. Rev. B* **35**, 1791 (1987).
 - [22] L. E. Wenger and P. H. Keesom, *Phys. Rev. B* **13**, 4053 (1976).
 - [23] S. Inagaki and H. Fukuyama, *J. Phys. Soc. Jpn.* **52**, 2504 (1983); **52**, 3620 (1983).
 - [24] J. P. Pouget *et al.*, *Phys. Rev. Lett.* **72**, 4037 (1994); K. Irota *et al.*, *ibid.* **73**, 736 (1994).