UC Irvine

UC Irvine Previously Published Works

Title

Growth of the optical conductivity in the Cu-O planes.

Permalink

<https://escholarship.org/uc/item/13x1t3w5>

Journal

Physical review. B, Condensed matter, 41(16)

ISSN

0163-1829

Authors

Cooper, SL
Thomas, GA
Orenstein, J
et al.

Publication Date

1990-06-01

DOI

10.1103/physrevb.41.11605

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at <https://creativecommons.org/licenses/by/4.0/>

Peer reviewed

Rapid Communications

The Rapid Communications section is intended for the accelerated publication of important new results. Since manuscripts submitted to this section are given priority treatment both in the editorial office and in production, authors should explain in their submittal letter why the work justifies this special handling. A Rapid Communication should be no longer than 3½ printed pages and must be accompanied by an abstract. Page proofs are sent to authors, but, because of the accelerated schedule, publication is not delayed for receipt of corrections unless requested by the author or noted by the editor.

Growth of the optical conductivity in the Cu-O planes

S. L. Cooper, G. A. Thomas, J. Orenstein, D. H. Rapkine, A. J. Millis, S-W. Cheong, and A. S. Cooper
AT&T Bell Laboratories, Murray Hill, New Jersey 07974

Z. Fisk

Los Alamos National Laboratory, Los Alamos, New Mexico 87545
(Received 7 March 1990)

We have studied the development of the optical conductivity as electrons are added to the Cu-O planes in $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ by varying x ($0 \leq x \leq 0.2$). In the metallic phases, contributions to the optical conductivity below 3 eV arise from three sources: mobile carriers, mid-infrared excitations, and charge-transfer excitations. The mobile carrier spectral weight grows roughly linearly with x , while the mid-infrared band appears to evolve at low doping via a transfer of spectral weight from the charge-transfer band. Comparing these results with hole doping in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$ indicates an electron-hole symmetry that is not anticipated by standard charge-transfer insulator models.

In spite of much study, little is understood about either the normal-state excitation spectrum of the high- T_c compounds,^{1,2} or the manner in which this spectrum develops from the insulating phase as a function of doping. We address these issues here in an optical-reflectivity study of n -type $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ for $0 < x < 0.2$ and $\delta \sim 0$. At $x=0$, Pr_2CuO_4 is an insulator with negligible absorption below the charge-transfer gap ($\omega \sim 1.5$ eV). Our study indicates that light doping ($x \sim 0.04$) gives rise to an unexpectedly large growth of spectral weight in the mid-infrared frequency range (i.e., $0.1 \leq \omega \leq 0.5$ eV), and an accompanying decrease in the charge-transfer band. Further doping ($0.04 < x \leq 0.2$) leads to an x -dependent increase in absorption at low frequencies ($\omega < 0.1$ eV), but causes little change in the mid-infrared or charge-transfer contributions. Notably, similar behavior has also been observed recently in p -type $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$,³ indicating a qualitative particle-hole symmetry associated with the doping process in high- T_c cuprates. These optical results appear to be inconsistent with standard charge-transfer insulator models.

The optical measurements reported in this paper were performed on single crystals of T' -phase $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ grown in Pt crucibles with no after-synthesis polish. Pr_6O_{11} , CeO_2 , and CuO powders were mixed in a concentration ratio of $\text{Pr}:\text{Ce}:\text{Cu} = 1-x:x:2.8$, then heated above the peritectic melting point ($\sim 1275^\circ\text{C}$ for $\text{Pr}_2\text{CuO}_{4-\delta}$, slowly cooled down to the eutectic point ($\sim 1030^\circ\text{C}$ for $\text{Pr}_2\text{CuO}_{4-\delta}$), and finally quenched to

room temperature. Large crystals (as large as $3 \times 3 \times 0.1$ cm³) with flat and shiny surfaces were grown on the surface of the flux. After they were mechanically removed from the flux, the crystals were annealed at 875°C with Ar-gas flow for 5 h and then furnace cooled to room temperature. Magnetic measurements of crystals⁴ in the concentration range $x \leq 0.12$ indicated that these samples were antiferromagnetic with sharp transition widths < 10 K. The $x=0.2$ crystal was nonmagnetic and nonsuperconducting (the superconducting phase occurs between $0.14 \leq x \leq 0.18$).⁵ The Ce concentrations in these crystals were determined from lattice-parameter measurements by x-ray diffraction, and are accurate to $\pm 5\%$. Furthermore, the nominal O concentration was determined from neutron-scattering studies to be 4 oxygen atoms/unit cell,⁶ and consequently no carriers are expected to arise from oxygen vacancies (i.e., $\delta \sim 0$). Pt doping from the crucible is believed to be negligible because impurity contributions are not apparent in the insulating ($x=0$) crystals. In-plane thermoelectric power in all crystals were measured to be negative at room temperature, indicating electronic carriers. Reflectivity spectra from 100 to 20000 cm⁻¹ (12.5 meV to 2.5 eV) were performed close to a normal-incidence configuration using a rapid scanning interferometer. Mirror optics were used to focus the modulated, collimated light beam from the spectrometer onto the sample, and then onto a variety of detectors covering the above frequency range.

Figure 1 shows the frequency-dependent reflectivity R

FIG. 1. Room-temperature (300 K) frequency-dependent reflectivity of $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ for a series of Ce concentrations, x . The incident light was unpolarized in the a, b plane. Note that the frequency is plotted on a logarithmic scale.

between 100 and 20000 cm^{-1} for a series of Ce concentrations x . The most notable feature of these reflectivity spectra is the transition between insulating and metallic behavior that occurs with increased Ce substitution. The frequency-dependent R of undoped $\text{Pr}_2\text{CuO}_{4-\delta}$ ($x=0$) is characteristic of an insulator, exhibiting a response dominated at low frequencies by phonon peaks, and at high frequencies by a peak in reflectivity near 12000 cm^{-1} (1.5 eV). The latter peak, observed in the insulating phases of all high- T_c cuprates, has been attributed to the onset of Cu-O charge-transfer excitations.⁷ Upon substituting Ce^{4+} for Pr^{3+} ($x > 0$), the appearance of metallic behavior is betrayed by two changes: a rapid increase in the low-frequency reflectivity due to absorption by electronic process, and the development of a plasma edge near 1 eV (8000 cm^{-1}). Notably, the changes in R shown in Fig. 1 are consistent with samples that are homogeneously doped on a macroscopic length scale. For example, a Kramers-Krönig analysis of these data demonstrates that the phonons in $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ maintain roughly constant oscillator strengths with doping. By contrast, in samples composed of mixed insulating (with fraction f) and metallic (with fraction $1-f$) phases, the R would be given, within the effective-medium approximation, by $R(\omega) = fR_{\text{ins}}(\omega) + (1-f)R_{\text{met}}(\omega)$. In conductivity, σ , this mixed-phase response would give rise to an anomalous variation in phonon intensities with doping.

The influence of doping on the spectral response of $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ may be further examined by considering the optical conductivity, σ , in Fig. 2, obtained from a Kramers-Krönig transformation of the reflectivity data in Fig. 1. The σ of the insulating phase ($x=0$) exhibits phonons at low frequencies, a broad gap to electronic excitations, and an absorption edge near 1.5 eV. The absence of electronic absorption below this gap edge indicates negligible doping from O vacancies or other electrically active impurities. Light doping ($x=0.04$ electrons/unit cell) produces a large increase in low-frequency spectral

FIG. 2. Room-temperature (300 K) frequency-dependent conductivity, $\sigma(\omega)$, of $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ for a series of Ce concentrations x . These spectra were obtained from Kramers-Krönig transformations of the reflectivity spectra in Fig. 1.

weight, as well as a substantial decrease in spectral weight above the charge-transfer gap ($\omega > 1.5$ eV). The change in the optical conductivity is more clearly illustrated in Fig. 3, which shows the incremental changes in conductivity $\sigma_i - \sigma_j$ that occur between successive levels of doping. Here, the incremental change in conductivity,

FIG. 3. (a) Incremental change in the conductivity [$\sigma_i - \sigma_j$, where $\sigma_i \equiv \sigma(x_i)$] across the metal-insulator transition, i.e., between the insulating ($x=0$) and most lightly doped ($x=0.04$) phases. (b) Incremental change in the conductivity ($\sigma_i - \sigma_j$) between metallic phases, including $\sigma(x=0.12) - \sigma(x=0.04)$ and $\sigma(x=0.2) - \sigma(x=0.12)$.

$\sigma_i - \sigma_j$, is defined so that $\sigma_i - \sigma_j \equiv \sigma(x_i) - \sigma(x_j)$. The transfer of spectral weight as x changes across the metal-insulator transition is evident in Fig. 3(a), which plots the optical conductivity difference, $\sigma_i - \sigma_j$, between crystals with $x = 0.04$ and $x = 0$. Notably, increases in σ below 1.5 eV consist of two parts: a contribution centered at $\omega = 0$, presumably arising from mobile carriers, and a broad mid-infrared absorption band centered near 0.4 eV ($\sim 3000 \text{ cm}^{-1}$). Further doping ($x \geq 0.04$), as shown in Figs. 2 and 3(b), leads to a continued increase in the low-frequency mobile carrier contribution, but to little additional change in the mid-infrared and charge-transfer bands. These differences in growth rate distinguish between the mobile carriers and the mid-infrared absorption even when the two bands are not spectroscopically resolved. The presence of this two-component σ , and its behavior with doping, is similar to that observed in p -type high- T_c compounds $\text{YBa}_2\text{Cu}_3\text{O}_{6+x}$ (Ref. 8) and $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$.³

The doping dependence of the total integrated spectral weight below the charge-transfer band edge at 1.5 eV is shown for both $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ (triangles) and $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$ (solid circles) in Fig. 4. The integrated spectral weight, or normalized effective carrier density $N_{\text{eff}}(\omega)$, is defined by

$$N_{\text{eff}}(\omega) = \frac{2mV_{\text{cell}}}{\pi e^2} \int_0^\omega \sigma(\omega') d\omega', \quad (1)$$

where V_{cell} is the unit-cell volume divided by 2 (for the two Cu atoms per unit cell), m is the free electron mass, and e is the electron charge. The dashed lines are the weight calculated by assuming that each acceptor or donor contributes one carrier with an effective mass m^* equal to the free electron mass m_e . It is clear from Fig. 4 that the spectral weight below 1.5 eV is larger than that

FIG. 4. The total integrated spectral weights of the optical conductivities in both $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ (triangles) and $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$ (solid circles) up to $\omega = 1.5$ eV, plotted as a function of concentration x . The data from $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$ were taken from Ref. 3, while values for $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ were calculated from $\sigma(\omega)$ in Fig. 2 using Eq. (1) in the text. The dashed lines represent the anticipated spectral weight contributions from Ce or Sr substitution alone, assuming $m^* = m_e$ and that each Ce or Sr atom donates 1 mobile carrier/unit cell.

expected from the carrier concentration alone, suggesting that some charge-transfer spectral weight has shifted to low frequencies as a function of doping. Significantly, the integrated spectral weight below 4 eV in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$ was found to be approximately independent of doping,³ also indicating that spectral weight is redistributed to low frequencies from the charge-transfer band with doping. As illustrated in both Figs. 3(a) and 4, the redistribution of weight in $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ occurs at very low doping ($x \leq 0.04$), while additional increases in spectral weight for $x > 0.04$ are consistent with increases in the donor concentration alone [Fig. 3(b)]. Therefore, these data suggest two consequences of doping: first, the addition of x mobile carriers into a Drude-like band centered at $\omega = 0$, and second, an abrupt shifting of spectral weight from the charge-transfer gap to a mid-infrared band near the metal-insulator transition. Furthermore, a comparison of the two sides of Fig. 4 illustrates the qualitative symmetry between electron and hole doping.

The above experimental results are difficult to reconcile with simple models of doping in a charge-transfer insulator, in which one expects a weak dependence of spectral weight in the charge-transfer gap on doping, a spectral weight below the fundamental gap that scales with x , and a prominent particle-hole asymmetry that leads to more low-frequency spectral weight in the hole-doped than in the electron-doped materials. These simple expectations may be understood by first recalling that the CuO_2 planes in Pr_2CuO_4 and La_2CuO_4 are believed to contain one hole per CuO_2 unit, with the holes residing primarily on the Cu site. These materials are insulating because an energy difference $\epsilon_p - \epsilon_d$ inhibits promotion of a hole from Cu to O orbitals (i.e., charge transfer), and a larger correlation energy U inhibits double occupancy of a Cu site by holes.

When the CuO_2 planes are doped by electrons, as is indicated by room-temperature Hall effect data in $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$,⁵ the electrons eliminate holes by principally residing on Cu sites. Doping with x electrons/unit cell is expected to result in two optical processes: (1) The itinerant motion of holes, having relative spectral weight x (allowed because some Cu sites are now unoccupied); (2) charge-transfer absorption processes, having spectral weight $(1-x)$ (reduced from that in the insulator because x Cu sites no longer contain holes). In contrast, if the CuO_2 planes are doped by holes, as is indicated in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_{4-\delta}$ by Hall effect data,⁹ these carriers must reside on O sites. In this case, it is believed¹⁰ that each hole binds to a Cu spin, forming a local singlet. This binding should give rise to three allowed optical processes: (1) itinerant motion of singlets, having a spectral distribution centered at $\omega = 0$ with spectral weight x ; (2) unbinding of the O hole from the Cu spin, giving a contribution centered at finite frequency $\omega_0 \sim t_{pd}^2/\epsilon_p - \epsilon_d < \epsilon_p - \epsilon_d$ and also having relative weight x ; (3) Cu-O charge-transfer processes, having spectral weight that is only weakly doping dependent (since the number of occupied Cu sites is not changed by hole doping). Quantitative calculations of these effects for a $2d$ CuO_2 lattice with realistic parameters have not yet been performed. However, a particle-hole asymmetry in the optical properties is expected within the above picture, as may be illustrated by compu-

tation of the optical conductivity for simple Cu-O clusters and by approximate auxiliary boson calculations for infinite lattices.¹¹

It is evident from our data that $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ does not evolve with doping in a manner expected of a doped charge-transfer insulator, suggesting that such a simple picture is not adequate for describing these materials. In particular, the anomalously large growth of mid-infrared spectral weight near the metal-insulator transition of $\text{Pr}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$, and the concomitant decrease of weight above the ~ 1.5 eV gap, is unexpected. This behavior also differs from that observed in $\text{BaPB}_{1-x}\text{Bi}_x\text{O}_3$ (Ref. 12) and in doped semiconductors¹³ (e.g., Si:P), where the low-frequency spectral weight N_{eff} scales linearly with the number of donors. Notably, a recent photoemission study on $\text{Nd}_{2-x}\text{Ce}_x\text{CuO}_{4-\delta}$ has also concluded that electronic states near the Fermi level in the

metallic phases evolve from higher-frequency states found in the insulating phase.¹⁴ Our results illustrate not only that low-frequency weight in the metallic phases derive specifically from the charge-transfer band in the insulating phase, but also that this transferred weight goes principally into a mid-infrared band as the system is lightly doped.

Note added in proof. Using a first-principles density functional description of the Cu-O plane electronic structure, Hybertsen *et al.*¹⁵ find that the low-frequency carrier dynamics of the high- T_c cuprates exhibit a remarkable symmetry between electron and holes, in qualitative agreement with the data presented here.

We wish to thank B. Batlogg, R. N. Bhatt, M. Hybertsen, T. T. M. Palstra, B. S. Shastry, and C. M. Varma for helpful discussions.

¹J. G. Bednorz and K. A. Müller, Z. Phys. B **64**, 189 (1986).

²M. K. Wu, J. Ashburn, C. J. Torng, P. H. Hor, R. L. Meng, L. Gao, Z. J. Huang, Y. Q. Wang, and C. W. Chu, Phys. Rev. Lett. **58**, 908 (1987).

³S. Tajima, S. Tanaka, T. Ido, and S. Uchida (unpublished).

⁴H. Mook, G. Aeppli, S-W. Cheong, and Z. Fisk (private communication).

⁵H. Takagi, S. Uchida, and Y. Tokura, Phys. Rev. Lett. **62**, 1197 (1989).

⁶G. H. Kwei, S-W. Cheong, Z. Fisk, F. H. Garzon, J. A. Goldstone, and J. D. Thompson, Phys. Rev. B **40**, 9370 (1989).

⁷S. Tajima, H. Ishii, T. Nakahashi, T. Takagi, S. Uchida, M. Seki, S. Suga, Y. Hidaka, M. Suzuki, T. Murakami, K. Oka, and H. Unoki, J. Opt. Soc. Am. B **6**, 475 (1989).

⁸S. L. Cooper, G. A. Thomas, J. Orenstein, D. H. Rapkine, M. Capizzi, T. Timusk, A. J. Millis, L. F. Schneemeyer, and J. V. Waszczak, Phys. Rev. B **40**, 11 358 (1989); J. Orenstein, G.

A. Thomas, A. J. Millis, S. L. Cooper, D. H. Rapkine, T. Timusk, L. F. Schneemeyer, and J. V. Waszczak Phys. Rev. B (to be published).

⁹N. P. Ong, Z. Z. Wang, J. Clayhold, J. M. Tarascon, L. H. Green, and W. R. McKinnon, Phys. Rev. B **35**, 8807 (1987).

¹⁰T. M. Rice and F. C. Zhang, Phys. Rev. B **37**, 815 (1989).

¹¹M. Grill, B. G. Kotliar, and A. J. Millis (private communication).

¹²S. Tajima, S. Uchida, A. Masaki, H. Takagi, K. Kitazawa, S. Tanaka, and A. Katsui, Phys. Rev. B **32**, 6302 (1985).

¹³G. A. Thomas, M. Capizzi, F. De Rosa, R. N. Bhatt, and T. M. Rice, Phys. Rev. B **23**, 5472 (1981).

¹⁴J. W. Allen, C. G. Olson, M. B. Maple, J.-S. Kang, L. Z. Liu, J.-H. Park, R. O. Anderson, W. P. Ellis, J. T. Markert, Y. Dalichaouch, and R. Liu, Phys. Rev. Lett. **64**, 595 (1990).

¹⁵Mark S. Hybertsen, E. B. Stechel, M. Schluter, and D. R. Jennison, Phys. Rev. B (to be published).