Lawrence Berkeley National Laboratory

Recent Work

Title

CALCULATED BAND STRUCTURE AND REFLECTIVITY SPECTRA OF ZnGeP₂

Permalink

<https://escholarship.org/uc/item/169909m4>

Authors

Alvarez, Carmen Varea de
Cohen, Marvin L.

Publication Date

1973

CALCULATED BAND STRUCTURE AND REFLECTIVITY
SPECTRA OF ZnGeP_2

Carmen Varea de Alvarez and
Marvin L. Cohen

January 1973

RECEIVED
LAWRENCE
BERKELEY LABORATORY

LIBRARY AND
DOCUMENTS SECTION

Prepared for the U.S. Atomic Energy Commission
under Contract W-7405-ENG-48

For Reference

Not to be taken from this room

LBL-1480

c/

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

Calculated Band Structure and Reflectivity Spectra
of ZnGeP_2 .^{*}

Carmen Varea de Alvarez and Marvin L. Cohen

Department of Physics, University of California

and

Inorganic Materials Research Division, Lawrence Berkeley Laboratory

Berkeley, California 94720

Abstract

The imaginary part of the dielectric function, the energy band structure, reflectivity and modulated reflectivity of the ternary compound ZnGeP_2 are calculated using the Empirical Pseudopotential Method. A critical point analysis in the Brillouin Zone (BZ) is discussed in detail to explain prominent optical structure. Spin-orbit corrections to the band structure were calculated at a few points in the BZ.

There has been much interest recently in the structure of the reflectivity and modulated reflectivity spectra of II-IV-V₂ materials that crystallize in the chalcopyrite structure. Being the closest analogs of the III-V zincblende crystals, with electronic and optical properties close to those of its zincblende (zb) analogs, chalcopyrite crystals show considerably more structure in the experimental reflectivity and electreflectance spectrum¹ than that of the III-V compounds.

^{*}Supported in part by the National Science Foundation Grant GH 35688.

The chalcopyrite real space unit cell can be thought of as composed of two zb unit cells stacked and compressed along the c-axis. The two cations of the II-IV-V₂ crystal are in alternating positions along the c-axis substituting the cation in the III-V crystal. The anion is slightly displaced from its original position closer to the group IV cation (except in the ZnSn compounds). Using this real space structure, the zb BZ can be multiply mapped four times completely into the smaller chalcopyrite BZ.

Using a quasicubic model, transitions between the valence and conduction band of a chalcopyrite crystal have been divided by Shay² into two categories:

Direct transitions--those originating from direct transitions in a zb crystal.

Pseudodirect transitions--those originating from indirect transitions in a zb crystal.

It is important to determine if the reflectivity peaks are caused by direct or pseudodirect transitions and to what extent the band structure of a II-IV-V₂ crystal is only a slight perturbation of the band structure of its cubic analog.

We report here the first calculation of the reflectivity $R(\omega)$ as functions of photon energy ω for a II-IV-V₂ crystal in the chalcopyrite structure. The main purpose of this work is to identify the regions in the BZ responsible for the main structure in the measured¹ reflectivity and electroreflectance spectrum common to most of these compounds.

The crystal we have considered is ZnGeP_2 the analog of GaP; its crystal parameters are $a = 5.46\text{\AA}$, $c = 10.71\text{\AA}$ and $u = 0.2582$ (all at room temperature). The method used to calculate the energy bands and dipole matrix elements is the Empirical Pseudopotential Method.³ No attempt is made to fit the pseudopotential form factors $V(q)$ to experiment.

We define symmetric, antisymmetric, and antisymmetric cation pseudopotential form factors in the following way: $V_S = \frac{1}{4}(V_{\text{Ge}} + V_{\text{Zn}} + 2V_P)$, $V_A = \frac{1}{4}(V_{\text{Ge}} + V_{\text{Zn}} - 2V_P)$ and $V_A^C = \frac{1}{2}(V_{\text{Zn}} - V_{\text{Ge}})$. Our starting point was the form factors of GaP⁴ and Ge⁵; it is assumed that $V_S = V_S^{\text{GaP}}$ and $V_A^C = V_{\text{Ge}} - V_{\text{Ga}}$. For large wavevector, $\vec{q}$, the pseudopotential curves for GaP and Ge were free hand extrapolated. For $q^2 < 4(\frac{2\pi}{a})^2$ the pseudopotential curves were extrapolated to agree with $V_{\text{Zn}}(q=0) = V_{\text{Ge}}(q=0) = V_P(q=0) = -\frac{2}{3}\epsilon_F$, where ϵ_F is the Fermi level appropriate to the total number of valence electrons in this crystal. The method of calculation has been described elsewhere,³ hence we just give the parameters particular to this calculation. The wavefunctions were expanded in a set of 69-84 plane waves, 244 additional plane waves were used through the perturbation scheme developed by Löwdin.⁶ The energies and wavefunctions were calculated in 1/16 of the BZ at 288 grid points, and the $\epsilon_2(\omega)$ integration over k-space was performed by the method developed by Gilat and Raubenheimer⁷ in what we call the Practical Brillouin Zone (PBZ). The PBZ was chosen in the following way: it can easily be shown that the region in k-space surrounded by the planes $k_z = 0$, $k_z = 2\pi/c$, $k_x = k_y$, $k_y = 0$ and $k_z = \pi/a$ is completely equivalent to the usual irreducible part of the BZ (i.e. 1/16 of

the full BZ).

Spin orbit corrections were carried out at a few points in the BZ by extending the zb calculation.⁸ The fact that we are dealing with three kinds of atoms and a total of eight atoms in the primitive cell presents no problem, but the ratios of the cation spin orbit contribution to the anion spin orbit contribution have to be evaluated;⁹ this leaves us with one spin-orbit parameter which we choose to be that of Ge. The procedure now would be to fit this parameter to the spin-orbit splitting Δ_{SO} at the Γ point of the BZ. Since not much is known about Δ_{SO} for ZnGeP_2 , the parameter we choose was the one that gives the correct spin-orbit splitting for Ge in the diamond structure. The eigenvalues of the spin-orbit Hamiltonian involve the diagonalization of a 138×138 matrix and the computer time involved is too big to do calculations over the entire BZ.

A few remarks about notation: the point group of chalcopyrite structure is D_{2d}^{12} and the notation for symmetry points we use is that of Zak¹⁰. Inside square parentheses we will show the symmetry in the zb BZ from the quasicubic model; e.g. $X_1[\Sigma_2]$ denotes a wavefunction with symmetry X_1 originating from a Σ_2 wavefunction in the zb case.

In Fig. 1 we show the calculated band structure for ZnGeP_2 along some important symmetry directions. As one would expect from a quasicubic model for ZnGeP_2 , this band structure shows that the most important deviations from the band structure of a zb material (when folded into the chalcopyrite BZ) are at points where two bands with the same symmetry in the D_{2d}^{12} representation are degenerate in the latter band structure.

There is some controversy about the structure of the first gap of ZnGeP_2 . R. A. Bendorius et al.¹¹ find an absorption edge of 2 eV with a hydrostatic pressure coefficient of $dE_{\text{gap}}/dP = 1.2 \times 10^{-6}$ eV/bar; this indicates¹² that the first absorption edge of ZnGeP_2 is a pseudodirect gap $\Gamma_5[\Gamma_{15}] \rightarrow \Gamma_3[X_1]$ with small mixing of X_1 with Γ_1 . But values as different as 1.81 eV and 2.25 eV¹³ have been reported for the first absorption edge. Some reports indicate that the first direct gap is around 2.5 eV with a crystal field splitting of $\sim .08$ eV. First order perturbation theory predicts that crystal field splitting depends only on the tetragonal compression of the crystal, and therefore it depends only on the slopes of the pseudopotential curves near the reciprocal lattice vectors (2,0,0), (2,2,0) and (3,1,2). It would be easy to adjust the pseudopotential curves to give the observed crystal splitting. Calculated matrix elements for pseudodirect transitions $\Gamma_{15} - X_1$ are too weak to be observed in the reflectivity spectrum.

Recently much attention has been concentrated on the E_1 region of the II-IV-V₂ reflectivity spectrum. In the zb materials this region contains two spin-orbit split peaks E_1 and $E_1 + \Delta_1$. In the II-IV-V₂ crystals there is much more structure. Stokowski¹ has examined ZnSiAs_2 , CdSiAs_2 , CdSnAs_2 and CdSnP_2 . He suggests that the spectra are similar in the E_1 region and he labels the peaks $E_1(1)$, $E_1(2)$, $E_1(3)$ and $E_1(4)$. He also finds some structure at higher energies E_{C1} , E_{C2} and E_{C3} but these do not appear in all the crystals. At this point our calculations yield information on only part of the E_1 region (see table). The low energy part (the first two peaks which may be $E_1(1)$ and $E_1(2)$ for small spin-orbit splitting) come from transitions in the

N plane¹⁰ in the (X,X,2X) direction, and we get two peaks when spin-orbit splitting is included. We agree with Stokowski that the four peaks cannot arise from two spin-orbit split bands.¹¹ Analysis of dipole matrix elements give the $E_1(1)$ peak to be stronger in parallel polarization in agreement with experiment. We find two more pieces of structure above $E_1(1)$ and $E_1(2)$ which may be associated with $E_1(3)$ and $E_1(4)$, but further analysis is necessary before we can make definite assignments. From our critical point analysis, we conclude that the additional structure of the E_1 peak is mainly the result of strong mixing in the N plane ((x,x,z)) originating at the crossing point of the $\Gamma - \Sigma$ and W - L conduction bands on the (x,x,0) line, and also form strong mixing at the point X of the chalcopyrite BZ. For most z_b materials, the Σ_2 valence band at $(\frac{1}{2}, \frac{1}{2}, 0)$ is almost degenerate with the L_3 valence band.⁵ In the chalcopyrite structure these two points map into X; $X(L_3)$ is four-fold degenerate and $X_1(\Sigma_2)$ two-fold degenerate, the tetragonal compression splits the $X(L_3)$ level in two double degenerate levels. When the anti-symmetric cation potential is turned on, the interaction between these levels is quite strong allowing all three transitions to the bottom of the conduction band $X_1[L_1]$. Calculations in the E_C (3.9 - 4.1 eV) region yield a peak which is caused by one of these transitions $X_1[L_3 + \Sigma_2] \rightarrow X_1[L_1]$ between bands 11, 12 and 17, 18. This transition is allowed in both parallel and perpendicular polarization, but stronger in parallel polarization.

As shown in the table, most of the contribution to the E_2 structure comes from direct transitions in the Δ and Σ directions of the analog. The Δ

direction folds into the Δ , Λ and $(x, 0, 1)$ directions of the chalcopyrite BZ while the Σ direction is folded into the Σ , $(x, 0, x)$ and $(1-x, 0, 1-2x)$ directions. Partial summation over k space in these directions shows that in effect the E_2 peak is mainly a Δ , Σ peak. Additional structure in the E_2 peak comes from direct and pseudodirect transitions around the point $(\frac{1}{4}, \frac{1}{4}, \frac{1}{2})$ ($[\frac{1}{4}, \frac{1}{4}, \frac{3}{4}]$ in the cubic BZ). This point is three fold degenerate in the absence of crystal field splitting and antisymmetric cation potential, therefore the mixing is quite large. It is interesting to notice that $k = (\frac{1}{4}, \frac{1}{4}, \frac{1}{2})$ is the representative k -point for calculating the charge density¹⁵ for tetragonal body-centered structures.

The intensity of the E_2 peak is considerably reduced when compared with the intensity of the E_2 peak for zb crystals but still higher than the measured E_2 peak which is smaller in magnitude than the E_1 peak for most chalcopyrites.

After this calculation was completed, Petroff et al.¹⁶ did a reflectivity and wavelength modulation experiment for ZnGeP_2 . Their results show an E_1 and E_2 peak of the same intensity and are otherwise similar to our theoretical results. In fact, if the entire theoretical spectra were shifted to lower energies by around 0.3 eV, the agreement between theory and experiment for almost all the optical structure is very good. This is encouraging since no experimental data (except for structure constants) for ZnGeP_2 were used in our calculations. This result suggests that small changes in the pseudopotential form factors could give theoretical spectra in excellent agreement with experiment.

We would like to thank Dr. Y. Petroff for stimulating discussions.

Part of this work was done under the auspices of the U. S. Atomic Energy Commission.

References

1. J. L. Shay, E. Buehler, and J. H. Wernick, Phys. Rev. B2, 4104 (1970) and Phys. Rev. B3, 2004 (1971); J. L. Shay and E. Buehler, Phys. Rev. B3, 2598 (1971) and Phys. Rev. B4, 2479 (1971); S. E. Stokowski, Phys. Rev. B6, 1294 (1972); C. C. Y. Kwan and J. C. Woolley, Canad. J. Phys. 48, 2085 (1970); Phys. stat. sol. (b) 44, K93 (1971); Appl. Phys. Letters 18, 520 (1971); R. K. Karymshakov, Y. I. Ukhanov, and Y. V. Shmartsev, Fiz. Tekh. Poluprov. 5, 514 (1971) [Sov. Phys.-Semiconductors 5, 450 (1971)]; J. Kavaliauskas, G. F. Karavaev, E. I. Leonov, V. M. Orlov, V. A. Chaldyshev and A. Shileika, Phys. stat. sol. (b) 45, 443 (1971). [See also Ref. 11.]
2. J. E. Rowe and J. L. Shay, Phys. Rev. B3, 451 (1971).
3. M. L. Cohen and V. Heine, Solid State Physics 24, 37 (1970).
4. J. P. Walter and M. L. Cohen, Phys. Rev. 183, 763 (1969).
5. M. L. Cohen and T. K. Bergstresser, Phys. Rev. 141, 789 (1966).
6. P. Löwdin, J. Chem. Phys. 19, 1396 (1951).
7. G. Gilat and L. J. Raubenheimer, Phys. Rev. 144, 390 (1966).
8. G. Weisz, Phys. Rev. 149, 504 (1966); S. Bloom and T. K. Bergstresser, Solid State Commun. 6, 4651 (1968).
9. F. Herman and S. Skillman, Atomic Structure Calculations, (Prentice-Hall, Inc., Englewood Cliffs, N. J., 1966).
10. J. Zak, The irreducible representations of space groups (W. A. Benjamin, New York, 1969).

11. R. A. Bendorius, G. Z. Krivaite, A. Yu. Shileika, G. F. Karavaev, and V. A. Chaldyshev, International Conference on Semiconductors, Warsaw (1972) (to be published). R. Bendorius, V. D. Prochukhan and A. Shileika, Phys. stat. sol. (b) 53, 745 (1972).
12. W. Paul in Les proprietes physiques des solides sous pression, Colloques Internationaux du Centre National de la Recherche Scientifique, Grenoble, 1969, p. 199.
13. S. Isomura and K. Masumoto, Phys. stat. sol. 13, 223 (1972), report a value of 1.81 eV while B. Ray, A. S. Payne, and G. Burrell, Phys. stat. sol. 35, 197 (1969) report a value of 2.25 eV.
14. Y. Petroff (private communication).
15. J. Chadi and M. L. Cohen, to be published in Phys. Rev. B. A. Baldareschi, Bull. A.P.S., March 1972, p. 237.
16. Y. Petroff, S. Kohn and Y. R. Shen, International Conference on Modulation Spectroscopy, Nov. 23-26, 1972, Tucson, Arizona.

Table Caption

Table I Energies, critical point symmetry, and location in the Brillouin Zone for transitions responsible for prominent structure in the reflectivity of ZnGeP_2 .

Figure Captions

Fig. I Band structure of ZnGeP_2 along principal symmetry directions, irreducible part of the BZ and PBZ (dotted lines) showing the notation for symmetry points used in this work.

Fig. II Calculated reflectivity spectrum for ZnGeP_2 in the parallel and perpendicular polarizations.

Table I. Reflectivity Structure (eV)

Theory	Polarization	Peak	Location in zone	Symmetry	cp— energy (eV)
	, ⊥	A	$\Gamma_2-\Gamma_1$	M_0	2.31*
	⊥	B	$\Gamma_1-\Gamma_1$	M_0	2.27*
	, ⊥	C	$\Gamma_2-\Gamma_1$	M_0	2.43*
3.04	(⊥)	E_1	$X_1-X_1(15, 16-17, 18)$	M_0	3.04 { 3.05* 3.03*
3.37	⊥		$X_1-X_1(13, 14-17, 18)$	M_0	3.36 { 3.35* 3.37*
3.41	, ⊥		$N_1-N_1(16, 17)$ at (0.2, 0.2, 0.4)	M_1	3.42*
3.41	⊥,		$N_2-N_1(15, 17)$ at (0.2, 0.2, 0.4)	M_1	3.50*
3.5	⊥ ()		Vol in N plane centered near (0.3, 0.3, 0.38)	-	3.55
3.89	(⊥)	E_c	$X_1-X_1(11, 12-17, 18)$	M_0	3.87
4.76		E_2	$\Delta(15-17)$ at (0.34, 0, 0)	M_2	4.76
4.77	⊥		$\Gamma_5-\Gamma_3(12, 13-18)$ and along Σ and Λ	M_1	4.77
4.96	⊥		$X_1-X_1(15, 16-19, 20)$ and along Σ	M_1	4.9
5.05			(0.47, 0.16, 0.06) (14-17)	M_1	4.99
			$N_2-N_2(13-18)$ (0.25, 0.25, 0.5)		5.00
5.1	⊥		$N_1-N_2(14-20)$ (0.25, 0.25, 0.5)	M_0	5.11
5.21	(⊥)		$\Delta-\Delta(15-18)$ at (0.5, 0, 0)	M_2	5.18

* Spin orbit Hamiltonian included.

k
Fig. 1

Fig. 2

LEGAL NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

TECHNICAL INFORMATION DIVISION
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720