

Lawrence Berkeley National Laboratory

Recent Work

Title

X-RAY EMISSION SPECTROSCOPY STUDY OF IRON SILICATE CATALYST FEZSM-5

Permalink

<https://escholarship.org/uc/item/1fj642kt>

Authors

Csencsits, R.

Lyman, C.E.

Bronsky, R.

Publication Date

1988-03-01

c. 2

Center for Advanced Materials

CAM

RECEIVED
LAWRENCE
BERKELEY LABORATORY

JUN 17 1988

LIBRARY AND
DOCUMENTS SECTION

To be presented at the 46th Annual Meeting of the Electron
Microscopy Society of America, Milwaukee, WI,
August 7-12, 1988


X-Ray Emission Spectroscopy Study of Iron Silicate Catalyst FeZSM-5

R. Csencsits, C.E. Lyman, and R. Gronsky

March 1988

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.*



Materials and Chemical Sciences Division

Lawrence Berkeley Laboratory • University of California

ONE CYCLOTRON ROAD, BERKELEY, CA 94720 • (415) 486-4755

LBL-25172

c. 2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

X-RAY EMISSION SPECTROSCOPY STUDY OF IRON SILICATE CATALYST FeZSM-5

R. Csencsits*, C.E. Lyman** and R. Gronsky*

*Center for Advanced Materials, Materials and Chemical Sciences Division, Lawrence Berkeley Laboratory, and Materials Science and Mineral Engineering Department, University of California, Berkeley, CA

**Materials Science and Engineering Department, Lehigh University, Bethlehem, PA 18015

Iron silicate analogs of the zeolite ZSM-5 may be directly synthesized from iron silicate gels in a manner which differs slightly from the aluminosilicate ZSM-5.¹ The resultant white, crystalline iron silicate is referred to as FeZSM-5 in the as-synthesized form. Thermal treatment removes the organic crystal-directing agent and moves some of the framework iron into non-framework sites producing the calcined form of the molecular sieve FeZSM-5.²⁻⁴ Homogeneity in the distribution of catalytic iron throughout the particles is desired in an optimal catalyst. Distribution of the iron throughout the framework in the as-synthesized forms would affect the final distribution of catalytic iron in the calcined and steamed forms; thus, the iron distribution throughout the as-synthesized and calcined forms of FeZSM-5 were studied using the high spatial resolution of the analytical electron microscope.

X-ray emission spectroscopy (XES) performed in the transmission electron microscope (TEM) and the scanning transmission electron microscope (STEM) was used to determine the inter- and intra-particle composition variations for FeZSM-5. For the purposes of this discussion, the word "particle" is used to describe the particle agglomerates not the individual crystallites making up the agglomerate, as shown in Fig. 1. The effects of gel iron concentration, stirring during crystallization, particle size, as well as thermal treatment were considered. Specimens consisted of uniformly thin (90-100nm) sections of the iron silicate particles embedded in an acrylic resin (Fig. 1).⁵ These microtomed specimens met the thin-film conditions for XES (<150nm), thus absorption and fluorescence corrections were neglected.⁶

Energy dispersive x-ray spectra (EDS) of all FeZSM-5 samples showed silicon and iron peaks corresponding to the iron silicate molecular sieve particles, and copper peaks resulting from the copper support grids. Spectra collected using the Vacuum Generators HB-501 STEM equipped with a Link Analytical windowless x-ray detector also showed oxygen and carbon peaks corresponding to the catalyst and the carbon coating (applied to prevent charging) (Fig. 2). In some spectra, a small chromium peak was observed; this was probably due to a small amount of chromium contamination from the stainless steel crystallization vessel.

In the TEM, XES has shown that the Si/Fe-ratio of the as-synthesized FeZSM-5 particle aggregates is independent of particle size and stirring, although the homogeneity of the inter-particle iron distribution does improve slightly with stirring. As expected, thermal treatments do not significantly change the average Si/Fe-ratios of the FeZSM-5; however, the particle to particle variations do increase, particularly in very low iron samples.

Line profiles obtained in the STEM of 150nm wide calcined FeZSM-5 particles stirred during crystallization, showed that areas of very high iron concentration appear most frequently near the particle edges (Fig. 3). This suggests that iron migrates to and agglomerates on the surface during calcination.

Line profiles and spectra of calcined FeZSM-5, grown without stirring show increased iron concentration at the center of the particle agglomerate as compared to the agglomerate edges. This concentration gradient might be the result of enhanced iron incorporation during crystal nucleation, while continued crystal growth may occur from an iron-depleted gel.⁷

References

1. R. Szostak and T.L. Thomas, *J. Catal.* **100**, 555 (1986).
2. R. Szostak, V. Nair and T.L. Thomas, *J. Chem. Soc. Faraday* **83**, 487 (1987).
3. V. Nair, PhD Thesis, Georgia Institute of Technology, Atlanta, GA, 1987.
4. A. Meagher, V. Nair and R. Szostak, *Zeolites* (in press).
5. R. Csencsits, C. Schooley and R. Gronsky, *J. Electr. Microsc. Tech.* **2**, 643 (1985).
6. C.E. Lyman, P.W. Betteridge and E.F. Moran, *Intrazeolite Chemistry*, (American Chemical Society, Washington, D.C., 1983), pp.199-215.
7. The assistance of Dr. J.R. Michael and the Bethlehem Steel Corporation, Dr. R. Szostak and Dr. V.

Nair of the Zeolite Research at the Georgia Institute of Technology are gratefully acknowledged. This work has been supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Sciences Division, U.S. Department of Energy, under Contract DE-AC03-76SF00098 and under Contract DE-FG02-86ER45269.






FIG. 1-TEM image of microtomed thin section of stirred, as-synthesized FeZSM-5, embedded in acrylic resin. Bar = 100 nm. XBB 870-9599

FIG. 2-Representative x-ray spectrum taken on HB-501 STEM from calcined FeZSM-5 grown from unstirred gel with Si/Fe \approx 25. XBL 883-696

FIG. 3-Iron and silicon line profiles through stirred, calcined FeZSM-5 particle (Si/Fe \approx 25), showing high iron concentration near edge. Bar = 50 nm. XBL 883-697

*LAWRENCE BERKELEY LABORATORY
TECHNICAL INFORMATION DEPARTMENT
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720*