

Lawrence Berkeley National Laboratory

Advanced Light Source

Title

Development of near atomically perfect diffraction gratings for EUV and soft x-rays with very high efficiency and resolving power

Permalink

<https://escholarship.org/uc/item/1q9326m0>

Author

Anderson, Erik

Publication Date

2012-09-03

Development of near atomically perfect diffraction gratings for EUV and soft x-rays with very high efficiency and resolving power

D.L. Voronov,^{1,*} E.H. Anderson,¹ R. Cambie,¹ Peter Gawlitza,² L.I. Goray,³ E.M. Gullikson,¹
F. Salmassi,¹ T. Warwick,¹ V.V. Yashchuk,¹ and H.A. Padmore¹

¹Lawrence Berkeley National Laboratory, 1 Cyclotron Road, Berkeley, CA 94720, USA

²The Fraunhofer Institute for Material and Beam Technology, Winterbergstraße 28 01277 Dresden, Germany

³Saint Petersburg Academic University, 8/3 Khlopina, St. Petersburg, 194021, Russia

*email: dlvoronov@lbl.gov

ABSTRACT

Multilayer-coated Blazed Gratings (MBG) can offer high diffraction efficiency in high order with a high groove density are potentially of great importance for a wide range of extreme ultraviolet (EUV) and soft x-ray applications including EUV lithography and high-resolution Resonance Inelastic X-ray Scattering. The main challenges to realizing these optical elements are fabrication of nano-period sawtooth substrates with perfect groove profile and atomically smooth surface of the blazed facets, as well as deposition of a multilayer on the highly corrugated surface of the substrates. We report on recent progress achieved at the Advanced Light Source (ALS) on development, fabrication, and characterization of ultra-dense MBGs. Saw-tooth substrates with groove density up to 10,000 l/mm were fabricated using e-beam and interference lithography techniques followed by wet anisotropic etching of silicon. Growth of multilayers (ML) deposited on the sawtooth substrates via different sputter deposition techniques was investigated. The smoothening of the grooves in the course of multilayer deposition was found to affect greatly the blazing ability of the grating and can result in significant degradation of the diffraction efficiency. The deposition of the MLs was optimized to obtain good replication of the saw-tooth surface by the multilayer interfaces with minimal distortion of the groove shape by the growth process. The gratings coated with a variety of MLs demonstrated record diffraction efficiency in EUV wavelength range, for example with the achievement of 44% diffraction efficiency for a 5000 l/mm grating. Simulations of diffraction efficiency of soft x-ray MBGs showed that the efficiency of an optimized grating relative to the reflectance of the multilayer can approach 100%. This work now shows a direct route to achieving high diffraction efficiency in high order at wavelengths throughout the soft x-ray energy range with revolutionary applications in synchrotron science.

Key words: diffraction grating, multilayer, interference lithography, e-beam lithography, EUV, soft x-rays

The work was supported by the US Department of Energy under contract number DE-AC02-05CH11231.

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.