Lawrence Berkeley National Laboratory

Recent Work

Title

CRYSTAL STRUCTURES AND LATTICE PARAMETERS OF THE COMPOUNDS OF BERKELIUM.
IV. BERKELIUM TRIFLUORIDE

Permalink

<https://escholarship.org/uc/item/1mn5c30t>

Authors

Peterson, J.R.
Cunningham, B.B.

Publication Date

1967-11-01

ej. 2

University of California

Ernest O. Lawrence Radiation Laboratory

CRYSTAL STRUCTURES AND LATTICE PARAMETERS
OF THE COMPOUNDS OF BERKELIUM.
IV. BERKELIUM TRIFLUORIDE

J. R. Peterson and B. B. Cunningham

November 1967

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

UCRL-17912
ej. 2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

Submitted to
J. Inorg. Nucl. Chem.

UCRL-17912
Preprint

UNIVERSITY OF CALIFORNIA

Department of Chemistry and Lawrence Radiation Laboratory
Berkeley, California

AEC Contract No. W-7405-eng-48

CRYSTAL STRUCTURES AND LATTICE PARAMETERS OF THE COMPOUNDS
OF BERKELIUM. IV. BERKELIUM TRIFLUORIDE

J. R. Peterson and B. B. Cunningham

November 1967

CRYSTAL STRUCTURES AND LATTICE PARAMETERS OF THE COMPOUNDS
OF BERKELIUM. IV. BERKELIUM TRIFLUORIDE*

J. R. Peterson[†] and B. B. Cunningham

Department of Chemistry and Lawrence Radiation Laboratory
University of California
Berkeley, California

November 1967

ABSTRACT

BkF_3 has been found to exhibit a low-temperature, YF_3 -type orthorhombic structure and a high-temperature, LaF_3 -type trigonal structure. The lattice parameters of these two BkF_3 modifications are: $a_o = 6.70 \pm 0.01$ A, $b_o = 7.09 \pm 0.01$ A, $c_o = 4.41 \pm 0.01$ A (orthorhombic), and $a_o = 6.97 \pm 0.01$ A, $c_o = 7.14 \pm 0.01$ A (trigonal), where the error limits reflect the uncertainties in the derivation of the lattice parameters. The inversion temperature of BkF_3 lies in the range 350 to 600° C.

*The experimental work reported here is taken from a thesis submitted by J. R. Peterson to the Graduate Division of the University of California in partial fulfillment of the requirements for the degree of Doctor of Philosophy.

[†]Present address: Department of Chemistry, The University of Tennessee, Knoxville, Tennessee 37916.

INTRODUCTION

The preparation and crystallographic characterization of two structural forms of berkelium trifluoride are described in this paper.

EXPERIMENTAL

The berkelium used in this work was derived from two separate purification cycles, both carried out as described previously.⁽¹⁾ Mass analyses of the two berkelium solutions showed the Ce and Nd contents to be 0.27 atom percent Ce and 0.06 atom percent Nd in one Bk solution, as contrasted with 9.53 atom percent Ce and 0.03 atom percent Nd in the other. The difference is attributed to the failure of the alcoholic HCl column, used to separate Bk and Ce, in the second purification cycle. The presence of the cerium and californium (from decay of Bk²⁴⁹ at a rate of ~0.2% per day) contaminants prevented the determination of accurate lattice parameters for BkF₃.

Berkelium trifluoride samples were prepared by treatment of the oxides (stuck on a 5-mil Pt wire inside a hole in a 1/8-in Pt rod) with a one-to-two H_{2(g)}-HF(g) mixture at 600° C for one-half hour, followed by a second, similar treatment with a fresh H_{2(g)}-HF(g) mixture. The trifluoride samples were either cooled rapidly to obtain the high-temperature, LaF₃-type trigonal modification, or cooled slowly to obtain the low-temperature, YF₃-type orthorhombic modification. In both cases the samples were cooled in the reaction gas mixture and then flushed with argon gas before removal from the all-Monel vacuum system. The very pale yellow-green trifluoride samples were

"chipped off" the Pt wire into a quartz capillary, which was subsequently evacuated and sealed off for x-ray examination. Further details of the hydrofluorination techniques can be found in reference (2).

X-ray exposure times, using the same diffraction equipment and operating conditions as reported for the oxide work,⁽¹⁾ were from eight to twelve hours on the 0.2 μg BkF_3 samples.

RESULTS AND DISCUSSION

Berkelium trifluoride was found to exist in both the LaF_3 -type trigonal structure,⁽³⁾ characteristic of the lanthanide trifluorides of La through Pm, and the YF_3 -type orthorhombic structure,⁽⁴⁾ characteristic of the lanthanide trifluorides of Sm through Lu.

All of the BkF_3 powder patterns showed the presence of more than one phase. Usually all the lines were accounted for by a trigonal trifluoride phase plus an orthorhombic trifluoride phase, but in some cases other, unaccounted-for lines were present in the powder patterns. One phase was always dominant, however, and only the more intense lines of the other phases were observed. Because of the possible superposition of lines belonging to different trifluoride phases, the observed line intensities for each separate phase are subject to error. In one case (JP-VII, Film 2691A) enough of the minor YF_3 -type orthorhombic phase was observed to determine lattice parameters for it.

The observed lattice parameters of the individual trifluoride preparations along with their Cf^{249} and Ce contents are listed in Table 1.

Since CeF_3 does not exhibit an orthorhombic modification, the YF_3 -type berkelium trifluoride lattice parameters were initially corrected for the known Cf content of the Bk sample in accordance with Vegard's Law.⁽⁵⁾ The lattice parameters of orthorhombic CfF_3 ($a_o = 6.653 \pm 0.002$ A, $b_o = 7.041 \pm 0.002$ A, and $c_o = 7.395 \pm 0.001$ A) were derived from a single preparation by Peterson et al.⁽⁶⁾ These "corrected-for-Cf," orthorhombic BkF_3 lattice parameters were then plotted versus the Ce content of the berkelium sample and extrapolated to zero Ce content to obtain "best estimates" for the lattice parameters of orthorhombic BkF_3 : $a_o = 6.70 \pm 0.01$ A, $b_o = 7.09 \pm 0.01$ A, and $c_o = 4.41 \pm 0.01$ A, where the error limits reflect the uncertainties in the derivation of the lattice parameters.

Similarly for LaF_3 -type trigonal berkelium trifluoride, since the trigonal modification of CfF_3 is unknown, the lattice parameters were corrected for the known Ce content of the Bk sample using the parameters of Swanson et al. ($a_o = 7.112$ A and $c_o = 7.279$ A).⁽⁷⁾ These "corrected-for-Ce," trigonal BkF_3 lattice parameters did not vary in any regular fashion as the Cf content of the berkelium sample increased, so they were just averaged to obtain "best estimates" for the lattice parameters of trigonal BkF_3 : $a_o = 6.97 \pm 0.01$ A and $c_o = 7.14 \pm 0.01$ A, where again the lattice parameters are rounded off to the nearest hundredth and the error limits reflect the uncertainties in the derivation of the lattice parameters.

The Miller indices, observed and calculated 2θ values, and observed and calculated line intensities for one sample of each type of BkF_3 are given in Tables 2 and 3.

Thoma and Brunton studied the equilibrium dimorphism of the lanthanide trifluorides. (9) Dimorphism was not observed for the trifluorides of La through Nd. They determined equilibrium inversion temperatures for the trifluorides of Sm through Lu and found them to range from 555° C for SmF_3 to 1075° C for ErF_3 . The orthorhombic BkF_3 samples in this work were easily converted to the trigonal form by annealing at 600° C. The inversion temperature of BkF_3 lies between 350 and 600° C but could not be determined more precisely, since long-term annealings of trigonal BkF_3 samples failed to produce significant transformations to the orthorhombic form.

A summary of the pertinent crystallographic data of the lanthanide and actinide trifluorides along with calculated ionic radii is presented in Table 4. Crystallographic data for the high-temperature form of the heavier lanthanide trifluorides is given in reference (9). The trifluorides of Bk and Cf are the first of the actinide trifluorides to be prepared in the YF_3 -type orthorhombic modification.

By comparing the Bk^{3+} ionic radius, as calculated from the LaF_3 -type trifluoride, to the similarly calculated ionic radii of the light lanthanides, it is seen that the Bk^{3+} radius fits in after Pm, the last lanthanide to exhibit the trigonal trifluoride structure below ~550° C. Alternatively, by comparing the Bk^{3+} ionic radius, as calculated from the YF_3 -type trifluoride, to the similarly calculated ionic radii of the heavier lanthanides, it is seen that the Bk^{3+} radius fits in before Sm, the first lanthanide to exhibit the YF_3 -type orthorhombic trifluoride structure. These calculations and comparisons are consistent with the observed dimorphism in the BkF_3 system. It is important to note that comparisons of ionic radii can only be made

meaningful if the values compared are calculated in like fashion from the same type of compound, both with respect to composition and crystal structure.

From the data in Table 4 and by analogy with the work of Thoma and Brunton,⁽⁹⁾ one can predict that CfF_3 will exhibit the LaF_3 -type trigonal structure at temperatures greater than or equal to about 700°C .

The calculated density (x-ray) of YF_3 -type orthorhombic BkF_3 is 9.70 g/cc, whereas for the LaF_3 -type trigonal modification, it is 10.15 g/cc. These numbers reflect the general trend noted in the lanthanide trifluorides that the high-temperature, trigonal modification is the more dense one.

ACKNOWLEDGMENTS

The authors gratefully acknowledge the film reading assistance of Miss Judy Copeland and Mr. David Temple and the careful monitoring assistance of Mrs. Gertrude Bolz. This work was performed under the auspices of the U. S. Atomic Energy Commission.

REFERENCES

- (1) J. R. Peterson and B. B. Cunningham, *Inorg. Nucl. Chem. Letters* 3, 327 (1967).
- (2) J. R. Peterson, (Ph.D. Thesis), University of California Lawrence Radiation Laboratory Report, UCRL-17875 (October 1967).
- (3) Allan Zalkin, David H. Templeton, and Ted E. Hopkins, *Inorg. Chem.* 5, 1466 (1966).
- (4) Allan Zalkin and D. H. Templeton, *J. Am. Chem. Soc.* 75, 2453 (1953).
- (5) A. F. Wells, Structural Inorganic Chemistry, Chapter XXVII, pp. 971-1028, Oxford University Press, London (1962).
- (6) J. R. Peterson, J. C. Copeland, and D. Temple, University of California Lawrence Radiation Laboratory, unpublished results (1967).
- (7) H. E. Swanson et al., National Bureau of Standards Circular No. 539, Vol. 8, U. S. Government Printing Office, Washington, D. C. (1959); ASTM X-Ray Diffraction Card No. 8-45.
- (8) D. K. Smith, University of California Lawrence Radiation Laboratory Report, UCRL-7196 (1963).
- (9) R. E. Thoma and G. D. Brunton, *Inorg. Chem.* 5, 1937 (1966).
- (10) E. Staritzky and L. B. Asprey, *Anal. Chem.* 29, 856 (1957).
- (11) H. E. Swanson et al., National Bureau of Standards, ASTM X-Ray Diffraction Card No. 6-0325.
- (12) Fritz Weigel, "Präparative und röntgenographische Untersuchungen an stark radioaktiven Stoffen," University of Munich, Munich (1965).

- (13) W. H. Zachariasen, The Actinide Elements, Chapter 18, pp. 769-796, National Nuclear Energy Series, Vol. IV-14A, McGraw-Hill Book Company, Inc., New York (1954).
- (14) L. B. Asprey, T. K. Keenan, and F. H. Kruse, Inorg. Chem. 4, 985 (1965).

Table 1. Berkelium trifluoride lattice parameters.

Sample Number	Film Number	Structure Type	Cf ²⁴⁹ ^a Content (atom %)	Total Ce ^b Content (atom %)	Observed Lattice Parameters ^c (Å)		
					a _o ± 2σ	b _o ± 2σ	c _o ± 2σ
JRP-XXIII	2624A	YF ₃	7.03	0.27	6.695 ± 0.004	7.086 ± 0.004	4.407 ± 0.003
JP-VII	2691A	YF ₃	1.53	9.53	6.717 ± 0.015	7.114 ± 0.011	4.409 ± 0.005 ^d
JP-X	2713A	YF ₃	5.16	9.53	6.716 ± 0.001	7.103 ± 0.001	4.408 ± 0.001
JRP-XXI	2614A	LaF ₃	5.26	0.27	6.973 ± 0.002		7.143 ± 0.003
JRP-XXII	2619A	LaF ₃	6.20	0.27	6.965 ± 0.003		7.140 ± 0.003
JP-VII	2691A	LaF ₃	1.53	9.53	6.990 ± 0.001		7.157 ± 0.001
JP-X	2716A	LaF ₃	5.79	9.53	6.990 ± 0.001		7.158 ± 0.002
JP-X	2734A	LaF ₃	8.05	9.53	6.988 ± 0.001		7.156 ± 0.002

^aCalculated assuming Bk²⁴⁹ half life is 314 days.

^bDetermined by mass analysis. See text.

^cLattice parameters are the least squares value. The 2σ error limits represent the 95% confidence range reflecting only the internal consistency of the data for the individual preparation.

^dThe second phase in a predominantly trigonal BkF₃ powder pattern.

Table 2. Line list and indexing for YF_3 -type orthorhombic BkF_3 (JP-X, Film 2713A).

hkl	2θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
011	23.67	23.75	6.5	2.0
101	24.12	24.15	9.0	5.7
020	25.02	25.07	9.0	6.3
200	26.47	26.54	1.5	0.1
111	27.27	27.26	10.0	10.0
210	29.37	29.42	10.0	7.6
201	33.51	33.55	3.5	0.4
121	35.06	35.09	9.0	3.1
211	35.90	35.91	3.0	0.1
002	40.85	40.94	6.5	1.1
221	42.25	42.34	6.5	1.4
102	43.14	43.20	4.0	0.4
031		43.38		0.1
112	44.99	45.13	6.5	1.8
301	45.44	45.44	10.0	2.4
131		45.53		3.6
230	46.84	46.95	8.5	3.2
311	47.29	47.30	7.0	1.8
022	48.54	48.61	7.0	1.5
122	50.53	50.60	7.0	1.4
212	51.23	51.21	8.0 broad	2.3
040		51.46		1.2

Table 2. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
321	52.58	52.59	7.5	2.1
400	54.53	54.66	5.5	0.9
141	57.57	57.62	6.0	1.0
302	58.82	58.79	5.8	0.2
132		58.87		0.6
312	60.37	60.35	7.5	0.7
411		60.42		0.4
331		60.68		0.9
420	61.02	61.04	6.5	1.0
241	62.77	62.84	3.5	0.3
232	64.01	64.03	6.5	1.1
013	64.76	64.78	6.5	0.8
322		64.91		0.3
113	66.31	66.44	3.0	0.3
042	67.65	67.76	4.5	0.5
430	68.45	68.51	1.5	0.1
142	69.35	69.38	3.0	0.4
051		69.52		0.1
203	69.80	69.87	3.0	0.6
402	70.40	70.50	2.5	0.4
123	71.05	70.79	7.0	0.2
341		71.05		1.0
151		71.12		0.7

Table 2. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
332		72.17		0.2
250	72.15	72.20	5.5	0.6
431		72.23		0.2
511	75.10	75.13	4.0	0.8
223	75.45	75.52	6.0	1.2
422		76.14		0.8
033	76.15	76.26	5.0	0.4
440	78.39	78.38	3.5	0.6
521	79.19	79.29	3.0	0.3
060	81.23	81.26	4.3	0.4
342		81.88		0.2
152	81.83	81.95	4.0	0.3
351	83.63	83.52	3.0	0.4
531		86.10		0.7
161	86.23	86.30	6.5 broad	0.4
252		86.50		0.6
610	88.28	88.40	3.5 broad	0.5
413		89.75		0.8
522	89.73	89.86	5.5 broad	0.4
114		91.63		0.4
243	91.78	91.88	5.0	0.7
352		94.05		0.3
451	93.96	94.11	3.5 broad	0.2

Table 2. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
062	95.51	95.32	4.5 broad	0.2
541		95.56		0.2
124		95.69		0.4
532	96.81	96.63	1.5 broad	0.1
162		96.84		0.2
053	98.26	98.01	4.0	0.3
361		98.42		0.6
630	99.36	99.24	2.5 broad	0.4
343		99.47		0.1
153		99.54		0.1
433 α_1	100.51	100.49	3.5	0.4
304 α_1	102.36	102.34	4.0	0.1
612 α_1		102.40		0.3
134 α_1		102.41		0.3
314 α_1	103.91	103.72	4.0	0.3
171 α_1		103.87		0.3
270 α_1	104.95	104.93	3.5	0.3
460 α_1	105.50	105.52	2.0	0.3
542 α_1	106.09	106.15	1.8	0.2
542 α_2	106.59	106.53	1.3	0.1
551 α_1	107.84	107.86	4.0	0.3
324 α_1		107.92		0.2

Table 2. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
551 α_2	108.29	108.25	2.0	{ 0.1
324 α_2		108.31		{ 0.1
362 α_1	109.09	109.12	1.0 broad	0.1
701 α_1	110.54	110.49	2.0	0.2
711 α_1	112.29	111.94	3.0 broad	{ 0.1
144 α_1		112.30		{ 0.3
632 α_1	113.79	113.76	2.0	0.3
533 α_1	115.04	114.76	3.5	{ 0.1
172 α_1		115.02		{ 0.1
334 α_1		115.17		{ 0.4
721 α_1	116.39	116.37	3.0	0.4
371 α_1	116.78	116.76	2.3	{ 0.2
721 α_2		116.83		{ 0.2
263 α_1	120.13	120.09	5.5	{ 0.5
272 α_1		120.12		{ 0.3
080 α_1		120.34		{ 0.1
462 α_1	120.72	120.78	3.0	0.3
650 α_1	122.27	122.34	1.8	0.3
712 α_1	123.92	123.83	5.0	{ 0.3
453 α_1		123.94		{ 0.5
712 α_2	124.52	124.37	3.0	{ 0.1
561 α_1		124.43		{ 0.1
453 α_2		124.48		{ 0.3

Table 2. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
344 α_1	126.22	126.15	5.8	0.2
623 α_1		126.20		0.4
154 α_1		126.24		0.3
181 α_1		126.34		0.2
344 α_2	126.82	126.72	3.0	0.1
623 α_2		126.76		0.2
154 α_2		126.80		0.1
181 α_2		126.90		0.1
205 α_1	129.31	129.17	4.5	0.4
372 α_1		129.30		0.1
471 α_1		129.37		0.1
504 α_1		129.39		0.3
205 α_2	129.96	129.77	2.0	0.2
372 α_2		129.90		0.1
471 α_2		129.98		0.04
504 α_2		129.99		0.1
281 α_1	132.11	132.18	0.8	0.1
281 α_2	133.01	132.82	0.8	0.1
800 α_1		133.13		0.1
073 α_1	134.65	134.58	1.8	0.3
810 α_1	135.05	135.00	1.3	0.04
633 α_1		135.09		0.03
073 α_2		135.26		0.1

Table 2. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
225 α_1	136.60	136.53	6.0 broad	0.7
741 α_1		136.58		0.6
173 α_1		136.74		0.1
524 α_1		136.77		0.6
225 α_2	137.45	137.25	4.0	0.3
741 α_2		137.30		0.3
173 α_2		137.46		0.04
524 α_2		137.49		0.3
035 α_1	138.40	137.57	3.5 broad	0.4
732 α_1		138.15		0.3
035 α_2		138.31		0.2
562 α_1		138.46		0.3
082 α_1	141.00	138.54	4.5 broad	0.2
182 α_1		140.87		0.3
820 α_1		141.05		0.4
652 α_1		141.19		0.5
182 α_2	141.94	141.67	1.8 broad	0.1
820 α_2		141.86		0.2
652 α_2		142.00		0.2
354 α_1		143.28		0.5
381 α_1	143.44	143.41	4.5 broad	0.5
354 α_2	144.24	144.15	2.5 broad	0.3
381 α_2		144.28		0.2

Table 2. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
164 α_1	148.19	148.20	3.3 broad	0.6
571 α_1	150.73	150.59	6.0 broad	0.8
643 α_1		150.79		0.8
571 α_2	151.83	151.69	4.0 broad	0.4
643 α_2		151.90		0.4
480 α_1	157.97	157.83	4.0 broad	0.6
802 α_1		158.10		0.4
723 α_1	159.47	158.84	3.0 broad	0.3
480 α_2		159.33		0.3
802 α_2		159.62		0.2
751 α_1		159.72		0.3
373 α_1		159.83		0.1

^aTwo independent observers' averaged readings (2 θ values are $\pm 0.10^\circ$) and averaged intensities on a scale from 10 to 0.

^bBased on the orthorhombic lattice parameters $a_0 = 6.7162$ A, $b_0 = 7.1031$ A, $c_0 = 4.4084$ A, and $\lambda(\bar{\alpha}) = 1.54178$ A, $\lambda(\alpha_1) = 1.54051$ A, and $\lambda(\alpha_2) = 1.54433$ A.

^cCalculated using the POWD intensity program,⁸ assuming the atomic coordinates of YF_3 for those of BkF_3 , and scaled such that the most intense line had $I = 10.0$.

Table 3. Line list and indexing for LaF_3 -type trigonal BkF_3 (JP-VII, Film 2691A).

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
002	24.84	24.88	8.0	3.5
110	25.44	25.49	7.0	2.5
111	28.44	28.42	10.0	10.0
112	35.84	35.92	5.5	1.3
300	44.92	44.92	9.0	3.4
113	46.02	46.06	9.0	4.3
004	51.12	51.05	4.0	0.5
302	52.02	52.03	8.0	3.1
220		52.35		0.3
221	54.02	54.01	7.5	1.9
114	57.82	57.90	4.0	0.5
222	58.72	58.80	4.0	0.4
223	66.22	66.30	7.0	1.3
304	70.30	70.32	6.0	1.2
115	71.20	71.18	6.0	0.8
410		71.41		0.3
411	72.80	72.80	7.0	1.6
224	76.20	76.14	3.0	0.2
412	76.80	76.94	3.0	0.4
006	80.50	80.53	1.5	0.2
330	82.80	82.86	3.0	0.5
413	83.70	83.68	6.5	1.4
116	86.20	86.14	4.0 broad	0.2

Table 3. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
332	88.20	88.20	7.0	0.8
225		88.24		0.5
414 α_1	92.90	92.91	4.0	0.2
306 α_1	97.18	97.21	5.0	0.5
600 α_1	99.58	99.54	3.5	0.2
117 α_1	103.48	103.44	3.0	0.3
334 α_1	104.18	104.18	3.0	0.4
602 α_1	104.98	104.98	6.0	0.4
415 α_1		105.02		0.6
602 α_2	105.38	105.35	4.0	0.2
415 α_2		105.39		0.3
521 α_1	106.58	106.62	5.0	0.6
521 α_2	107.08	107.00	3.0	0.3
522 α_1	110.78	110.83	2.0	0.2
523 α_1	118.08	118.12	6.0	0.7
523 α_2	118.58	118.60	4.0	0.3
416 α_1	120.98	120.93	1.5	0.3
227 α_1	121.56	121.59	3.0	0.3
604 α_1	122.36	122.44	3.0	0.5
441 α_1	125.16	125.27	4.0	0.4
118 α_1		125.44		0.1
441 α_2	125.96	125.83	2.0	0.2
118 α_2		126.00		0.1

Table 3. (continued)

hkl	2 θ (deg)		Line Intensity	
	Observed ^a	Calculated ^b	Observed ^a	Calculated ^c
524 α_1	129.36	129.31	3.5	0.2
524 α_2	130.06	129.92	1.5	0.1
336 α_1	135.06	135.10	4.0	0.6
443 α_1	139.76	139.71	3.5	0.5
308 α_1	140.66	140.73	5.0	0.6
308 α_2	141.66	141.53	3.0	0.3
417 α_1	144.56	144.61	6.0	1.1
417 α_2	145.56	145.51	4.0	0.5
525 α_1	147.26	147.36	6.0	1.2
525 α_2	148.36	148.34	4.0	0.6
711 α_1	150.24	150.33	6.0	1.3
711 α_2	151.44	151.43	4.0	0.6
444 α_1	157.74	157.67	2.5	0.3
712 α_1	159.84	159.79	3.0	0.6
712 α_2	161.44	161.45	1.5	0.3

^aA single reading of the powder pattern (2 θ readings are $\pm 0.10^\circ$). Observed intensities are on a scale of 10 to 0 and may be in error due to the presence of a second phase (orthorhombic BkF_3).

^bBased on the trigonal lattice parameters $a_0 = 6.9899$ Å, $c_0 = 7.1566$ Å and $\lambda(\bar{\alpha}) = 1.54178$ Å, $\lambda(\alpha_1) = 1.54051$ Å, and $\lambda(\alpha_2) = 1.54433$ Å.

^cCalculated using the POWD intensity program, assuming the atomic coordinates of LaF_3 for those of BkF_3 , and scaled such that the most intense line had $I = 10.0$.

Table 4. Lattice parameters and ionic radii derived from the lanthanide and actinide trifluorides.

Trifluoride	Structure Type	Lattice Parameters (Å)			Reference	M ³⁺ Ionic Radius ^a (Å) (CN=6)
		a _o	b _o	c _o		
La	LaF ₃	7.186		7.352	10	1.006
Ce	LaF ₃	7.112		7.279	7	0.982
Pr	LaF ₃	7.075		7.238	11	0.968
Nd	LaF ₃	7.030		7.200	10	0.955
Pm	LaF ₃	6.970		7.188	12	0.945
Sm	YF ₃	6.669	7.059	4.405	4	0.921
Eu	YF ₃	6.622	7.019	4.396	4	0.909
Gd	YF ₃	6.570	6.984	4.393	4	0.900
Tb	YF ₃	6.513	6.949	4.384	4	0.888
Dy	YF ₃	6.460	6.906	4.376	4	0.877
Ho	YF ₃	6.404	6.875	4.379	4	0.868
Er	YF ₃	6.354	6.846	4.380	4	0.860
Tm	YF ₃	6.283	6.811	4.408	4	0.855
Yb	YF ₃	6.216	6.786	4.434	4	0.851
Lu	YF ₃	6.151	6.758	4.467	4	0.848
Ac	LaF ₃	7.41		7.55	13	1.076
U	LaF ₃	7.181		7.348	13	1.005
Np	LaF ₃	7.129		7.288	13	0.986
Pu	LaF ₃	7.093		7.254	13	0.974

Table 4. (Continued)

Trifluoride	Structure Type	Lattice Parameters (A)			Reference	M ³⁺ Ionic Radius ^a (A) (CN=6)
		a _o	b _o	c _o		
Am	LaF ₃	7.044		7.225	14	0.962
Cm	LaF ₃	6.999		7.179	14	0.946
Bk	LaF ₃	6.97		7.14	} This Work	0.935
Bk	YF ₃	6.70	7.09	4.41		0.928
Cf	YF ₃	6.653	7.041	4.395	6	0.915

^aCalculated according to the following formula:

$$\text{Ionic Radius} = (\text{Weight - averaged M-F bond distance}) - 1.33 - 0.11$$

where the fluoride ionic radius is taken to be 1.33 A¹³ and the 9-fold to 6-fold coordination correction number is taken to be 0.11 A.¹³

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.