UC Irvine

UC Irvine Previously Published Works

Title

Magnetic ordering in dilute $GdxEu_{1-x}Ba_2Cu_3O_{7-6}$ superconductors

Permalink

<https://escholarship.org/uc/item/1pv3r247>

Journal

Physica C: Superconductivity and its applications, 153-155(PART 1)

ISSN

0921-4534

Authors

Causa, MT
Dutrus, SM
Fainstein, C
[et al.](#)

Publication Date

1988

DOI

10.1016/0921-4534(88)90545-X

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at <https://creativecommons.org/licenses/by/4.0/>

Peer reviewed

MAGNETIC ORDERING IN DILUTE $\text{Gd}_x\text{Eu}_{1-x}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ SUPERCONDUCTORS

M. T. CAUSA¹, S. M. DUTRUS¹, C. FAINSTEIN¹, G. NIEVA¹, R. SANCHEZ¹, L.B. STEREN¹, M. TOVAR¹, R. ZYSLER¹, S. B. OSEROFF², D. C. VIER³, S. SCHULTZ³, Z. FISK⁴ and J.L. SMITH⁴

¹ Centro Atómico Bariloche and Instituto Balseiro, 8400 Bariloche, Argentina

² San Diego State University, San Diego, CA 92182, USA

³ University of California, San Diego, La Jolla, CA 92093, USA

⁴ Los Alamos National Laboratory, Los Alamos, NM 87545, USA

We have measured the specific heat of $\text{Gd}_x\text{Eu}_{1-x}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ ($0 \leq x \leq 1$). The data show a λ -type anomaly at high concentrations and a broad Schottky type anomaly at intermediate and low concentrations. We compare this behavior with theoretical predictions for a 2-dimensional Ising system.

The occurrence of long range antiferromagnetic ordering at low temperatures in the high- T_C superconductor $\text{GdBa}_2\text{Cu}_3\text{O}_{7-\delta}$ has been established through specific heat and magnetic susceptibility measurements (1-3) as well as neutron diffraction (4) and Mössbauer spectroscopy (5). Two important questions remain: what is the nature of the magnetic interactions, and what is the dimensionality of the magnetic ordering? Recent neutron diffraction experiments indicate the existence of a 3-d antiferromagnetic order (4). However, van der Berg et al. (6) have proposed a description based on a magnetic transition with 2-d Ising character, driven by superexchange interactions. This 2-d character is supported by the crystalline structure of the Gd lattice and the magnetic behavior above the Néel temperature, T_N . We report here specific heat data for $\text{Gd}_x\text{Eu}_{1-x}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ that also support this description.

The samples were prepared by sintering mixed powders of Eu_2O_3 , Gd_2O_3 , BaCO_3 , and CuO in an oxygen atmosphere, as described in (3).

The specific heat was measured down to 0.45K in a semiadiabatic calorimeter (7) using a standard pulse technique. In Fig. 1 we show the magnetic specific heat, C_m , obtained after subtracting the specific heat of a sample with $x = 0$. The data for $\text{GdBa}_2\text{Cu}_3\text{O}_{7-\delta}$ shows a λ -type anomaly peaked at $T_N = 2.24\text{K}$, as we have previously reported (2) and which is in agreement with other reports (1,6). Above T_N , the integrated area under the curve is much larger for this system than for typical 3-d antiferromagnets. This feature indicates that short-range magnetic order is important well above T_N . A measure of this effect is the entropy fraction, $S(T_N)/R \ln 8$, where $R \ln 8$ is the entropy calculated for Gd^{3+} free ions ($4f^7$; $8S_{7/2}$). In order to estimate the entropy, $S(T)$, we have integrated our experimental data for $C_m(T)/T$ vs. T , extrapolating linearly to zero below 0.45K and assuming $C(T) \propto T^{-2}$ above 5K. For $S(T \rightarrow \infty)$ we obtained 96% of the theoretical value. Only about 60% of this amount is removed below

T_N . This entropy fraction is much lower than expected (8) for 3-d systems (0.85-0.90) and supports the 2-d description of the magnetic ordering.

As $x \rightarrow 0$, the λ -type feature of C_m decreases in intensity and a broad Schottky type maximum develops, as shown in

Fig. 1. Specific heat of $\text{Gd}_x\text{Eu}_{1-x}\text{Ba}_2\text{Cu}_3\text{O}_{7-\delta}$ vs. temperature. Note (a) the λ anomaly for $x > .7$ and (b) the broad Schottky anomaly for $x < .5$.

Fig. 1(b). This behavior has been predicted for dilute 2-d Ising lattices (9) and interpreted as a progressive freezing out of local disorder. In our case the λ -type maximum is observed for $0.8 \leq x \leq 1$ and the broad maximum appears for $x \leq 0.5$. For $x \sim 0.7$, it is possible to barely distinguish a second peak below the broad maximum. In Fig. 2 we present the temperature at the maximum C_m , T_{max} vs. x .

The λ -peak shifts to lower temperatures with initial normalized slope, $dt/dx \equiv d[(T_{max}(x)/T_{max}(x=1))]/dx = 1.32$. This value is slightly smaller than the predictions of Monte Carlo calculations ($dt/dx = 1.47$) for the 2-d Ising system (10). The intercept of $T_{max} = 0$ occurs at a finite concentration, which suggests the existence of a percolation threshold. This would indicate that the ordering mechanism for samples with $x \sim 1$ arises from short-range interactions, probably due to superexchange through oxygen ions.

When only nearest-neighbor interactions between Gd ions are taken into account, the maximum of the broad anomaly has been predicted to occur (9) at temperatures of the order of J/k_B . For our samples this maximum is strongly concentration dependent, and it is therefore not possible to estimate a unique value for J/k_B . This may indicate the existence of a spread of magnetic coupling constants with more distant neighbors, characteristic of longer range interactions. We suggest that dipolar couplings between Gd moments ($E_{dd} \propto \mu^2/R^3$) may play a significant role at low concentrations in addition to superexchange interactions.

Fig. 2. Temperature, T_{max} , for which C_m is a maximum vs. x , the fractional concentration of Gd. The arrow indicates the calculated position of the crystal field Schottky anomaly.

The Schottky anomaly tail observed for $x = 0.02$ is related to the crystal field splitting, as discussed in (3). The single ion anisotropy energy associated with this interaction, $E_a = 21 |D|/2 \sim 1.4K$, is of the same order of magnitude as the calculated dipolar coupling energies (5) and it should be included when magnetic anisotropy effects are evaluated. If D were negative, the orientation of the magnetic moments would be favored along the c -axis, as found experimentally. As a result, the magnetic interaction between Gd moments might be described by an Ising Hamiltonian as proposed in (6).

In conclusion, we have shown that the specific heat data for the $Gd_xEu_{1-x}Ba_2Cu_3O_{7-\delta}$ dilute antiferromagnetic system presents characteristics of a 2-dimensional Ising model; i.e. a large tail above T_N , and a relatively large rate of depression of T_N upon dilution. The concentration dependence of T_N seems to indicate that, besides superexchange between nearest Gd atoms, magnetic interactions between farther neighbors should be considered.

We acknowledge partial support from CONICET (Argentina), NSF-DMR 86-13856, and USDOE, Los Alamos National Laboratories.

REFERENCES

- (1) J.O. Willis, Z. Fisk, J.D. Thompson, S.W. Cheong, R.M. Aikin, J.L. Smith, and E. Zirngiebl, *J. Magn. Mater.* **67** (1987) L139.
- (2) M.T. Causa, S.M. Dutrás, C. Fainstein, G. Nieva, H.R. Salva, R. Sánchez, L.B. Steren, M. Tovar and R. Zysler, *Int. J. Mod. Phys. B* **1** (1987) 989.
- (3) M.T. Causa, C. Fainstein, G. Nieva, R. Sánchez, L.B. Steren, M. Tovar, R. Zysler, S.B. Oseroff, D.C. Vier, S. Schultz, Z. Fisk and J.L. Smith, submitted to *Phys. Rev. B*.
- (4) D. McK-Paul, H.A. Mook, B.C. Sales, L.A. Boatner, J.R. Thompson, Mark Mostoller and A.W. Hewat, *Phys. Rev.* (in print).
- (5) H.H.A. Smit, M.W. Dirken, R.C. Thiel, and L.J. de Jongh, *Solid St. Commun.* **64** (1987) 695.
- (6) J. van der Berg, C.J. van der Beek, P.H. Kes, J.A. Mydosh, G.J. Nieuwenhuys and L.J. de Jongh, *Solid St. Commun.* **64** (1987) 699.
- (7) J. Sereni, PhD. Thesis (1974), unpublished.
- (8) L.J. de Jongh and A.R. Miedema, *Adv. Phys.* **23** (1974) 1, and references therein.
- (9) L.J. de Jongh, *Springer Ser. Solid State Sci.* **48** (1983) 172, and references therein.
- (10) W.Y. Ching and D.L. Huber, *Phys. Rev.* **B13** (1976) 2962.