

e2



Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

Materials & Chemical Sciences Division

RECEIVED
MATERIALS & CHEMICAL
SCIENCE DIVISION
NOV 30 1987

DOCS. COLLECTION

Presented at the International Workshop on Novel Mechanisms
of Superconductivity, Berkeley, CA, June 22-26, 1987

Non-Phonon Mechanisms of Superconductivity in High T_c Superconducting Oxides and Other Materials and Their Manifestation

V.Z. Kresin

June 1987

COPY
copy
no weeks.



LBL-24073
e2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

NON-PHONON MECHANISMS OF SUPERCONDUCTIVITY IN HIGH T_c SUPERCONDUCTING
OXIDES AND OTHER MATERIALS AND THEIR MANIFESTATION

Vladimir Z. Kresin

Materials and Chemical Sciences Division
Lawrence Berkeley Laboratory
University of California, Berkeley
Berkeley, California 94720

ABSTRACT

Low dimensionality and the unusual parameter values in the high T_c materials lead to a key contribution of the plasmon mechanism of superconductivity. In addition, these systems provide a unique opportunity to observe a multigap structure. The problem of the lattice instability is discussed. A manifestation of non-phonon mechanisms (NPM) in Nb_3Ge and the contribution of the intramolecular vibrations are analyzed. Proximity systems containing high T_c superconductors are promising from the point of view of possible applications.

I. INTRODUCTION

Recently discovered high T_c materials^{1,2} are characterized by "exotic" properties. This paper is concerned with the description of properties and with the analysis of the mechanisms of high T_c superconductivity. In addition we are going to analyze the appearance of the non-phonon mechanism in some conventional systems. The structure of the paper is as follows. Section II contains analysis of the properties of high T_c materials. The problems of the lattice instability, the appearance of a multigap structure and the influence of the proximity effect will be discussed. We are going to discuss in detail the plasmon mechanism and its coexistence with strong electron-phonon interaction. Section III contains an analysis of some conventional systems.

II. HIGH T_c MATERIALS

A recent exciting development, the discovery of new high T_c superconducting oxides^{1,2} brought up the problem of mechanisms of superconductivity in these materials. An analysis of their structure and parameters leads to the conclusion that their superconducting state is greatly affected by NPM, namely, by exchange of 2D (two-dimension) plasmons.

1. Low Dimensionality and "Exotic" Properties of High T_c Superconductors

Main parameters. Lattice instability. The new high T_c materials are low dimensional systems. For example, $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ ($x=2$) is two dimensional (the interlayer distance $d \approx 6.5 \text{ \AA}$), while $\text{Y}_1\text{Ba}_2\text{Cu}_3\text{O}_7$ contains one dimensional chains. S. Wolf and the present author³ have carried out our evaluation of the parameters of high T_c materials based on specific heat data.⁴ We think that these data are the most reliable source; they can be used with high accuracy for analysis even polycrystalline samples.

Low dimensionality is taken into account in a consistent way and plays a key role in the analysis.³ According to,³ $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ is characterized by a large value of the effective mass: $m^* \approx 5 m_e$. A most striking feature is the small value of the Fermi energy: $\epsilon_F \approx 0.12 \text{ eV}$.

The situation with such a small value of ϵ_F along with large, comparable value of the energy gap Δ is unique. In connection with it I would like to stress that the superconducting transition affects the state of the lattice and this influence is determined by the parameter $\sim (\Delta/\epsilon_F)^2$ (see refs. 5 and 6). This parameter is usually small. However, the situation is entirely different in high T_c superconducting oxides. A large value of (Δ/ϵ_F) leads to a drastic change of the phonon spectrum. The following increase in T_c (and Δ) leads to the lattice instability. We think that the upper limit of T_c is determined by this factor.

Coherence length. Multigap structure. According to the analysis³ the coherence length ξ_0 appears to be very small ($\sim 20 \text{ \AA}$). Such small value of ξ_0 leads to the unique opportunity to observe a multigap structure.⁷ The appearance of a such structure is connected with the presence of the overlapping energy bands.

The two-gap model has been introduced by Suhl, Matthias and Walker.⁸ Afterwards it has been studied by Geilikman, Zaitsev, and the present author^{6,9} and by the present author in ref. 10. The difficulty of observing multigap effects, as well as effects caused by gap anisotropy are due to the Anderson theorem.¹¹ Namely, the inequality $\ell \ll \xi_0$ (ξ_0 is the coherence length, ℓ is the mean free path) results in the gap averaging into a single one. Interband transitions are the main mechanism of this averaging.

The new high T_c materials provide a unique opportunity to observe, under certain conditions, effects due to the presence of several gaps. For relatively clean samples, the criterion $\xi_0 \ll \ell$ can be met.

Note that the Anderson criterion allows one to determine whether one is dealing with a multigap case. Indeed, additional doping of these materials will result in a decrease of ℓ and, subsequently, in becoming less than ξ_0 , when a transition to the one-gap picture will

take place. Such a transition can be observed experimentally, because the tunneling spectrum and the temperature dependences, e.g., of the kinetic coefficients are different in the one gap and multigap cases.

High T_c superconductivity and the proximity effect. The proximity effect allows one to induce the superconducting state in materials which are not superconductors by themselves. If, for example, this material is a semiconductor, then, as a result, one can take advantage of both superconductivity and semiconducting properties. An important example of such an application of the proximity effect is the tunneling system Nb-InAs-Nb, studied experimentally.¹² An externally applied electric field changes noticeably the amplitude of the flowing Josephson current, which is promising from the point of view of making a three-terminal device. A theoretical analysis^{13a} shows that the sharpness of the field effect depends strongly on the temperature and increases with increasing T . That is why the use of high T_c superconductors, namely, the systems S_h -InAs- S_h , or S_h -S-InAs-S- S_h , where S_h is a high T_c superconductor, and S is a conventional material (e.g., Nb or NbN) is promising for the field effect.

Another interesting proximity system is S_α - S_β consisting of two superconductors (assume that $T_c^\alpha > T_c^\beta$). Such a system is characterized by a single T_c with $T_c^\alpha > T_c > T_c^\beta$ (a general expression has been obtained by the present author in ref. 13b. As a result of the proximity effect, one effectively increases the T_c of the S_β superconductor.

Consider the case with S_β is an A-15 compound with high values of such critical parameters as the critical current and the critical field. If S_α is a high T_c superconductor, one can use the proximity effect in order to increase T_c of the A-15 film and to take advantage of its high values of the critical parameters.

2. Mechanisms of High T_c Superconductivity. Plasmon Mechanism.

The low dimensionality along with the presence of several overlapping energy bands and a small value of ϵ_F makes the appearance of the plasmon mechanism of superconductivity very favorable. This mechanism has been proposed by the present author (see refs. 14 and 15) and then developed by H. Morawitz and the author.¹⁶ Later the plasmon mechanism in high T_c oxides has been studied in.¹⁷ The new materials are characterized by a relatively small carrier concentration n ,¹⁸ and it is important that the intensity of the electron-plasmon interaction increases with decreasing n .

As is known in the three dimension (3D) case the plasmon branch has a gap ω_0 at momentum $q=0$, and the plasma frequency is very high. In the 2D case the situation is entirely different. Namely, the plasmon dispersion relation does not contain an energy gap and in the region of small q has the form (see, e.g., ref. 19) $\omega \sim q^{1/2}$. As a matter of fact, there are several plasmon branches. The existence of the $\omega \sim q^{1/2}$ branch is connected with the low dimensionality of the system and is present even for a single 2D group of carriers. The presence of several overlapping energy bands lead to the appearance of

an additional acoustic plasmon branch. In the 3D case this acoustic branch was introduced in;²⁰ its contribution to the superconducting state was studied in.²¹⁻²⁴

The presence of the plasmon branches results in electron-electron attraction which appears to be large for systems with small carrier concentration.

The effect at the plasmon branch $\omega \sim q^{1/2}$ on the superconducting properties of an inversion layer was studied in.²⁵ Our approach is based on the method of the thermodynamic Green's function. The plasmon mechanism is affected by a number of factors. The high T_c oxides do not contain just one 2D sheet. They have a layered structure and, strictly speaking, one should take into consideration the interlayer interaction. One can show (see below) that the main contribution comes from the short wavelength region and the interlayer interaction does not play an important role. Moreover, it is necessary to take into account the presence of several energy bands.

The order parameter $\Delta(\omega_n, \vec{\kappa})$ describing the pairing in a 2D layer is described by the following equation, which is a generalized Eliashberg's equation:

$$\Delta(\omega_n, \vec{\kappa}) = \frac{\Gamma}{(2\pi)^2 Z} \sum_{n'} \int d\vec{\kappa} \Gamma(\omega_n - \omega_{n'}, \vec{\kappa} - \vec{\kappa}') F^+(\omega_{n'}, \vec{\kappa}') \quad (1)$$

Here $\omega_n = (2n+1)\pi T$, $\vec{\kappa}$ is the 2D momentum, F^+ is the anomalous Green's function, and Γ is the total vertex. The vertex Γ can be written as a sum of the plasmon and phonon terms: $\Gamma = \Gamma_{pl} + \Gamma_{ph}$.

Consider the vertex $\Gamma_{pl}(\omega, \vec{\kappa})$. Its poles correspond to collective excitations, i.e., plasmons.

Let us study the properties of a single 2D sheet. Consider the general case of overlapping energy bands. The structure of the vertex in the 3D case was studied by Geilikman^{22a} and by Geilikman and the author.²⁶ The case of 2D bands has been studied by Tavger and author.²⁷ According to^{22a, 27}, the vertex $\Gamma_{11} \equiv \Gamma_{11;11}$ is equal to:

$$\Gamma_{11} = (V_{11} + \Pi_{22} R) S^{-1} \quad (2)$$

where

$$S = 1 + V_{11} \Pi_1 + V_{22} \Pi_2 + \Pi_1 \Pi_2 R \quad (3)$$

$$R = V_{12}^2 - V_{11} V_{22}.$$

Here V_{11} , V_{12} , V_{22} are Coulomb matrix elements and Π_1 , Π_2 are polarization operators. The case of a single 2D energy band is described by Eqs. (2) and (3) with $\Pi_{22} = 0$. Equations (2) and (3) are written in the random phase approximation. The quantities Π_1 and Π_2 are given by

$$\Pi_i(\vec{q}, \omega) = -\frac{m_i}{2\pi^2} \int_0^{2\pi} d\phi \frac{\cos\phi}{\alpha_i - \cos\phi + i\delta \cos\phi} \quad i = \{1, 2\} \quad (4)$$

Here $\alpha_i = (\omega/V_{Fi}q)$, V_{Fi} is the Fermi velocity for i -th band; the polar axis is chosen along the 2D vector \vec{q} . Consider the region in the (ω, q) plane which corresponds to $\alpha_1 \gg 1$, $\alpha_2 \gg 1$. Then $\Pi_i = -(\epsilon_{iF}/\pi)q^2/\omega^2$. The equation $S=0$ determines the plasmon branch $\omega_{p\ell; b}$ which has the dispersion relation $\omega \sim q^{1/2}$ in the region of small q . Contrary to the usual (see below) acoustic plasmon branch, the branch $\omega_{p\ell; b}$ exists even in the case of a single energy band. The dispersion relation $\omega \sim q^{1/2}$ and the absence of an energy gap at $q=0$ is a consequence of the low dimensionality. The analysis of a more general case $\alpha_i > 1$ will be given separately. If $\alpha_1 \ll 1$, $\alpha_2 \ll 1$, we obtain

$$\Pi_1 \approx m_1/\pi; \quad \Pi_2 = -(\epsilon_{2F}/\pi) q^2/\omega^2 \quad (5)$$

As a result, we obtain the acoustic plasmon branch $\omega_{p\ell, a} \sim q$. For 3D system this branch, which is due to the presence of the overlapping bands was obtained in,¹⁹ see also.²⁰⁻²⁴ The vertex $\Gamma(\omega_n, \vec{\kappa})$ obtained by substituting $\omega \rightarrow -i\omega_n$, can be written in the form:

$$\Gamma(\omega_n, \vec{\kappa}) = \Gamma_0 + D_{\text{eff}}(\omega_n, \vec{\kappa}) \quad (6)$$

where $\Gamma_0 = v_1^{\text{src}}$ describes the Coulomb repulsion and

$$D_{\text{eff}} = \Gamma_0 \frac{\omega_{p\ell, a}^2(q)}{\omega_{p\ell, a}^2(q) + \omega_n^2} \quad (7)$$

has the form of the usual phonon Green's function with the dispersion relation $\omega_{q\ell, a}(q)$ and describes the electron-electron attraction via plasmon exchange.

Consider the effect of the interlayer interaction. One has to introduce quantity $\Gamma_i(\vec{\kappa}, z; \omega)$; this function is the Fourier component of the vertex $\Gamma(\vec{r}, \omega)$ with respect to \vec{r} (the axis z is chosen to be perpendicular to the layer). Let layer "a" be located at $z=0$ and let us evaluate the quantity $\Gamma_i(\vec{\kappa}, 0; \omega)$. The equation for this quantity contains the same terms as Eq. (2), but, in addition, we should take into account its Coulomb interaction with other sheets. For example, the presence of sheet b at $z=d$ leads to the appearance of the terms $v_1^{ab}(q_1, d) \Pi^b(q_1; d; \omega) \Gamma^{ba}$, etc. These additional terms contain $(v_1^{ab})^2$ in the lowest order (v_1^{ab} describes the Coulomb interaction between carriers, in layers "a" and "b"). It is easy to see that the additional contribution of Γ_1 due to the presence of a layer at $z=d$ is proportional to $e^{-2q_1 d}$. Hence, in the region of small q_1 it is

necessary to take into account the interlayer interaction and we are dealing with a 3D problem. But this interaction can be neglected in the short wavelength region ($2q_d \gg 1$). For the high temperature oxide $\text{La}_{1.8}\text{Sr}_{0.2}\text{CuO}_4$, $d = 6.5\text{\AA}$.¹ The Fermi momentum $p_F \approx 3.7 \times 10^{-20}$ gm x cm sec⁻¹ (see ref. 3), and therefore, if $q_1 \gtrsim 0.5 p_F$, we can consider the 2D sheet only.

The above analysis was carried out in the RPA (see e.g., refs. 28 and 29). One can show¹⁶ that the main conclusions concerning the different plasmon branches the effective electron-electron attraction via plasmon exchange are valid for high T_c systems and play an important role in the understanding of the basic mechanisms of high T_c superconductivity.

Strong electron-phonon coupling. Consider the phonon part of the total vertex Γ (see Eq. (1)). Speaking of the electron-phonon interaction (EPI), one should stress that the BCS theory, based on an analysis of EPI, does not restrict the values of T_c to the low temperature region. The Eliashberg equation (see below, Eq. (8)) is valid if $\tilde{\Omega} \ll \epsilon_F$, where $\tilde{\Omega}$ is the characteristic phonon frequency ($\tilde{\Omega} \sim \Omega_D$) and has a solution with a high $T_c \gtrsim \tilde{\Omega}$ (strong EPI). We are going to describe the mechanism of the appearance of strong electron-phonon coupling λ and the problem of describing a state with arbitrary λ .

The low dimensionality implies the necessity to analyze the properties of a 2D gas of carriers. Such a system is characterized by a Fermi curve $\epsilon(\vec{k}) = \epsilon_F$ instead of a Fermi surface (\vec{k} is the two-dimensional momentum). If the 2D system of carriers contains a subgroup with a high DOS near the Fermi level (its presence in the superconducting high T_c oxides is due to the mixed valence state of Cu), then the Fermi curve has sections which are almost linear nesting states. Such a situation has been studied by the author.³⁰ In³⁰ the properties of a size-quantizing Bi film were studied. Although Bi films and the layered superconducting oxides are entirely different systems, there is a strong analogy in some aspects of their behavior (anisotropy of the Fermi curve, small carrier concentration, etc.). The method developed³⁰ can be applied to study the low dimensional superconductors.

One can show by analogy with³⁰ that the presence of linear sections (nesting state) of the Fermi curve leads to lattice instability. This instability comes from the interaction of phonons with electronic states attached to these linear sections and manifests itself in the appearance of an imaginary pole in the phonon Green's function. The transition (at some $T = T_p$) to the charge density wave state becomes favorable. A decrease in temperature in the region $T > T_p$ is accompanied by a decrease in the phonon frequency (phonon softening). If $T_c > T_p$ (such situation is perfectly realistic for the high T_c materials), then a low phonon mode with finite momentum appears, and the smallness of the phonon frequency makes EPI strong ($\lambda \sim \tilde{\Omega}^{-2}$).

The T_c for an arbitrary value of the electron-phonon coupling can be determined³¹ from the usual Eliashberg equation which can be written in the form (at $T = T_c$):

$$\Delta(n)Z = \sum_{n'} [K_{n-n'}^{-2\mu*}] \Delta(n') \left| 2n'+1 \right|^{-1} \Big|_{T_c} \quad (8)$$

where

$$K_{n-n'} = 2 \int d\Omega g(\Omega) \Omega \left[\Omega^2 + (n-n')^2 (2\pi T)^2 \right]^{-1} \quad (9)$$

and Z is the renormalization function

$$Z = 1 + (2n+1)^{-1} \sum_{n'} K_{n-n'} (2n'+1) / |2n'+1|_{T_c}^{-1}; \quad (10)$$

$$g(\Omega) = \alpha^2(\Omega) F(\Omega).$$

Equations (8) and (10) can be solved by the matrix method developed by Owen and Scalapino.³² The solution for any λ is obtained by the author;³¹ with high accuracy, it can be written in the form (if $\mu^*=0$)

$$T_c = 0.25 \tilde{\Omega} [e^{\frac{2}{\lambda}} - 1]^{-1}. \quad (11)$$

$$\tilde{\Omega} = \langle \tilde{\Omega}^2 \rangle^{1/2}, \langle \Omega^2 \rangle = (2/\lambda) \int d\Omega g(\Omega) \Omega$$

If $\lambda \lesssim 1$, we obtain $T_c = 0.25 \tilde{\Omega} \exp(-1/\lambda)$, $\lambda = \int \Omega dr g(\Omega) \Omega^{-1}$, see ref. 33; one can show that (see ref. 31) that the expression

$T_c = 1.14 \tilde{\Omega} \exp\{(1+0.5\rho)\rho^{-1}\} = 0.25 \tilde{\Omega} \exp(-1/\lambda)$ does not differ noticeable from the well-known expression obtained in ref. 34; here $\rho = \lambda(1+\lambda)^{-1}$. In the opposite limit we obtain from Eq. (11) $T_c = 0.18\lambda^{1/2} \tilde{\Omega}$, in accord with refs. 34-36.

If $\mu^* \neq 0$, we obtain

$$T_c = 0.25 \tilde{\Omega} [\exp(2/\lambda_{\text{eff}}) - 1]^{-1} \quad (12)$$

where $\lambda_{\text{eff}} = (\lambda - \mu^*)(1 + 2\mu^* + \lambda\mu^*t(\lambda))^{-1}$, the function $t(\lambda)$ is defined.³¹

Strong EPI has been found in organic superconductor (see ref. 37). A major manifestation of the strong coupling is the difference $\beta - \beta_{\text{BCS}}$, where $\beta = \varepsilon_0/T_c$, and ε_0 is the energy gap at $T=0$. In the weak coupling approximation, $\beta \equiv \beta_{\text{BCS}} = 1.76$. The organic superconductor $\beta - (\text{ET})_2 \text{AuI}_2$ is characterized by the value $\beta \approx 4\beta_{\text{BCS}}$, obtained from tunneling spectroscopy.³⁷ Tunneling data show large value $\beta \gg \beta_{\text{BCS}}$ for the new high T_c superconductors.

Recent experimental data (D. Morris and A. Zettl, private communication) show the presence of the isotope effect in La-Sr-Cu-O. This means that the electron-phonon interaction contributes to superconductivity. However, the coupling constant λ_{ph} is not large enough to provide high T_c . Indeed, according to neutron data, $\tilde{\Omega} \approx 120\text{K}$, and hence in superconducting oxides $\pi T_c \sim \tilde{\Omega}$. In this case, the electron-phonon interaction could provide high T_c if λ_{ph} were large enough (according to Eq. (12) this would require $\lambda_{\text{ph}} \approx 5$).

But if this were so, the ratio $2\epsilon_0/T_c$ would have to be large.⁷ At present, a lot of data indicate that $2\epsilon_0/T_c \approx 5$ which corresponds to intermediate coupling ($\lambda_{ph} \approx 2$).

Hence, the electron-phonon interaction plays an important role, but in order to provide high T_c , it is necessary to have an additional mechanism. We think that 2D plasmons (this type of excitations exists in the materials of interest) provide this additional attraction.

We came to the conclusion that our concept of a coexistence of phonon and non-phonon mechanisms proposed in¹⁴⁻¹⁵ is receiving experimental support. In the next section we are going to discuss the problem of the coexistence of the phonon and non-phonon mechanisms.

Coexistence of the Plasmon and Electron-Phonon Mechanisms. The Possibility of Experimental Observation of the Plasmon Mechanism.

Based on the generalized Eliashberg equation (1) one can evaluate T_c and the order parameter. It is important that the part of $\Gamma_{p\ell}$ which provides the electron-electron attraction via exchange of 2D plasmons can be written in the form of the usual D-function. As a result, Eq. (1) can be written as a usual Eliashberg equation:

$$\Delta(\omega_{n'}) Z = \pi T \sum_{\omega_n} \int d\Omega [g(\Omega) D(\omega_n - \omega_{n'}, \Omega) - 2\mu^*] \frac{\Delta(\omega_n)}{|\omega_n|} \quad (13)$$

Here $D(\omega_n, \Omega) = \Omega^2 / (\Omega^2 - \omega_n^2)$ is a D-function, and $g(\Omega) = g_{ph}(\Omega) + g_{p\ell}(\Omega)$ where $g_i(\Omega) = \alpha_i(\Omega) F_i(\Omega)$, $i = \{ph; p\ell\}$. F_i is the phonon (plasmon) density of states, α_i describe the electron-phonon and the electron-plasmon interactions, respectively. In addition, one can introduce the coupling constant $\lambda = 2 \int d\Omega g(\Omega) / \Omega$ which can be written as a sum $\lambda = \lambda_{e,ph} + \lambda_{e;p\ell}$, $\lambda_i = 2 \int d\Omega g_i(\Omega) / \Omega$.

The critical temperature in the presence of both the electron-phonon and the plasmon mechanisms can be evaluated from Eq. (13) (see ref. 15). We assume weak electron-plasmon coupling (a more general case will be described elsewhere). Then we obtain

$$T_c = T_c^{ph} (\Omega_{p\ell} / T_c^{ph})^h \quad (14)$$

Here T_c^{ph} is the critical temperature in the absence of the plasmon mechanism, $\Omega_{p\ell} \approx 0.5 \epsilon_F$, $h = \lambda_{p\ell} (\lambda_{ph} + \lambda_{p\ell})$. Note that the large value of the ratio $\Omega_{p\ell} / T_c^{ph}$ makes the contribution of 2D plasmons crucial even for small $\lambda_{p\ell}$. For example, if $\lambda_{ph} = 1.5$, $\Omega_{p\ell} / T_c^{ph} = 15$, we obtain $T_c \approx 2T_c^{ph}$.

The very important question arises of how to detect the presence of the non-phonon plasmon mechanism. Such a separation can be carried out experimentally because the plasmons are excitations of carrier system whereas the phonons involve ionic motion. It would be important to carry out a tunneling and neutron scattering experiment. Tunneling spectroscopy based on inversion of the Eliashberg equation will display all modes, including plasmons. As for neutron scattering, it will show

the function $F_{ph}(\Omega)$ only, because neutron scattering is not affected by the carriers subsystem. Usually $F_{ph}(\Omega)$ and $g_{ph}(\Omega)$ have a similar structure (position and number of peaks, the value of Ω_{max}). If the plasmons play an important role (this is the case for the high T_c superconductors), then comparison of the neutron and tunneling data would allow one to detect the presence of the additional (plasmon) mode. It would be particularly important to compare the frequency ranges.

It is essential to stress two points. First of all, the smallness of the Fermi energy (e.g., for $La_{1.8}Sr_{0.2}CuO_4$ the value $\epsilon_F \approx 0.12$ eV, see ref. 3), leads to the plasmon edge within the region suitable for tunneling spectroscopy.

In addition, the electron-plasmon coupling constant λ_{pl} depends on the carrier concentration ($\lambda_{pl} \sim v_F^{-1} \sim n^{-1/2}$, see, e.g., ref. 15 and increases with decreasing n . This is important because the new high T_c materials are characterized by small values of n . This fact makes the plasmon contribution crucial for explaining high T_c in these materials.

III. NON-PHONON MECHANISMS OF SUPERCONDUCTIVITY IN CONVENTIONAL SUPERCONDUCTING SYSTEMS

Despite the considerable theoretical progress and support for the existence of a non-phonon mechanism (NPM) of superconductivity, (see e.g., refs. 38-40, 21-27) the situation with NPM remains peculiar. Strictly speaking, it is impossible to point out a single superconductor and state that the superconductivity in this material is caused by NPM. We do not have any definite experimental evidence of a non-phonon mechanism. Unusual properties of high T_c superconductors make the appearance of the non-phonon mechanism very favorable (see above). NPM does not necessarily lead to high T_c . On the other hand, it is known that the BCS theory based on an analysis of the electron-phonon interaction (EPI) is not restricted to small T_c values. It is difficult to imagine a situation in which EPI would not play any role. Rather, it is more realistic that the phonon and non-phonon mechanisms coexist, although their relative contributions may be different. One can synthesize materials with the desired structure favorable for appearance of NPM. But there are also many existing superconductors which might benefit greatly from NPM. Substances containing non-uniform structures with spatial separation between different groups of electrons, or those with complex band structures, can be expected to have a significant contribution from NPM. We should be able to prove experimentally the presence of a non-phonon mechanism. In other words, it should be possible to separate the contributions of NPM and EPI.

It has been noted (see above, Sec. II) that the analysis of the tunneling and neutron data will allow one to determine the presence of the plasmon mechanism in the high T_c oxides. In this section we consider the usual low T_c superconducting system.

Non-phonon contribution from a high frequency peak. Consider the case when the non-phonon mode is located higher than the tunneling

region. In the paper⁴¹ the present author proposed a method allowing one to carry out a separation of this mode. The method is based on tunneling spectroscopy and on measurements of electronic heat capacity, or on the temperature dependence of the effective mass.

The powerful technique of tunneling spectroscopy allows one to determine the function $g(\Omega) = \alpha^2(\Omega) F(\Omega)$ ($F(\Omega)$ is the phonon density of states, $\alpha^2(\Omega)$ describes EPI). This function can be obtained by an inversion procedure (see, e.g., refs. 42-43) based on the Eliashberg equation

$$\Delta(\omega) = Z^{-1}(\omega) \int d\omega' \left\{ \int d\Omega g(\Omega) [D(\omega'+\omega) + D(\omega'-\omega) - \mu^*] \operatorname{Re} \{ \Delta(\omega') [\omega'^2 - \Delta^2(\omega')]^{-1/2} \} \right. \quad (15)$$

where $\Delta(\omega)$ is the order parameter, D is the phonon Green's function, μ^* is the Coulomb pseudopotential, and Z is the renormalization function. It is important that the Eliashberg equation (15) is written under the assumption that the superconducting state is caused by EPI only; this interaction corresponds to the energy range suitable for tunneling spectroscopy.

The same function $g(\Omega)$ affects the behavior of the electronic heat capacity $C_e(T)$. EPI leads to a deviation of $C_e(T)$ from the linear law. The analysis of the tunneling data and the behavior $C_e(T)$ allows one to determine the presence of the NPM (see ref. 41).

Recently a detailed analysis of the properties of Nb_3Ge aimed at the search for NPM has been carried out by Kihlstrom, Hovda, Wolf, and the present author.⁴⁴ The obtained results manifest a major contribution of NPM to the superconducting state Nb_3Ge .

Nb_3Ge has the highest T_c among A-15 compounds ($T_c^{\text{Nb}_3\text{Ge}} = 22.3\text{K}$). Band structure calculations⁴⁵ show that Nb_3Ge is an unusual material among A-15 superconductors, and the usual EPI is not sufficient to provide its high T_c . The density of states at the Fermi level is relatively small (see e.g., ref. 46). On the other hand, the band structure of Nb_3Ge is favorable for an NPM.^{24,45} The presence of overlapping bands might result in pairing in one band via virtual transitions to another band.^{22a} In addition, the acoustic plasmon branch (see above) can also provide electron-electron attraction.

The selection of Nb_3Ge was motivated by these reasons. An analysis based on the method⁴¹ (see ref. 44) has resulted in a picture entirely different from those obtained for Pb and V_3Si . According to⁴⁴ one can state that the non-phonon mechanism plays the key role in Nb_3Ge .

Pairing via molecular excitations. In the previous section, we studied the case when the energy of virtual transitions $\Delta\varepsilon_{\text{virt}}$ exceeds greatly the tunneling region. Let us discuss now a different case when

$\Delta\epsilon_{\text{virt.}}$ lies within this region. For concreteness consider the system studied by the author.⁴⁷ If the superconductor contains complex molecules (e.g., if the molecules are placed on the surface of a thin film), then additional electron-electron attraction arises via vibrational excitation of the molecules. This might result in an increase in T_c (see ref. 47). This change of T_c can be treated on the basis of the interesting theory of local modes developed in.⁴⁸ From this point of view, aromatic molecules are best because their vibrational spacing is relatively small ($\sim 10^2\text{K}$) and the contribution to coupling is notable. This mechanism of superconductivity based on intramolecular virtual excitations can be detected by the tunneling technique and will manifest itself as an additional peak. The position of the peak can be obtained from the second derivative of the tunneling characteristic.

It is important that the molecular frequencies are known independently from molecular spectroscopy. If the position of the peak coincides with the molecular frequency, this will manifest a new mechanism of superconductivity, namely the effect of intramolecular degrees of freedom on pairing.

SUMMARY

In this paper we consider several superconducting systems which are greatly affected by non-phonon mechanisms. The main results can be summarized as follows:

1. The low dimensionality and the small value of the carrier concentration in new high T_c oxides lead to unusual values of the main parameters such as ϵ_F , m^* , ξ_0 . As a result, one can observe a multigap structure.
2. The state of the lattice is greatly affected by the superconducting transition.
3. Exchange of 2D plasmons plays a key role in high T_c superconductivity. Its manifestation can be determined experimentally.

The superconducting state in high T_c materials is due to the coexistence of the phonon and non-phonon mechanisms.

4. Superconducting state Nb_3Ge is due to non-phonon interaction. Intramolecular excitations can provide additional attraction which can be detected by molecular spectroscopy and by tunneling.
5. Effective increase of T_c of A-15 superconductors can be achieved with the use of the proximity effect.

ACKNOWLEDGMENTS

The author is grateful to M. L. Cohen, D. Gubser, K. Kihlstrom, W. A. Little, H. Morawitz, and S. Wolf for many valuable discussions. This work was supported by the U. S. Office of Naval Research under Contract No. N00014-86-F0015 and carried out at the Lawrence Berkeley Laboratory under Contract No. DE-AC03-76SF00098.

REFERENCES

1. J. Bednorz and K. Müller, Z. Phys. B66, 189 (1986).
2. S. Uchida, et al., Jpn. J. Appl. Phys. Lett. 26, L1 (1987); C. Chu, et al., Phys. Rev. Lett. 58, 405 (1987); R. Cava, et al., Phys. Rev. Lett. 58, 408 (1987); M. Wu, et al., Phys. Rev. Lett. 98, 908 (1987).
3. V. Z. Kresin and S. Wolf, Solid State Comm. (in press).
4. N. Phillips, et al., (preprint); R. Battlogg, et al., Phys. Rev. B35, 5340 (1987); S. Tanaka, et al., Proc. of MRS meeting (Anaheim, 1987), in press.
5. J. Bardeen and M. Stephen, Phys. Rev. 136, 1485 (1964).
6. B. Geilikman and V. Z. Kresin, in Kinetic and Non-Stationary Phenomena in Superconductors, Wiley, New York (1974), p. 87.
7. V. Z. Kresin, Solid State Comm. (in press); Proc. of MRS meeting (Anaheim, 1987), in press.
8. H. Suhl, B. Mattias, and L. Walker, Phys. Rev. Lett. 3, 552 (1959).
9. B. Geilikman, R. Zaitsev, and V. Kresin, Proc. of LT-X, vol. IIA, Moscow (1967), p. 173; Sov. Phys. - Solid State 9, 642 (1967).
10. V. Z. Kresin, J. Low Temp. Phys. 11, 519 (1973).
11. P. Anderson, J. Phys. Chem. Sol. 11, 26 (1959).
12. H. Takayanagi and T. Kawakami, Phys. Rev. Lett. 54, 2449 (1985).
13. a) V. Z. Kresin, Phys. Rev. B34, 7587 (1986); b) V. Z. Kresin, Proc. LT-17, ed. by U. Eckern, A. Schmid, W. Weber, and H. Wuhl, North-Holland, Amsterdam (1984), p. 1029.
14. See Physics Today 40, 22 (1987); presented at Special Sessions at APS (March, 1987, New York) and MRS (April 1987, Anaheim).
15. V. Z. Kresin, Phys. Rev. B35, xxx, (1987).
16. V. Z. Kresin and H. Morawitz (preprint).
17. J. Ruvalds, Phys. Rev. B35, xxx, (1987).
18. A. Panson, et al., Appl. Phys. Lett. 50, 1104 (1987).
19. T. Ando, A. Fowler, and F. Stern, Rev. Mod. Phys. 54, 437 (1982).
20. D. Pines, Can. J. Phys. 34, 1379 (1956).
21. H. Fröhlich, J. Phys. C1, 544 (1968).
22. a) B. Geilikman, Sov. Phys.-Usp. 8, 2032 (1966); 16, 17 (1973);
b) E. Pashitskii, Sov. Phys.-JEPT 28, 1267 (1969).
23. J. Ihm, M. L. Cohen, and S. Tuan, Phys. Rev. B23, 3258 (1981).

24. J. Ruvalds, Adv. in Phys. 30, 677 (1981).
25. Y. Takada, J. Phys. Soc. Japan 45, 786 (1978); 49, 1713 (1980).
26. B. Geilikman and V. Z. Kresin, Sov. Phys.-Semiconductors 2, 639 (1968).
27. V. Z. Kresin and B. Tavger, Sov. Phys.-JETP 23, 1124 (1966); Phys. Lett. 20, 595 (1966).
28. D. Pines, Elementary Excitations in Solids (Benjamin, 1963).
29. P. Vashishta and K. Singwi, Phys. Rev. B6, 875 (1972).
30. V. Z. Kresin, J. Low Temp. Phys. 57, 549 (1984).
31. V. Z. Kresin, Phys. Lett. (in press).
32. C. Owen and D. Scalapino, Physica 55, 691 (1971).
33. B. Geilikman, V. Z. Kresin, and N. Masharov, J. Low Temp. Phys. 18, 241 (1975).
34. R. Dynes, Solid State Comm. 167, 331 (1968).
35. P. Allen and R. Dynes, Phys. Rev. B12, 905 (1975); C. Leavens, Solid State Comm. 17, 1499 (1975); S. Louie and M. L. Cohen, Solid State Comm. 22, 1 (1977).
36. V. Z. Kresin, H. Gutfreund, and W. A. Little, Solid State Comm. 51, 339 (1984).
37. M. Hawley, et al., Phys. Rev. Lett. 57, 629 (1986).
38. W. A. Little, Phys. Rev. 134A, 1416 (1964); H. Gutfreund and W. A. Little, in Highly Conducting One Dimensional Systems, ed. by J. Derreese, R. Errard, and V. van Doren (Plenum, New York, 1979), p. 305.
39. High Temperature Superconductivity, ed. by V. Ginzburg and D. Kirzhnits (Plenum, New York, 1982).
40. D. Allander, J. Bray, and J. Bardeen, Phys. Rev. B37, 1020 (1973).
41. V. Z. Kresin, Phys. Rev. B30, 450 (1984).
42. W. McMillan and J. Rowell, in Superconductivity, ed. by R. Parks (Dekker, New York, 1969), vol. 1, p. 561.
43. E. Wolf, Principles of Electron Tunneling Spectroscopy, Oxford University Press, New York, 1985.
44. K. Kihlstrom, P. Hovda, V. Z. Kresin, and S. Wolf (preprint).
45. B. Klein, L. Boyer, D. Papaconstantopoulos, and L. Matteis, Phys. Rev. B18, 641 (1978).
46. G. Stewart, in Superconductivity in d- and f- Band Metals, ed. by W. Buckel and W. Weber, Kernforschungszentrum, Karlsruhe (1982), p. 81.

47. V. Z. Kresin, Phys. Lett. 49A, 117 (1974).
48. H. Schuttler, M. Jarrell, and D. Scalapino, Phys. Rev. 58, 1147 (1987).

*LAWRENCE BERKELEY LABORATORY
TECHNICAL INFORMATION DEPARTMENT
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720*