Lawrence Berkeley National Laboratory

Recent Work

Title

MAGNETIC AND ELECTRONIC PROPERTIES OF Ni FILMS, SURFACES AND INTERFACES

Permalink

<https://escholarship.org/uc/item/2472c8v4>

Authors

Tersoff, J.
Falicov, L.M.

Publication Date

1982-05-01

Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

Materials & Molecular Research Division

RECEIVED
LAWRENCE
BERKELEY LABORATORY

JUL 15 1982

LIBRARY AND
DOCUMENTS SECTION

Submitted to Physical Review B

MAGNETIC AND ELECTRONIC PROPERTIES OF Ni FILMS,
SURFACES AND INTERFACES

J. Tersoff and L.M. Falicov

May 1982

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 6782.*

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

Magnetic and electronic properties of Ni films, surfaces and interfaces

J. Tersoff* and L.M. Falicov

Materials and Molecular Research Division, Lawrence Berkeley Laboratory and Department of Physics, University of California, Berkeley, California 94720

Results of various calculations lead to a unified understanding of the magnetic behavior of thin nickel films. We thus explain disparate experimental results. We report results for magnetic and electronic properties of Ni films of 1 to 5 atomic layers on Cu(100) and (111); of the Ni-Cu(100) and (111) interfaces; and of the Ni (100) and (111) surfaces. Results are in good agreement with the few published calculations. We find that magnetization is suppressed at the Ni-Cu interface, but enhanced in isolated thin films. The net effect of this competition is that a Ni monolayer is substantially magnetic on Cu(100) but paramagnetic (or nearly so) on Cu(111). Film magnetization is found to be very sensitive to substrate composition. For substrates which couple strongly to the Ni film, ferromagnetism first appears at about three atomic layer Ni, in quantitative agreement with experiments based on Al and Pb-Bi substrates. The crucial mechanism acting to suppress Ni magnetization is sp-d hybridization, just as in most Ni alloys.

*Current address--Bell Laboratories, Murray Hill, NJ 07974

I. INTRODUCTION

Recent studies¹⁻⁵ of the magnetic behavior of thin films have yielded disparate and apparently contradictory results. In particular, the question of the presence or absence of magnetically "dead" (i.e. paramagnetic) layers of Ni or Fe has attracted attention and generated some controversy. Despite the increasing care and sophistication of recent work, a consistent picture of the magnetic behavior of ultra-thin films remains elusive.

A major factor contributing to the confused situation is, we believe, the absence of a simple, coherent theoretical perspective from which to view the experimental results. Nickel is an itinerant ferromagnet; that is, its magnetization derives from the spin-polarization of the itinerant d electrons. These d electrons are very sensitive to local environment, and so the magnetic properties become intertwined with the electronic structure in a complex manner. In the simplest case, that of a pure infinite crystal, the simple rigid-band model of Stoner⁶ gives a reasonable account of itinerant ferromagnetism at $T=0$. For inhomogeneous systems, however, the picture is far from clear. For surfaces and, a fortiori, thin films, while some theoretical calculations have been reported⁷⁻¹¹, these have been too limited in scope to form the basis for a unified understanding of surface and film magnetism.

Our primary aim in this paper is to gain insight into the mechanisms determining the magnetic behavior of films, surfaces and interfaces. We choose Ni-Cu systems for theoretical investigation. These metals have very similar properties, and so form ideal substitutional alloys and epitaxial films with minimal charge transfer. While the calculations we present are mostly for Ni and Ni-Cu systems, the understanding gained permits us to draw conclusions about other systems too.

From the calculations reported here, together with available experimental results, a coherent picture of the important factors determining local magnetization in these inhomogeneous systems emerges. We thus place most of the disparate experiment results in a satisfying, consistent perspective.

It is not yet feasible to carry out such an extensive program of calculations using the most sophisticated computational tools currently available. Fully self-consistent methods are so numerically intensive that only a few simple ferromagnetic surfaces⁷⁻⁹, and only one film system¹⁰, have been studied to date. Our results are in excellent overall agreement with these state-of-the-art calculations. At the same time, the simpler methods used here permit a convenient, unified treatment of a relatively wide range of systems. By such a unified handling of surfaces, interfaces, and films, we develop the experience to draw simple general-

izations about the dominant physical effects.

The remainder of this Introduction is divided into three parts. Part A gives background on the available experimental results for films, surfaces and interfaces; part B gives theoretical background, in particular a discussion about the best available calculations for such systems; and part C summarizes the scope of this paper, and our results. Section II of this paper presents details of the calculation, section III discusses our results, and the conclusions are set forth in section IV.

A. Experimental Background

Over a decade ago Liebermann et al¹ sparked interest in film magnetism by reporting the observation of magnetically "dead" (i.e. paramagnetic) layers in thin Ni films on a Cu substrate. They interpreted this as a surface effect, supposing that a few layers at the surface of Fe or Ni are magnetically dead, so that for sufficiently thin films only these "dead" surface layers remain. This interpretation, while physically plausible, is almost certainly incorrect, and has had the unfortunate effect of distracting attention from the crucial role of the substrate.

More recent experiments have directly probed the magnetization of a Ni surface using photoemission¹², electron capture spectroscopy (ECS)^{2,13}, and spin-polarized low-energy electron diffraction (PLEED)¹⁴. While none of

these methods provides a quantitative determination of the surface magnetization, all experiments agree that the surface layer of Ni is magnetic.

Results for thin Ni films are more complex and, on their face, inconsistent. Liebermann et al¹ generated their thin films by electroplating, rather than by clean ultra-high-vacuum methods as in more recent work. The possibility that they were observing some effect of surface oxidation or hydrogenation cannot therefore be ruled out. Later careful experiments with thin Ni films on Cu substrates^{2,3} have failed to find any evidence of magnetically "dead" layers. We note however that none of these experiments has examined Ni films of less than two atomic layers. Rau², by means of ECS, found that a two-layer Ni film was definitely magnetic. Pierce and Siegmann³ found similar results using spin-polarized photoemission. While they extrapolate their results to thinner films, the extrapolation assumes a fixed number of "dead" layers independent of film thickness; we find that such an assumption is unwarranted and probably incorrect, as discussed later in this paper.

On the other hand, experiments by Bergmann⁴ and Meservy et al⁵ clearly show a transition from ferromagnetism to paramagnetism as Ni film thickness is reduced below 2.5 - 3 atomic layers. These experiments were carried out using a Pb-Bi alloy substrate and an Al substrate, respectively. We demonstrate below that the mag-

netic behavior of the Ni film may be expected to depend sensitively on substrate composition, in agreement with the available data.

Bergmann⁴ and Meservey et al⁵ also found that Fe retained its magnetic moment down to sub-monolayer film thickness, even on the substrates where Ni lost its moment at 2.5 - 3 atomic layers. This too is consistent with our results, though it is not surprising in any case.

It is unfortunate that, to date, no one has systematically studied the dependence of Ni films magnetization on substrate composition (though a related experiment by Gradmann¹⁵ is very suggestive); nor has the study of Ni films on Cu been carried to monolayer and submonolayer coverage. Nevertheless, the available experimental information, together with the results presented below, form a compelling picture regarding the role of film thickness and substrate composition in determining film magnetization.

B. Theoretical Background

In the brief history of fully self-consistent calculations of surface magnetism, no system has been more widely studied than the ideal Ni(100) surface. In fact, few other systems have been studied at all. Wang and Freeman⁷ reported a substantial decrease (about 25%) in the surface magnetization, relative to the bulk value. That calculation used a 9-layer film to mimic the semi-infinite crystal. On the other hand results of Jepsen et al⁸ and Krakauer and

Freeman⁹ suggest a small enhancement in the surface magnetism; a quantitative value is however difficult to extract because of the thin 5-layer films used.

The apparent discrepancy among reported calculations is somewhat worrisome, but may be attributable simply to aspects of the numerical implementation in early work. A more fundamental problem is the difficulty in finding relevant comparisons to experiment, in order to gauge the true accuracy of any theoretical results. For now, the quantitative reliability of any theoretical treatment of surface magnetism remains an open question.

Wang and Freeman have also reported¹⁶ a substantial enhancement ($\sim 50\%$) of the surface magnetization of Fe(100) relative to the bulk; and Noffke and Fritsche¹¹ and Wang et al¹⁰ find that (hypothetical) monolayer films of Ni and Fe, with vacuum on both sides, have magnetizations substantially greater than the metallic bulk values (though still smaller than the respective atomic spin values). These results clearly controvert the suggestion¹ of magnetically "dead" surface layers. They suggest, on the contrary, that surfaces and especially thin films tend to have enhanced magnetization. This tendency is moreover consistent with the naive argument that reduced coordination number will lead to band narrowing and a larger density of states (DOS) at the Fermi level (E_F), and hence to stronger magnetization. We argue that it is the interaction with a

nonmagnetic substrate which overwhelms this tendency and suppresses the film magnetization in experiments on supported Ni films.

Only one calculation has been reported for the magnetization of a supported film. Wang et al¹⁰ find that a monolayer Ni film on Cu(100) is substantially magnetic, with a magnetic moment per Ni atom which is reduced about 40% from the bulk value. That calculation employed one of the most advanced techniques now available; unfortunately, no comparison with experiment or with comparable calculations is yet possible.

It is interesting to note that no calculation has been reported for a (111) surface, even though this orientation predominates in polycrystalline Ni samples, which are often used in experiments. The methods used in the calculations cited above are so numerically intensive, that the reduction in computation which results from the extra (in-plane) reflection symmetry of the (100) film has been a major factor in determining the direction of theoretical investigation. Here we compare behavior of (100) and (111) films, surfaces and interfaces. We find interesting systematic difference between the two orientations.

There is actually a substantial body of theoretical work which is immediately relevant to the problem of magnetic films, and yet whose relevance has not been emphasized. We refer to work on magnetic alloys¹⁷ and impurities¹⁸.

We argue that the suppression of film magnetism by the nonmagnetic substrate is quite analogous to the suppression of impurity magnetism by the nonmagnetic matrix, or of Ni magnetism in alloys by the nonmagnetic constituent. This point is discussed later in the paper.

C. Scope and Results of This Work

In this paper we present results of calculations for the magnetic and electronic properties of the ideal Ni(100) and (111) surfaces, the Ni-Cu (100) and (111) interfaces, and ideal epitaxial Ni films of from one to five atomic layers on Cu(100) and (111). The Ni(100) surface has been extensively studied⁷⁻⁹, and one calculation¹⁰ for a monolayer Ni film on Cu(100) has been reported. Otherwise these results are all completely new. In addition we have performed some numerical "experiments" which illuminate the crucial factors determining film magnetic behavior. From these results, we attempt to extract a coherent picture of the magnetic properties of these systems, which sheds light on the disparate experimental results¹⁻⁵, and suggests possible directions for future experiments.

For our calculations we have employed the simplest techniques consistent with the treatment of real systems. We use a tight-binding scheme, with the exchange interaction treated self-consistently in a single-site approximation. Only properties at temperature $T=0$ are considered. We find excellent agreement with available results of fully self-consistent calculations.

We conclude this introduction by summarizing the most important of our results. The monolayer Ni film on Cu(100) is found to be substantially magnetic, whereas on a Cu(111) substrate it is magnetically "dead", or nearly so. The surprising sensitivity to substrate orientation is easily understood in view of other results presented. The Ni magnetization at a Ni-Cu interface is suppressed substantially, by approximately 30%, relative to Ni bulk. On the other hand, the magnetization of an isolated monolayer Ni film is considerably enhanced relative to the bulk. The two effects compete, and they almost cancel each other for the monolayer Ni film on Cu(100). For the monolayer of Ni on Cu(111) the delicate balance of effects is no longer present. For other substrates such as Al, which are expected to couple more strongly to the Ni, a paramagnetic Ni monolayer is expected.

Because of the short screening length, the effect of both the interface and the surface are confined to one or two atomic layers in Ni. Thus for films of four and even three atomic layers, the behavior of the film surface and the film-substrate interface are quite similar to the ideal surface and interface.

We find that the major physical cause of magnetization suppression in the interface and film, is hybridization between the Ni d band and substrate conduction band, which affects the projected local DOS at the interface. The same mechanism responsible for the suppression of Ni magnetization in Ni

alloys¹⁷. Unfortunately the useful analogy between alloy and interface has been largely overlooked.

The cause of the enhancement in magnetization for isolated thin films is d-band narrowing and sp-d dehybridization, which result from reduced coordination number.

To verify these conclusions, and to learn more about the effect of sp-d hybridization, we have artificially varied the coupling between Ni d band and substrate conduction band. Such an approach, which bridges the gap between realistic and model calculations, proved highly instructive. The magnetization of a monolayer Ni film is extremely sensitive to the degree of film-substrate coupling, with the realistic Ni-on-Cu case falling in the intermediate regime of coupling strength. If we consider Ni on some substrate, to which it couples more strongly than to Cu, a quite different picture emerges. For one or two layer of Ni, the film is paramagnetic, but for three or more layers the film is ferromagnetic, with an abrupt magnetic transition as thickness is increased. The critical film thickness (for strong film-substrate coupling) is determined by the screening length in Ni, and represents a substrate-independent upper bound for the critical film thickness at which ferromagnetism first appears. This conclusion is supported by experiments^{4,5}, which find that, for simple metal substrates, magnetism appears at a film thickness of 2.5-3 atomic layers.

II. CALCULATION

This section describes our calculations. We used a tight-binding Hamiltonian, with the exchange interaction in the single-site approximation. This is the simplest method consistent with the treatment of real systems. Comparison with available fully self-consistent calculations suggests that our methods are quantitatively reliable. Such comparisons are drawn where appropriate throughout the discussion of results in section III.

More important, this work complements the few fully self-consistent results available, by allowing the inclusion of a broader range of systems.

A. The Hamiltonian

We take our Hamiltonian to be the sum of a one-electron term H_0 and an electron-electron interaction term H_{ee} . For H_0 we choose the parameterized tight-binding scheme of Slater and Koster¹⁹. The Hamiltonian H_0 is written in terms of one and two-center integrals, which are treated as parameters chosen to fit the bulk band structure. We include s, p and d orbitals, with interactions up to second-nearest neighbor. For the matrix elements between Ni and Cu, we take the geometric mean of the respective Ni-Ni and Cu-Cu matrix elements. The two sets of intersite matrix elements are very similar, so the results are insensitive to the precise scheme for choosing the Ni-Cu matrix elements.

The electronegativities of Ni and Cu are the same to

within about 0.1 eV²⁰, so we choose the zeros of energy for the two metals so as to line up their bulk Fermi levels. However the final self-consistent results are not sensitive to physically reasonable (~ 0.2 eV) differences in the respective Fermi levels.

For the electron-electron interaction we use a single-site approximation, which has been extensively discussed²¹,

$$H_{ee} = \sum_{i\sigma\sigma'} \sum_{\alpha\beta\gamma\delta} U_{\alpha\beta\gamma\delta} c_{i\alpha\sigma}^{\dagger} c_{i\beta\sigma'}^{\dagger} c_{i\gamma\sigma} c_{i\delta\sigma} \quad , \quad (1)$$

where $c_{i\alpha\sigma}^{\dagger}$ creates an orbital of symmetry α and spin σ at site i . Intersite Coulomb terms can be neglected here, since results for the single-site approximation are already essentially charge-neutral at each site.

We treat H_{ee} in the Hartree-Fock approach; we can, with some approximations, reduce H_{ee} to a simple form for the on-site potential shifts,

$$\begin{aligned} \Delta E_{dv\sigma} = & -\frac{1}{2}(U-J)\langle m_{dv\sigma} \rangle - \frac{1}{2} J \langle m_{d\sigma} \rangle \\ & + V_{sd} \langle n_s - n_s^0 \rangle + V_{dd} \langle n_d - n_d^0 \rangle \end{aligned} \quad (2)$$

$$\Delta E_{s\sigma} = V_{ss} \langle n_s - n_s^0 \rangle + V_{sd} \langle n_d - n_d^0 \rangle$$

Here $\Delta E_{dv\sigma}$ is the on-site potential shift for a d orbital of symmetry v and spin σ , measured relative to the value for the pure paramagnetic metal. By $m_{dv\sigma}$ we denote the spin polarization ($n_{dv\sigma} - n_{dv\bar{\sigma}}$) in the d orbital of symmetry v at a given site, and $m_{d\sigma} \equiv \sum_v m_{dv\sigma}$. The total d occupancy at the

site is denoted by $(n_d \equiv \sum_{\nu\sigma} n_{d\nu\sigma})$, and the value for the respective pure metal is n_d^0 . Quantities for s and p orbitals are similarly defined. In (2), s refers to the entire sp complex.

We define U as the on-site direct Coulomb integral between d orbitals of the same symmetry (rescaled by correlation effects, see below); U' is the integral between d orbitals of different symmetry; and J is the exchange integral. We define $V_{dd} \equiv U' - \frac{1}{2}J$, which give the effective (repulsive) interaction between d electrons, aside from magnetic effects. We similarly define an effective interaction V_{ss} among sp electrons, and V_{sd} between sp and d electrons. We neglect the on-site exchange integrals other than between d orbitals. The ratios $U:U':J$ are taken to be 5:3:1 as suggested by Herring²¹; this incidentally allows us to cancel a term involving $U+J-2U'$. These ratios are not crucial. Similar results are obtained for $J=0$ or $J=U$ as long as the absolute magnitude is scaled to give the correct²² bulk Ni magnetization, $\mu=0.616\mu_B$. Such scaling is necessary in any case when we work in the Hartree-Fock approximation, since the effective interaction is reduced by correlation effects²¹.

It is difficult within the tight-binding approximation to treat charge transfer accurately at the surface. To avoid this problem and still treat charge transfer and potential

shifts at the surface in a simple way, we impose upon our potential the constraint

$$\Delta n_{sp} = \Delta n_d = 0 \quad . \quad (3)$$

That is, the average on-site potential of the d orbitals, and of the s and p orbitals, are fixed by the requirement that the total occupancies of the sp and d complexes at any site not differ from the bulk values. More fully self-consistent calculations^{11,23} suggest a transfer of about 0.1 electrons per atom from the sp band to the d band at the surface. By neglecting this, we may expect to exaggerate the surface magnetization by roughly $0.1\mu_B$ per atom, an acceptable level of error.

B. Evaluation of Electronic Properties

In calculating electronic properties of surfaces, it is usual to replace the real semi-infinite geometry with a thin "slab" of a few atomic layers. For example, the most sophisticated calculations^{8,9} for the Ni surface reported to date have been limited to (100) films of five atomic layers. Wang and Freeman⁷, using a somewhat less fully self-consistent method, have treated a nine-layer film. Many electronic properties are not sensitive to film thickness; the magnetic behavior of a (100) film proves to be an exception.

In these calculations we have used two complementary

methods. One is the usual "slab" method; the other is a Green's function method, developed elsewhere²⁴, which permits us to treat a semi-infinite geometry. We find that a realistic semi-infinite geometry has a significant effect on the results for magnetization only for the case of the ideal (100) Ni surface.

Spin-oscillations are relatively long-ranged because they are not screened. For a Ni film on a Cu substrate, the Ni-Cu interface imposes a correct boundary condition on the oscillations; since there is effectively no penetration of the magnetization into the Cu, the thickness of the Cu substrate is relatively unimportant.

Because the Green's function method is less widely used than the slab method, we sketch out the essential points. Let ϕ_{iR} denote the i^{th} local orbital, centered on lattice site $\vec{R}$. Also let $\vec{R}_m$ denote a lattice vector lying in the m^{th} plane of atoms from the surface. For our basis we take Bloch sums in a single plane, $\phi_{im}(\vec{k}) = N^{-1/2} \sum_R \phi_{iRm} \exp[i\vec{k} \cdot \vec{R}_m]$, where $\vec{k}$ is a wavevector parallel to the surface, and N is the number of atoms in a layer.

The Green's function is defined by Dyson's equation, which for our one-electron Hamiltonian is simply $I = (\epsilon - H)G$. We handle the orbital indices implicitly in matrix notation, but write the layer indices explicitly as subscripts. For example, $\tilde{G}_{mn}(\vec{k}, \epsilon)$ is a matrix such that $[\tilde{G}_{mn}(\vec{k}, \epsilon)]_{ij} \equiv \langle \phi_{im}(\vec{k}) | G(\epsilon) | \phi_{jn}(\vec{k}) \rangle$. Then Dyson's equation leads to an infinite set of simultaneous equations involving

different layers.

For example, with only neighboring layers interacting, we can write

$$\tilde{I} = (\epsilon - \tilde{H}_{11}) \tilde{G}_{11} - \tilde{H}_{12} \tilde{G}_{21} ,$$

$$0 = (\epsilon - \tilde{H}_{22}) \tilde{G}_{21} - \tilde{H}_{21} \tilde{G}_{11} - \tilde{H}_{23} \tilde{G}_{31} , \quad (4)$$

$$0 = (\epsilon - \tilde{H}_{33}) \tilde{G}_{31} - \tilde{H}_{32} \tilde{G}_{21} - \tilde{H}_{34} \tilde{G}_{41} , \text{ etc.}$$

To uncouple these equations we note that in the bulk, the relation between Green's function matrix elements for successive layers must be independent of the particular layer. We therefore define the transfer matrix $\tilde{T} = \tilde{G}_{m+1,n} (\tilde{G}_{m,n})^{-1}$, which is independent of $\underline{m}$ and $\underline{n}$, for $\underline{m}$ is sufficiently large. The transfer matrices for each $\vec{k}$ and ϵ may be calculated once and stored.

In equations (4) above, we include self-consistency only as a shift in the diagonal elements of the Hamiltonian. For example, if we treat two layers self-consistently, i.e. only H_{11} and H_{22} differ from the bulk value, then $\tilde{G}_{31}$ is related to $\tilde{G}_{21}$ by an equation with only bulk-like terms, and we can write $\tilde{G}_{31} = \tilde{T} \tilde{G}_{21}$. Thus we uncouple the infinite set (4) of equations, and reduce it to two simultaneous

matrix equations. For the ideal surface, we obtained accurate results with only one layer self-consistent. In that case (4) reduced to a single matrix equation.

Once we have $\tilde{G}_{mm}$ for the layers of interest, it is trivial to define the local density of states and local occupancy. For example, we can define a partial density of states $D_{md}(\epsilon)$ in which we project out the contribution from the $\underline{d}$ orbitals in layer $\underline{m}$,

$$D_{md}(\epsilon) = -\frac{1}{\pi} \text{Im} \sum_{\vec{k}} \text{Trd} \tilde{G}_{mm}(\vec{k}, \epsilon) ,$$

where Trd denotes a partial trace, taken only over the indices corresponding to $\underline{d}$ orbitals. The $\underline{d}$ occupancy on a site in layer $\underline{m}$ is $n_d = \int_{-\infty}^{\epsilon_F} D_{md}(\epsilon) d\epsilon$.

C. Accuracy

Here we discuss, first, the numerical accuracy of our calculations, and second, the crucial approximations in our Hamiltonian and their effect on the reliability of the model.

Magnetic surface calculations pose unusual problems for numerical convergence. A significant portion of the magnetization at the surface may derive from surface states which intersect the Fermi level. In this case the magnetization converges rather slowly with respect to wavevector sample $\sqrt{25}$. For example, for the (100) surface, 15 wave-

vectors in the surface Brillouin zone gave excellent convergence for bulk properties (obtained by using a thick slab with periodic boundary conditions); however on increasing the sample to 21 wavevectors, the Ni-Cu(100) interface magnetization changed by 10%, because of better resolution of interface states. We obtained good convergence of all properties using 21 wavevectors in the irreducible wedge of the (100) surface Brillouin zone, and 30 wavevectors in the (111) irreducible wedge.

Convergence of the potential can also be somewhat tricky for inhomogeneous magnetic systems. For a paramagnetic calculation, a small error in the input potential (relative to the self-consistent value) gives rise to a small error in the charge density; this in turn results in a large change in the calculated output potential, on account of the large Coulomb restoring forces. Thus good agreement between input and calculated output potential insures that the input potential and calculated charge density are very close indeed to the self-consistent values. On the other hand, while a small error in charge density gives rise to a large restoring force, a small error in spin density has the opposite effect. Increasing the spin-polarization beyond its equilibrium value results in a stronger exchange splitting, which reduces the exchange energy. The "restoring force" is the deviation from a weak minimum in the sum of "band" energy and exchange energy, and so is not directly

reflected in the potential. Thus, the magnetization can "drift" over many iterations with little apparent change in the degree of convergence, as judged by the potential. Because the methods used here are relatively inexpensive, we were able to insure in every case that our results were well converged. In particular, our potentials were converged to 10^{-4} rydbergs, and the magnetizations were seen to converge exponentially with iteration, so that final values were numerically reliable to roughly $3 \times 10^{-3} \mu_B$ or better.

We now recapitulate the most crucial approximations in our Hamiltonian, and consider their effects. The most drastic approximation here is (3), in which the self-consistent change in the potential is approximated by an on-site term, determined by imposing a zero-charge-transfer condition on the sp and d projected subbands separately at each site. Comparison with fully self-consistent calculations^{11,23} suggests that this is an excellent approximation. Still, the uncertainty of up to 0.1 electron in the local d occupancy corresponds to a possible error of up to $0.1 \mu_B$, which is significant for Ni systems. However there is no evidence that any available methods are accurate to better than $0.1 \mu_B$ for inhomogeneous systems in any case. Approximation (3) also neglects the crystal-field splitting of the on-site potential.

Our Hartree-Fock treatment necessarily exaggerates the exchange splitting, which is reduced by correlation effects.

This is not a serious problem for bulk calculations, where the majority-spin band is essentially full. For heterogeneous systems, where the majority-spin band may be less full at some sites, the exaggerated exchange splitting could conceivably be a source of error in the magnetization.

Finally, the use of a tight-binding Hamiltonian should be analyzed with care. This method provides a rather good treatment of the d band, but the handling of the sp band is less accurate. Since sp-d hybridization plays an important role here, the tight-binding approximation introduces some risk of reduced quantitative accuracy.

We must ultimately base our assessment of overall accuracy upon comparison with reported results of fully self-consistent calculations, for simple systems and with experiment. Such comparisons are few, but they suggest that our methods are reliable even for the quantitative magnetization of heterogeneous systems. Moreover, the most important results here are trends and comparisons of different systems; differences between comparable systems (e.g. different surface orientations) should be much more reliable than absolute magnetization. It is our hope that this work will stimulate experiments to test our conclusions.

III. RESULTS

The discussion of results is divided into four parts. Part A treats the ideal Ni(100) and (111) surfaces. Besides

presenting results for the magnetization and electronic structure, we introduce the basic ideas used later.

Part B presents results for the Ni-Cu interface. In addition to its intrinsic interest, an understanding of ideal interface magnetic behavior is helpful in analyzing results for thin films, where several effects are present at once.

Part C discusses results for thin Ni films on Cu. By considering a range of thicknesses we follow the evolution of magnetic behavior from the Ni monolayer to the thick-film limit, where the surface and interface decouple.

Finally, in part D we present results of some numerical "experiments". By artificially altering the film-substrate coupling, we are able both to isolate the essential physical mechanism acting to suppress film magnetization, and to understand the qualitative effect of varying substrate composition.

A. The Ideal Ni Surface

Previous theoretical investigations of the surface magnetism of Ni⁷⁻⁹ focused exclusively on the (100) surface, even though the (111) surface is energetically favored. In our discussions we stress the systematic differences between these two surfaces. The ideas developed also prove fruitful in understanding the magnetic behavior of ultra-thin Ni films.

Table I summarizes our results for the layer-by-layer

magnetization at ideal Ni(100) and (111) surfaces. The spin-polarization at the surface is probably exaggerated by our approximation (3), as discussed above.

The most interesting feature of these results is the difference in magnetization between the two surfaces. The spin polarization of the (100) surface is significantly stronger. While we know of no unambiguous experimental determination of the relative magnetization of the two surfaces, the results of $R_{\text{Au}} \sqrt{2}$ suggest a possible confirmation of our result.

Figure 1 shows the majority and minority-spin density of states (DOS) of bulk Ni for comparison with layer-projected results presented below. As in all the DOS plots in this paper, we have projected out only the contribution from the d orbitals, and we have smoothed the DOS by convolution with a Gaussian of half-width 0.08eV at half-height.

Figure 2 shows the spin-projected DOS at the Ni(100) and (111) surfaces. There are two differences between the (100) and (111) results which explain the larger (100) surface magnetization. First, the (100) surface DOS is narrower than the (111) DOS. This may be simply a consequence of lower coordination; in the fcc lattice an atom has 8 nearest neighbors at the (100) surface versus 9 at the (111) and 12 in the bulk. Also, the (100) surface DOS has a very sharp upper d-band edge. These factors result in a large

DOS at the Fermi level, E_F , which is conducive to a large magnetization.

The second important difference between the (100) and (111) results lies in the high-energy tail of the DOS. Recall that we have projected out only the d-orbital contribution, which extends well above the d-band "edge" due to hybridization with sp-like (free-electron-like) states. This high energy "hybridization tail" of the d band tends to reduce the magnetization. By preventing the complete filling of the majority-spin d band, it inhibits polarization of the available d holes. This hybridization tail is suppressed at the (100) surface. There is a dehybridization of the sp and d bands there, which contributes to the (100) surface magnetization. (The difference appears very small visually, since the scale of the figure is determined by the d-band, which contains five electrons. We are however concerned with shifts of much less than 0.1 electron from one spin-band to the other.) This sp-d dehybridization probably also contributes to the narrowing of the DOS at the (100) surface.

Figures 3 and 4 show the dispersion of surface states and surface resonances at the (100) and (111) surfaces respectively. The two-dimensional surface Brillouin zones and the labeling of symmetry points are also shown. Because a small change in the potential can change a resonance into a bona fide surface state, or vice versa, we have made no

attempt to distinguish the two precisely. Instead, we consider a seven-layer Ni slab. For a given (two-dimensional) wavevector we plot a solid circle for each eigenstate which is over 80% localized in the surface layers of the slab, and an open circle if the state is between 40% and 80% surface-localized. We make no attempt to correct or suppress the small spurious doubling which results from mixing of surface states localized on the two surfaces.

Such an analysis, while of only limited use for comparison with photoemission results, is the clearest way to draw the connection between surface states and resonances, and the local DOS at the surface.

The (100) results show a wealth of surface states and resonances near the Fermi level. These contribute to the large local DOS at E_F for the surface. The (111) surface does not display surface states near E_F , except in the vicinity of the symmetry point $\bar{M}$.

Our results for the relative position and dispersion of the surface states and resonances appear to be in excellent agreement with those of Wang and Freeman⁷. While a detailed comparison is difficult because of the manner in which those results were presented, the evident overall agreement is encouraging. There is however a significant difference in the overall position of the two sets of spin-bands, for two reasons. First, our Hartree-Fock calculation overestimates the exchange splitting, which is reduced by

correlation effects. These effects are included in an approximate way in the local-density-functional calculation of Wang and Freeman. Second, our results give a somewhat larger surface magnetization than Wang and Freeman, adding to the difference between our exchange splitting and theirs. A larger surface magnetization is consistent however with more recent calculations^{8,9}; approximation (3) doubtless also contributes to the discrepancy.

The Ni(100) surface results in Figure 3 give the appearance of rather well-defined two-dimensional surface bands. One can follow the dispersion of a given resonance across the whole Brillouin zone in several cases. The (111) surface results of Figure 4 display less structure, with many "bulk" states contributing more or less equally to the surface-projected bandstructure.

Many of the results noted so far suggest that the (100) surface exhibits more quasi-two-dimensional behavior than the (111). This is evidenced in the surface bands, strong magnetization and sp-d dehybridization, which are reminiscent of unsupported monolayer behavior^{10,11}.

Finally, we call attention to an interesting symmetry-related feature of the surface bands. Both the (100) and (111) surfaces exhibit surface states which split off the top of the d band at the symmetry points $\bar{M}$. (The coincidence of labelling, determined by established convention is accidental.) For the (100) surface, $\bar{M}$ corresponds to

the projection of the line W-X in the fcc bulk Brillouin zone. There is an extremely flat bulk band along this line. For the relevant d-state symmetry, the nearest-neighbor interaction between layers vanishes. Therefore at $\bar{M}$, a small change in potential at the surface is sufficient to create a surface state. As one moves away from $\bar{M}$, the layer decoupling disappears. The peculiar dispersion of the surface state at $\bar{M}$ is attributable to the wavevector-dependent coupling between layers, and cannot be understood in a strictly two-dimensional model.

In the (111) surface the surface state at $\bar{M}$ has a similar origin. In that case, $\bar{M}$ corresponds to the line L-X in the bulk, where there is again an extremely flat band. (Unlike W-X, this symmetry-related flat band has not been previously discussed, since it does not fall on the symmetry lines traditionally used in plotting fcc band structures.)

B. The Ni-Cu Interface

While much experimental¹⁻⁵ and theoretical¹⁰ attention has been paid to the magnetic behavior of thin films, such work has often emphasized the supposed analogy between film and surface, while neglecting the film-substrate interface. We argue that the surface and the film-substrate interface have radically different and competing effects on film magnetism. Thus it is of great importance to understand the magnetic behavior of the interface between a ferromagnet

and a normal metal, before attacking the conceptually more complex film problem.

We approach the interface problem by considering thin Cu films on a Ni(100) or (111) substrate. These systems are of particular interest because ideal (surface insensitive) interface behavior develops after only one or two atomic layers of Cu have been deposited. The interface is therefore accessible to such sensitive probes as photoemission and spin-polarized electron diffraction. Moreover, Cu is easily deposited on Ni in almost perfect epitaxial layers. (For Ni on Cu it is difficult to avoid clumping of the Ni atoms and diffusion of the Ni into the Cu bulk.)

The method of calculation has been discussed in detail above. Results for the layer-by-layer Ni spin polarization at the (100) and (111) Ni-Cu interface are given in Table II, for Cu films of one and two atomic layers on Ni. The magnetization in the Cu is in every case negligible ($\leq 0.02\mu_B$, almost entirely caused by the small negative polarization of the sp band).

The results in Table II show that the magnetization at the interface is reduced substantially, about 30%, from the bulk value. The effect does not differ much between the (100) and (111) interfaces, though the sensitivity to Cu thickness is slightly greater for the (111) interface. Even for the (111) interface, a single atomic layer of Cu on Ni provides a reasonable approximation to the ideal interface

for experimental purposes.

The effect of the interface on magnetization is large only in the first Ni layer, and is negligible, ($\leq 0.02\mu_B$), at the third and more distant layers. Note that because of approximation (3), the results presented here tend to underestimate the suppression of the magnetization at the interface. In a previous calculation without this approximation²⁶, we found that local band narrowing at the interface caused a transfer of almost 0.1 electrons from the sp orbitals into the d orbitals in the Ni interface layer. This local d-band filling contributed to the larger suppression of interface magnetization ($\sim 50\%$) reported there, though subsequent improvements in our wavevector sample also contribute to the difference.

The cause of the reduced local magnetization at the interface can be seen in Figure 5, which shows the local d-projected DOS in the Ni interface layer for the (100) and (111) interfaces. The most apparent change from the bulk DOS (Figure 1) is that the interface DOS has become rounded, losing the sharp upper d-band edge seen in the bulk. Elsewhere, in treating the Ni-Cu alloy¹⁷, we have discussed the importance of this sharp band edge for the ferromagnetism of Ni. For a band with a "tail" in the DOS, it is difficult to achieve saturation, i.e. one spin band completely full; whereas, in a Stoner-type rigid band model, if the DOS of a ferromagnet is constant with a sharp cutoff, the spin

polarization will always proceed to saturation.

We must emphasize that the interface behavior is entirely analogous to that of the Ni-Cu alloy¹⁷. Both systems share the characteristic changes in projected Ni d-band shape caused by reduced local symmetry, reduced Ni-Ni coordination number and enhanced sp-d hybridization.

The validity of the analogy between alloy and interface appears to be experimentally confirmed by recent studies²⁷ of compositionally modulated Ni-Cu epitaxial film structures. In these systems, alternating films of Ni and Cu are deposited in turn. The structure is then annealed to allow interdiffusion of the Cu and Ni. The smooth crossover observed, between the sharp-interface regime and the compositionally-modulated-alloy regime, suggests that there is no fundamental difference between the important mechanisms in these two cases.

It is important to notice that, from the point of view of the d orbitals alone, the Ni surface and Ni-Cu interface are very similar. The Cu d band is centered well below the Fermi level, and because of the large energy denominator the Cu d orbitals have almost negligible interaction with the states near E_F . We have verified this explicitly by artificially removing the Cu d orbitals from the Hamiltonian, and finding insignificant change ($\sim 0.02\mu_B$) in the interface magnetization. Thus, considering the d orbitals alone, a Ni atom interacts only with its Ni neighbors at the Ni-Cu

interface, just as at an ideal Ni surface.

It is the interaction between the Ni d orbitals and the free-electron-like sp states which accounts for the radical difference in magnetic behavior between the two geometries. This interaction tends to broaden and "smear" the d band. Comparison of the surface d-band DOS (Figure 2) with the interface DOS (Figure 5) shows that at the interface the d band is broadened and rounded, relative to the surface. In particular, the upper edge of the minority-spin band is less sharp at the interface, resulting in a reduced DOS at E_F . These changes are caused entirely by the greater sp-d hybridization at the interface.

We have also looked for interface states at the (100) and (111) Ni-Cu interfaces. The interface states and resonances are shown in Figures 6 and 7. We find no evidence of interface states or interesting resonances, except for states near $\bar{M}$ in the Brillouin zone for both surfaces. These states are similar to those at the surface, discussed at the end of section IIIA. Because of the symmetry-induced decoupling of successive layers, even the interface represents a sufficient perturbation to split off an interface state near the $\bar{M}$ points for both interfaces.

C. Thin Ni Films on Cu(100) and (111)

While several fascinating experiments probing Ni film magnetism have been reported¹⁻⁵, the theoretical understanding of ultra-thin films is in its infancy. Only one

self-consistent calculation for a real system has been reported -- Wang et al¹⁰ have studied a monolayer Ni film on Cu(100). Here we present the first investigation of the roles of film thickness and substrate orientation (crystal face) in determining the magnetic and electronic properties of the films. Part D below examines the role of substrate composition in a qualitative way.

Results for the layer-by-layer spin-polarization of Ni films of from one to five atomic layers, on Cu(100) and (111) substrates, are presented graphically in Figure 8, which also includes data from Tables I and II for the surface and interface magnetization; these correspond to the limit of infinite film thickness.

Each data point in Figure 8 gives the spin polarization of one layer in the respective film. In these results the magnetization decreases monotonically from surface to interface; the only exceptions are unimportant, and correspond to Friedel oscillations in layers in the interior of thicker films, which have nearly equal polarization. We therefore omit labelling of the individual points.

The first result to notice concerns the presence or absence of magnetically "dead" layers. For the (100) surface, we find no evidence of such dead layers; even the monolayer film has its moment reduced only about $0.1\mu_B$ relative to Ni bulk. This is in excellent agreement with the only fully self-consistent calculation reported for a sup-

ported Ni film; there, Wang et al¹⁰ found a reduction in the magnetization of a monolayer Ni film on Cu(100) of slightly over $0.2\mu_B$. The discrepancy of $0.1\mu_B$ is consistent with the level of accuracy expected from approximations such as (3), and is typical of the agreement among various a priori calculations⁷⁻⁹.

For the (111) films, the situation is radically different. While the magnetic behavior varies smoothly with film thickness down to two atomic layers, at a single layer the magnetization drops abruptly to less than $0.1\mu_B$. In view of the fact that our approximations consistently overestimate surface magnetization, this result is consistent with a magnetically "dead" Ni monolayer on Cu(111). Finite temperature would probably kill such weak ferromagnetism in any case.

The surprising sensitivity of the film magnetization to substrate orientation is attributable to the delicate balance here between competing effects. Calculations^{10,11} for an isolated Ni film find a magnetization substantially greater than in bulk Ni. On the other hand, coupling to the substrate tends to suppress the magnetization. For the Ni monolayer on Cu(100) there is a substantial cancellation between these competing effects. Any change in the film electronic structure can upset this fortuitous balance, and drastically change the magnetization.

For thicker films, the magnetization of the interior layers tend to cluster closely around the bulk value, with substantial changes in magnetization restricted to the surface and interface layers. Only for films of one or two layers, where there are no "interior" layers, does this simple picture break down.

It is interesting to note that the interface magnetization displayed in Figure 6 exhibits substantial oscillations with film thickness for the (100) films, but very little for the (111) films. This illustrates the sensitivity of Ni(100) films to thickness-imposed boundary conditions. In calculations where (100) slabs are used ^{7-9,16} to mimic the ideal surface, this sensitivity poses a problem. We have performed such slab calculations, and find that the Friedel-like spin oscillations are not noticeable for (111) slabs. Thus a five layer slab provides a good approximation for the (111) surface, while for the (100) surface even a seven layer slab noticeably exaggerates the spin oscillations.

Only for the thinnest films does the film behavior deviate qualitatively from that of the ideal surface and interface; we therefore discuss in detail the electronic structure only of the monolayer films.

Figure 9 shows the d-projected local DOS in the Ni monolayer films, decomposed by spin. The (100) monolayer has a very narrow d-band with a sharp upper band edge, and a large DOS at E_F . The (111) monolayer DOS is broad by

comparison ("fragmented" might be a better word), and exhibits a small peak above the main band, resulting in a rather small DOS at E_F . Moreover, the (111) monolayer appears to show a stronger hybridization tail in the d-projected DOS than the (100), which also may play an important role in determining the weakness or nonexistence of Ni (111) monolayer magnetism.

The dispersion of surface states and resonances in the monolayer films are shown in Figures 10 and 11. For the (100) monolayer film, a very flat band of surface states along $\bar{\Gamma}$ - $\bar{X}$ gives rise to the sharp upper band edge in the DOS. In contrast, the only film-localized states at E_F for the (111) monolayer belong to the steeply dispersing surface state around $\bar{M}$, so the local DOS at E_F is small.

The symmetry-related surface states at the points $\bar{M}$ in the (100) and (111) surface Brillouin zones, were discussed above in the context of the ideal surface and interface; in the monolayer film these states split off from the continuum in a dramatic way. Unfortunately at $\bar{M}$, where the states are most localized, they lie above E_F and are not observable in photoemission experiments.

D. Model Film Systems

In the preceding section we emphasized the role of the nonmagnetic substrate in suppressing Ni film magnetization. We have moreover asserted that sp-d hybridization is the most important mechanism determining film magnetization.

The degree of hybridization depends on the strength of the coupling between Ni d and substrate sp bands; we anticipate that this coupling is stronger for normal metals than for noble metals, and this explains the greater effectiveness of Al substrates, compared to Cu, in suppressing film magnetism.

In this section, we report results of numerical "experiments" which we have performed in order to study the dependence of film magnetization on substrate composition, and to illustrate the crucial role of film-substrate coupling. In the first "experiment", we artificially vary the strength of the coupling between the Ni film d-band and substrate conduction band; in the second, we examine the thickness-dependence of film magnetization in the case of relatively strong film-substrate coupling. The results nicely illustrate both the crucial role of sp-d hybridization, and the qualitative affects of varying substrate composition.

To vary the film-substrate coupling, we multiply each matrix element in the Hamiltonian which couples Ni d orbitals to substrate s and p orbitals, by a factor t. Thus t=1 corresponds to the realistic Ni-on-Cu case, whereas t>1 gives an artificially enhanced coupling. For the Ni monolayer on Cu(100), we performed self-consistent calculations of Ni magnetization for various values of t. The results are given in Figure 12. [For these calculations we sampled

15 wavevectors in the irreducible square Brillouin zone.]

The realistic Ni-Cu case, $t=1$, has already been discussed. As the film-substrate coupling t is increased, the magnetization drops rapidly until, for $t \geq 1.8$, the film magnetization has completely disappeared. Thus the absence of magnetically "dead" layers of Ni on Cu is consistent with the existence of such layers on other substrates.

As t is reduced below one, the magnetization increases to well above the Ni bulk value. This illustrates that, in the absence of coupling to a substrate, a monolayer Ni film should exhibit enhanced magnetization, in accord with calculations^{10,11} for a hypothetical isolated Ni film. The magnetization of a real, supported Ni film is determined by the competition between thinness-induced enhancement, and substrate-induced suppression of the magnetization.

We point out that the similarity of the spin polarization of a Ni monolayer on Cu(100), to the bulk spin polarization, must be viewed as fortuitous. Two large effects almost cancel; but as illustrated in Figure 12, a change in the effective coupling strength can upset the balance. This is why merely switching from a (100) to a (111) substrate orientation can so drastically change the net result.

Several elegant experiments^{4,5} have examined the onset of ferromagnetism with Ni film thickness on simple-metal substrates. In order to examine the qualitative differences between this case and the case of a noble-metal substrate,

we have calculated the magnetization of Ni(111) films of thickness from one to four layers, for the case of strong ($\underline{t}=3$) film-substrate coupling. Results are presented in Figure 13.

The most striking feature here is the sudden onset of magnetization with film thickness. The one and two-layer films are paramagnetic, yet the three-layer film is similar to the thicker film in its magnetization. This behavior is consistent with the abrupt onset of magnetization observed experimentally^{4,5}.

Note that for the thicker films, the suppression of magnetization is confined to the interface region. Such behavior is to be expected, in view of the short screening length in metals. We might therefore expect that the critical film thickness for the onset of magnetization is determined (in the case of large film-substrate coupling) by the screening length rather than by the coupling strength. To test this hypothesis, we repeated the calculation for the three-layer film, using a very large film-substrate coupling, $\underline{t}=9$. This large increase in coupling strength resulted in a small (20%) reduction in the magnetization of the middle Ni layer, relative to the $\underline{t}=3$ case. The surface layer changed only 3%, and the interface layer is effectively paramagnetic in both cases. This suggests that the observed^{4,5} appearance of ferromagnetism at three atomic layers of Ni or less, represents a universal, substrate-

independent phenomenon (once the nickel-substrate coupling reaches its strong-coupling limit).

In conclusion, these numerical experiments reveal several important points. First, the coupling of film and substrate via sp-d hybridization is the crucial physical effect suppressing film magnetization. Second, the film magnetization, for the case of monolayer films, is extremely sensitive to the strength of the film-substrate coupling, and hence is strongly dependent on substrate composition. Third, for thicker films, the substrate effect is limited to roughly two layers, independent of coupling strength (i.e., independent of substrate composition). Films of three atomic layers or more should therefore be magnetic, regardless of the substrate.

IV. CONCLUSION

By means of simple calculations for a variety of systems, we have developed a clear, consistent picture of the magnetic behavior of Ni films, surfaces and interfaces. The main qualitative features of the results can be understood in terms of two competing effects: suppression of Ni magnetization due to increased sp-d hybridization, when a Ni atom is adjacent to noble or normal-metal atoms; and enhancement of Ni magnetization due to d-band narrowing and sp-d dehybridization, at sites of low coordination number.

Our results are consistent with all the experiments we know of (except perhaps that of Liebermann et al¹, as discussed in section IA), and serve to identify the factors responsible for the dramatic differences among different experiments. In particular, we have shown that the dependence of film magnetization on substrate composition can explain the various experimental results.

Our analysis suggests two experiments which would be helpful in tying together previous results. First, the magnetization of Ni on Cu could be carried to monolayer and submonolayer coverage on well-characterized Cu(100) and especially Cu(111) surface. Second, a systematic investigation of the role of substrate composition in determining film magnetization is greatly needed. Our results suggest that trends in film magnetization with substrate composition will follow trends in Ni alloy magnetization with composition of the non-magnetic components of the alloy.

Finally, we should add a word about the relevance of these results to other magnetic materials. The major factor acting to suppress Ni magnetization at the Ni-Cu interface is sp-d hybridization, which changes the shape of the band edge and reduces the "effective" number of d holes. These effects are important because the Ni d-band is almost full, with the Fermi level close to the upper band edge. For metals such as Fe and Mn, with more holes in the d band, the precise shape of the band edge is unimportant; and sp-d

hybridization has a relatively small effect on the middle of the band. This explains why metallic substrates are not effective in suppressing the magnetization of even sub-monolayer Fe films $\sqrt{4,5}$.

ACKNOWLEDGEMENTS

This work was supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Sciences Division of the U.S. Department of Energy under Contract Number DE-AC03-76SF00098. The financial support of the Exxon Education Foundation is gratefully acknowledged.

REFERENCES

1. L. Liebermann, J. Clinton, D.M. Edwards and J. Mathon, Phys. Rev. Lett. 25, 323 (1970).
2. C. Rau, Comments Solid State Phys. 9, 177 (1980).
3. D.T. Pierce and H.C. Siegmann, Phys. Rev. B 9, 4035 (1974).
4. G. Bergmann, Phys. Rev. Lett 41, 264 (1978) and Physics Today 32:8, 25 (1979).
5. R. Meservey, P.M. Tedrow and V.R. Kalvey, Solid State Commun. 36, 969 (1980).
6. E.C. Stoner, Phil. Mag. 15, 1018 (1933).
7. C.S. Wang and A.J. Freeman, Phys. Rev. B 21, 4585 (1980).
8. O. Jepsen, J. Madsen and O.K. Andersen, J. Magn. Magn. Mater. 15-18, 867 (1980).
9. H. Krakauer and A.J. Freeman, Bull Amer. Phys. Soc. 26, 356 (1981).
10. D.S. Wang, A.J. Freeman and H. Krakauer; Phys. Rev. B 24, 1126 (1981).
11. J. Noffke and L. Fritsche, J. Phys. C 14, 89 (1981).
12. E.W. Plummer and W. Eberhardt, Phys. Rev. B 20, 1444 (1979).
13. C. Rau and S. Iechner, Phys. Rev. Lett. 47, 939 (1981).
14. G.P. Felcher, S.D. Bader, R.J. Celotta, D.T. Pierce and G.C. Wang, in Ordering in Two Dimensions, S.K. Sinha, ed. (elsevier North Holland, 1980) p. 107.
15. U. Gradmann, J. Appl. Phys. 40, 1182 (1969).
16. C.S. Wang and A.J. Freeman, Phys. Rev. B 24, 4364 (1981).

17. J. Tersoff and L.M. Falicov, Phys. Rev. B 25 (1982).
(Scheduled to appear April 15, 1982).
18. P.W. Anderson, Phys. Rev. 124, 41 (1961).
19. J.C. Slater and G.F. Koster, Phys. Rev. 94, 1498 (1954).
20. G.V. Samsonov, ed., Handbook of Physico-chemical Properties of the Elements (Plenum, New York, 1968).
21. C. Herring, Exchange Interaction Among Itinerant Electrons, Vol. IV of Magnetism, ed. G.T. Rado and H. Suhl (Academic Press, New York, 1966); and references therein.
22. H. Danna, R. Heer and A.J.P. Meyer, J. Appl. Phys. 39, 669 (1968). The measured bulk magnetization of $0.616\mu_B$ is believed to reflect a spin imbalance $n_{\uparrow} - n_{\downarrow} = 0.56$ electrons per atom, with a g-factor of 2.2 due to spin-orbit coupling; see ref. 21.
23. C.S. Wang and A.J. Freeman, Phys. Rev. B 19, 793 (1979).
24. L.M. Falicov and F. Yndurain, J. Phys. C 8, 147 and 8, 1563 (1975).
25. S.L. Cunningham, Phys. Rev. B 10, 4988 (1974).
26. J. Tersoff and L.M. Falicov, Phys. Rev. B 25, 2959 (1982).
27. E.M. Gyorgy, J.F. Dillon, Jr., D.B. McWhan, L.W. Rupp, Jr., L.R. Testardi and P.J. Flanders, Phys. Rev. Lett. 45, 57 (1980).

TABLE I

Spin polarization by layer at
Ni surface ($n_{\uparrow}-n_{\downarrow}$ per atom)

layer	(100)	(111)
S	0.74	0.65
S-1	0.55	0.62
S-2	0.56	0.56
bulk	0.56	0.56

TABLE II

Spin polarization of Ni layers at
Ni-Cu interface ($n_{\uparrow}-n_{\downarrow}$ per atom)

Ni layer	(100)		(111)	
	Cu1-Ni	Cu2-Ni	Cu1-Ni	Cu2-Ni
I	0.39	0.37	0.43	0.38
I-1	0.51	0.50	0.54	0.54
I-2	0.57	0.57	0.57	0.57
bulk	0.56	0.56	0.56	0.56

FIGURE CAPTIONS

Figure 1 d-orbital component of the density of states of bulk Ni metal. Broken line--majority spin; solid line--minority spin.

Figure 2 d-orbital component of the density of states, projected at a site at ideal Ni surfaces. Top--(100) surface; bottom--(111). Broken line--majority spin; solid line--minority spin.

Figure 3 Surface states and resonances at the surface of a seven layer Ni(100) slab. Top and bottom are majority and minority spin, respectively. Solid circles denote states which are over 80% localized in the surface layers; open circles denote states with weights at the surface layers between 40% and 80%. Inset--(100) surface Brillouin zone.

Figure 4 Surface states and resonances at the surface of a seven layer Ni(111) slab. Top and bottom are majority and minority spin, respectively. Solid circles denote states which are over 80% localized in the surface layers; open circles denote states with weights at the surface layers between 40% and 80%. Inset--(111) surface Brillouin zone.

Figure 5 d-orbital component of the density of states, projected at a site in the Ni interface layers of Ni-Cu interfaces. Top--(100) interface; bottom--(111). Broken line--majority spin; solid line--minority spin.

Figure 6 Interface states and resonances at the Ni interface layer of a six layer Ni(100) slab with one layer Cu on each face. Solid circles denote states which are over 80% localized in the Ni interface layers; open circles denote states with weights at the Ni interface layers between 40% and 80%.

Figure 7 Interface states and resonances at the Ni interface layer of a six layer Ni(111) slab with one layer Cu on each face. Solid circles denote states which are over 80% localized in the Ni interface layers; open circles denote states with weights at the Ni interface layers between 40% and 80%.

Figure 8 Layer by layer spin polarization of epitaxial Ni films of thicknesses from one to five atomic layers, on Cu(100) (top) and Cu(111) (bottom). Triangle--surface layer; square--interface layer; circle--interior layers of film. The three data points for the limit of infinite film thickness correspond to ideal surface, bulk and interface.

Figure 9 d-orbital component of the density of states, projected at a Ni site in a Ni monolayer film on Cu. Top--(100) monolayer; bottom--(111). Broken line--majority spin; solid line--minority spin.

Figure 10 Surface states and resonances at the monolayer Ni film, for a four layer Cu(100) slab with one layer of Ni on one side. Solid circles denote states which are over 80% localized in the Ni monolayers; open circles denote states with weight at the Ni monolayers between 40% and 80%.

Figure 11 Surface states and resonances at the monolayer Ni film, for a four layer Cu(111) slab with one layer of Ni on one side. Solid circles denote states which are over 80% localized in the Ni monolayers; open circles denote states with weight at the Ni monolayers between 40% and 80%.

Figure 12 Spin polarization of a Ni monolayer on Cu(100), as a function of the (artificially altered) coupling $\underline{t}$ between the Ni $\underline{d}$ band and the substrate conduction band.

Figure 13 Layer by layer spin polarization for Ni films of thickness from one to five atomic layers, on a (111) substrate. The film-substrate coupling is enhanced by a factor of $\underline{t}=3$ from the realistic Ni-Cu value.

Figure 1

Figure 2

(100) Ni Surface

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7

Figure 8

Figure 9

Figure 10

(111) Ni Monolayer

Figure 11

Figure 12

Figure 13

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720