

Lawrence Berkeley National Laboratory

Lawrence Berkeley National Laboratory

Title

A Review of Stress and Strain Effects on Bi-2212

Permalink

<https://escholarship.org/uc/item/2d54c1vq>

Author

Godeke, Arno

Publication Date

2008-04-18



A Review of Stress and Strain Effects on Bi-2212

Arno Godeke



Bi-2212 Workshop, Tallahassee, FL

November 6, 2006

Funded by the US Department of Energy under contract No. DE-AC02-05CH11231

LAWRENCE BERKELEY NATIONAL LABORATORY

Bi-2212?




Engineering $J_E(H)$!

• 20 T, 30 T, 50 T....?

But...

• Bi-2212 is stress/
strain limited !



• K.R. Marken, MRS spring meeting 2006

Stress and strain in superconductors



Magnet systems

- Thermal contraction differences
- Lorentz loads


Short sample tests

- Axial load
- Transverse pressure
- Hydrostatic pressure

Nb₃Sn in a nutshell: Axial strain




Axial strain dependence



Reversible:

- $\Delta\varepsilon \rightarrow \Delta N(E_F), \Delta\lambda_{ep}$
- ΔT_c and ΔH_{c2}
- ΔJ_c
- Slope depends on H and T



• Godeke, SuST, 2006

Nb₃Sn in a nutshell: Crack formation



'Preliminary' J_c collapse

- Irreversible
- Crack formation
- ➔ Two (*unrelated*) ITER IT wires





Figure 4: The deformation measurements for conductors B1 and B2 (open and filled markers). The points are measured and the solid lines are calculated with (8), with parameters as listed in Table 2 and Table 3. The dashed lines indicated the deviation from (8).

➔ Godeke, TAS, 1999



➔ Jewell, SuST, 2003

Nb₃Sn in a nutshell: Transverse pressure



On short tape samples

- Worrying ?





Fig. 4 The relative current density as a function of the transverse pressure at 4.2 K.

➔ Ten Haken, TAS, 1993

On cables

- OK !

➔ Sensitive to proper experiment



➔ Godeke, Report, 1993

Bi-2212 – Typical axial tensile behavior



Strain dependence

- Independent of H and T
- Always irreversible
 - ➔ Crack formation
- J_c collapse point depends on pre-strain





Figure 6.7: A comparison of the axial strain dependent critical current at two different conditions, n on the A-19 sample (Critical-current criterion: $E_c = 10^{-3}\text{ V/m}$).

➔ Ten Haken, PhD Thesis, 1994

Compressive: U-shaped bending springs



► Ten Haken, TAS, 1993

Generalized axial behavior



3 regions

- I and III
 - ➔ J_c collapses
 - ➔ Significant cracks
- II
 - ➔ Quasi constant
 - (Still irreversible)
 - Quasi-elastic behavior
 - Small cracks?
 - ➔ Length corresponds to pre-strain




Fig. 1. The normalized critical current as a function of the axial strain. Measured on different samples for compressive and tensile strains (measured at 4.2 K and 8 or 16 T).

➔ Ten Haken, ToM, 1996

Generalized axial behavior: A model



Model...





Fig. 2. The proposed description for the $I_c(\epsilon_a)$ dependence of Bi-2212.



...and measurement




Fig. 3. The normalised critical current as a function of the axial strain measured on three pairs of pre-strained samples (measured at 4.2 K and 16 T).

• Ten Haken, ToM, 1996

- All axial compressive strain irreversibly reduces J_c

Model and irreversibility



Repetitive 'low' strain variations

- All strain irreversible





Fig. 5. The I_c versus strain in two samples of conductor A. First a cyclic deformation between 0 and 0.28% axial strain and then between 0 and -0.28% strain. The solid and dotted line follows the measuring sequence. The solid lines indicate two sequential I_c measurements and a dotted line is used when one or more strain cycles are skipped.

- Ten Haken, TAS, 1997

Crack formation?



Strain and X-ray diffraction



➡ Ten Haken, ACE, 1997

Microscopic strain analysis with X-rays



Apply external axial strain

- Shift in 2Θ for 0020 peak
 - Strain in c direction
 - $\epsilon_y = \nu_y \epsilon_z$





Fig. 1. Bi-2212 sample on the brass sample holder for the X-ray diffraction experiment.




Fig. 2. The diffraction pattern with Cu-K α radiation on polycrystalline Bi-2212 at 300 K, on a non-deformed sample holder.

➤ Ten Haken, PhysC, 1996

Shift 0020 position versus tensile strain



Strain behavior

- c-axis compression with axial tensile strain
 - ➔ Elastic up to +0.2% axial
 - ➔ Cracks above +0.2% axial




Fig. 3. The position of the diffraction peak of the 0020 reflection as a function of the applied axial strain as measured with the strain gauge at 300 K.

➔ Ten Haken, PhysC, 1996

c-axis deformation and $J_c(\epsilon_{axial})$



At $J_c(\epsilon_{axial})$ plateau

- c-axis deformation proportional to ϵ_{axial}
- Elastic behavior

Outside $J_c(\epsilon_{axial})$ plateau

- c-axis is constant
- Elastic behavior disappears
- Cracks formation







Fig. 4. The deformation of the c-axis as a function of the applied strain at 300 K, compared with the normalised J_c measured at 77 K on a deformed Bi-2212 mono-core wire [4].

► Ten Haken, PhysC, 1996


Cracks: MOI on strained Bi-2212




Unstrained Bi-2212



Strained Bi-2223



Strained Bi-2212



D.C. van der Laan – Ph.D. thesis, U. Twente 2004 (see Schwartz talk)

Crack formation confirmed with MOI



Axial strain results: Crack formation from MOI and $J_c(\epsilon)$




Figure 3.25. Normalized critical current vs. strain of Bi-2212 tape B-3 at 4.2 K. Cracks appear at applied strain of 0.41 % (1st), 0.48 % (2nd) and 0.70 % (3rd). The arrow shows the direction in which the curve shifts when correcting for the difference in pre-compression.

D.C. van der Laan – Ph.D. thesis, University of Twente 2004

Transverse pressure on Bi-2212 tapes



From the 'House of Horrors'...

→ Very discouraging!





Figure 6.16: The normalised critical-current reduction of the Bi-2212 tape conductor (T-19) subjected to a transversal pressure, measured on the $F_1 // B$ transverse press. The measured $I_c(\sigma_t)$ is compared with two lines representing the calculated I_c versus pressure dependence for two different Young's moduli ($E_{eff} = 20$ and 3.5 GPa).

→ Ten Haken, TAS, 1993; PhD thesis, 1994

Transverse pressure on Bi-2212 cables



Better than tapes...

- ...but insufficient?
- Limited to 60 MPa broad face load?




Fig. 3. Variation of the critical current (4 T, 4 K) with stress for a cable loaded on the broad face of the cable.




Fig. 4. Variation of the critical current (self-field, 4 K) with stress for a cable loaded on the edge of the cable.

➔ Dietderich, TAS, 2001

Summary



- All strain causes an irreversible reduction of J_c
 - ➔ Avoid it! (e.g. match thermal contractions)
- Irreversibility is a result of crack formation
 - ➔ Confirmed with X-ray diffraction
 - ➔ Confirmed with MOI
- No contradictive results found to 1996 model
 - Plateau length grows with pre-strain
 - Apparent larger 'strain margin'
 - ➔ At the cost of irrecoverable J_c reduction
- Transverse pressure effects cables better than on tapes
 - ➔ Similar as for Nb_3Sn
 - But limits appear far from Nb_3Sn 's 200 MPa
 - ➔ Conductor reinforcement / stress relieve required