

Lawrence Berkeley National Laboratory

Recent Work

Title

The Separation of Zirconium and Hafnium by Extraction with Thenoyltrifluoroacetone

Permalink

<https://escholarship.org/uc/item/2kv4t9td>

Authors

Huffmam, E.H.
Beaufait, L.J.

Publication Date

1948-10-07

UNIVERSITY OF
CALIFORNIA

*Radiation
Laboratory*

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

BERKELEY, CALIFORNIA

UCRL-194
C.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

[illegible]

Chemistry-General

~~RESTRICTED~~

CLASSIFICATION CANCELLED BY AUTHORITY
OF THE DISTRICT ENGINEER
UNIVERSITY OF CALIFORNIA BY THE DECLASSIFICATION COMMITTEE

Radiation Laboratory

THE SEPARATION OF ZIRCONIUM AND HAFNIUM
BY EXTRACTION WITH THENOYLTRIFLUOROACETONE

E. H. Huffman and L. J. Beaufait

Special Review of Declassified Reports

Authorized by USDOE JK Bratton

Unclassified TWX P182206Z May 79

REPORT PROPERLY DECLASSIFIED

J N Green
Authorized Derivative Classifier

8/16/79
Date

R O K Hunt
By

8/17/79
Date

Berkeley, California

Chemistry-General

-2-

CLASSIFICATION CANCELLED BY AUTHORITY
OF THE DISTRICT ENGINEER
BY THE DECLASSIFICATION COMMITTEE

Standard DistributionCopy Nos.

Argonne National Laboratory	1-8
Armed Forces Special Weapons Project	9
Atomic Energy Commission, Washington	10-11
Battelle Memorial Institute	12
Brookhaven National Laboratory	13-22
Carbide & Carbon Chemicals Corp. (K-25 Area)	23-26
Carbide & Carbon Chemicals Corp. (Y-12 Area)	27-30
Columbia University (Failla)	31
General Electric Company	32-35
Hanford Directed Operations	36-42
Iowa State College	43
Kellogg Corporation	44-45
Los Alamos	46-48
Massachusetts Institute of Technology	49
Monsanto Chemical Company, Dayton	50-51
National Bureau of Standards	52-53
Naval Radiological Defense Laboratory	54
NEPA	55
New York Directed Operations	56-57
Oak Ridge National Laboratory	58-69
Patent Advisor, Washington	70
Technical Information Division, ORDO	71-85
UCLA Medical Research Laboratory, (Warren)	86
University of California Radiation Laboratory	87-91
University of Rochester	92-93
Western Reserve University (Friedell)	94
Chicago Directed Operations	95
Declassification Procedure	
Declassification Officer	96-99
Publication Officer	100
Patent Department	101-102
E. O. Lawrence	103
Area Manager	104
Information Division	105

Total

105

Information Division
Radiation Laboratory
University of California
Berkeley, California

The Separation of Zirconium and Hafnium
by Extraction with Thenoyltrifluoroacetone

DECLASSIFICATION CANCELLED BY AUTHORITY
OF THE DISTRICT ENGINEER
BY THE DECLASSIFICATION COMMITTEE

E. H. Huffman and L. J. Beaufait
Radiation Laboratory, University of California
Berkeley, California
October 7, 1948

ABSTRACT

Distribution ratios for zirconium and hafnium have been found for extraction from 2 M perchloric acid with thenoyltrifluoroacetone of varying concentration and the equilibrium constants for the extractions determined.

Two extractions with 0.025 M thenoyltrifluoroacetone of a solution containing 59% as much zirconium as hafnium yielded 27% of the original hafnium with a content of less than 2% zirconium.

CLASSIFICATION CANCELLED BY AUTHORITY
OF THE DISTRICT ENGINEER
BY THE DECLASSIFICATION COMMITTEE

The Separation of Zirconium and Hafnium
by Extraction with Thenoyltrifluoroacetone

E. H. Huffman and L. J. Beaufait
Radiation Laboratory, University of California
Berkeley, California

¹ This paper is based on work done under the auspices of the Atomic Energy Commission.

The synthesis of thenoyltrifluoroacetone has recently been reported by Reid and Calvin² and a study of the extraction of its

² J. C. Reid and M. Calvin, MDDC-1405 (BC-75), August 13, 1947.

zirconium chelate into benzene reported by Connick and McVey³. The

³ R. E. Connick and W. H. McVey, The Aqueous Chemistry of Zirconium, UCRL-101, March 1, 1948.


work reported in this paper on the separation of zirconium and hafnium by means of this β -diketone was undertaken at the suggestion of M. Calvin and G. T. Seaborg. A study has been made of some differences in the extractions of zirconium and hafnium by benzene solutions of thenoyltrifluoroacetone (referred to as HT in equations and tables) from aqueous 2 M perchloric acid and the results applied to a successful separation of these elements.

It is believed that the zirconium is principally in the form of Zr^{+4} in 2 M perchloric acid.⁴ The complexing of zirconium by the

⁴ W. H. Reas, Thesis, University of California, 1948.

diketone is negligible in the aqueous phase and the only important

species in the benzene phase is ZrT_4 .³ The reaction then is expressed by the equation



and, assuming constant acid concentration, the equilibrium constant
 CLASSIFICATION CANCELLED BY AUTHORITY
 OF THE DECLASSIFICATION COMMITTEE
 by

$$\log K = \log \frac{[ZrT_4]}{[Zr^{+4}]} - 4 \log [HT] = \log R - 4 \log [HT]$$

where R is the extraction coefficient.

Values for R and K have previously been determined³ for zirconium using trace amounts of radioactive Zr^{95} .

The determination of values for R and K for both zirconium and hafnium, using macro quantities and concentrations for which the zirconium ion has been shown to be a monomer in 2.0 M perchloric acid⁴, has been carried out in this work in the thenoyltrifluoroacetone concentration range of 4×10^{-3} to 3×10^{-2} for zirconium and 10^{-2} to 7×10^{-2} for hafnium.

Experimental

Materials. - Thenoyltrifluoroacetone of 99.5% purity was obtained from M. W. Davis and H. R. Lehman of this laboratory. Weighed amounts were dissolved in reagent thiophene-free benzene to give solutions of the desired concentrations.

Zirconium solutions were prepared in a manner similar to that of Connick and McVey³. Recrystallized $ZrOCl_2 \cdot 8H_2O$ was dissolved in 2.0 M perchloric acid to prepare a stock solution of approximately 0.09 M zirconium.

Tracer zirconium solutions were prepared from carrier-free Zr^{95} in 5% oxalic acid which was received from the Isotopes Branch, United States Atomic Energy Commission. This solution was made about 10 M in nitric acid and carrier zirconium added from the above stock solution. The solution was purified by the following treatment³. A small amount of 0.1 N potassium permanganate was added to precipitate manganese dioxide which carries the radioactive columbium but not zirconium. This precipitation was carried out three times to remove both oxalic acid and columbium. The zirconium solution was then diluted to about 1 M nitric acid and extracted with 0.02 M thenoyltrifluoroacetone in benzene, and the benzene phase washed twice with 2 M perchloric acid. The benzene solution was removed to a platinum dish and fumed with sulfuric acid with the addition of small amounts of 30% hydrogen peroxide to destroy organic matter. It was then diluted and zirconium hydroxide precipitated with ammonium hydroxide. The precipitate was dissolved in hydrochloric acid and the zirconium hydroxide precipitated twice more to remove sulfate. Concentrated hydrochloric acid was then used to dissolve the hydroxide and this solution diluted to 6-7 M hydrochloric acid to precipitate $\text{ZrOCl}_2 \cdot 8\text{H}_2\text{O}$. A weighed amount of this salt was then dissolved in 2 M perchloric acid to give a stock solution approximately 0.003 M in zirconium.

Hafnium solutions were prepared from hafnium dioxide which contained 0.4% zirconium. A weighed amount was warmed with concentrated nitric acid and a small amount of 48% hydrofluoric acid in a platinum dish until a clear solution was obtained which was then

evaporated to near dryness. About 0.5 ml of concentrated sulfuric acid was added and fumed for 5-10 minutes. The preparation of $\text{HfOCl}_2 \cdot 8\text{H}_2\text{O}$ then followed the method given above for tracer $\text{ZrOCl}_2 \cdot 8\text{H}_2\text{O}$, beginning with dilution of the sulfuric acid solution. Tracer Hf^{181} solutions were prepared in the same way, using hafnium dioxide obtained from the Isotopes Branch, United States Atomic Energy Commission.

Analysis. - Colorimetric analyses were made with a Beckman spectrophotometer by G. Iddings who adapted the following method from that of Liebhafsky and Winslow⁵ to correct for the effects of

⁵ H. Liebhafsky and E. Winslow, J. Am. Chem. Soc. 60, 1776 (1938).

the organic substances and perchloric acid present. One-half ml. of saturated alizarin is added to a 25 ml. volumetric flask and then, in order, 10 ml. 95% ethanol, 4 ml. 2 M perchloric acid including that to be added from the sample, 1.0 ml. 0.02 M thenoyltrifluoroacetone in benzene including that to be added from the sample, benzene or aqueous phase sample containing 25-90 μg . Zr or 25-125 μg . Hf, and 1 ml. 2 M hydrochloric acid. After mixing add ammonium hydroxide carefully until the red color just appears and allow to stand for 5 minutes. Add 1 N hydrochloric acid until the red color disappears and then 0.10 ml. 7 M hydrochloric acid. Make to 25 ml. volume with 95% ethanol and allow to stand for 4 hours before taking the spectrophotometer reading. Standard curves prepared by this procedure show that the zirconium and hafnium are colorimetrically equivalent, on a mole basis, in contrast to previous results⁵.

Radioactive analyses of zirconium were made using micropipets to obtain samples containing 500-1500 counts per minute. The samples were evaporated on platinum discs under an infra-red lamp and counted in a Geiger counter, first with an aluminum absorber of 30 mg/cm^2 . and then with one of 150 mg/cm^2 . The difference in the two counts gives that of the zirconium alone without the count of the active columbium which had grown in. The ratio of count to weight was obtained by evaporating a larger sample of the stock solution, igniting to zirconium dioxide and weighing. Hafnium radioactive analyses were made in a similar manner but counted without absorbers.

Experimental. - For the determination of extraction coefficients micro-pipets were used to obtain approximate weights of zirconium or hafnium from the stock solutions and the volume made to 5 ml. with 2 M perchloric acid. Five ml. of a benzene solution of thenoyltri-fluoroacetone was then added and the mixture shaken for 80 minutes, although equilibrium was found to be reached within 40 minutes for these amounts. Aliquots of the benzene and aqueous phases were then taken for analysis.

Results

Table I gives the results found for zirconium on the distribution ratios and equilibrium constant. Columns one, two and three give, respectively, the molar concentrations of diketone added, the micrograms per ml. of zirconium in the benzene phase and the micrograms per ml. in the aqueous phase at equilibrium. The free diketone concentration, not allowing for solubility in the aqueous phase, is obtained by multiplying the molar concentration of zirconium found

in the benzene phase by four and subtracting the product from the molar concentration of diketone added. This answer is then multiplied by 0.974 to correct for solubility in 2 M perchloric acid⁴ and to obtain the diketone concentration in the benzene phase. In column four are given the activity coefficients for these corrected diketone concentrations⁶. These also represent the activity

⁶ E. L. King and W. H. Reas, U. C. R. L. BC-69, July 1947.

coefficients of the chelate³. Column five gives the diketone activities found by multiplying the corrected concentrations by the corresponding activity coefficients. The distribution ratios in column six are obtained by multiplying the ratios of values from columns two and three by the activity coefficients of column four. Table II gives similar results for hafnium.

The dependence of the extraction coefficients on the diketone activities for zirconium and hafnium are given in the figure. The straight lines are drawn with a slope of four and corresponding to the average values found for the equilibrium constants.

A good separation of hafnium was carried out on a solution in 2 M perchloric acid containing 22.9 mg. hafnium and 13.6 mg. zirconium in 150 ml. Two extractions were made with 150 ml. portions of 0.025 M thenoyltrifluoroacetone and 6.31 mg. hafnium recovered in the aqueous phase. The zirconium present in the aqueous phase was then too small to be determined by a combination of colorimetric and tracer Hf^{181} analysis. Spectrographic analysis, made by J. Conway and M. Moore of this laboratory, showed the presence of

less than 2% zirconium based on the hafnium present. Calculations from the curves show that about 1% zirconium should be present.

Summary

Distribution ratios for zirconium and hafnium have been found for extraction from 2 M perchloric acid with thenoyltrifluoroacetone of varying concentration and the equilibrium constants for the extractions determined.

Two extractions with 0.025 M thenoyltrifluoroacetone of a solution containing 59% as much zirconium as hafnium yielded 27% of the original hafnium with a content of less than 2% zirconium.

Table I
Zirconium

(HT) _B added	($\mu\text{g Zr/mt}$) _B	($\mu\text{g Zr/ml}$) _W	Act. Coef. of HT and of ZrT ₄	Activity of HT in benzene [HT]	Dist. Ratio R	log [HT]	log R	K
0.005	6.50	181	0.999	0.00460	0.0359	-2.3372	-1.4449	8.02 x 10 ⁷
.01	37.0	80.0	.997	.00814	.0461	-2.0894	-0.3363	10.50
.01	43 *	136 *	.997	.00783	.0316	-2.1035	-0.5003	8.20
.015	81.0	56.7	.995	.01109	1.42	-1.9551	0.1523	9.39
.015	86.8	75.3	.995	.01085	1.14	-1.9646	0.0569	8.23
.02	101	19.3	.990	.01502	5.18	-1.8233	0.7143	10.17
.02	115	39.5	.992	.01445	2.89	-1.8401	0.4612	6.63
.02	35.7	5.00	.988	.01772	7.05	-1.7515	0.8482	7.15
.02	104	41.0	.991	.01490	2.53	-1.8268	0.4031	5.13
.02	178	123	.994	.01180	1.44	-1.9281	0.1584	7.43
.02	224	235	.996	.00988	0.949	-2.0052	-0.0227	9.96
.02	135 *	108 *	.993	.01361	3.04	-1.8661	0.4829	8.86
.03	126	5.33	.982	.0235	23.2	-1.6289	1.3655	7.61
.035	173	3.42	.979	.0261	49.6	-1.5834	1.6955	10.67
.04	120	0.940	.973	.0329	125	-1.4828	2.0969	10.69

* Analysis by count of radioactive Zr⁹⁵

Table II
Hafnium

(HT) _B added	($\mu\text{g Hf/ml}$) _B	($\mu\text{g Hf/ml}$) _W	Act. Coef. of HT and of HfT ₄	Activity of HT in benzene [HT]	Dist. Ratio R	log [HT]	log R	K
0.01	15.0	296	0.996	0.00937	0.505	-2.0283	-1.2967	6.55 x 10 ⁶
.015	41.0	234	.993	.0136	0.174	-1.8665	-0.7570	5.12
.02	73.8	212	.988	.0177	0.344	-1.7520	-0.4634	3.50
.02	83.0	202	.988	.0174	0.406	-1.7595	-0.3915	4.43
.02	89.0	282	.988	.0173	0.312	-1.7620	-0.5058	3.48
.02	70 *	270 *	.988	.0177	0.258	-1.7520	-0.5884	2.63
.025	132	148	.989	.0212	0.882	-1.6737	-0.0545	4.37
.03	184	90.5	.981	.0247	1.99	-1.6073	0.2989	5.35
.03	221	128	.982	.0240	1.70	-1.6198	0.2304	5.12
.03	205 *	135 *	.980	.0252	1.49	-1.5986	0.1732	3.69
.04	238	31.8	.973	.0329	7.29	-1.4828	0.8627	6.22
.04	272	66.7	.974	.0321	3.97	-1.4935	0.5988	3.74
.04	261 *	79 *	.974	.0324	3.22	-1.4895	0.5079	2.92
.05	233	19.0	.964	.0420	11.9	-1.3768	1.0755	3.83
.05	266	19.0	.965	.0414	13.5	-1.3830	1.1303	4.60
.05	260	19.0	.965	.0416	13.2	-1.3809	1.1206	4.41
.06	320	20.0	.958	.0492	15.3	-1.3080	1.1847	2.61
.06	272	9.67	.957	.0502	26.9	-1.2993	1.4298	4.24
.06	292	13.3	.957	.0499	21.1	-1.3019	1.3243	3.40
.06	324	15.0	.958	.0491	20.7	-1.3089	1.3160	3.56
.06	321 *	19.0 *	.958	.0492	16.1	-1.3080	1.2068	2.75
.08	263	2.16	.943	.0382	115	-1.1662	2.0607	5.32

* Analysis by count of radioactive Hf¹⁸¹.




FIG. 1

[REDACTED]
[REDACTED]

CLASSIFICATION CANCELLED BY AUTHORITY
OF THE DISTRICT ENGINEER
BY THE DECLASSIFICATION COMMITTEE

[REDACTED]
[REDACTED]

CLASSIFICATION CANCELLED BY AUTHORITY
OF THE DISTRICT ENGINEER
BY THE DECLASSIFICATION COMMITTEE

RESTRICTED