Lawrence Berkeley National Laboratory

Recent Work

Title

PROPOSED SEARCH FOR SUPERCONDUCTIVITY IN THE SEMICONDUCTOR SiTe

Permalink

<https://escholarship.org/uc/item/30g9h507>

Author

Dalven, Richard.

Publication Date

1974-12-01

Submitted to Physical Review B 10
(August 1, 1974)

LBL-2525
Preprint c. *2*

PROPOSED SEARCH FOR SUPERCONDUCTIVITY IN THE
SEMICONDUCTOR SiTe

Richard Dalven

December, 1974

RECEIVED
LAWRENCE
RADIATION LABORATORY

FEB 20 1975

LIBRARY AND
DOCUMENTS SECTION

Prepared for the U. S. Atomic Energy Commission
under Contract W-7405-ENG-48

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

LBL-2525
c. *2*

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

ZBX-2525

ERRATA

**Erratum: Proposed search for superconductivity in the semiconductor SiTe
[Phys. Rev. B 10, 870 (1974)]**

Richard Dalven

The following reference was called to the author's attention too late to include in the published paper. L. G. Bailey [J. Phys. Chem. Solids 27, 1593 (1966)] has reported that the compound SiTe does not exist in the silicon-tellurium system. There is thus a discrepancy between the results of Bailey and those of Smirous *et al.* Until this question is definitely resolved, the results on possible superconductivity in SiTe, which were based on Smirous's published work, remain unchanged.

Proposed search for superconductivity in the semiconductor SiTe

Richard Dalven

Department of Physics, University of California, Berkeley, California 94720

(Received 5 December 1973)

It is shown, based on experimental data in the literature, that silicon telluride is a semiconductor with an energy gap of approximately 0.47 eV at 0°K. It is suggested that SiTe is likely to be a superconductor with a transition temperature higher than that of GeTe with the same carrier concentration.

The only known superconducting semiconductors¹ are SnTe, GeTe, and SrTiO₃. Since two of these are IV-VI semiconductors, it is interesting to investigate other group-IV tellurides as possible superconductors. The object of this article is to point out the existence of the semiconductor silicon telluride, to determine its energy gap from experimental data in the literature, and to suggest that SiTe will very possibly be a superconductor for values of the carrier concentration typical of those of the other group-IV tellurides.

The only paper published in the last twenty years on the electronic properties of SiTe is that of Smirous *et al.*² These workers synthesized SiTe and determined that its crystal structure is *not* of the NaCl type. They also measured the electrical conductivity σ of polycrystalline samples of SiTe as a function of temperature. In the temperature range from 210 to 430 °K, $d\sigma/dT$ was observed to be positive, and it was concluded that silicon telluride is a semiconductor. Measurement of the thermoelectric power indicated hole conductivity.

Given these experimental results, the following investigation may be made of the quantities appearing in the BCS equation³ based on the BCS (single-square-well) model⁴:

$$T_c \propto T_D e^{-1/N(0)V}. \quad (1)$$

In Eq. (1), T_c is the superconducting transition temperature, T_D is the Debye temperature, $N(0)$ is the electronic density of states at the Fermi energy, and V is the attractive electron-electron interaction. The aim of this paper is the qualitative comparison of probable values of $N(0)$ and T_D for SiTe with values for SnTe and GeTe, both of which are known to be superconducting semiconductors.

To discuss the value of $N(0)$ for SiTe, we note that a parabolic-band model yields the relation

$$N(0) \propto m^* n^{1/3}, \quad (2)$$

where m^* is the effective mass and n is the carrier concentration. We may estimate the relative magnitude of m^* for SiTe as follows. The experimental plot of $\ln\sigma$ as a function of $1/T$ given by Smirous *et al.* has the shape characteristic of an

intrinsic semiconductor, and these workers report it intrinsic above room temperature. Making the usual assumptions⁵ concerning such data, the slope $d(\ln\sigma)/d(1/T)$ of the intrinsic line ($300 < T < 430$ °K) yields a value of the energy gap of SiTe at 0°K of approximately 0.47 eV. Using the f -sum rule⁶ and considering a band model including only the lowest conduction band and the highest valence band, it can be shown⁷ that

$$m^*/(m \pm m^*) = (m/2 |M|^2) E_G, \quad (3)$$

where E_G is the minimum energy gap, m is the free-electron mass, M is the f -sum matrix element, and the plus and minus signs are appropriate for holes and electrons, respectively. If we assume⁸ that the matrix element M is the same for all members of the sequence SnTe, GeTe, and SiTe, then the fact that E_G for SiTe is larger than E_G for GeTe⁹ or SnTe⁹ implies that m^* is larger for SiTe than for either GeTe or SnTe. Equation (2) then states that for a given carrier concentration n , the density of states $N(0)$ will be larger¹⁰ for SiTe than for the other two group-IV tellurides. In addition, the Debye temperature T_D would be expected to be larger for SiTe than for SnTe and GeTe because of the decrease in atomic mass upon going from tin to germanium to silicon.

Since $N(0)$ and T_D may be expected to be larger for SiTe than for SnTe and GeTe, it is concluded, based on Eq. (1), that T_c for silicon telluride should, for a given value of n , be larger than T_c for SnTe and GeTe *if* the electron-electron interaction V remains approximately constant within the sequence of group-IV tellurides. (From a more empirical point of view, it may be argued that since T_c is larger¹¹ for GeTe than for SnTe for all values of carrier concentration, it is likely that T_c for SiTe would be larger than for GeTe, all other things being equal.)

Even though the discussion given above is qualitative and several simplifying assumptions are made, it seems that the conclusion that silicon telluride is likely to be a superconducting semiconductor is a reasonable one. For this reason, and because of the very small number of super-

conducting semiconductors presently known, it is proposed that the preparation of samples of silicon telluride (*p* type due to an excess of tellurium) be investigated experimentally with the aim of obtaining hole densities in the 10^{21} cm^{-3} range. A search for superconductivity in such samples would be interesting, and, based on the discussion above, quite probably fruitful. If superconductivity is indeed observed in SiTe, a comparison of the results with those for SnTe and GeTe would be

most interesting to interpret in terms of current theoretical models.¹²

The author would like to thank the Department of Physics of the University of California at Berkeley for its kind hospitality while this work was being done, and to thank J. Clarke and M. L. Cohen for useful comments on the manuscript. The generous assistance of the Inorganic Materials Research Division of the Lawrence Berkeley Laboratory is also acknowledged.

¹M. L. Cohen, Phys. Rev. **134**, A511 (1964).

²K. Šmirous, L. Štrouač, and J. Bednař, Czech. J. Phys. **7**, 120 (1957).

³See, for example, C. Kittel, *Quantum Theory of Solids* (Wiley, New York, 1963), p. 163.

⁴M. L. Cohen, in *Superconductivity*, edited by R. D. Parks (Dekker, New York, 1969). See also Sec. IVB, p. 661 for a discussion of the applicability of the BCS model to degenerate semiconductors.

⁵See R. A. Smith, *Semiconductors* (Cambridge U. P., Cambridge, 1961), p. 320ff for a discussion of the determination of energy gaps of semiconductors from conductivity data.

⁶See, for example, Ref. 3, p. 186.

⁷R. Dalven, J. Phys. C **6**, 671 (1973), and references therein.

⁸It appears that this assumption may be rather risky since the crystal structure of SiTe is known to be different from those of SnTe and GeTe, so the band structure of SiTe may also be significantly different.

⁹See F. Herman *et al.*, J. Phys. (Paris) **29**, C4-62 (1968) for values and for references to the original work.

¹⁰In this connection, it should be noted [M. L. Cohen (private communication)] that SiTe may not have a many-valley band structure because its crystal structure is not cubic, thereby decreasing $N(0)$.

¹¹See Ref. 4, Fig. 15.

¹²See, for example, Ref. 4, for a review.

—LEGAL NOTICE—

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

TECHNICAL INFORMATION DIVISION
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720