UC Irvine

UC Irvine Previously Published Works

Title

Pressure dependence of the exchange interaction in La₂CuO₄

Permalink

<https://escholarship.org/uc/item/3267018x>

Journal

Physica B: Physics of Condensed Matter, 169(1-4)

ISSN

0921-4526

Authors

Aronson, MC
Dierker, SB
Dennis, BS
[et al.](#)

Publication Date

1991-02-02

DOI

10.1016/0921-4526(91)90356-J

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at <https://creativecommons.org/licenses/by/4.0/>

Peer reviewed

PRESSURE DEPENDENCE OF THE EXCHANGE INTERACTION IN La_2CuO_4

M. C. ARONSON^{*†}, S. B. DIERKER^{††}, B. S. DENNIS[†], S.-W. CHEONG[†], and Z. FISK^{*}

^{*} Los Alamos National Laboratory, Los Alamos, NM 87544

[†] A. T. & T. Bell Laboratories, Murray Hill, NJ 07974

We report the results of Raman scattering measurements which determine the pressure dependence of the in-plane exchange coupling constant J in magnetic La_2CuO_4 for pressures between 1 bar and 100 kbar. We find that pressure increases the Neel temperature T_N much more rapidly than J . This result together with the theory for a quasi two-dimensional magnetic system then suggests that the interplanar exchange coupling decreases with pressure.

1. INTRODUCTION

Raman scattering studies of the magnetic excitations of both the oxide superconductors and their insulating parent compounds have played a central role in elucidating the importance of spin fluctuations in high temperature superconductors(1). At the same time, both the superconductivity(2) and the magnetism(3) are remarkably sensitive to pressure, although the fundamental mechanism for this remains unclear. Although Raman scattering has been used to study the pressure dependence of the phonons in several of these materials(4), it has not previously been used to study the effects of pressure on the spin fluctuations. We present here the first report of the pressure dependence of the two-magnon excitation spectrum of magnetic La_2CuO_4 , directly probed by Raman scattering.

2. EXPERIMENTAL TECHNIQUES

The light scattering experiments were performed on a mechanically polished single crystal of La_2CuO_4 , grown from CuO flux. The as-grown crystal was annealed in nitrogen at 650 C for ten hours, a procedure which reduces the oxygen doping level, yielding an antiferromagnet with a measured Neel temperature of 305 K. The sample was mounted in the (110) orientation in a specially designed high pressure diamond anvil cell, using a stainless steel gasket and krypton as a pressure transmitting medium(5). The pressure was determined by the frequency shift of the luminescence of a small ruby chip placed near the sample. The Raman scattered light was analyzed with a CCD camera and a SPEX triple spectrometer(6). Laser power was kept below 7 mW to minimize sample heating.

3. EXPERIMENTAL RESULTS

The room temperature Raman spectra of B_{1g} symmetry for our oriented single crystal sample of La_2CuO_4 at pressures ranging from 1 bar to 100 kbar and laser wavelength of 4579 Å are graphed in Fig. 1. The data have been corrected for the wavelength dependent response of the collec-

Figure 1: Pressure dependent Raman spectra of B_{1g} symmetry for a La_2CuO_4 single crystal at room temperature excited by laser light of 4579 Å. The spectra are offset vertically for clarity and the separate baselines indicated.

tion optics, spectrometer, and detector. A linear fluorescence background has been subtracted. We focus our attention on the broad peak centered near $\sim 3200 \text{ cm}^{-1}$ which has previously been identified as two-magnon scattering in a Neel ground state(1). From these data, we have determined the pressure dependence of the two-magnon peak frequency ω_p . The peak frequency ω_p is related(7) to the Cu superexchange interaction J in a two-dimensional quantum antiferromagnet by the proportionality $\omega_p = 3.18 J$. The pressure dependence of J extracted from this relationship is plotted in Fig. 2, demonstrating that pressure increases J monotonically in La_2CuO_4 . The break in J near 60 kbar may reflect the pres-

[†] Current Address: Department of Physics, University of Michigan, Ann Arbor, MI 48109.

sure at which the tetragonal to orthorhombic phase transition passes through room temperature(8).

4. DISCUSSION

As a result of a residual interlayer exchange interaction $J_\perp$, an ensemble of two dimensional magnetic sheets having an in-plane correlation length ξ and staggered magnetization M^2 may order in three dimensions if the condition $T_N \approx J_\perp M^2 \xi^2$ is met (9). Reference (9) suggests that for a choice of parameters consistent with neutron scattering experiments at 1 bar, both ξ and M increase with the in-plane exchange coupling J . Assuming that the renormalization constants describing the effects of the two-dimensional fluctuations are independent of pressure, the pressure dependence of T_N is given by $T_N \propto J_\perp(P) J^3(P) \exp(1.4 J(P)/k_B T)$.

With this expression in mind, it is instructive to compare the pressure dependence of T_N from neutron scattering experiments³, plotted in Fig. 2, with that of $J(P)$, deter-

Figure 2: Pressure dependences of the Neel temperature T_N (O, Reference 3), multiplied by 3.0 for comparison to the exchange interaction J (X). Solid lines are guides for the eye.

mined by the present Raman scattering experiment. Note that T_N has been multiplied by a factor of 3.0 in order to make it equal to $J(P)$ at 1 bar. It is clear that while T_N is more sensitive to pressure than $J(P)$, the theoretical expression predicts a much stronger dependence of $T_N(P)$ on $J(P)$ than is observed. This discrepancy suggests that pressure rapidly decreases $J_\perp$. Alternatively, the renormalization factors describing the effects of the two-dimensional fluctuations may be pressure dependent. More detailed investigation of the two-magnon lineshapes, which may shed light on this point, are underway.

5. CONCLUSIONS

We have presented here the first direct measurement of the pressure dependence of the in-plane exchange interaction $J(P)$ in magnetic La_2CuO_4 . We find that pressure increases $J(P)$, but apparently either magnetically decouples the CuO_2 planes or fundamentally affects the two-dimensional fluctuations.

ACKNOWLEDGMENTS

We are indebted to Dr. David Schiferl for numerous useful discussions. Work at Los Alamos performed under the auspices of the U. S. Department of Energy. M. C. A. is grateful to the Los Alamos National Laboratory E.R.D.C. for travel assistance.

REFERENCES

- (1) For a review, see K. B. Lyons and P. A. Fleury J. Appl. Phys. 64 (1988) 6075.
- (2) R. Griessen Phys. Rev. B 36 (1987) 5284.
- (3) S. Katano et al. JAERI memo 01-391 (to be published).
- (4) K. Syassen et al., Physica 153-155C (1988) 264; V. D. Kulakovskii et al, JETP Lett. 47 (1988) 536; L. V. Gasparov et al. Solid State Commun 72 (1989) 465.
- (5) S. B. Dierker et al. (to be published).
- (6) C. A. Murray and S. B. Dierker, Journal of the Optical Society of America A3 (1986) 2151.
- (7) R. R. P. Singh et al. Phys. Rev. Letts. 62 (1989) 2736.
- (8) H. J. Kim and R. Moret Physica C 156 (1988) 363.
- (9) S. Chakravarty et al. Phys. Rev. Letts. 60 (1988) 1057.