UC Irvine

UC Irvine Previously Published Works

Title

Magnetic ordering in the high T_c superconductor Eu_{0.1}Gd_{0.9}Ba₂Cu₃O_x

Permalink

<https://escholarship.org/uc/item/33q1j6c9>

Journal

Hyperfine Interactions, 42(1-4)

ISSN

0304-3843

Authors

Taylor, RD

Willis, JO

Fisk, Z

Publication Date

1988-02-01

DOI

10.1007/BF02395626

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at

<https://creativecommons.org/licenses/by/4.0/>

Peer reviewed

MAGNETIC ORDERING IN THE HIGH T_c SUPERCONDUCTOR $\text{Eu}_{0.1}\text{Gd}_{0.9}\text{Ba}_2\text{Cu}_3\text{O}_x^{\dagger c}$

R.D. TAYLOR, J.O. WILLIS and Z. FISK

Physics Division, Los Alamos National Laboratory, Los Alamos, New Mexico 87545, USA

Superconducting transition temperatures T_c near 95 K have been found for a number of $\text{R Ba}_2\text{Cu}_3\text{O}_x$ systems, where R includes most of the rare earths /1/. Even magnetic ions such as Gd^{3+} have little effect on T_c . Heat capacity measurements of $\text{GdBa}_2\text{Cu}_3\text{O}_x$ show a λ -like feature at 2.24 K thought to be associated with magnetic ordering, and superconductivity persists below this temperature /2/.

We have made ^{151}Eu Mossbauer Effect (ME) measurements on $\text{EuBa}_2\text{Cu}_3\text{O}_x$ at temperatures down to 1.3 K. The isomer shift in $\text{EuBa}_2\text{Cu}_3\text{O}_x$ clearly shows the Eu to be in the 3+ state, and the absence of any hyperfine field shows it to be non-magnetic at all temperatures studied. For $\text{Eu}_{0.1}\text{Gd}_{0.9}\text{Ba}_2\text{Cu}_3\text{O}_x$ we find a transferred hyperfine field at the Eu-sites developing below 2.1 K. These results are shown in Fig. 1 from data fitted with a magnetic Hamiltonian for the unresolved hyperfine spectra. The curve shown is a Brillouin fit to the data assuming $g = 2$ and a moment of $7\mu_B$ for Gd^{3+} . The fit gives a saturation hyperfine field of 2.9(3) T and a magnetic ordering temperature T_N of 2.09(11) K. The temperature of the peak in the heat capacity for $\text{Eu}_{0.1}\text{Gd}_{0.9}\text{Ba}_2\text{Cu}_3\text{O}_7$ was determined to be 1.95(5)K.

The measurements show that $\text{Eu}_{0.1}\text{Gd}_{0.9}\text{Ba}_2\text{Cu}_3\text{O}_x$ becomes magnetically ordered below 2.1 K with the temperature dependence expected for spontaneous ordering of Gd^{3+} ions. The magnitude of the hyperfine field transferred to the ^{151}Eu sites is roughly that expected from the dipole field from the Gd^{3+} neighbors; the Eu retains its Eu^{3+} nonmagnetic character. The ordering temperature T_N and the heat capacity peak are of common origin. Superconductivity masks the presence of magnetic ordering in magnetic susceptibility measurements, but a long extrapolation of the high temperature susceptibility /2/ of $\text{GdBa}_2\text{Cu}_3\text{O}_7$ gives $T_0 \sim -4.8$ K. Below 2.1 K, magnetism and superconductivity coexist.

Fig. 1. Transferred hyperfine field at ^{151}Eu sites as a function of temperature.

[†]Work supported by Department of Energy, Basic Energy Sciences, Materials Science

References

- /1/ Z. Fisk, J. D. Thompson, E. Zirngiebl, J. L. Smith, and S-W. Cheong, Solid State Commun., 62 (1987) 743.
- /2/ J. O. Willis, Z. Fisk, J. D. Thompson, S-W. Cheong, R. M. Aikin, J. L. Smith, and E. Zirngiebl, J. Magn. Magn. Mat. 67 (1987) L139.