

Lawrence Berkeley National Laboratory

Recent Work

Title

ONE-MAGNON LUMINESCENCE SIDEBANDS OF THE EXCITONIC TRANSITION IN MnF_2

Permalink

<https://escholarship.org/uc/item/3j60z129>

Author

Chiang, T.C.

Publication Date

1977-12-01

Submitted to Solid State Communications

LBL-7335
Preprint c.2

ONE-MAGNON LUMINESCENCE SIDEBANDS OF THE
EXCITONIC TRANSITION IN MnF_2

T. C. Chiang, P. R. Salvi,
J. Davies, and Y. R. Shen


December 1977

RECEIVED
LAWRENCE
BERKELEY LABORATORY
MAR 8 1978
LIBRARY AND
DOCUMENTS SECTION

Prepared for the U. S. Department of Energy
under Contract W-7405-ENG-48

TWO-WEEK LOAN COPY

**This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5716**



LBL-7335
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

ONE-MAGNON LUMINESCENCE SIDEBANDS OF THE
EXCITONIC TRANSITION IN MnF_2

T. C. Chiang, P. R. Salvi,^{*} J. Davies,[†] and Y. R. Shen

DECEMBER 1977

Prepared for the U. S. Energy Research and
Development Administration under Contract W-7405-ENG-48

^{*} Permanent address: Istituto di Chimica Fisica, Via G. Capponi 9,
50121 Firenze, Italy.

[†] Permanent address: Physics Department, University College of Swansea,
Singleton Park Swansea SA2 8PP, Great Britain.

ONE-MAGNON LUMINESCENCE SIDEBANDS OF THE
EXCITONIC TRANSITION IN MnF_2

T. C. Chiang, P. R. Salvi,^{*} J. Davies,[†] and Y. R. Shen

Department of Physics, University of California
Berkeley, California 94720

and

Materials and Molecular Research Division
Lawrence Berkeley Lab, Berkeley, California

DECEMBER 1977

ABSTRACT

We report the first observation of the π -polarized one-magnon excitonic luminescence sideband in MnF_2 . The theory of Loudon is used to fit the experimental spectrum quantitatively. An effective temperature of the crystal is deduced from the simultaneously observed antiStokes sideband emission.

*Permanent address: Istituto di Chimica Fisica, Via G. Capponi 9,
50121 Firenze, Italy.

†Permanent address: Physics Department, University College of Swansea,
Singleton Park Swansea SA2 8PP, Great Britain.

One-magnon sideband of the excitonic transition in the ${}^6A_{1g}({}^6S) - {}^4T_{1g}({}^4G)$ manifold in MnF_2 has been well studied in the literature.¹⁻³ In absorption, while the discrepancy between theory and experiment in the α - and σ -polarization spectra is small, it is quite large in the π -polarization. The discrepancy presumably results from ignoring the exciton-magnon interaction⁴ in the theoretical calculation. In emission, since the exciton and magnon are not simultaneously present, the exciton-magnon interaction does not come into play. Then the theoretical calculation agrees very well with the experimental α - and σ -polarization spectra.² However, so far as we know, observation of the π -polarized one-magnon luminescence sideband, although predicted by theory,³ has never been reported probably because of its much weaker intensity. Recently, in studying multi-magnon luminescence sidebands⁵ in MnF_2 , we have been able to observe clearly the π -polarized one-magnon sideband which is much weaker than those with α - and σ -polarizations. The spectrum can indeed be described almost perfectly by the theory without the exciton-magnon interaction. At higher temperatures, antiStokes luminescence of the sideband has also been observed. The temperature deduced from the Stokes-antiStokes ratio agrees with that obtained from the $E_1 - E_2$ exciton luminescence ratio.

The experiment was done using either a CW dye laser or a flash-pumped dye laser as the excitation source. The MnF_2 sample properly oriented was cooled by either gas or superfluid helium. Luminescence from the sample was analyzed by a double monochromator and detected by either a photon-counting system or a gated boxcar integrator.

Typical polarized luminescence spectra obtained with the pulsed laser are shown in Fig. 1. Impurity luminescence in this case was suppressed by

the gated detection scheme.^{5,6} The observed exciton lines E_1 and E_2 in the ${}^4T_{1g} \rightarrow {}^6A_{1g}$ transitions and the α, σ -polarized one-magnon sidebands associated with E_1 agree well with those reported in the literature. The corresponding π -polarized one-magnon sideband is appreciably weaker and broader. At relatively higher temperatures, the antiStokes sideband emission is also clearly visible, and is relatively more intense for the π -polarization. In order to determine the sideband lineshape more accurately, we have also recorded the luminescence spectrum with the CW Ar⁺ laser and photon-counting system. The result for the π -polarization is shown in Fig. 2, where in (a) the spectrum was obtained with the sample immersed in superfluid helium, and in (b) the spectrum was obtained with the sample in cold helium gas at 13°K. A strong impurity luminescence line is clearly present on the low-energy side of the sideband in Fig. 2(a), while the same line is apparently thermally quenched in Fig. 2(b).

The dispersions of the E_1 and E_2 excitons and the magnons in MnF_2 are shown in Fig. 3(a). To explain the observed sidebands, we use the theory of Loudon.³ In his formalism, two-ion exchange interaction is responsible for the magnon creation or annihilation and the exciton-magnon interaction is neglected. If only the interaction between next-nearest neighbors on the opposite sublattice is taken into account, then the one-magnon sideband absorption $A^{\text{nn}}(\omega)$ and emission $E^{\text{nn}}(\omega)$ in the α or σ polarization are given, in the zero-temperature approximation, by

$$\begin{aligned} \left\{ \begin{array}{l} A_{\alpha, \sigma}^{\text{nn}}(\omega) \\ E_{\alpha, \sigma}^{\text{nn}}(\omega) \end{array} \right\} &= \sum_{\vec{k}} \left[C^2 \cos^2\left(\frac{k_x a}{2}\right) \cos^2\left(\frac{k_y a}{2}\right) \right. \\ &\quad \left. + D^2 \sin^2\left(\frac{k_x a}{2}\right) \sin^2\left(\frac{k_y a}{2}\right) \right] \sin^2\left(\frac{k_z c}{2}\right) \begin{Bmatrix} u_k \\ v_k \end{Bmatrix} \delta[\hbar\omega - \epsilon_0 \mp \epsilon_m(\vec{k})] \end{aligned} \quad (1)$$

and those in the π -polarization by

$$\begin{aligned} \begin{pmatrix} A_{\pi}^{\text{nn}}(\omega) \\ E_{\pi}^{\text{nn}}(\omega) \end{pmatrix} &= F^2 \sum_{\vec{k}} \left[\sin^2\left(\frac{k_x a}{2}\right) \cos^2\left(\frac{k_y a}{2}\right) \right. \\ &\quad \left. + \cos^2\left(\frac{k_x a}{2}\right) \sin^2\left(\frac{k_y a}{2}\right) \right] \cos^2\left(\frac{k_z c}{2}\right) \begin{pmatrix} u_k^2 \\ 2 \\ v_k^2 \end{pmatrix} \delta[\hbar\omega - \epsilon_0 \mp \epsilon_m(\vec{k})] \end{aligned} \quad (2)$$

where C, D, and F are coupling constants of the same order of magnitude, a and c are lattice constants, ϵ_0 is the E_1 exciton energy, $\epsilon_m(\vec{k})$ is the magnon energy at \vec{k} , and u_k and v_k are defined in Ref. 3 and reproduced here in Fig. 3(b). Similarly, one finds that the interaction between nearest neighbors on the same sublattice contributes to the sideband absorption and emission in the α or σ polarization as

$$\begin{pmatrix} A_{\alpha,\sigma}^{\text{n}}(\omega) \\ E_{\alpha,\sigma}^{\text{n}}(\omega) \end{pmatrix} = G^2 \sum_{\vec{k}} \sin^2(k_z c) \begin{pmatrix} v_k^2 \\ 2 \\ u_k^2 \end{pmatrix} \delta[\hbar\omega - \epsilon_0 \mp \epsilon_m(\vec{k})] \quad (3)$$

but contributes nothing to the sideband absorption and emission in the π -polarization, where G is again a coupling constant of the same order of magnitude as C, D, and F.

The summations over \vec{k} in the above equations are weighted heavily towards the Brillouin zone edges by the large magnon density of states. However, near the zone edges, v_k^2 tends to zero while u_k^2 remains finite as shown in Fig. 3(b). It is then easy to see that

$$A_{\sigma,\alpha}^{\text{n}}(\omega) \cong A_{\sigma,\alpha}^{\text{nn}}(\omega) + A_{\sigma,\alpha}^{\text{n}}(\omega) \cong A_{\sigma,\alpha}^{\text{nn}}(\omega); \quad (5)$$

$$E_{\sigma,\alpha}(\omega) \cong E_{\sigma,\alpha}^{\text{nn}}(\omega) + E_{\sigma,\alpha}^{\text{n}}(\omega) \cong E_{\sigma,\alpha}^{\text{n}}(\omega); \quad (6)$$

$$E_{\pi}(\omega) \cong E_{\pi}^{\text{nn}}(\omega) \quad ; \quad A_{\pi}(\omega) \cong A_{\pi}^{\text{nn}}(\omega) \quad (7)$$

and $E_{\pi}(\omega) \ll A_{\pi}(\omega)$, $A_{\sigma,\alpha}(\omega)$, $E_{\sigma,\alpha}(\omega)$.

Dietz et al.² has used Eq. (3) to fit quantitatively the observed one-magnon luminescence sideband in the α,σ -polarization. Similarly, we can use Eq. (2) to fit the luminescence sideband in the π -polarization. Figure 2(a) shows that the agreement between theory and experiment is indeed excellent. In the inset of Fig. 2, we also show the comparison between theory and experiment on the π -polarized one-magnon absorption sideband. The discrepancy is obvious. Agreement in the luminescence case and disagreement in the absorption case clearly indicates that the exciton-magnon interaction is non-negligible in the absorption process. This interaction should appreciably broaden the sideband absorption and shift it to lower energy.⁴ We notice that because of the difference in u_k^2 and v_k^2 associated with the sine and cosine terms in Eq. (2), the theoretical lineshapes of the π -polarized absorption and emission sidebands are very different. Also, the integrated strength ratio of absorption to emission is about 23.

We realize from Eq. (2) that in the π -polarization the antiStokes sideband emission is simply the inverse process of the sideband absorption only if the thermal population of magnons is properly taken into account. Therefore, we can expect to obtain the antiStokes sideband spectrum by simply multiplying the experimental absorption sideband, normalized to yield

the correct sideband absorption-to-Stokes-emission ratio of 23, by a Bose-Einstein distribution function at a proper temperature. This is shown in Fig. 2(b). The theoretical antiStokes spectrum corresponding to a temperature of 13.3°K fits very well with the observed spectrum. This temperature is in good agreement with the one deduced from the luminescence intensity ratio of the E_1 and E_2 exciton lines. In the α - and σ -polarizations, deduction of the effective temperature from the antiStokes sideband emission is not possible because of lack of a normalization constant relating the strengths of the absorption and Stokes emission sidebands.

In summary, we have shown that the theory of Loudon gives an excellent description of the observed π -polarized one-magnon luminescence sideband in MnF_2 . The effective temperature of the crystal can be deduced from the simultaneously observed π -polarized antiStokes luminescence sideband.


This work was supported by the Division of Basic Energy Sciences, U.S. Department of Energy.

References

1. D. D. Sell, R. L. Greene, and R. M. White, Phys. Rev. 158, 489 (1967).
2. R. E. Dietz, A. E. Meixner, H. J. Guggenheim, and A. Missetich, J. Luminesc. 1, 2, 279 (1970).
3. R. Loudon, Advan. Phys. 17, 243 (1968).
4. Y. Tanabe, K-I. Gondaira, and H. Murata, J. Phys. Soc. Japan 25, 1562 (1968).
5. T. C. Chiang, P. R. Salvi, J. Davies, and Y. R. Shen, to be published.
6. R. L. Greene, D. D. Sell, R. S. Feigelson, G. F. Imbusch, and H. J. Guggenheim, Phys. Rev. 171, 600 (1968).


Figure Captions

- Figure 1 Polarized intrinsic luminescence spectra of MnF_2 obtained by the pulsed excitation-detection scheme. The laser excitation had a wavelength of 5200 Å, a pulsewidth of 0.4 μsec , a peak power of $\sim 30 \text{ MW/cm}^2$ for the π -polarization and $\sim 20 \text{ MW/cm}^2$ for the α - and σ -polarizations, and a repetition rate of 6 pps. The boxcar used for detection had a gate width of 1 μsec . The sample was immersed in superfluid helium but laser heating was still apparent. The effective sample temperature was 12°K for the α - and σ -polarizations and 13.8°K for the π -polarization.
- Figure 2 π -polarized CW luminescence spectra of MnF_2 obtained with a 92 mW, 5145 Å, Ar^+ laser light: (a) with the sample immersed in superfluid He, and (b) with the sample at 13°K. The spectrum in (b) is amplified by 10 relative to that in (a). Solid lines are theoretical curves with the background taken into account. The inset shows the comparison between theoretical and experimental absorption sideband spectra.
- Figure 3 (a) Schematic dispersion curves of excitons and magnons in MnF_2 .
 (b) u_k^2 and v_k^2 as functions of k in the Brillouin zone.





XBL781-4410

Fig. 1



XBL78I-4411

Fig. 2



XBL 781-4409

Fig. 3

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720