Lawrence Berkeley National Laboratory

Recent Work

Title

HOT STAGE HVEM DYNAMIC STUDIES OF ORDER-DISORDER TRANSITIONS IN LITHIUM FERRITE

Permalink

<https://escholarship.org/uc/item/3mx8c9vm>

Authors

Biest, O. Van der
Butler, E.P.
Thomas, G.

Publication Date

1975-04-01

To be presented at the 33rd Annual
Meeting of the Electron Microscopy
Society of America, Las Vegas, NV,
August 11 - 15, 1975

LBL-3762

81

HOT STAGE HVEM DYNAMIC STUDIES OF ORDER-DISORDER
TRANSITIONS IN LITHIUM FERRITE

O. Van der Biest, E. P. Butler, and G. Thomas

April 1975

Prepared for the U. S. Energy Research and
Development Administration under Contract W-7405-ENG-48

For Reference

Not to be taken from this room

LBL-3762

81

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

HOT STAGE HVEM DYNAMIC STUDIES OF ORDER-DISORDER TRANSITIONS IN LITHIUM FERRITE

O. Van der Biest, E. P. Butler* and G. Thomas

Department of Materials Science and Engineering, University of California, Berkeley, California 94720. *Imperial College, London, U.K.

Lithium ferrite (LiFe_5O_8) is a ferrimagnetic compound with some interesting technological properties(1). In the disordered state the compound has the spinel structure with a random mixture of Li^+ and 3Fe^{3+} on the octahedral sites (spacegroup $\text{Fd}3\text{m}$). Below 750°C the lithium ions and iron ions on the octahedral sites order and the spacegroup symmetry is lowered to $\text{P}4_132$ ($\text{P}4_332$). The resulting domain structure has been described in detail by Van der Biest and Thomas(2).

The kinetics of the ordering reaction have been studied "in situ" in the hot stage of a HVEM. Annealing in the normal atmosphere of the microscope leads to a reduction of the compound in a way similar to that found for CoFe_2O_4 (3). In order to control the stoichiometry of the compound during the ordering reaction, it is necessary to maintain an oxygen atmosphere around the specimen, hence the use of an "environmental" cell is necessary. In this study the environmental cell designed by Swann (4) for the Imperial College HVEM was used. An oxygen pressure of 40 Torr was found to be high enough to prevent rapid reduction of the compound and low enough to have sufficient penetration and contrast in the images. Radiation damage definitely played a role during the experiments. Prolonged focussing of the beam (>10 min) on one spot caused voids to nucleate and grow until holes were formed. It was also observed that the amount of damage was proportional to the time the specimen had spent above the ordering temperature. This suggests that the rate of damage is an order of magnitude larger in the disordered state for approximately the same temperature. The specimen was heated up above T_c to about 770°C and then cooled as fast as the stage permits to temperatures slightly below the ordering temperature (735°C - 745°C). The changes in microstructure were followed in dark field with a superlattice spot. Images were recorded with a low light level TV system on videotape with a speed of 25 frames/sec. Fig. 1 shows a disordering sequence. It can be seen that disordering starts at the anti-phase boundaries, which are replaced by a layer of disordered material. The domains subsequently shrink and disappear, if heating is slow or the contrast may fade uniformly before the domains can disappear by shrinking. Fig. 2 shows an ordering sequence. Individual domains can be seen nucleating and growing, until they impinge and form antiphase domain boundaries.

We thank Dr. P. R. Swann for providing the 1 MeV facilities at Imperial College and Mr. D. Morgan, I.V.C. Corp., Sunnyvale for assistance with videotape processing. Financial assistance from Energy Research Development Administration and National Science Foundation is acknowledged.

1. Von Aulock, W. H.: Handbook of Microwave Materials, Academic Press (1965).
2. Van der Biest, O. and Thomas, G.: Acta Cryst., A31, 70 (1975).
3. De Jonghe, L. C. and Thomas, G.: Materials Science and Eng'g., 8, 259 (1971).
4. Swan, P. R.: in Electron Microscopy and Structure of Materials, G. Thomas, R. Fulrath and R. Fisher, Eds., University of California Press, 878 (1972).

0 0 0 0 4 3 0 3 0 7 4

-2-

XBB 753-2230

Fig. 1. Disordering sequence.

XBB 753-2231

Fig. 2. Ordering sequence.

LEGAL NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

TECHNICAL INFORMATION DIVISION
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720