

Lawrence Berkeley National Laboratory

LBL Publications

Title

The Photovoltaic Effect and Photoconductivity In Laminated Organic Systems

Permalink

<https://escholarship.org/uc/item/3ps687qs>

Authors

Kearns, David

Calvin, Melvin

Publication Date

1958-09-01

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at <https://creativecommons.org/licenses/by/4.0/>

UNIVERSITY OF
CALIFORNIA

*Radiation
Laboratory*

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

BERKELEY, CALIFORNIA

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

UCRL-8441

UNIVERSITY OF CALIFORNIA

Radiation Laboratory
Berkeley, California

Contract No. W-7405-eng-58

THE PHOTOVOLTAIC EFFECT AND PHOTOCONDUCTIVITY IN
LAMINATED ORGANIC SYSTEMS

David Kearns and Melvin Calvin

September 1958

Printed for the U. S. Atomic Energy Commission

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission to the extent that such employee or contractor prepares, handles or distributes, or provides access to, any information pursuant to his employment or contract with the Commission.

THE PHOTOVOLTAIC EFFECT AND PHOTOCONDUCTIVITY IN
LAMINATED ORGANIC SYSTEMS*

David Kearns and Melvin Calvin

Department of Chemistry and Radiation Laboratory
University of California, Berkeley, California

September 1958

* The work described in this paper was sponsored by the U. S. Atomic Energy Commission.

As a result of a wide variety of studies on photosynthesis in living plants and plant fragments, together with the development of photosensitive, photo-voltaic junctions in inorganic crystals¹ and the discovery and exploration of semiconduction in organic molecular substances^{2, 3, 4, 5, 6, 7} a suggestion has been made^{8, 9, 10, 11, 12, 13} that the primary quantum conversion process in

-
1. D. M. Chapin, C. S. Fuller and G. L. Pearson, Bell Lab. Record, 33, 241 (1955).
 2. D. D. Eley, G. D. Parfitt, M. J. Perry and D. H. Taysum, Trans. Faraday Soc. 49, 79 (1953); D. D. Eley and G. D. Parfitt, Trans. Faraday Soc. 51, 1529 (1955).
 3. H. Mette and H. Pick, Z. Physik, 134, 566 (1953).
 4. H. Akamatu, H. Inokuchi and Y. Matsunaga, Bull. Chem. Soc. Japan, 29, 213 (1956).
 5. For a recent survey see Felmayer and Way, J. Electrochem. Soc. 105, 141 (1958).
 6. A. S. Vartanyan, J. Chem. Phys. U. S. S. R., 20, 1065 (1946) Zhur. Fiz. Khim., 24, 1361 (1950).

-
7. D. C. Northrop and G. Simpson, Proc Phys. Soc. (London) B67, 892 (1954).
 8. D. F. Bradley and M. Calvin, Proc. Nat. Acad. Sci. 41, 563 (1955).
 9. E. Katz in Photosynthesis in Plants, Iowa State College Press, Ames, Iowa (1949), 291.
 10. G. Tollin, P. B. Sogo and M. Calvin, Ann. N. Y. Acad. Sci., in press (1958).
 11. W. Arnold and H. K. Sherwood, Proc. Nat. Acad. Sci. 43, 105 (1957).
 12. M. Calvin, in Brookhaven National Laboratory Symposium on "Photochemical Apparatus: Its Structure and Function," June 1958.
 13. W. Arnold and H. Macley, in Brookhaven National Laboratory Symposium on "Photochemical Apparatus: Its Structure and Function," June 1958.
-

photosynthetic tissues involves the creation and separation of charge to opposite sides of an asymmetrically-constructed lamina, followed by the trapping of both the electrons and the holes which then lead to their respective chemical processes, namely, reduction of carbon dioxide and oxidation of the water to oxygen. This has led us to study model systems¹ as semiconductors with a view to creating an organic photovoltaic junction.¹⁴

We have found that magnesium phthalocyanine (MgPh) discs coated with a thin film of air-oxidized tetramethyl p-phenylenediamine (TM ϕ D) are organic systems which do show the photovoltaic effect. The maximum voltage as yet developed by one of these discs was 200 mv. The rise and decay is instrument-limited (\sim 1 sec). The maximum power output was only 3×10^{-12} watts. The power output appears to be limited by an internal cell resistance of 10^8 ohms and by the maximum radiant energy incident on the junction.

Discs 1.5 cm in diameter and 0.1 cm thick were formed by pressing powdered MgPh in a die. These discs were then made photovoltaic when coated with a film of air-oxidized TM ϕ D by evaporation of an acetone solution of the amine. The coated sides of the discs were pressed in contact with a conducting glass electrode by a stainless steel piston applied to the back of the disc. This formed the photovoltaic cell which was placed in a vacuum chamber along with suitable electrical


14. D. Kearns and M. Calvin, unpublished results from this laboratory.

leads in insulation. During measurements a mechanical pressure of 9 kg/cm^2 held the disc against the glass and a gas pressure of 10^{-4} mm Hg was maintained. The junction was illuminated by passing light from a 500-watt projection lamp through a window in the chamber and through the conducting glass electrode. A recording vibrating reed electrometer was used to measure the photovoltage, photoconductivity and resistance of the cells. Action spectra for the photovoltaic effect and the photoconductivity were obtained by use of a Bausch and Lomb monochromator.

In all cases the MgPh layer was at a positive potential with respect to the oxidized TM ϕ D layer, indicating electron transfer from the MgPh to the TM ϕ D. Several junctions were made with MgPh and TM ϕ D where precautions were taken to prevent air oxidation of the amine. These junctions produced little or no detectable photovoltage, indicating that the oxidized TM ϕ D is required. Space-charge effects were present only when there was a visible amount of white unoxidized TM ϕ D on the coated MgPh discs. The MgPh alone exhibited no photovoltaic effect. The oxidized TM ϕ D alone gave a very small photovoltaic effect, appearing slightly negative with respect to the stannic oxide layer of the conducting glass. The action spectra of the photovoltaic effect and the photoconductivity of a representative cell are shown in Fig. 1.

The action spectrum, although resembling that of the absorption of solid magnesium phthalocyanine, does not coincide with it. This is to be expected since the action spectrum should be that of the junction layer rather than of the magnesium phthalocyanine itself and perhaps has more in common with Wurster's blue than with the phthalocyanine derivative.

A completely different system has also been investigated in a preliminary way. A matrix of coronene was coated with a thin layer of *o*-chloranil as an electron acceptor. In this case the internal resistance of the cell was extremely high (10^{11} ohms) but a photovoltaic effect was easily measured in which the coronene was positive and the chloranil layer was negative. These and other systems involving matrices of much better conductivity and both electron donor and electron acceptor layers are being investigated in greater detail.



THE UNIVERSITY OF CHICAGO
DIVISION OF THE PHYSICAL SCIENCES
DEPARTMENT OF CHEMISTRY
5708 SOUTH CAMPUS DRIVE
CHICAGO, ILLINOIS 60637