Lawrence Berkeley National Laboratory

Recent Work

Title

ZERO FIELD NMR STUDY OF THE BIAXIAL SMECTIC E PHASE

Permalink

<https://escholarship.org/uc/item/4qv682z7>

Authors

Thayer, A.M.

Luzar, M.

Pines, A.

Publication Date

1986-11-01

Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

RECEIVED
LAWRENCE
BERKELEY LABORATORY

DEC 23 1986

LIBRARY AND
DOCUMENTS SECTION

Materials & Molecular Research Division

Submitted to Liquid Crystals

ZERO FIELD NMR STUDY
OF THE BIAXIAL SMECTIC E PHASE

A.M. Thayer, M. Luzar and A. Pines

November 1986

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks*

LBL-22441
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

Zero Field NMR Study of the Biaxial Smectic E Phase

A.M. Thayer, M. Luzar[†] and A. Pines

Department of Chemistry, University of California and
Materials and Molecular Research Division, Lawrence Berkeley Laboratory
Berkeley, California 94720

[†]Current Address: J. Stefan Institut and Department of Physics
University of Ljubljana, Yugoslavia

Abstract

Preliminary results on the measurement of smectic liquid crystal phases by zero field NMR methods are presented. The nonaxial symmetry of the Smectic E phase is immediately apparent in the zero field NMR dipolar spectrum of a CH_2Cl_2 probe molecule.

Recently, we have conducted a number of zero field NMR experiments on liquid crystalline systems. Initial experiments on aligned nematics sought to measure the order parameters in the absence of an applied magnetic field.¹ The usefulness of the zero field NMR experiment lies in the ability to obtain sharp well-resolved spectra on disordered materials.² Whereas in an applied field the orientational anisotropy of the nuclear spin interactions produces a broadened dipolar or quadrupolar spectrum, in zero field the isotropy of space makes all interactions identical in the molecular frame. Thus even for a powder distribution of orientations, the zero field NMR spectrum consists of discrete frequencies corresponding to the nuclear spin interactions.

Many of the more interesting liquid crystalline mesophases are the smectic phases which do not necessarily order in a magnetic field³ unless heated. More complex phases show a more diverse arrangement of the molecules of which it would be desirable to gain a direct measure. For example, as shown schematically for two layered phases in Figure 1, the molecules arrange themselves not only in layers but also in more complicated intralayer structures. The smectic B phase in Figure 1 shows the rotational freedom of the molecules in the layers which leads to an axially symmetric phase. In contrast, phases such as the smectic E have restricted rotational freedom of the molecules about the long molecular axes which is expected to lead to a biaxiality of the phase. This biaxiality has been observed in the high field deuterium spectra of aligned samples⁴, and in the motional effects on the deuterium asymmetry parameters in a selectively deuterated smectic E phase.⁵ These studies required the use of aligned samples measured at many different orientations with respect to the applied field,

to derive complete information on the system. The effect of the biaxiality is often quite small and may not be observable in unaligned samples.

Zero field NMR spectra are very sensitive to the perturbations of small amplitude motions and the motionally induced asymmetry in dipolar coupling tensors.⁶ We have recently obtained the zero field NMR spectra of a few liquid crystalline smectic phases and report a direct observation of the symmetry of the phase. The zero field NMR spectrum of a CH_2Cl_2 probe molecule in an unaligned smectic B sample⁷ (5 wgt % CH_2Cl_2 in a binary mixture of 60% 4-n-butyloxybenzylidene-4'-n-octylaniline (40.8) and 40% 4-n-octyloxycyanobiphenyl (80CB)) appears in Figure 2. In the smectic B phase, where there is freedom of rotation about the long molecular axes, the resulting spectrum is a triplet of lines² corresponding to the axially symmetric dipolar coupling of the two protons scaled by the order parameter. The separation in frequency from zero is given by $\nu = S \cdot 3\gamma^2 h / 8\pi r^3$ and is a direct measure of the order parameter. The zero field NMR spectrum of the disordered smectic E phase appears in Figure 2. This sample consists of ~5-10 wgt % CH_2Cl_2 in a 50%-50% binary mixture of the same components as the smectic B phase and forms a very stable room temperature smectic E phase.⁷ The zero field NMR spectrum does not show the expected three lines but an additional splitting which yields a pattern of six lines (and one at zero frequency due to residual field effects⁸) and is directly attributable to the nonaxial symmetry in the dipolar coupling as induced by the symmetry of the phase. An asymmetry parameter of $\eta=0.208$ can be calculated from the spectrum.

These experiments demonstrate the applicability of the zero field NMR experiment to the study of liquid crystalline phases. The spectra provide

direct observation of subtle features of the phases by measuring nuclear spin interactions on a molecular scale. A more in depth report of this work and applications to other phases will appear in the near future.⁹

Acknowledgments

We thank Prof. J.W. Doane for valuable discussions concerning the Smectic E samples. This work was supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Sciences Division of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098. AMT was supported by a General Motors Industrial Fellowship during the course of this work.

References

1. A.M. Thayer, J.M. Millar, M. Luzar, T.P. Jarvie and A. Pines, J. Phys. Chem. **90**, 1577 (1986).
2. D.P. Weitekamp, A. Bielecki, D. Zax, K. Zilm and A. Pines, Phys. Rev. Letts, **50**, 1807 (1983).
A.M. Thayer and A. Pines, Acct. Chem. Res., in press.
3. P. de Gennes, The Physics of Liquid Crystals, (Clarendon, Oxford, 1974).
4. J.W. Doane, Chapters 18 and 19 in Nuclear Magnetic Resonance in Liquid Crystals, ed. J.W. Emsley (D. Reidel, Dordrecht, 1983).
5. N.A. Vaz, M.J. Vaz and J.W. Doane, Phys. Rev. A. **30**, 1008 (1984).
6. J.M. Millar, A.M. Thayer, D.B. Zax and A. Pines, J. Amer. Chem. Soc. **108**, 5113 (1986).
7. P.E. Cladis, Mol. Cryst. Liq. Cryst. **67**, 177 (1981).
8. M. Luzar, A.M. Thayer and A. Pines, submitted to J. Magn. Reson.
9. M. Luzar, A.M. Thayer and A. Pines, submitted to J. Phys. Chem.

Figure Captions

Figure 1: Schematic drawing of the molecular ordering within a layer of two different smectic liquid crystalline phases. In the smectic B phase, at left, the molecules are free to rotate about their long molecular axes (as illustrated by the circles) and there is positional order within the plane. The smectic E phase shows a molecular packing in which the molecules can oscillate between two positions (represented by ellipses) within the layers. There no longer is the freedom of rotation about the long molecular axes which leads to a biaxiality to the phase. The CH_2Cl_2 probe molecules are expected to reside between the molecules exhibiting the local symmetry.

Figure 2: Zero field NMR spectra of the two protons in a CH_2Cl_2 probe molecule in smectic B and E phases. At top, the unaligned smectic B sample produces the usual dipolar triplet in zero field from which the order parameter can be measured. The differing linewidths can be attributed to residual field effects and are not a function of the symmetry of the phase. The spectrum of the smectic E phase shows a more complicated pattern of six lines (plus one at zero frequency due to residual field effects). The asymmetry parameter induced in the dipolar coupling by the biaxiality of the phase can be calculated directly from the spectrum.

XBL 8610-9664

Figure 2
Thayer et al.
Zero Field NMR of Smectic E

XBL 866-11157A

Figure 1
Thayer et al.
Zero Field NMR of Smectic E

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

*LAWRENCE BERKELEY LABORATORY
TECHNICAL INFORMATION DEPARTMENT
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720*