Lawrence Berkeley National Laboratory

Recent Work

Title

STRUCTURE AND CHEMISORPTIVE PROPERTIES OF THE Pt₃Ti SURFACE

Permalink

<https://escholarship.org/uc/item/56g0q1c9>

Authors

Bardi, U.
Dahlgren, D.
Ross, P.N.

Publication Date

1985-08-01

Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

RECEIVED
LAWRENCE

BERKELEY LABORATORY

NOV 4 1985

LIBRARY AND
DOCUMENTS SECTION

Materials & Molecular Research Division

Submitted to Journal of Catalysis

STRUCTURE AND CHEMISORPTIVE PROPERTIES
OF THE Pt_3Ti SURFACE

U. Bardi, D. Dahlgren and P.N. Ross

August 1985

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.*

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

STRUCTURE AND CHEMISORPTIVE
PROPERTIES OF THE Pt_3Ti SURFACE

U. Bardi
Dipartimento di Chimica
Universita di Firenze
50121 Firenze, Italia

D. Dahlgren^{*} and P.N. Ross
Materials and Molecular Research Division
Lawrence Berkeley Laboratory
Berkeley, CA 94720, USA

^{*}Present Address: Photometric Inc., Huntington Beach,
CA 92649

ABSTRACT

Low energy electron diffraction (LEED), x-ray photoelectron spectroscopy (XPS), and Auger electron spectroscopy were used to determine the structure and composition of the surfaces of [111] and [100] oriented crystals of an ordered alloy of bulk stoichiometry Pt_3Ti . Thermal desorption spectroscopy (TDS) was used to study the adsorption of carbon monoxide and hydrogen on these surfaces. The clean annealed surface of [111] orientation has the ordered structure expected from truncation of the bulk crystal, consisting of alternating atomic rows of (50% Pt + 50% Ti) and 100% Pt. The surface of [100] orientation also has a regular truncation structure with the outermost layer being 50% Ti in a $c(2 \times 2)$ lattice and the second layer the 100% Pt layer. At near-ambient temperature, the adsorption of CO at the Ti sites is dissociative and at the Pt sites is molecular. The orderly substitution of Ti for Pt atoms in the surface changes the Pt-Pt pair site distribution such as to eliminate most of the sites for bridge bonding of the CO molecule. Only a single symmetric TDS peak was observed for CO desorbing from the alloy surface, as opposed to the asymmetric peak shape observed from pure Pt surfaces, which we suggest is a consequence of bridge-site elimination. At low temperature (230 K), a second molecular state of CO was observed which we assigned to a pre-dissociative state on Ti sites with CO lying parallel to the surface. No hydrogen could be observed to desorb from clean annealed Pt_3Ti surfaces dosed with hydrogen at room temperature. Unfortunately, we were not able to distinguish between the possibilities: (1) that hydrogen does not adsorb on the surface at room temperature; or (2) that hydrogen adsorbed at room temperature is not desorbed by flashing the surface temperature to ca. 900 K.

1. INTRODUCTION

Pt_3Ti is an intermetallic compound which can be considered representative of a class of compounds (Engel-Brewer type) (1) characterized by a highly negative enthalpy of formation, which have been object of intensive study for their catalytic properties in the reduction of oxygen to water in fuel cells (2). The adsorptive properties of an intermetallic compound of this type are of interest because the strength of the intermetallic bond is likely to favor the formation of a well-ordered surface where enrichment phenomena are expected to play a minor role (3,4,5). In such a surface, the chemisorptive properties may be modified by effects due to either the dilution of the active atoms in the bimetallic surface (ensemble effects) or by modifications of the electronic properties of the atoms due to the intermetallic bond (ligand effects). Another important point relative to this type of surface lies in its relation with "SMSI" type systems (6,7). In these systems the adsorptive properties of the active metal are strongly modified by the interaction with the support. It is possible that an intermetallic bond plays a fundamental role in SMSI and the formation of a compound such as Pt_3Ti was initially suggested as a possible explanation for SMSI properties (7). Although there is an accumulation of evidence implicating TiO_x overlayer formation as the key phenomenon in SMSI (8,9,10), a study of the adsorptive properties of the Pt_3Ti surface may still furnish information on the role of the intermetallic bond in modifying the adsorptive properties of each metal and on the possible relationship of

SMSI-type systems to binary "Engel-Brewer" type alloys.

In the present study, we used the surface techniques of AES, XPS and LEED to characterize the structure and composition of the alloy surface. TDS was the main tool used to investigate the adsorption properties of CO and H₂. The LEED analysis of the structures of Pt₃Ti(111) and (100) surfaces is published elsewhere (11,12), and preliminary results for CO and H₂ adsorption on polycrystalline Pt₃Ti appeared in a previous communication (13). In the present paper we summarize and discuss all the results obtained in this study both on polycrystalline and on single crystal [100] and [111] oriented Pt₃Ti surfaces. The results show that in all cases the clean surface at equilibrium contains both Ti and Pt atoms in the outermost layer. In general, we observed significant variations in the reactivity of the Pt₃Ti surface with respect to pure Pt. These variations can be interpreted in part as the result of the geometric effect due to the presence of titanium in the surface and in part as due to electronic effects from the intermetallic bonding.

EXPERIMENTAL

Pt₃Ti polycrystalline material was prepared arc melting the base metals in argon atmosphere (Ti and Pt nominal purity, 99.99%). X-ray examination indicated the formation of the fcc, AuCu₃ type structure (14). Single crystal samples were prepared from the polycrystalline material by recrystallization in a zone melting furnace. Samples oriented along the [001] and [111] directions by Laue diffraction methods were spark cut from the single crystal material. One of the crystal faces was mechanically polished, while the other was gold

brazed on tantalum foil. Tantalum wires were spotwelded on this foil to support the sample and to anneal it by resistive heating. The sample temperature was measured by means of a chromel-alumel thermocouple spotwelded on the tantalum foil. Two different UHV systems were used for the present study. One was equipped with LEED, a single pass CMA with glancing electron gun for AES and quadrupole mass spectrometer for TDS. This system was also equipped with an electron beam evaporator located in a separate chamber. This evaporator was used to coat the sample surface with a Pt film in order to compare the properties of pure Pt and Pt_3Ti in the same experimental conditions. Films of titanium, deposited by means of a Ta-Ti alloy filament, were used for the same purposes of comparison.

The second vacuum chamber was equipped with a MgK_α X-ray source and a hemispherical analyzer with multichannel counting capability (15). TDS spectra could also be recorded by means of a quadrupole mass spectrometer. In this chamber, a pure Pt(111) sample was used to compare the properties of pure Pt with those of $\text{Pt}_3\text{Ti}(111)$.

Due to the different experimental set-up, different annealing rates were used for TDS experiments. In the first vacuum chamber, a rate of 26 deg/sec was used for the $\text{Pt}_3\text{Ti}(111)$ surface and higher rates for the (100) and polycrystalline surfaces. In the second chamber, a rate of 6 deg/sec was used for the same experiments. The TDS spectra were qualitatively reproducible from the same crystal in the two chambers. However, the CO TDS peaks from the same sample was consistently shifted towards higher temperature in the experiments performed with the higher heating rates. Simple calculations based on

the equations reported in (16) show that this difference is due solely to the difference in the heating rate.

3. RESULTS

3.1 Clean Surface Characterization

Most of the initial contamination present on the Pt_3Ti surfaces upon introduction in the vacuum chamber could be removed by room temperature ion bombardment. It was not possible, however, to remove all the oxygen and carbon in this way. Further cleaning could be obtained annealing the sample in UHV conditions at temperatures higher than about 500 K, which resulted in the removal of oxygen apparently by reaction with surface carbon to form CO. Usually, after this treatment, only carbon remained on the surface. A further reduction of the carbon could be obtained by a high temperature treatment involving sequential oxygen dosing and thermal annealing. Oxygen dosing must be carefully controlled, since excessive treatment in oxygen can cause the formation of surface of surface titanium oxide and deplete the subsurface region of Ti. We succeeded eventually in obtaining an oxygen free surface with less than 5% monolayer contamination of carbon as determined by XPS and by AES (in the latter case using the calibration reported in (17)).

In general, the ion bombardment Pt_3Ti surface showed a much higher Ti/Pt signal ratio than the annealed one. This result can be interpreted in terms of preferential sputtering of Pt atoms. Using the model developed in (18) with the data for relative sputtering cross-sections reported in (19), it can be shown that the bombarded surface composition does not correspond to the equilibrium, but it is

enriched in Ti as a result of the sputtering process. From this calculation it appears that the enrichment in platinum of the surface observed upon annealing after sputtering is simply the restoring of the equilibrium composition.

The intensity of the Pt and Ti AES peaks can be used to estimate the surface composition of the clean, annealed alloy. The values reported in literature for the absolute dN/dE intensities of these peaks appear to be unreliable for this purpose, since the actual intensity depends in general on the experimental conditions especially in the case of titanium (20). Instead, we used evaporated Ti and Pt films as internal standards to calibrate the intensities of the AES signals. The Ti concentration in the surface was assumed to be proportional to the dN/dE intensity of the Ti AES peak at 385 eV. Therefore, the Ti concentration in the Pt_3Ti surface can be measured as the ratio of the intensity of the Ti peak for Pt_3Ti and for a pure Ti film. The composition of the Pt_3Ti surface can also be determined by the same procedure from the intensity of the Pt (238 eV) peak using pure Pt films as reference.

Several measurements were performed depositing Pt and Ti films on the polycrystalline Pt_3Ti surface, obtaining a surface composition of 29 ± 2 at% in Ti based on the Pt AES peak height and a composition of 28 ± 1 at% in Ti based on the Ti AES peak height. The compositions of the single crystal surfaces were obtained by comparison of the relative Ti/Pt AES peak height ratio to that for the polycrystalline surface. The resulting calculated composition were 26 at% Ti for the (111) surface and equal to 30 at% Ti for the (100) surface. All the

composition analyses are summarized in Table 1. These data indicate a nearly bulklike composition of the clean, annealed Pt_3Ti surfaces. We remark, however, that when the surface was oxidized, the relative intensity of the Ti AES peaks was much higher, indicating segregation of oxidized titanium species onto the surface. A detailed study of the oxidation process of these surfaces has been reported elsewhere (21). We note also that upon annealing a clean Pt_3Ti surface in the absence of reactive gases, no significant variation of the Ti/Pt dN/dE ratio was found for temperatures up to about 900 K. For higher temperatures, an irreversible increase of the relative Ti intensity was found, accompanied by an increase of the carbon AES signal. This result is attributed to the formation of titanium carbide on the surface, possibly arising from the reaction with carbon segregating from the interior of the crystal.

The LEED results relative to the $\text{Pt}_3\text{Ti}(100)$ and (111) surfaces have been reported (12) and will be only briefly summarized here. The Pt_3Ti fcc lattice has cell parameters which are less than 1% different from those of pure Pt (14). It is, therefore, possible to interpret the Pt_3Ti diffraction patterns as "superstructures" of the basic Pt pattern. Using the Wood notation, the LEED pattern observed for the $\text{Pt}_3\text{Ti}(111)$ surface corresponds to a $p(2 \times 2)$ type cell, while the pattern relative to the $\text{Pt}(100)$ surface corresponds to a $c(2 \times 2)$ cell. These cells correspond exactly to the cells expected from a structural model which assumes that the surface structure of Pt_3Ti derives from simple truncation of the bulk. In such a model, the outermost plane of $\text{Pt}_3\text{Ti}(111)$ contains exactly 25% of Ti atoms, as all (111) type planes

are identical. The $\text{Pt}_3\text{Ti}(100)$ plane may be either one of two possible alternating (100) planes: one pure Pt and the other containing 50% of Ti atoms. In both cases, a $c(2 \times 2)$ LEED pattern would result. These models for the structure of the (100) and (111) surfaces are shown in Fig. 1.

3.2 Adsorptive Properties

3.2.1 Carbon Monoxide

On all three types of Pt_3Ti surfaces studied, upon exposure to carbon monoxide at room temperature at pressures up to 1×10^{-6} torr we obtained evidence of undissociated (i.e. molecular) adsorption from AES and UPS measurements. The carbon KLL AES lineshape results typical of undissociated CO (22) and UPS measurements showed the molecular bands of undissociated CO. The He(II) UPS spectra after exposure to CO of the $\text{Pt}_3\text{Ti}(111)$ and $\text{Pt}(111)$ surfaces are shown in Fig. 3. In both cases, the most prominent features appearing after CO adsorption are at ca. 9 eV and 12 eV below E_f , indicative of the $4s$ and $1\pi-5\sigma$ molecular orbital bands of undissociated CO. The main features of the CO molecular bands appear to be the same on both surfaces.

The XPS data gave clear indication that a fraction of the adsorbed CO dissociates on the surface at room temperature and/or upon flashing the surface to the desorption temperature of the reversibly bound CO. Figure 4 shows the $0\text{ }1s\text{-Pt }4p$ region of binding energy for the clean $\text{Pt}_3\text{Ti}(111)$ surface, the surface after 15 L dose of CO and after thermal desorption of the CO. After the thermal flash, an oxygen signal is still detectable. Higher resolution comparison of these features is shown in Fig. 5. The double $0\text{ }1s$ peak observed here can be compared to

the double peak reported by Norton et al. (23) after CO adsorption on Pt(111). The doublet on Pt₃Ti is much more pronounced, with the low binding energy peak much more intense than on Pt(111). The O 1s remnant after flashing is shifted to slightly lower binding energy and corresponds exactly to the O 1s peak observed after direct exposure to oxygen of the Pt₃Ti(111) surface. From these data it can be concluded that CO dissociates on part of the Pt₃Ti surface. To determine whether CO dissociates upon adsorption or as an effect of the thermal flashing during TDS experiments, XPS spectra were recorded at incremental temperatures above 228 K. Figure 6 shows the comparison of the O 1s structure at 313 K vs. 228 K. The low energy feature of the O 1s peak is shifted towards even lower energy at low temperature. This shift can be attributed to a different chemical state of the adsorbed CO at low temperature and possibly to undissociated (molecular) CO adsorbed on Ti atoms with the oxygen end down at Ti sites (24).

The relative intensity of the O 1s remnant feature on the Pt₃Ti(111) surface after CO thermal desorption was not very reproducible, e.g. variable from ca. 10 to 20% of the total oxygen signal immediately after CO adsorption. Deconvolution of the oxygen 1s feature showed that the low binding energy peak is 20±2% of the total peak at 313 K. The poor reproducibility can be attributed to the difficulty in obtaining a perfectly clean Pt₃Ti surface. Therefore, quantitative estimates of the fraction of surface which dissociates CO are not very reliable. However, it is estimated that this fraction is 15-25%, which is consistent with the hypothesis that CO is dissociated only on Ti sites, considering that some of these sites are blocked by

carbon contamination at any given time.

On all three types of Pt_3Ti surfaces studied we observed virtually the same CO TDS spectrum once the effect of the different heating rates used was taken into account. The CO thermal desorption spectrum for $\text{Pt}_3\text{Ti}(111)$ is shown relative to that for $\text{Pt}(111)$ in Fig. 7. The maximum of the thermal desorption peak is shifted about 50 K lower on $\text{Pt}_3\text{Ti}(111)$. This temperature did not vary if the Pt_3Ti surface were exposed to CO at room temperature. The results for the intermetallic surface for lower CO exposures showed that the adsorption kinetics is second order, as on pure Pt. The same CO TDS peak shape was observed for $\text{Pt}_3\text{Ti}(100)$ and polycrystalline Pt_3Ti . A comparison of the TDS results for polycrystalline Pt and the three types of Pt_3Ti surfaces is shown in Fig. 8. In this case the high temperature peak of the polycrystalline Pt surface is suppressed on the alloy. Also, the temperature of the peak maximum for the Pt_3Ti surfaces in Fig. 8 appears higher than that for $\text{Pt}_3\text{Ti}(111)$ as shown in Fig. 7. This discrepancy is, however, to be attributed solely to the different heating rates, as discussed in the "Experimental" section.

The area under the CO TDS peak, after exposure at room temperature, was always smaller for the Pt_3Ti surface than for the Pt surface, e.g. the ratio of the areas for the alloy and for the pure metal was ca. 0.5 for the (111) oriented surfaces. This value is smaller than expected if we assume that the coverage in terms of CO molecules per platinum atom (only CO on Pt sites desorb intact) is the same in Pt_3Ti as in Pt. This discrepancy appears to be caused by geometric effects due to the dispersion of Ti atoms in the surface, as

it will be discussed in detail in 4.2.

We found also that the surface titanium oxide formed upon exposure of the surface to O_2 (21) could block the underlying metal surface to CO adsorption. If the Pt_3Ti surface was only partly oxidized, CO desorption could still be detected. In these conditions, CO desorption was always accompanied by the formation of CO_2 desorbing at higher temperatures (Fig. 9) and by a partial reduction of the titanium oxide on the surface. No CO_2 desorption could be detected if the surface was not previously oxidized. Also CO_2 desorption was not detectable from oxidized Ti in absence of Pt (i.e. from an oxidized Ti foil).

3.2.2 Hydrogen

Hydrogen adsorption on all three types of surfaces studied was strongly dependent of the previous thermal treatment. On the (111) surface, saturation dosing with H_2 at room temperature after a moderate pre-annealing (T ca. 500 K) gave rise to an H_2 TDS spectrum shown in Fig. 10a; the corresponding TDS spectrum for the (100) surface after the same treatment is reported in Fig. 10b. The H_2 TDS peak areas were highly sensitive to the annealing temperature and progressively decreased in intensity as the crystals were annealed over ca. 500 K. This progressive disappearance is illustrated in Fig. 10b in the case of the $Pt_3Ti(100)$ surface. This result can be attributed only in part to impurities segregating on the surface. The position of the peaks in Fig. 10b is modified as a function of the annealing, a result which is not expected if adsorbing sites are simply sterically blocked. Moreover, AES measurements appear to rule out complete blocking of all Ti sites and show that the amount of surface carbon in these conditions

is certainly insufficient to block a significant fraction of the Pt sites. Indeed the presence of free Pt sites was verified by the observation that CO could still be reversibly adsorbed. Although the presence of free Ti sites cannot be considered certain, it appears evident that the lack of H_2 desorption from Pt sites on the Pt_3Ti is not primarily caused by steric blocking.

4. DISCUSSION

4.1 Surface Structure

The first step in understanding the chemical properties of a bimetallic system is to determine the structure and composition of the outermost layer. As it is well-known, in most cases the surface composition of an alloy differs from that of the bulk. Several theoretical treatments can be applied to exothermic binary alloys in order to predict the surface composition. Van Santen and Sachtler (4) have developed a treatment based on the "broken bond" model for the Pt_3Sn compound, which has the same $AuCu_3$ type structure as Pt_3Ti . Pt-Ti alloys of variable stoichiometry have been examined by Spencer (3), again using an approach based on the broken bond model. A more sophisticated treatment of surface enrichment in exothermic alloys, valid for the (110) plane of a 1:1 alloy, has been developed by Moran-Lopez and Falicov (5). From a qualitative viewpoint, all these treatments indicate that, in general, a highly negative enthalpy of formation does not favor surface enrichment at low temperature, and, therefore, the surface composition of Pt_3Ti should be similar to that of the bulk. This conclusion is explicitly stated in (3) for the Pt_3Ti stoichiometric compound, although it is also stated that Ti segregation

should occur for lower (non-stoichiometric) titanium contents. The latter prediction agrees with the usually valid prediction that the surface will be enriched in the component which has the lower enthalpy of sublimation. Enrichment should also occur by exchange of atoms in the two outermost surface planes. Another prediction of the theory (4) is that, below the critical temperature, the surface composition should be weakly dependent on temperature.

The relative tendency of Pt_3Ti to show surface enrichment in comparison to other alloys can be illustrated by the following calculations. It can be shown (4,5) that in a binary intermetallic compound, the degree of surface enrichment is correlated to a dimensionless, Δ , parameter defined as:

$$\Delta = (U_{aa} - U_{bb}) / (U_{aa} + U_{bb} - 2U_{ab})$$

where " U_x " are the pair energies relative to the A and B components of the alloy. In general, low values of delta correspond to little or no surface segregation. From the heats of sublimation of Pt and Ti (1) and from the enthalpy of formation of Pt_3Ti (25), we can estimate the value of the pair energies and obtain a value of Δ (Pt_3Ti) = 0.26. This value is very small in comparison to that of other isostructural alloys, such as AuCu_3 ($\Delta=1.37$) and Pt_3Sn ($\Delta=1.44$). The low value of Δ for Pt_3Ti is due to two factors: the high value of U_{ab} (27.4 kcal/mole) and the small difference between U_{bb} (18.8 kcal/mole) and U_{aa} (22.4 kcal/mole). The calculated value of Δ can be used for an estimation of the amount of surface segregation on the basis of the

results reported in (5). These results show that an exothermic alloy surface enrichment is negligible for delta values of the order of the one calculated for Pt_3Ti , as long as the temperature is much below the critical temperature (for order, disorder transformation) value. Since the critical temperature for Pt_3Ti can be estimated as higher than 1800 K, it can be concluded that in the range of temperatures used in the present study surface enrichment should play a very minor role in the Pt_3Ti surface in comparison to other alloys, and that most likely no surface enrichment should occur at all.

Experimentally, the AES and LEED results are in good agreement with the above theoretical predictions. Firstly, we observed no dependence of the ratio of the Ti and Pt AES signal on temperature, in agreement with one of the predictions. Secondly, both the LEED results and the results of the AES measurements (Table 1) show that the surface composition is close to that of the bulk. $\text{Pt}_3\text{Ti}(111)$ in particular, may have a composition of the outermost layer which is identical to that of the bulk. The $\text{Pt}_3\text{Ti}(100)$ surface, instead, appear to contain more titanium. This fact is explainable assuming that, of the two possible (100) planes in Pt_3Ti , the one with a 1:1 ratio of Pt and Ti atoms forms the outermost layer, while the other (composed of pure Pt) forms the second outermost layer. This hypothesis is in agreement with the results of dynamical calculations of the LEED intensities (11). Calculations of the relative intensities of the Ti and Pt AES peaks based on the Gallon formalism (26) show that this model is compatible with the $\text{Ti}(387 \text{ eV})/\text{Pt}(235 \text{ eV})$ dN/dE ratios observed for the $\text{Pt}_3\text{Ti}(111)$ and $\text{Pt}_3\text{Ti}(100)$ surfaces (Table 1).

4.2 CHEMISORPTION PROPERTIES

In general, the chemisorptive properties of a metal in a binary alloy change only slightly, or not at all, in comparison to the reactivity of the same metal in pure form. This rule is followed by many of the binary alloy surfaces studied so far (27,29). However, our results for the Pt_3Ti surface show that the adsorptive properties of CO and H_2 are considerably changed in comparison to those relative to pure platinum. We performed experiments on Pt and Ti films as well as on a (111) oriented Pt sample in order to compare the properties of Pt_3Ti with those of the pure metals. In general, the results were in agreement with the available literature data on the adsorptive properties of platinum and titanium.

Considering titanium first, it is known that hydrogen diffuses into the titanium bulk after adsorption and that the CO molecule dissociates, at least in part, on the titanium surface (30,31). Titanium also reacts rapidly with oxygen forming a surface oxide (32). All these results could be reproduced in our apparatus with Ti films.

Platinum has a more complex behavior. It is known that CO is molecularly bound to the Pt surface and it has been shown that the CO TDS spectrum depends strongly on the Pt surface morphology. The presence of defects on the surface affects the adsorption parameters (33). In general, polycrystalline Pt gives rise to a double CO desorption peak (33,34). Single crystal Pt faces have a different behavior: the (111) face shows a single CO desorption peak, with a maximum for saturation coverage reported in the range 410-420 K by several authors (33,35-38). The same maximum is reported at much

higher temperatures by other authors (39,40), presumably as the result of the presence of defects in the surface. We found a value of 413 K for the maximum of this peak, Fig. 7. The Pt(100) surface has a more complex TDS CO spectrum, showing at least two peaks (37,39) at temperatures similar to those relative to the polycrystalline surface. Considering H₂ adsorption, the literature data (41-43), as well as our experiments, agree on the fact that a single H₂ desorption peak is detectable from clean polycrystalline Pt after room temperature exposure. However, the peak area decreases if the Pt surface is "smoothed" by high temperature annealing, indicating that surface defects play a major role in the adsorption of hydrogen on the surface (33), a result confirmed by studies of H₂ adsorption on stepped surfaces (44,45).

In comparing the results relative to CO adsorption of the alloy and of pure Pt and Ti, it must be recognized that titanium in the alloy surface may behave like titanium metal and dissociation of CO at titanium sites is a possibility. From the XPS data, it is clear that CO dissociates on part of the Pt₃Ti surface, with the proportionality consistent with the hypothesis that the dissociation occurs on titanium sites. This result is in keeping with the known properties of titanium metal and with previously observed reactivity of titanium sites in the Ni₃Ti alloy surface (46).

In general, modifications of the chemisorptive properties of metals in alloys can be attributed to two different factors: 1.) ensemble effects and 2.) ligand effects (27-29). Ensemble effects are caused by the disappearance (or reduction in number) of specific

adsorption sites caused by the dilution of like atoms in the surface. Ligand effects are caused instead by a modification of the electronic properties of one or both metals caused by the intermetallic bond. It is obvious that both effects can play a role in the surface properties of an alloy, and it is often difficult to separate the part of each. However, the Pt_3Ti single crystal surfaces are formed by an ordered array of Pt and Ti atoms, so that, in this specific case, considerations based on the surface structure should be helpful to establish the role of "geometric effects", i.e. site modification effects.

If the surface structure of Pt_3Ti corresponds to the model developed in the previous section (that is bulk truncation), then titanium atoms are dispersed in the surface in such a way as to be in contact only with platinum atoms, independently of the crystallographic orientation of the surface. On the other hand, Pt-Pt bonds are still present. On the (111) oriented Pt_3Ti surface, the Pt sites necessary for the adsorption of CO in both top and bridge orientation are present. However, their relative number is not the same as on Pt(111).

In this surface, every Pt atom is bound to only 4 Pt atoms in the surface plane in contrast to the 6 Pt-Pt bonds existing in the Pt(111) surface. This has the effect of eliminating 33% of the Pt-Pt bridge sites on the alloy which would otherwise exist if the same number of Pt atoms were arranged as on the Pt(111) surface. On the $\text{Pt}_3\text{Ti}(100)$ surface, neither the "short" Pt-Pt bridge sites nor Pt 4-fold sites exist. Pt and Ti atoms are arranged in a checkerboard pattern and only mixed 2-fold (Pt-Ti) and mixed 4-fold sites (2Pt and 2Ti) exist.

These changes in the number of specific sites may have important effects in CO adsorption. In the $\text{Pt}_3\text{Ti}(111)$ case, the reduction in the number of bridge sites may explain the experimental observation that the area of the CO TDS peak is only 0.5 of the peak area relative to $\text{Pt}(111)$, instead of the expected 0.75 if only the geometrical area occupied by Ti atoms is taken into account. In this case, the effect of the dispersion of the Ti atoms is to block a fraction of the surface which is larger than the fraction geometrically occupied by Ti. The suppression of the Pt 2-fold and 4-fold sites on the $\text{Pt}_3\text{Ti}(100)$ surface may cause the suppression of the high temperature CO TDS peak typical of polycrystalline and (100) oriented platinum (Fig. 8). This peak is generally attributed to CO adsorbed on Pt 4-fold sites, as for example shown in work of Doyen and Ertl (47) and of Barteau, et al. (42). However, on the $\text{Pt}_3\text{Ti}(100)$ face, as well as on (100) facets on the Pt_3Ti polycrystalline surface, Pt 4-fold sites do not exist. According to the calculations of Mehandru, et al. (24), the adsorption of CO on mixed Pt-Ti 4-fold sites is energetically unfavorable in comparison to adsorption on top of the Ti sites. Therefore, the site that is related to the high temperature CO TDS peak on Pt surfaces does not exist on Pt_3Ti , and only the low temperature peak should be observed, in agreement with the results (Fig. 8). It appears, therefore, that most aspects of the CO TDS spectra for the alloy surfaces can be explained by purely geometrical "ensemble" effects.

Considerations based on pure ensemble type effects cannot, however, explain the shift of the CO TDS peak temperature observed on $\text{Pt}_3\text{Ti}(111)$ in comparison to $\text{Pt}(111)$. Assuming that this peak is

produced by CO molecules desorbing only from Pt sites, the shift of the maximum of the peak for $\text{Pt}_3\text{Ti}(111)$ in comparison to $\text{Pt}(111)$ (Fig. 7) amounts to 50 degrees and corresponds to a lowering of the activation energy to desorption from platinum sites on the alloy surface. This energy can be estimated as 14% lower on the $\text{Pt}_3\text{Ti}(111)$ surface assuming that the desorption process can be described by an Arrhenius type equation (16). The adsorption energy at zero coverage has been estimated as ca. 28 kcal/mole for CO on $\text{Pt}(111)$ (33,35,37) and can, therefore, be estimated to be ca. 24 kcal/mole for $\text{Pt}_3\text{Ti}(111)$. This value will be considerably smaller for finite coverages since in both the Pt_3Ti and Pt surface CO desorbs with a second order kinetics, i.e. the intermolecular interaction is repulsive. Dipole-dipole interactions may play a role in the coverage dependence of the bond energy, but since the temperature of the maximum in the CO TDS peak does not vary even for an equal coverage on the alloy and pure Pt (Fig. 7), it is a reasonable assumption that the CO-CO repulsion due to dipole-dipole effects is approximately the same on both surfaces. Therefore, to account for the reduced adsorption energy of CO on Pt_3Ti , it appears necessary to invoke the existence of ligand effects, that is of modifications of the Pt electronic properties due to the intermetallic bond.

According to Brewer (1), the stability of the Pt-Ti bond (as well as that of the bond of other alloys of Pt with metals of the IVB and VB group) can be explained in terms of the interaction of electrons of the d orbitals from both metals. Specifically, d electrons from Ti (d^3s) would combine with empty Pt d orbitals (d^7sp) to form a filled alloy

d-band. As a consequence, platinum in the alloy would have fewer atomic-like d-orbitals available for CO bonding. The possibility of such an electronic effect is entirely consistent with the UPS results that show a modification of the structure of the valence band in Pt_3Ti indicative of rehybridization. The XPS data also suggest a charge transfer between Pt and Ti (48). CO adsorption on the (100) and (111) faces of Pt_3Ti has been object of a theoretical study (24) which takes into account the modification of the Pt orbitals due to the intermetallic bonding. The calculation predicts a decrease in the binding energy of the CO molecules bound to Pt atoms in the alloy surface (this decrease occurs only if the Ti sites are occupied by a small electropositive adsorbate, such as O). The calculations also predict that CO should be adsorbed parallel to the surface with the oxygen end on the Ti sites. The calculation indicates weakening of the C-O bond and a low activation barrier to dissociation of the molecule at the Ti sites. All of these expectations of the theory are consistent with our experimental observations.

Considering the results for H_2 adsorption, the effect of alloying on the adsorptive properties of Pt and Ti atoms in the surface is more complex than in the case of CO. A basic point here is that hydrogen has to be dissociated in order to be adsorbed and must recombine in order to desorb. Both dissociation and recombination phenomena may require more than a single atomic site: an ensemble of 3 Ti atoms has been reported as the site needed to dissociate H_2 on Ti(0001) (49) and steps and defects in general are reported necessary for H_2 dissociation on Pt (33). Since Pt and Ti are interspersed in an ordered fashion on

the Pt_3Ti surfaces, certain types of sites are not available: no Pt-Pt or Ti-Ti nearest neighbor pairs are present on the (100) surface plane; on the (111) plane no Ti-Ti pairs exist, although Pt-Pt pairs and 3-fold Pt sites exist. Because of this structure, on both (100) and (111) surfaces, a hydrogen atom bonded to titanium can only be desorbed either after recombination with one previously adsorbed on Pt or after moving from titanium to a platinum site. Another basic point which one must consider for hydrogen adsorption studies by TDS is that in TDS one observes only the hydrogen desorbing from the surface, which does not necessarily represent the amount of hydrogen adsorbed on the surface. Unlike the CO adsorption experiments, AES, XPS and UPS were not useful (in our experiments) in determining the coverage (or absence) of hydrogen on the Pt_3Ti surfaces. Thus, the fundamental observation we made related to hydrogen adsorption, that little or no hydrogen was observed to desorb from any of the well-annealed stoichiometric Pt_3Ti surfaces, does not enable us to distinguish between the possibilities (1) that hydrogen is not chemisorbed on the Pt_3Ti surface at room temperature or (2) that hydrogen adsorbed on Pt_3Ti surfaces at room temperature is not desorbed by flashing the surface temperature to ca. 900 K. As these two possibilities lead to essentially diametrically opposed conclusions regarding the interaction of hydrogen with the Pt_3Ti surface, a direct determination of hydrogen coverage (or absence) on the surface by another spectroscopy is required before these results can be related to the surface chemistry of Pt_3Ti . Having made this disclaimer, we feel it is reasonable to put forth some speculation on what these results may indicate about Pt_3Ti surfaces.

If we attempt to generalize the CO adsorption results, it seems that the Pt and Ti atoms in the alloy surface retain much of the chemical character they have in the pure metal, i.e. CO is still adsorbed molecularly on Pt sites and dissociatively on Ti sites. The details of the interaction with the adsorbate, such as the binding energy on site geometry, are the aspects of the chemistry that are modified by alloying. By analogy then, one might expect the hydrogen interaction with Pt and Ti atoms in the alloy surface to retain the essential character of the interaction in the pure metals, i.e. strong interaction with Ti, forming a hydride type bond, and possibly absorption of hydrogen into the bulk. It is possible that the "clean" annealed surface of Pt_3Ti (already) has hydrogen atoms adsorbed on Ti sites, due to the difficulty of detecting hydrogen while it is on the surface. Occupation of Ti sites may make it difficult to dissociate hydrogen on the alloy surface by eliminating suitable unoccupied site pairs, as discussed above. Because of the hydride nature of the Ti-H bond, and the fact the titanium-transition-metal alloys are known to form bulk hydrides, it is also possible that hydrogen adsorbed onto Pt_3Ti preferentially dissolves into the bulk rather than desorbing on heating. The progressive decrease in the quantity of hydrogen desorbing from the surface as the sputtered surface was annealed at progressively higher temperatures tends to favor the site-elimination interpretation. The sputtered surface was Ti rich (relative to Pt_3Ti) and yet the largest quantity of hydrogen was observed from this surface. If hydrogen had a tendency to absorb rather than desorb, it should have happened on this surface as well as the annealed surface.

Annealing eliminated defects and restored the stoichiometry and pair-site distribution to that in Fig. 1. During the annealing/cooling stage Ti sites may become saturated with hydrogen by interaction with the relatively high background pressure (ca. 10^{-9} torr) of hydrogen in our UHV system, and this Ti self-poisoning may make it difficult to dissociate hydrogen to cover the Pt sites. A residual hydrogen effect on the properties of metals has been discussed at length by Paal and Menon (50). Menon and coworkers have suggested that residual hydrogen plays a role in the SMSI effect with Pt/TiO₂, and our results with hydrogen on Pt₃Ti, with the foregoing interpretation of these results, are consistent with many of the effects of residual hydrogen described by Paal and Menon.

Finally, we suggest some similarities in the properties of the Pt₃Ti surface with the SMSI-type systems such as Pt supported on reduced TiO₂. According to Tauster, et al. (6,7), SMSI systems are characterized by the lack of adsorption of CO and H₂ at near-ambient temperature. The Pt₃Ti surface qualified only in part as having SMSI-type adsorptive properties since, although H₂ adsorption appears to be suppressed on annealed surfaces, CO adsorption is still present. The shift towards low temperatures of the CO TDS peak is, however, indicative of a lower adsorption energy, so that the properties of the Pt₃Ti surface can be seen as intermediate between those of pure Pt and of Pt/reduced TiO₂. When the Pt₃Ti surface is partly oxidized, the formation of CO₂ upon exposure to CO is a reaction which does not occur on Pt nor on titanium oxide. This observation points towards a special synergic effect of surfaces where moieties of oxidized Ti and active

metal (Pt) coexist, as suggested by some recent studies of the SMSI effect (9,10).

5. CONCLUSION

The structure of the $\text{Pt}_3\text{Ti}(111)$ and (100) surfaces are formed by simple truncation of the bulk lattice. These surfaces consist of ordered arrays where both Pt and Ti atoms are present with a known distribution of adsorption sites of different types, e.g. Pt-Pt and Pt-Ti pair sites, 3-fold Pt sites, etc. We found that CO was adsorbed molecularly on Pt sites while it was dissociated on Ti sites. At sufficiently low temperature, there was evidence of a pre-dissociated molecular state of CO on Ti sites indicative of an O-end down (i.e. CO molecule lying parallel to surface plane) geometry. CO adsorbed on Pt sites on the alloy surface has a lower binding energy than on pure Pt. This result can be interpreted in terms of both ligand and ensemble effects. Little or no hydrogen was observed to desorb from annealed stoichiometric alloy surfaces. Unfortunately, we could not distinguish experimentally between the possibilities: 1.) that hydrogen does not chemisorb on the alloy surface at room temperature; 2.) that hydrogen adsorbed on the alloy surface does not desorb from the surface upon flashing to 900 K. Some similarities can be found in the behavior of Pt_3Ti and SMSI-type systems such as Pt supported on TiO_2 . These similarities suggest that the Pt-Ti bond may play an important role in the chemical properties of a system where both metallic platinum and oxidized titanium interact with gases. However, the fact that the Pt_3Ti surface adsorbs CO at room temperature, in contrast with the properties of SMSI type systems, indicates that the formation of a binary alloy cannot be taken as the primary factor causing the SMSI effect.

ACKNOWLEDGMENT

This work was supported in part by funds from Consiglio Nazionale delle Ricerche (Italy) and by the Assistant Secretary for Fossil Energy, Office of Fuel Cells, Advanced Concepts Division of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098.

REFERENCES

1. Brewer, L. in "Phase Stability in Metals and Alloys," P. Rudman, J. and P.I. Jaffee, eds., p. 39, McGraw-Hill, New York, 1967.
2. Ross, P.N., Electric Power Research Institute, Palo Alto, Calif. Report EM-1553, Sept. 1980.
3. Spencer, M.S., Surface Science, 145, 145 (1984).
4. VanSanten, R.A. and Sachtler, W.M.H., J. Catalysis, 33, 202 (1974).
5. Moran-Lopez, J.L. and Falicov, L.M., Phys. Rev. B., 18, 2542 (1978).
6. Tauster, S.J. and Fung, S.C., J. Catalysis 55, 29 (1978).
7. Tauster, S.J., Fung, S.C. and Garten, R.L., J. Amer. Chem. Soc. 100, 170 (1978).
8. Demmin, R.A., Ko, C.S. and Gorte, R.J., J. Phys. Chem. 89, 1151, (1985).
9. Resasco, D.E. and Haller, G.L., J. Catal. 82, 279 (1984).

10. Sadeghi, H.R. and Henrich, V.E., J. Catal. 87, 279 (1980).
11. Bardi, U., Torrini, M., Zanazzi, E., Rovida, G., Maglietta, M., Ross, P.N. and Van Hove, M.A., Proc. 1st Intern. Conf. on Structure of Surfaces, Berkeley 1984.
12. Bardi, U. and Ross, P.N., Surf. Sci., 146, L555 (1984)
13. Bardi, U. Somorjai, G.A. and Ross, P.N., J. Catalysis, 85, 272 (1984).
14. Krautwasser, P., Bhan, S. and Schubert, K., Z. Metallkde., 59, H9 (1968).
15. Kevan, S., Ph.D Thesis, Univ. of California, LBL 11017, May 1980.
16. Redhead, P.A., Vacuum, 12, 203 (1962).
17. Biberian, J.P. and Somorjai, G.A., Appl. Surf. Sci., 2, 352 (1979).
18. Shimizu, H., Ono, M. and Nakayama, K., Surf. Sci., 36, 817 (1973).
19. Oechsner, H., Appl. Phys., 8, 185 (1975).
20. Davis, G., Natan, M. and Anderson, K.A., Surf. Sci., 150, 321 (1983).
21. Bardi, U. and Ross, P.N., J. Vac. Sci. Technol., A2, (1984) p. 1467.
22. Netzer, F.P. and Matthew, J.A.D., J. Electron Spectroscopy and Related Phenomena, 16, 50 (1974).
23. Norton, P.R., Goodale, J.W. and Selkirk, E.B., Surf. Sci., 83, 189 (1979).

24. Mehandru, S.P., Anderson, A.B., and Ross, P.N., to be published.
25. Meschter, P.J. and Worrell, W.L., Met. Trans. 7A, 299 (1976).
26. Gallon, T.E., Surf. Sci., 17, 486 (1969).
27. Kelley, M.J. and Ponec, V., Progress in Surf. Sci., 11, 139 (1981).
28. Sachtler, W.M.H., Le Vide, 164, 67 (1973).
29. Sachtler, W.M.H. and Van Santen, R.A., Applications of Surf. Sci., 3, 121 (1979).
30. Eastman, D.E., Solid State Comm., 10, 1033 (1972).
31. Fukuda, Y., Lancaster, G.M., Honda, F. and Rabelais, J.W., J. Chem. Phys., 68, 3447 (1978).
32. Bignolas, J.B., Bujor, M. and Bardolle, J., Surf. Sci., 24, L453 (1971).
33. Collins, D.N. and Spicer, W.E., Surf. Sci., 69, 85 (1977).
34. Winterbottom, W.L., Surf. Sci., 36, 195 (1973).
35. Ertl, G., Neumann, M. and Streit, K.M., Surf. Sci., 64, 393 (1977).
36. Crossley, A. and King, D.A., Surf. Sci., 95, 131 (1980).
37. McCabe, R.W. and Schmidt, L.D., Surf. Sci., 66, 101 (1982).
38. Garfunkel, R. and Somorjai, G.A., J. Phys. Chem., 86, 312 (1982).

39. Lambert, R.M. and Comrie, C.M., Surf. Sci., 46, 61 (1974).
40. Shigeishi, P.A. and King, D.A., Surf. Sci., 58, 379 (1976).
41. Nishiyama, Y. and Wise, H., J. Catalysis, 32, 62 (1974).
42. Barteau, M.A., Ko, E.J. and Madix, R.J., Surf. Sci., 102, 99 (1981).
43. Schwarz, J.A., Polizzotti, R.S. and Burton, J.J., J. Vacuum Sci. Technol., 1, 457 (1977).
44. Christmann, K., Ertl, G. and Pigned, T., Surf. Sci., 60, 365 (1976).
45. Christmann, K. and Ertl, G., Surf. Sci., 54, 365 (1976).
46. Fischer, T.E., Kelemen, S.R. and Polizzotti, R.S., J. Catalysis, 69, 345 (1981).
47. Doyen, G. and Ertl, G., Surf. Sci., 43, 197 (1974).
48. Derry, G.N. and Ross, P.N., Solid State Comm., 52, 151 (1984).
49. Cremaschi, P. and Whitten, J.L., Surf. Sci., 112, 265 (1981).
50. Paal, Z. and Menon, P.C., Catal. Rev. Sci. Eng., 25 (2), 229 (1983).

Table 1. Composition of the Single Crystal and Polycrystalline Pt₃Ti Surfaces, as Determined by AES.

Surface Type	Ti(387)/Pt(237) dN/dE	Composition (% Ti)
Pt ₃ Ti(111)	1.7	26%
Pt ₃ Ti(100)	2.1	31% [†] or 47% [‡]
Pt ₃ Ti(polycrystalline)	1.9	28%

[†]Composition averaged over first two layers.

[‡]Composition of outermost layer calculated from observed AES ratio using the two-layer Gallon equation (26) assuming a pure Pt second layer.

FIGURE CAPTIONS

- Fig. 1. Bulk truncation models for the structure of the (a) $[100]$ and (b) $[111]$ oriented Pt_3Ti surface.
- Fig. 2. Comparison of the UPS valence spectrum of the $\text{Pt}_3\text{Ti}(111)$ and $\text{Pt}(111)$ surfaces.
- Fig. 3. UPS valence spectrum for $\text{Pt}(111)$ and $\text{Pt}_3\text{Ti}(111)$ after saturation with CO.
- Fig. 4. Oxygen 1s XPS spectrum on the $\text{Pt}_3\text{Ti}(111)$ surface: (top) clean surface, (center) after exposure to CO, (bottom) after flash desorption of CO.
- Fig. 5. High resolution O 1s XPS spectrum on the $\text{Pt}_3\text{Ti}(111)$ surface after exposure to CO (a) and after CO thermal desorption (b).
- Fig. 6. Comparison of the O 1s peak after exposure of the $\text{Pt}_3\text{Ti}(111)$ surface at (a) 228 K and (b) 313 K.
- Fig. 7. Comparison of the TDS spectrum after saturation with CO of the $\text{Pt}_3\text{Ti}(111)$ and of the $\text{Pt}(111)$ surface.
- Fig. 8. Comparison of the TDS spectra observed after saturation with CO of the three types of CO surfaces studied.
- Fig. 9. CO_2 thermal desorption after saturation with CO from (1) clean polycrystalline Pt_3Ti and (2) partially oxidized polycrystalline Pt_3Ti .
- Fig. 10. a) Evolution of the H_2 TDS spectrum for successive pre-annealing of the $\text{Pt}_3\text{Ti}(100)$ surface, curve 1: after pre-annealing at 623 K, curve 2: after pre-annealing at 973 K, curve 3: after pre-annealing at 1093 K.
- Fig. 10. b) H_2 TDS spectrum from the $\text{Pt}_3\text{Ti}(111)$ surface. Curve 1: Surface pre-annealed at 573 K; curve 2: surface pre-annealed at 1198 K.

XBL 858-11665

Fig. 1

XBL 844-1327

Fig. 2

XBL 844-1328

Fig. 3

XBL 858-3298

Fig. 4

XBL 858-3297

Fig. 5

XBL 858-3300

Fig. 6

XBL 858-3295

Fig. 7

XBL 858-3535

Fig. 8

XBL 857-11657

Fig. 9

XBL 857-11656

Fig. 10a

XBL 857-11655

Fig. 10b

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

*LAWRENCE BERKELEY LABORATORY
TECHNICAL INFORMATION DEPARTMENT
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720*