Lawrence Berkeley National Laboratory

Recent Work

Title

HOLE MOBILITY IN MODULATION-DOPED HETEROSTRUCTURES: GaAs-AlGaAs

Permalink

<https://escholarship.org/uc/item/5q20w7gz>

Author

Walukiewicz, W.

Publication Date

1984-12-01

LBL-18832
c.2

LBL-18832
Preprint

RECEIVED
LAWRENCE
BERKELEY LABORATORY

FEB 11 1985

LIBRARY AND
DOCUMENTS SECTION

Submitted to Physical Review
Letters

HOLE MOBILITY IN MODULATION-
DOPED HETEROSTRUCTURES:
GaAs-AlGaAs

W. Walukiewicz

December 1984

CCM

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.*

Lawrence Berkeley Laboratory
University of California
Berkeley, California 94720

Prepared for the U.S. Department of Energy
under Contract DE-AC03-76SF00098

**Center
for
Advanced
Materials**

LBL-18832
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

HOLE MOBILITY IN MODULATION-DOPED
HETEROSTRUCTURES: GaAs-AlGaAs

Wladyslaw Walukiewicz

Center for Advanced Materials
Lawrence Berkeley Laboratory
University of California
Berkeley, CA 94720 U.S.A.

Abstract

A comprehensive model for the hole mobility in a two-dimensional hole gas confined at a modulation-doped heterostructure interface is proposed. All the major scattering processes in the two uppermost spin subbands are taken into account. The calculations are substantially simplified by effects of a strong free hole screening. The model explains quantitatively experimental results of the temperature dependence of the hole mobility. It is shown that at large spacer widths, the predicted mobility limit exceeds 2×10^5 cm/Vs and is entirely determined by acoustic phonon deformation potential scattering.

Introduction

Recent years have witnessed an unprecedented growth of interest in two-dimensional electron gas systems. A number of new phenomena such as fractionally quantized Hall effect¹ and extremely high electron mobilities^{2,3} have been observed for the electron gas confined at the interface of GaAs-AlGaAs modulation-doped heterostructure (MDH)^{4,5}. In this system, the highest reported mobilities exceed 2×10^6 cm²/Vs². At present, the role of different scattering processes limiting the two-dimensional electron gas mobility is quite well understood⁶⁻⁸.

Considerably much less effort has been directed towards the study of two-dimensional hole systems, although it is believed that such systems are interesting not only from the point of view of fundamental physics, but also because they may have important practical applications⁹. In a number of recently published papers, various aspects of the two-dimensional hole gas in GaAs-AlGaAs have been studied¹⁰⁻¹⁴. It has been shown that improved modulation doping techniques lead to increased hole mobilities^{11,14}. To date the highest reported hole mobility is $\sim 9.7 \times 10^4 \text{ cm}^2/\text{Vs}$ at 4.2 K¹⁴. Although experimental data on hole mobility is accumulating, there has been no attempt to formulate a theoretical model which could explain the existing data and predict hole mobility limits in p-type MDH's.

In this paper we show for the first time that the present understanding of the electronic structure of p-type GaAs-AlGaAs MDH's allows the formulation of a relatively simple model of the hole mobility. The model assumes that the holes are confined in a triangular quantum well on the GaAs side of the interface. A lack of the inversion symmetry and strong spin-orbit coupling in this system results in splitting of the fourfold degenerate valence band into a series of subbands. The two uppermost heavy hole spin subbands are degenerate for $\vec{k} = 0$ and are well separated from the lower lying subbands so that for typical hole concentrations, only the highest subbands are occupied¹³. Because these two subbands have different spins, there exists no substantial intersubband scattering for all the important scattering processes. Scattering rates can be calculated separately for each subband. They can be combined according to the well-known formula for the total Hall mobility¹⁶. Recent theoretical results show that in a limited energy range, these two highest subbands are parabolic¹³, and therefore, they can be characterized by effective

masses m_1^* and m_2^* . Adapting results of Ref. 15, one finds that the z-component of the envelope wave function for the hole gas confined in a triangular well can be written in the form:

$$\chi_h(z) = \frac{z \exp\left(-\frac{b_h z}{2}\right)}{\left(\frac{b_h}{2}\right)^{3/2}} \quad (1)$$

where
$$b_h^3 = b_{1h}^3 + b_{2h}^3 \quad (2)$$

$$b_{ih}^3 = \frac{33\pi m_i^* e^2}{2 \epsilon_s \hbar^2} p_i \quad (3)$$

p_i ($i = 1, 2$) is the hole concentration in the i -th subband.

Scattering Rates

There are a number of scattering processes which have to be considered for a two-dimensional hole gas in MDH's. In addition to all the scattering mechanisms important for n-type MDH⁸, one also has to take into account optical phonon deformation potential scattering. This mechanism plays an important role in limiting high-temperature hole mobility in bulk GaAs¹⁶.

The long range electrostatic potentials are screened by the two-dimensional hole gas. The screening parameter is given by the expression:

$$q_s = \frac{e^2(m_1^* + m_2^*)}{\epsilon_s \hbar^2} (1 - e^{-\alpha}) \quad (4)$$

where
$$\alpha = \frac{\pi \hbar^2 (p_1 + p_2)}{(m_1^* + m_2^*) kT}$$

For a degenerate hole gas at low temperatures, $\alpha \gg 1$ and,

$$q_s = \frac{e^2 (m_1^* + m_2^*)}{\epsilon_s \hbar^2} \quad (5)$$

It should be noted that q_s is much larger for holes than for the much lighter electrons. Using the aforementioned approximations, it has been found that the acoustic phonon deformation potential scattering rate for holes has the same form as the one for electrons^{17,8} with b_0 replaced by b_h and the conduction band deformation potential replaced by $\sqrt{5/8} E_{AC}$ where E_{AC} is an effective valence band deformation potential¹⁶. The factor $\sqrt{5/8}$ accounts for the p-type symmetry of the valence band Bloch functions. The deformation potential relaxation time does not depend on the hole energy. It weakly depends on the hole concentration through the parameter b_h . In contrast to the two-dimensional electron gas⁸, the piezoelectric acoustic phonon scattering of holes does not contribute to the total scattering. This is the result of very efficient screening of this electrostatic interaction. Alloy disorder scattering is a process resulting from a finite penetration of the hole gas into the AlGaAs layer. Just as for the electron gas, this scattering process depends on the valence band offset, V_{oh} , and the total free carrier concentration, $p_1 + p_2$ ⁸.

Although in MDH's the ionized impurity scattering is substantially reduced, it still plays a significant role in limiting the low temperature mobility. Similarly as in the case of a two-dimensional electron gas, the holes in p-type MDH's are scattered by remote, ionized impurities from the highly-doped AlGaAs

region and by background impurities located in GaAs. The remote impurities are separated from the hole gas by the spacer of width "d". The width of the depletion region in highly doped AlGaAs is $(L - d) = (p_1 + p_2)/N_r$ where N_r is the remote ionized acceptor concentration. It can be shown that the remote ionized impurity scattering rate is proportional to $e^{-2qd} - e^{-2qL}$ where q is the wave vector transfer in the scattering process. Therefore the largest contribution to the scattering comes from the terms with $q < 2d$. For the spacer width, $d \geq 100 \text{ \AA}$, one obtains $q_s \gg q$ and $b_h \gg q$ and the expression for the microscopic mobility has the form:

$$\frac{1}{\mu_r} = \frac{\pi^{\frac{1}{2}} \hbar^4 N_r (m_1^* + m_2^*)^{-2} (1 - e^{-\alpha})^{-2} E^{-3/2}}{8 \sqrt{2} \sqrt{m_1^*}} \left(\frac{1}{d^2} - \frac{1}{L^2} \right) \quad (6)$$

In high quality MDH's, the concentration of residual impurities is normally very low ($\leq 10^{15} \text{ cm}^{-3}$). However, since residual background impurities are located in the immediate vicinity of the hole gas, they can still contribute to the total scattering. There is no simple analytic expression for the background impurity scattering rate¹⁸. To estimate a contribution from this scattering process at low temperatures, we have used the approach developed for n-type MDH⁸ and have adapted it to the subbands with p-type symmetry.

Optical phonon scattering plays a very important role in limiting the high temperature hole mobility. Analogous to the case of a two-dimensional electron gas⁸, it can be argued that because hole states in a wide energy range are involved in this scattering, all the features characteristic of a two-dimensional system are smeared out and the optical phonon electron mobility can be approximated by the mobility calculated for three-dimensional hole gas. Here we adopted an approach which utilizes an approximation of partially coupled valence bands¹⁹.

Results and Discussion

The valence band parameters of GaAs are not very well known. Thus, there exists substantial discrepancy between hole effective masses determined from experiments¹⁰ and those obtained from theoretical calculations¹³. The reason for this discrepancy is not clear at present although it has been suggested that it can be related to hole-hole interaction¹³. In the present paper we have adopted experimental values for the effective masses $m_1 = 0.6 m_0$ and $m_2 = 0.38 m_0$ ¹⁰. Values of the valence band offsets were adopted after Ref. 14 to be 170 meV and 210 meV for 0.48 and 0.5 Al content, respectively. It has been found that even with the highest reported²⁰ estimate for the alloy disorder scattering parameter ($V_{oh} = 0.7$ eV), the alloy disorder scattering contribution to the total scattering does not exceed 10%. Values of all the other parameters are the same as those used in Ref. 8.

The hole Hall mobility for different scattering processes is shown in Fig. 1. The inherent mobility limit is defined as a mobility determined by the intrinsic scattering processes which are always present for a specific MDH and by remote ionized impurity scattering⁸. We find that the inherent mobility is dominated by the optical phonons at high temperatures > 150 K. In the intermediate temperature range 20 - 100 K, the largest contribution to the mobility comes from the acoustic deformation potential scattering. We have found that the best agreement with experimental data is obtained when the value 6.7 eV for the deformation potential is used. This value is slightly higher than the effective deformation potential $E_{AC} = 5$ eV as given in Ref. 16 but agrees very well with the value $E_{AC} = 7$ eV as determined in Ref. 20. At the lowest temperatures $T < 10$ K, remote ionized impurity scattering sets the

inherent mobility limit. The alloy disorder and piezoelectric acoustic phonon scattering do not contribute importantly to the total scattering. The piezo-acoustic mobility is $\sim 10^7 \text{ cm}^2/\text{Vs}$ for the case presented in Fig. 1. The triangles in Fig. 1 represent experimental data of Ref. 11. At high temperatures $T > 100 \text{ K}$ when the inherent mobility limit is set by phonon scattering, the experiment agrees very well with the calculated mobility. However, at lower temperatures the experimental mobility falls below the inherent limit which is determined mostly by remote impurity scattering indicating the existence of yet another scattering mechanism. The scattering process which most likely would contribute to the scattering at low temperatures is background impurity scattering. The calculations have shown that the background impurities of concentration $4 \times 10^{15} \text{ cm}^{-3}$ resulting in a temperature independent hole mobility of $\sim 9 \times 10^4 \text{ cm}^2/\text{Vs}$ account very well for the difference between the inherent limit and the experimental data.

Spacer width dependence of the hole mobility for $\text{GaAs-Al}_{0.5}\text{Ga}_{0.5}\text{As}$ MDH with remote acceptor concentration $1.5 \times 10^{18} \text{ cm}^{-3}$ which corresponds to the case analyzed in Ref. 14 is given in Fig. 2. As can be seen, only at the lowest spacer width $\sim 100 \text{ \AA}$ is the inherent mobility limit affected by remote impurity scattering. At higher spacer widths the limit is entirely determined by acoustic deformation potential scattering. The highest experimental mobility $9.7 \times 10^4 \text{ cm}^2/\text{Vs}$ was observed for $d = 443 \text{ \AA}$ ¹⁴. The corresponding inherent mobility limit is $2.1 \times 10^5 \text{ cm}^2/\text{Vs}$ indicating a significant contribution of background scattering. The difference between the experimental and calculated mobilities can be accounted for by background impurities of concentrations $\sim 10^{15} \text{ cm}^{-3}$. It can thus be concluded that a further increase of two-dimensional hole gas mobility is expected upon a decrease in background doping. Our calculations

show that at large spacer widths, the acoustic deformation potential is the dominant scattering process at very low temperatures. Therefore the two-dimensional hole gas is an ideal system to study the effect of hole gas heating at low electric fields. This effect was predicted to occur in the electron gas at very low temperatures²¹. However, it cannot be easily detected in the two-dimensional electron gas where, unlike for holes, remote impurity scattering is always an important process limiting the low temperature electron mobility⁸.

In Fig. 2 the total hole concentration $p_1 + p_2$, and the Hall hole concentration $P_H = 1/eR_H$ are given. In general, $p_1 + p_2 \neq P_H$ and the difference between these two concentrations depends on the effective mass and the mobility ratio. We have found that the difference is quite significant for acoustic phonon limited mobilities and is becoming smaller when ionized impurity scattering is a dominant scattering process.

In conclusion, we have presented the first quantitative model to calculate the two-dimensional hole gas mobility in p-type MDH. The model accounts very well for the temperature dependence of the hole mobility in GaAs-AlGaAs MDH. It has been found that the acoustic phonon deformation potential is the dominant scattering process responsible for mobility limits at low temperatures. The model gives a value of $\sim 2 \times 10^5 \text{ cm}^2/\text{Vs}$ for the mobility limit in p-type GaAs-AlGaAs MDH at 4.2 K for the hole density $\sim 2.5 \times 10^{11} \text{ cm}^{-2}$. This result is about two times higher than the highest reported experimental values.

Acknowledgments

The author thanks Prof. E. Haller and Prof. H. Ruda for useful discussions. This work was supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Science Division of the U.S. Department of Energy under Contract DE-AC03-76SF00098.

References

1. D.C. Tsui, H.L. Stormer and H.C. Gossard, Phys. Rev. Lett. 48, 1559 (1982).
2. S. Hiyamizu, J. Saito, K. Nanbu and T. Ishikawa, Jpn. J. Appl. Phys. 22, L609 (1983).
3. J.C.M. Hwang, A. Kastalsky, H.L. Stormer and V.G. Keramidas, Appl. Phys. Lett. 44, 802 (1984).
4. R. Dingle, H.L. Stormer, A.C. Gossard and W. Wiegmann, Appl. Phys. Lett. 33, 665 (1978).
5. L.C. Witkowski, T.J. Drummond, C.M. Stanchok and H. Morkoc, Appl. Phys. Lett. 37, 1033 (1980).
6. T. Ando, J. Phys. Soc. Jpn. 51, 3900 (1982).
7. F. Stern, Appl. Phys. Lett. 43, 974 (1983).
8. W. Walukiewicz, H.E. Ruda, J. Lagowski and H.C. Gatos, Phys. Rev. B30, 4571 (1984).
9. H.L. Stormer, K. Baldwin, A.C. Gossard and W. Wiegmann, Appl. Phys. Lett. 44, 1062 (1984).
10. H.L. Stormer, Z. Schlesinger, A. Chang, D.C. Tsui, A.C. Gossard and W. Wiegmann, Phys. Rev. Lett. 51, 126 (1983).
11. H.L. Stormer, A.C. Gossard, W. Wiegmann, R. Blondel and K. Baldwin, Appl. Phys. Lett. 44, 139 (1983).
12. E.E. Mendez, W.I. Wang, L.L. Chang and L. Esaki, Phys. Rev. B30, 1087 (1984).
13. U. Ekenberg and M. Altarelli, Phys. Rev. B30, 3569 (1984).
14. W.I. Wang, E.E. Mendez and F. Stern, Appl. Phys. Lett. 45, 639 (1984).

15. F.F. Fang and W.E. Howard, Phys. Rev. Lett. 16, 797 (1966).
16. J.D. Wiley in: Semiconductors and Semi-metals, ed. R.K. Willardson and A.C. Beer (Academic Press, New York, 1975) Vol. 10, Chapt. 2.
17. P. Price, Annals of Physics 133, 217 (1981).
18. F. Stern and W. Howard, Phys. Rev. 163, 816 (1967).
19. W. Walukiewicz, L. Pawlowicz, J. Lagowski and H.C. Gatos, Proc. Conference on Semi-Insulating III-V Materials (Evian 1982), ed. Sherif Makram-Ebeid and Brian Tuck, Shiva Publishing Ltd., p. 121.
20. K. Masu, E. Tokumitsu, M. Konagai and K. Takahashi, J. Appl. Phys. 54, 5786 (1983).
21. P.J. Price, Phys. Rev. B30, 2236 (1984).

Figure Captions

Fig. 1. Temperature dependence of the hole mobility in GaAs-AlGaAs heterostructure. Points represent experimental data of Ref. 10 for the hole Hall concentration of $4.57 \times 10^{11} \text{ cm}^{-2}$ and remote acceptor concentration of $2 \times 10^{18} \text{ cm}^{-3}$.

Fig. 2. Hole mobility and concentration as functions of the spacer width for the case considered in Ref. 14 with a remote acceptor concentration of $1.5 \times 10^{18} \text{ cm}^{-3}$.

XBL 8412-5261

Figure 1.

XBL 8412-5262

Figure 2.

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720