Lawrence Berkeley National Laboratory

Recent Work

Title

Insight into 3D micro-CT data: exploring segmentation algorithms through performance metrics.

Permalink

<https://escholarship.org/uc/item/5q32w3rb>

Journal

Journal of synchrotron radiation, 24(Pt 5)

ISSN

0909-0495

Authors

Perciano, Talita
Ushizima, Daniela
Krishnan, Harinarayan
et al.

Publication Date

2017-09-01

DOI

10.1107/s1600577517010955

Peer reviewed

Insight into 3D micro-CT data: exploring segmentation algorithms through performance metrics

TALITA PERCIANO,^{a,*} DANIELA USHIZIMA,^{a,b} HARINARAYAN KRISHNAN,^a
 DILWORTH PARKINSON,^c NATALIE LARSON,^d DANIEL M. PELT,^a WES BETHEL,^a
 FRANK ZOK^d AND JAMES SETHIAN^e

^a*Computational Research Division, Lawrence Berkeley National Laboratory,*
^b*Berkeley Institute for Data Science, University of California Berkeley,* ^c*Advanced*
^d*Light Source, Lawrence Berkeley National Laboratory,* ^d*Materials Department,*
^e*University of California Santa Barbara, and* ^e*Math Department, University of*
California Santa Barbara. E-mail: tperciano@lbl.gov

Unsupervised segmentation; micro-tomography; ceramic matrix composites; image analysis

Abstract

3D micro-tomography (μ -CT) has proven to be an important imaging modality in industry and scientific domains. Understanding the properties of material structure and behavior has produced many scientific advances. An important component of the 3D μ -CT pipeline is image partitioning (or image segmentation), a step that is used to separate various phases or components in an image. Image partitioning schemes require specific rules for different scientific fields, but a common strategy consists of devising metrics to quantify performance and accuracy. The present article proposes a set of protocols to systematically analyze and compare the results of unsupervised

classification methods used for segmentation of synchrotron-based data. The proposed dataflow for Materials Segmentation & Metrics (**MSM**), provides 3D micro-tomography image segmentation algorithms, such as statistical region merging (SRM), K-means algorithm, and parallel Markov random field (PMRF), while offering different metrics to evaluate segmentation quality, confidence and conformity with standards. We assess both experimental and synthetic data, illustrating quantitative results through the **MSM** dashboard, which can return sample information such as media porosity and permeability. The main contributions of this work are: (a) to deliver tools to improve material design and quality control; (b) to provide datasets for benchmarking and reproducibility; (c) to yield good practices in the absence of standards or ground-truth for ceramic composite analysis.

1. Introduction

X-ray synchrotron facilities regularly produce terabytes of data, with imaging beam-lines commonly storing data as 2D and 3D images (Bethel *et al.*, 2015). The data volume generated daily and the variety of samples in terms of complexity and features is a challenge for effective data analysis of the experiments, particularly given frequent upgrades of the instruments brightness, resolution and throughput. Specific characteristics of the image data such as the presence of heterogeneous structures in multiple scales and their complex architecture hinder the accuracy of current image processing algorithms. Nonetheless, micro-computed tomography (μ -CT) continues to be an essential imaging technique employed for the non-destructive three-dimensional characterization of objects. This approach is widely used in academia and industry, including medical imaging, material science, electronics and geology.

In spite of the success of this imaging technique, some challenges still remain when analyzing this type of data, starting with the tomographic reconstruction and going

through all image processing steps. For example, trying alternative acquisition schemes and experimental setups and/or quantitatively evaluating reconstruction methods is still a challenge. The work described in (Ching & Gürsoy, 2017) addresses this specific topic. The authors propose software that generates complex simulated phantoms and evaluates new or existing data acquisition schemes and image reconstruction algorithms for targeted applications. Following a similar strategy, the present paper addresses the problem of comparing and evaluating different image segmentation algorithms.

Given large data rates and sizes, machine learning for data acquisition (Yang *et al.*, 2017) as well as for the automation of feature detection and extraction represents key steps into reducing data while gaining insight from μ -CT image structures. Many different categories of automated feature extraction exists (Hintermüller *et al.*, 2010; Chen *et al.*, 2012), but most of them are reliant on image segmentation techniques supported by unsupervised learning (Khanum *et al.*, 2015). Broadly used to analyze experimental data, unsupervised segmentation algorithms (Chen *et al.*, 2013) enable grouping picture elements, somewhat collecting tokens that “belong together”. Such algorithms can gather meaningful groups by searching for hidden structures from unlabeled data. Some of the advantages are dispensable training data and potential for data reduction, for example, removal of non-contributing image portions, such as background and artifacts.

Two important tasks during μ -CT data analysis are (1) selecting the best segmentation algorithm and (2) determining the best evaluation metrics. Those two choices highly impact the performance and quality of the results. Even harder to evaluate, the cases that lack ground-truth can lead to incomplete and/or ambiguous results, many times assisting only in qualitative terms. Therefore, we have employed a few strategies to evaluate image segmentation problems before we allude to the most

appropriate algorithm for a specific application, for example, through direct comparison of algorithms based on a given ground-truth (Ushizima *et al.*, 2011; Arbelaez *et al.*, 2011; Perciano *et al.*, 2016; Tassani *et al.*, 2014; Sheppard *et al.*, 2014) and combination of different algorithms (Polak *et al.*, 2012) allied to confluence analysis as an indicator of result agreement.

In this work, we propose the MSM dataflow that runs different algorithms separately, but checks for their agreement in terms of their segmentation results by using performance metrics. Suitability of metrics depends on the scientific goals of the experiment, that can be, for example, calculating porosity of a sample or counting the number of targeted objects. This article describes a multidisciplinary project involving experimental investigations of 3D micro-tomography (μ -CT) data of different materials performed at the Advanced Light Source (ALS) at the Lawrence Berkeley National Laboratory (LBNL), and development of algorithms for unsupervised image analysis, performed by investigators at the Center for Advanced Mathematics for Energy Research Applications (CAMERA), also at LBNL. We introduce a process for segmentation and analysis of 3D micro-tomography data, which offers strategies to evaluate algorithms and metrics applied to 3D micro-tomography experiments. Here, we use the proposed process to investigate geological samples and Ceramic Matrix Composites (CMCs). These examples illustrate a strategy for executing different algorithms, extracting respective criteria, and parameter ranges to arrive at an appropriate answer.

Fig. 1. Image analysis process employed for x-ray micro-tomography data included in MSM.

Previous works on micro-CT data analysis described in (Ushizima *et al.*, 2011; Ushizima *et al.*, 2012) address the problem of segmenting geological samples being studied to understand carbon sequestration – geologic storage of captured CO₂ in underground rock formations. The authors developed tools for providing precise measurements of porosity and permeability, and for visualizing pore structures.

More recently, we have focused on yet another material sample: CMCs, which are based on continuous Silicon Carbide (SiC) fibers and SiC matrices. With a high impact in industrial manufacturing, CMCs are an enabling element in the development of gas turbine engines that can operate at higher temperatures and therefore yield higher efficiency (Zok, 2016). Although there have been several recent studies related to computed tomography of CMCs, computational tools to automate and streamline image analysis are presently lacking (Bale *et al.*, 2012).

In this article we: (a) introduce an analysis pipeline with different strategies for segmentation and evaluation; (b) demonstrate the use of this process in the detection of different structures in synthetic and experimental micro-CT datasets such as geological samples, glass beads, and CMCs; and (c) make a critical assessment of the accuracy of the algorithms in determining various quantitative characteristics of the extracted

structures using general and specific metrics. Fig. 1 presents the analytical dataflow of MSM. The figure highlights the transformations that the 3D image stacks undergo before MSM can deliver the materials characteristics list. The raw μ -CT image stack passes through a preprocessing step based on 3D non-linear filtering. The preprocessed data serves as input for different segmentation algorithms (SRM, k-means and PMRF). The results from different segmentation algorithms undergo an analysis step based on both general and specific metrics. The evaluation takes into account a reference data obtained from a semi-automated segmentation process.

The remainder of the article is organized as follows. The segmentation methods for sample partitioning, and the metrics used are described in Sec. 2. In Sec. 3, we present different types of experiments using synthetic and experimental data to assess the accuracy of the results. In doing so, we show how the proposed process can be applied to evaluate different segmentation algorithms and to find the necessary metric in each case. Finally, Sec. 4 summarizes the key accomplishments of our investigation.

2. Materials and Methods

This section describes the algorithms used in each step of the proposed process pipeline: image enhancement, image segmentation, and measurements.

2.1. Image Enhancement

Image enhancement techniques ensure that input data are well-suited for a specific task, such as image segmentation or feature extraction. The challenge is to improve image quality while retaining essential information about the true structure. In the present study, we apply two main strategies: mathematical morphology (MM) (Pinoli & Debayle, 2012) and non-linear edge-preserving filtering (Tomasi & Manduchi, 1998a). Previously we developed “F3D” – a graphics-card aware image

processing plug-in for Fiji (Schindelin *et al.*, 2012) that employs MM and non-linear filters and can handle data sets whose size exceeds the amount of RAM available in the computer system (Ushizima *et al.*, 2014). Details on those techniques are out of the scope of this work.

F3D gray-level MM operators are one-pass, constant-time methods that can perform morphological transformations with structuring elements oriented in several directions. MM operators consist of two parts: (i) a reference shape or structuring element, which translates over the image, and (ii) a mechanism that defines the comparisons performed between the image and the structuring element (Van Droogenbroeck & Talbot, 1996). In this work, we use the *closing operator*, which is given by the combination of the *dilation* and the *erosion* operators (Gonzalez & Woods, 2006), to improve image contrast. The procedure involves the following steps:

1. Define a structuring element based on the shape of the geometry to be detected in the image;
2. Apply the *closing* operator using the structuring element defined in step 1 (Fig. 2 (b));
3. Subtract the input image from the result obtained in step 2 (Fig. 2 (c));
4. Subtract the result obtained in step 3 from the input image (Fig. 2 (d)).

Fig. 2. Example of contrast improvement using F3D with a circle of size 20 pixels as structuring element. (a) Original region of interest (b) Result of step 2 (c) Result of step 3 (d) Result of step 4.

Additionally, we apply a non-linear image denoising filter with edge-preserving characteristics (Tomasi & Manduchi, 1998b; Bethel, 2012). A weighted average of nearby pixels replaces each intensity value of the original image. This filter takes into account differences in intensity values in neighboring pixels to preserve edges while smoothing. Consequently, the influence between neighboring pixels depends on the similarity of their intensity values. It is defined as $\hat{I}_p = \frac{1}{N_p} \sum_{q \in S_p} I_q G_{\sigma_r}(|I_p - I_q|) G_{\sigma_s}(\|p - q\|)$, where $N_p = \sum_{q \in S_p} G_{\sigma_r}(|I_p - I_q|) G_{\sigma_s}(\|p - q\|)$, I is the input image, G_r and G_s are spatial Gaussian kernels, p and q are pixel locations, and S is the neighborhood.

The parameter G_r , called range kernel, smooths differences within intensities, while the parameter G_s , referred to as spatial kernel, smooths differences within coordinates. When the value of G_r increases, the filter comes closer to a Gaussian convolution. The value of the spatial kernel is directly proportional to the size of the features to be smoothed. Fig. 3 shows an example of bilateral filter applied to an image varying both parameters.

Fig. 3. Example of bilateral filter applied to an image. (a) Original image (b) Bilateral filter with $G_r = 50$ and $G_s = 3$ (c) Bilateral filter with $G_r = 250$ and $G_s = 3$ (d) Bilateral filter with $G_r = 25$ and $G_s = 3$ (e) Bilateral filter with $G_r = 25$ and $G_s = 30$

Upon application of the enhancement process, the images present improved contrast and reduced noise, making them more suitable for use as inputs to the image

segmentation algorithms, described in the next section.

2.2. Unsupervised segmentation

In this section we present the three algorithms that are currently part of **MSM**: SRM, k-means and PMRF. SRM and k-means, are among the most commonly used image segmentation strategies, yet due to the sensitivities of these methods the results can vary depending both on the dataset and parameters used. Additionally we evaluate PMRF a novel extension to SRM as another candidate to produce equivalent results, but addressing performance issues that traditional SRM and k-means lack.

2.2.1. Statistical Region Merging (SRM) Nock and Nielsen (Nock & Nielsen, 2004) proposed an efficient region growing segmentation algorithm based on adaptive statistical threshold merging predicate on intensity levels. As in other region segmentation algorithms, it aims at associating a pixel to a region using a similarity criteria.

The iterative process starts with one region per pixel, followed by merging phases after the calculation of a statistical test that take neighboring regions into account. This test considers an ascending order of intensity differences and checks if the mean intensities are sufficiently similar to be merged. The merging predicate, $\mathcal{P}(R_i, R_j)$, regulates whether the observed regions R_i and R_j belong to the same statistical region. The merging predicate assumes that the pixels from a statistical region have the same expectation, and it is represented as $\mathcal{P}(R_i, R_j) = \begin{cases} \text{true} & \text{if } |\bar{R}_i - \bar{R}_j| \leq b(R_i) + b(R_j) \\ \text{false} & \text{otherwise} \end{cases}$, where the right-hand side of equation is the center value between R_i and R_j , and it is used as a merging threshold. The variable b is a function of g (the largest possible intensity value): $b(R) = g\sqrt{\frac{1}{2Q|R|} \left(\frac{\ln |S_l|}{\delta} \right)}$. S_l is the set of regions with l pixels, δ is the probability error and takes values in $0 \leq \delta \leq 1$. Q stands for the number of random variables, which somewhat translates the complexity of the scene and controls

the coarseness of the segmentation. In other words, Q roughly estimates the number of regions in the image. The function $|\cdot|$ represents the number of elements in the set of pixels. Even though the default μ -CT image output is 32-bit, we propose the use of $g = 255$, therefore the methods take images in 8-bit as input, given that we empirically verified that this is enough bit depth to represent more than 95% of the relevant intensity values from the original image.

2.2.2. K-Means The k-means algorithm (Macqueen, 1967) is a non-hierarchical unsupervised clustering method that classifies the input data points into k classes based on the inherent distance between point pairs. The algorithm assumes that the data features form a vector space and tries to find natural clusters, iteratively minimizing the distance between the points and a set of centroids $\mu_i \forall i = 1 \dots k$. The minimization function is given by $V = \sum_{j=1}^k \sum_{x_i \in S_j} (x_i - \mu_j)^2$, where there are k clusters $S_j, i = 1, 2, \dots, k$ and μ_j is the centroid of all points $x_i \in S_j$. The general k-means algorithm for image segmentation consists of the following steps:

1. Compute the histogram of pixel intensities;
2. Initialize the centroids with k random intensities;
3. Repeat the following steps until the cluster labels of the image converge:
 - (a) Cluster the pixels based on the distance of their intensities from the centroid intensities: $c_j = \arg \min_j \|x_i - \mu_j\|^2$, add i to S_j
 - (b) Compute the new centroid of each cluster: $\mu_j = \frac{1}{|S_j|} \sum_{i \in S_j} x_i$,

where k is the preferred number of clusters (usually set empirically and higher than the number of phases), i iterates over all intensities, j iterates over all centroids and μ_i are the centroid intensities.

2.2.3. Parallel Markov Random Field (PMRF) In (Perciano *et al.*, 2016) we proposed a graph-based model called PMRF, which exploits the Markov random fields (MRF) framework to segment images. PMRF makes use of the Linear and Parallel (LAP) method (Mizrahi *et al.*, 2014) – a graph partitioning algorithm for MRF parameter estimation. In a MRF model, the optimization process uses a global energy function to find the best solution to a similarity problem, such as the best pixel space partition or the best matching. The energy function consists of a data term and a smoothness term. For image segmentation, we use the mean of the intensity values of a region as the data term. The smoothness term takes into account similarities between regions. The goal is to find the best labeling for the regions, so that the similarity between two regions with the same labels is optimal for all pixels (Mahapatra & Sun, 2012).

Given an image represented by $\mathbf{y} = (y_1, \dots, y_N)$, where each y_i is a region, we seek a configuration of labels $\mathbf{x} = (x_1, \dots, x_N)$ where $x_i \in L$ and L is the set of all possible labels, $L = \{0, 1, 2, \dots, M\}$. The MAP criterion (Li, 2013) states that one wants to find a labeling $\mathbf{x}^*$ that satisfies $\mathbf{x}^* = \underset{\mathbf{x}}{\operatorname{argmax}} \{P(\mathbf{y}|\mathbf{x}, \Theta)P(\mathbf{x})\}$, which can be rewritten in terms of the energies (Li, 2013) as $\mathbf{x}^* = \underset{\mathbf{x}}{\operatorname{argmin}} \{U(\mathbf{y}|\mathbf{x}, \Theta) + U(\mathbf{x})\}$.

The prior probability $P(\mathbf{x})$ is a Gibbs distribution, and the joint probability distribution is $P(\mathbf{y}|\mathbf{x}, \Theta) = \prod_i P(y_i|\mathbf{x}, \Theta) = \prod_i P(y_i|x_i, \theta_{x_i})$, where $P(y_i|x_i, \theta_{x_i})$ is a Gaussian distribution with parameters $\theta_{x_i} = (\mu_{x_i}, \sigma_{x_i})$ and $\Theta = \{\theta_l | l \in L\}$ is the parameter set.

The general PMRF segmentation framework works as follows. Initially, the input image passes through a feature extraction algorithm or an oversegmentation method to transform the voxel-domain image data into a less noisy representation. Next, the resulting regions compose the nodes of a graph representation of the image. The graph partitioning process is done using the LAP algorithm, allowing simultaneous parallel parameter estimation and optimization for each subgraph. This parallelization strategy makes PMRF scalable, i.e. suitable for large experimental datasets. Finally, the

iterative optimization process aggregates the graph nodes reaching an optimal segmentation through expectation maximization (EM) and maximum a posteriori (MAP) calculations.

2.3. Quantification Metrics

In this section we describe metrics used to assess the accuracy of the unsupervised segmentation methods as applied to the μ -CT datasets.

2.3.1. General metrics Our pipeline uses two sets of general evaluation measurements: binary segmentation metrics and material metrics.

The binary segmentation metrics consist of *precision*, *recall* and *accuracy*. Precision represents the proportion of voxels correctly classified as material, i.e., measures the performance of the algorithm with respect to false positives. It is given by $precision = \frac{TP}{TP+FP}$, where TP stands for True Positives, and FP for False Positives. Recall measures the performance of the segmentation algorithm with respect to false negatives (FN), and it is given by $recall = \frac{TP}{TP+FN}$. Finally, the accuracy gives the proportion of true segmentations among the total number of voxels. It is given by $accuracy = \frac{TP+TN}{TP+TN+FP+FN}$, where TN stands for True Negatives.

We calculate two additional metrics related to the material of the sample: the volume of the solid component of the sample, shown in cm^3 , and the porosity of the material, given by $\phi = \frac{V_v}{V_v+V_s}$, where V_v is the volume of the void space (empty space) and V_s is the volume of the solid component.

All the metrics described in this section are calculated with respect to the reference data of each analyzed sample.

2.3.2. Characteristics of Fiber Beds To evaluate the CMC samples with fiber beds, in addition to the general metrics described in the previous section, we use more specific metrics to obtain additional scientific information about the samples. In a cross-section of a 3D μ -CT stack for these samples, each fiber is contained within a polygonal cell whose boundaries are defined by the perpendicular bisectors of lines joining the centroid of that fiber with the centroids of its nearest neighboring fibers. A Voronoi tessellation (Aurenhammer, 1991) defines these cells. Fig. 4 shows an example of a Voronoi tessellation for a small region of fibers. The collection of cells can be interrogated in order to quantify various characteristics of the fiber bed. We compute three such characteristics for each cross-section through the stacks:

- (i) the *mean cell area*, $\mu_{\mathbf{A}}$, given by $\mu_{\mathbf{A}} = \frac{1}{N} \sum_{i=1}^N \mathcal{A}_i$, where $\mathcal{A}_i$ is the area of one cell and is expressed in units of pixels;
- (ii) the *non-uniformity of cell areas* (Shou *et al.*, 2014), characterized by $\alpha = \frac{\frac{1}{N}(\mathbf{A} \cdot \mathbf{A})}{\mu_{\mathbf{A}}^2}$, where $\mathbf{A} = [\mathcal{A}_1, \mathcal{A}_2, \dots, \mathcal{A}_N]$ is the entire set of cell areas; and
- (iii) the *mean porosity*, given by $\rho = \frac{\sum_{i=1}^N \mathcal{A}_{U_i}}{\sum_{i=1}^N \mathcal{A}_i}$, where $\mathbf{A}_{\mathbf{U}} = [\mathcal{A}_{U_1}, \mathcal{A}_{U_2}, \dots, \mathcal{A}_{U_N}]$ is the set of unoccupied areas within the cells.

Fig. 4. Example of a Voronoi tessellation calculated from fiber segmentation.

The α metric was proposed in (Shou *et al.*, 2014) for the analysis of permeability of the fiber reinforcement, and applied to simulated random fiber arrays. We propose

to use the others to enrich the analysis of the samples. These metrics are calculated in 2D for each cross section of the 3D stack.

Generally, the 2D cross sections used are the transverse slices of the 3D stack. However, the domain of analysis can be changed, i.e., the user can slice the data in different directions so that the metrics are calculated based on the selected domain. This flexibility allows taking into account that, due to the nature of a 3D tomographic reconstruction, characteristics and artifacts can vary depending on how the data is sliced.

3. Experiments

In this section we present a set of different *in silico* experiments using the proposed analysis pipeline. The experiments are carried out in an increasing order of complexity: (1) synthetic data corrupted with noise, (2) experimental data of geological sample, and (3) experimental CMC sample with fiber beds. We show how to use the proposed process to evaluate the segmentation algorithms and suitability of different metrics presented in Sec. 2.3 for each case.

3.1. Synthetic Samples

3.1.1. Description For the first set of experiments we use synthetic data corrupted with artifacts. In doing so, we have totally control of the samples and the ground-truth to demonstrate the accuracy of the segmentation algorithms. We use benchmark images available at the Network Generation Comparison Forum (NGCF) ¹, a forum that provides binary images with geometry that resembles porous media, which we contaminate with several levels of noise, similarly to (Ushizima *et al.*, 2012).

To produce images similar to the images obtained from tomographic experiments,

¹http://xct.anu.edu.au/network_comparison

we simulated a tomographic synchrotron experiment for each phantom image, and computed tomographic reconstructions. The ASTRA toolbox (Aarle *et al.*, 2015) simulates tomographic projections for each phantom using 1025 angles over a 180° range. Afterwards, we add various sources of noise to the projections, simulating common artifact sources in practice, such as Gaussian white noise, miscalibrated detector pixels, and shifting illumination, which typically result in ring-like artifacts in reconstructed images. The simulated projections were processed similarly to actual experimental data by applying a ring-removal algorithm (Münch *et al.*, 2009) and computing a reconstructed image using the popular filtered backprojection algorithm (Kak & Slaney, 2001).

3.1.2. Analysis Pipeline For the synthetic μ -CT image stacks, we apply F3D and non-linear image denoising to enhance image quality and then, the three segmentation algorithms detect the phases of interest. Here, the algorithms separate two phases: structure and void space. To calculate all the measures described in Sec. 2.3.1, a voxel-to-voxel comparison is made against the reference data (ground-truth) for each sample.

Empirically found values used for the parameters G_r and G_s by the edge-preserving filtering were 50 and 5. PMRF converges after 5 iterations in average, SRM algorithm used $Q = 8$ and k-means used $k = 6$.

3.1.3. Results The first synthetic data simulates a glass bead column with μ -CT artifacts as shown in Fig. 5(a). Fig. 5(b) presents the reference data and Fig. 5(c) shows the 3D rendering of the corrupted data masked with the reference segmentation.

Fig. 5. Result of one slice from the two-phases segmentation of the synthetic glass bead column. (a) Synthetic corrupted data (b) Reference data (c) 3D rendering of the corrupted data masked with the reference (d) Result using PMRF algorithm (e) Result using SRM algorithm (f) Result using k-means algorithm. The colors blue, red, yellow and black represent TP , FP , FN and TN .

We apply the segmentation algorithms following the analysis pipeline described before. Fig. 5(d)-(f) present the results for the 46th slice using PMRF, SRM and k-means, respectively. The colors blue, red, yellow and black represent TP , FP , FN and TN .

Tab. 1 summarizes the quantitative results using the general metrics described in Sec. 2.3.1 for this dataset. Notice that the quantitative results are compatible with the visual results shown in Fig. 5, i.e. the three algorithms perform similarly with small variations, and all of them approach the reference data. When these different algorithms and respective metrics somewhat coincide, our hypothesis is that the μ -CT

segmentation worked properly.

Table 1. *Metrics for the synthetic glass bead column. Notice that the three algorithms provide similar results converging to the reference data.*

	Reference	PMRF	SRM	K-MEANS
Precision	1.0	0.995	0.993	0.996
Recall	1.0	0.993	0.996	0.9896
Accuracy	1.0	0.992	0.994	0.991
Porosity	0.378	0.380	0.377	0.3833
Volume (cm³)	0.0603	0.0604	0.0607	0.0601

The second experiment aims to evaluate the segmentation algorithms applied to a material with peculiar characteristics, including complex geometries and high curvature points. This synthetic data represents a geological formation similar to rocks. In this case, the material has a lower porosity, smaller and more connected structures. Additionally, the same approach for adding artifacts is applied to the synthetic data.

Fig. 6(d-f) depict the segmentation results compared to the reference data, presented in Fig. 6(b). Fig. 6(a) shows the synthetic corrupted data and Fig. 6(c) presents the 3D rendering of the corrupted data masked with the reference segmentation. The colors blue, red, yellow and black represent TP , FP , FN and TN .

Fig. 6. Result of one slice from the two-phases segmentation of the synthetic rock-like sample. (a) Synthetic corrupted data (b) Reference data (c) 3D rendering of the corrupted data masked with the reference (d) Result using PMRF algorithm (e) Result using SRM algorithm (f) Results using k-means algorithm. The colors blue, red, yellow and black represent TP , FP , FN and TN .

Notice again the visual similarity of the results. Tab. 2 summarizes the general metrics values obtained for this experiment. Despite the fact that the simulated material in this case has a more challenging set of characteristics as described before, the results of the three algorithms also approach the reference data, with precision achieving values higher than 0.99, which is often enough to enable scientific interpretation of the sample.

Table 2. *Metrics for the synthetic rock-like sample showing the small variation on the metrics for the three segmentation algorithms, indicating total agreement.*

	Reference	PMRF	SRM	K-MEANS
Precision	1.0	0.996	0.993	0.996
Recall	1.0	0.969	0.989	0.972
Accuracy	1.0	0.972	0.986	0.975
Porosity	0.206	0.227	0.210	0.2248
Volume (cm³)	0.077	0.0752	0.0769	0.0755

3.2. Glass Beads

3.2.1. Description This real dataset presents the observation of a geological carbon sequestration experiment, which uses glass beads as a proxy for sand grains for in-situ studies of infiltration and storage. Fig. 7 illustrates an experimental outcome using glass bead-packed columns in biogenic mixture where calcite precipitation was induced by using the microbe *S. pasteurii*. The glass beads data set originally contains a 10GB image stack and represents a 4.49 mm field of view, with a smaller core region corresponding with x-y dimensions of 1393×1398 , as previously described in (Ushizima *et al.*, 2011).

Fig. 7. Result of one slice from the two-phases segmentation of the glass bead column. (a) Original slice (b) Reference data (c) 3D rendering of the reference segmentation (d) Result using PMRF algorithm (e) Result using SRM algorithm (f) Results using k-means algorithm. The colors blue, red, yellow and black represent TP , FP , FN and TN .

3.2.2. Analysis Pipeline Following the procedure used for the synthetic datasets, firstly the F3D plugin combined with edge-preserving filtering enhances image quality and then, the three segmentation algorithms detect the phases of interest. Here, besides separating two phases, material and void space, we apply the algorithms to find an additional phase representing the precipitation of calcium carbonate. The general metrics described in Sec. 2.3.1 are also used to evaluate the results on this dataset.

The values used for the parameters G_r and G_s by the edge-preserving filtering were 50 and 5. PMRF converges after 5 iterations in average, SRM algorithm used $Q = 8$

and k-means used $k = 2$ for the two-phase segmentation and $k = 6$ for the three-phase segmentation.

3.2.3. Results We apply the pipeline described before to the experimental data of the glass bead column firstly aiming the separation between material and void space. Fig. 7 presents a summary of the results for the 1st slice of the 3D stack. In the original data presented in Fig. 7(a), three phases can be identified by the difference of intensity values of the pixels: void space (darkest gray level), glass beads (intermediate gray level) and precipitate (brightest gray level). Fig. 7(b) presents the used reference for this slice for the two-phases segmentation. Fig. 7(c) shows the 3D rendering of the original data masked with the reference data. Finally, Fig. 7(d-f) present the results obtained by PMRF, SRM and k-means respectively. For the purposes of this work, the reference data used is the best result found in the literature for this dataset (Ushizima *et al.*, 2011), which was validated by a material scientist expert. We observe a close agreement among the results compared to the reference data according to the values of TP , FP , FN and TN represented by the colors blue, red, yellow and black, respectively.

Tab. 3 presents the values for the metrics described in Sec. 2.3.1 calculated for this experiment. The results of the three algorithms are in close agreement with the reference data, and accuracy achieved values higher than 0.94 indicating that the algorithms successfully segmented the solid component of the material from the void space.

Table 3. *Metrics for the two-phases segmentation of the glass bead column. The three algorithms are in agreement with the reference data.*

	Reference	PMRF	SRM	K-MEANS
Precision	1.0	0.957	0.962	0.952
Recall	1.0	0.935	0.939	0.941
Accuracy	1.0	0.940	0.945	0.940
Porosity	0.436	0.449	0.450	0.443
Volume (cm³)	0.04882	0.04774	0.04764	0.04823

Now we apply the same algorithms aiming to separate the three different phases: void space, glass beads and precipitate. Using the same previous slice, Fig. 8 shows the results for the three algorithms. In this case, the algorithms are able to separate the void space (black), the glass beads (red), and obtain a phase which is the combination of precipitate and vessel (cyan).

Fig. 8. Result of one slice from the three-phases segmentation of the glass bead column.
 (a) Original slice (b) Result using PMRF algorithm (c) Result using SRM algorithm
 (d) Result using k-means algorithm. The colors red, cyan and black represent the solid, precipitate and void phases, respectively.

Tab. 4 presents the volumes calculated for each phase. The reference data for the three-phases segmentation is unavailable, however we can notice the similarity among the results also indicating total agreement of the three algorithms, making the results valuable for visual analysis and characterization of this kind of material. As mentioned before, the phase representing the precipitation is combined with the vessel, which affects the calculation of the metrics for this phase. However, from the experimental point of view, it is possible to have the initial state of the experiment, i.e., the state of the glass bead column before infiltration. Consequently, it is feasible to subtract the initial state in order to obtain a phase which purely represents the precipitate.

Table 4. *Metrics for the three-phases segmentation of the glass bead column. Reference data is not available, however it is noticeable the agreement of the algorithms.*

	PMRF	SRM	K-MEANS
Volume of beads (cm³)	0.0391	0.04178	0.04301
Volume of precipitation (cm³)	0.005827	0.005851	0.00522
Total volume (cm³)	0.04882	0.04764	0.04823

The values obtained for the general metrics are calculated based on the full 3D binary results from the segmentation algorithms. The boundary shown in Fig. 7 was used for visualization purposes only, it is not a requirement for the metrics calculation. However, it is important to emphasize that if a specific boundary is selected from the original image (a region of interest), then the calculated values for the metrics are going to vary accordingly.

3.3. Ceramic Matrix Composite

3.3.1. Description Our last set of experiments focuses on the analysis of CMC samples with fiber beds. The specimens analyzed in this work are CMC mini-composites. Each specimen contains approximately 5000-6000 unidirectionally-aligned SiC fibers, each about 10 μm in diameter, surrounded by a cured pre-ceramic polymer matrix. The matrix had been introduced through pressure-assisted axial infiltration of a liquid polymer precursor into dry fiber beds encased in glass capillary tubes. The uniformity of fiber packing is of interest because it influences void formation during PIP processing. μ -CT imaging of the infiltrated specimens was conducted at Beamline 8.3.2 at ALS. The distance between the sample and the detector was 1.5-2.0 cm. The data were reconstructed using filtered back projection with Octopus software (Inside Matters NV, 2016). Reconstruction required approximately two hours when running on a standard desktop computer. The reconstructed results consist of sets of cross-sections, recorded as 2D images. Brought together, the images can be used to recover the 3D structures.

Fig. 9 presents a cross-section from one of the nine stacks studied. Three different regions are evident in the interior of the tubes: (i) fibers (lightest gray); (ii) cured precursor (medium gray) and (iii) voids (darkest gray). In this work, the precursor and the voids are together distinguished from the fibers.

Fig. 9. Original slice from one of the μ -CT stacks and its respective reference data.

3.3.2. Analysis Pipeline The segmentation and analysis pipeline was applied to nine 3D μ -CT image stacks, each approximately $2000 \times 2000 \times 2160$ voxels. For each stack, F3D was first used to enhance image quality. Then, the image segmentation algorithms recover binary masks representing the separation of two phases: fiber beds and void space (combination of cured precursor and voids). From the binary masks, we calculate the general metrics described in Sec. 2.3.1.

Additionally, we use the binary masks to construct the Voronoi tessellation, which combined with the segmentation results, enables calculation of the three specific metrics in Eqs. 2.3.2, 2.3.2, and 2.3.2. The parameter Q for the SRM algorithm is set to 8, k-means was applied with $k = 4$ and PMRF executes an average of 5 iterations. Automated threshold estimators are applied to obtain the binary results from SRM (Otsu) and k-means (Iso-data). The values used for the parameters G_r and G_s by the

edge-preserving filtering were 50 and 5.

The results from the three segmentation algorithms are compared with corresponding results of the reference segmentation. The latter segmentation was obtained using matlab scripts combined to manual (and time-consuming) intervention, customized to each sample. The parameter values obtained from the reference segmentation are deemed to be the best estimates of their true values.

3.3.3. Results Fig. 10 presents the segmentation result for a region of interest from a 2D plane of a stack. In this set of results, differences among the segmentation results can be observed, indicating that the algorithms are not in agreement and further analysis is necessary.

Fig. 10. Comparisons of the segmentation results for a representative region of the original image. (a) Original image (b) Reference data (c) Result using PMRF (d) Result using SRM (e) Result using k-means. The colors blue, red, yellow and black represent TP , FP , FN and TN .

Following the same procedure used for the previous experiments, firstly we analyze the results using general metrics. Fig. 11 presents the graphics for the porosity and volume obtained for the nine stacks. The graphics show the curves in increasing order for both metrics. Observe that there is a weak indication that the PMRF algorithm approaches slightly more the reference results.

Fig. 11. Values of porosity and volume calculated for the nine stacks analyzed. Curves plotted in increasing order for both metrics based on the reference data. Notice the close result of the three algorithms with a weak advantage for the PMRF algorithm.

Tab. 5 presents the average segmentation performance of the algorithms applied to the nine stacks, which is in agreement with the other metrics results, where the PMRF algorithm achieves a slightly higher average accuracy. In general, it is clear that the three algorithms perform well considering these metrics. It is possible to have an overall understanding of the samples. However, it is difficult to draw any precise conclusions from these results regarding the fiber-beds.

Taking a closer look at the results in Fig. 8, the fiber beds obtained by the k-means algorithm suffer from missing fiber regions due to inaccurate pixel segmentation (observe the spread yellow regions in Fig. 8(e)). In contrast, being graph-based, both the SRM and the PMRF algorithms allow use of higher-level information, correctly merging similar homogeneous regions.

Table 5. *Average for precision, recall and accuracy obtained from the three segmentation algorithms for the nine CMC 3D stacks. Notice although the results are very similar, there is an indication that the PMRF algorithms performs better.*

		Mean	Standard Deviation
Precision	PMRF	0.9278	0.020
	SRM	0.946	0.001
	KMEANS	0.945	0.005
Recall	PMRF	0.939	0.023
	SRM	0.891	0.009
	KMEANS	0.896	0.007
Accuracy	PMRF	0.942	0.018
	SRM	0.931	0.007
	KMEANS	0.933	0.005

However, the SRM algorithm is negatively impacted by the final threshold, leading to occasional missing or misclassified fiber regions (notice the yellow regions in Fig. 8(d)). So, in fact, there are more details about the results that the general metrics are not able to capture. Consequently, we need more specific criteria for a more precise evaluation.

The three fiber bed characteristics defined in Sec. 2.3.2 are now used. Fig. 12 shows the variation in the average value of each characteristic across each sectioning plane with position in the stack. The result based on the PMRF method is consistently in close agreement with the one from the reference segmentation. In contrast, the result from k-means differ considerably from the reference values, over-estimating both the non-uniformity of cell area, α , and the porosity, ρ , while underestimating the cell area, $\mu_{\mathbf{A}}$.

Tab. 6 summarizes the errors in the three computed characteristics from the three segmentation methods for all nine data sets. The PMRF method consistently yields the best results. For example, the error in α is a mere 0.0096. (For reference, $\alpha=1$ corresponds to uniform fiber packing; values obtained in the present composite specimens are typically about $\alpha=1.1$.) The errors in $\mu_{\mathbf{A}}$ and ρ from this method are 0.012 and 0.0073, respectively. (For reference, the average values of $\mu_{\mathbf{A}}$ and ρ are about 430

and 0.28.) Higher errors (in some cases by an order of magnitude) are obtained for the other methods.

Fig. 12. α , μ_A , and ρ calculated for each slice through the 3D volume, for each segmentation algorithm and the segmentation reference, for the sample presented in Fig. 9. Gray region around the curves represents the standard deviation.

Table 6. *Errors in α , μ_A and ρ , calculated over all nine stacks. Best results are emphasized in bold text.*

	α	μ_A	ρ
PMRF	0.0096	0.012	0.0073
SRM	0.025	0.026	0.17
KMEANS	0.087	0.109	0.149

Notice that the results obtained using the specific metrics are different and more clear from the ones obtained using the general metrics. The reason behind is that the

specific metrics capture details of the fibers individually for each 2D plane throughout the 3D stacks, giving a more precise analysis of this structure. In doing so, the PMRF algorithm is in fact considerably more precise in this case than the other two algorithms, meaning that this algorithm appears to be more suitable to the analysis of this kind of samples. The main reason behind the better results obtained by the PMRF algorithm is its ability to estimate and separate more precisely the regions of interest based on a contextual model, not only on the intensity values of the pixels.

The set of experiments carried out was only possible and feasible given the proposed pipeline. The methodology described here uses different strategies for segmentation and evaluation of μ -CT samples, and also enables the critical assessment of the accuracy of the algorithms in obtaining scientific information about the samples. The results demonstrated the impact of choosing the suitable segmentation algorithms and evaluation metrics when analyzing 3D μ -CT data, and how the proposed pipeline facilitates this exploration and evaluation process.

4. Concluding Remarks

Segmentation algorithms enable quantitative characterization of different materials in μ -CT data through measurements that extract physical properties from samples. However, finding the most appropriate segmentation algorithm for the data and finding the best evaluation metrics are a constant challenge, while those two choices heavily impact the performance of the results in obtaining valuable information from the data.

We have presented an automated pipeline called MSM for the analysis of 3D μ -CT images that offers different strategies to evaluate combinations of segmentation algorithm and metric for different scientific problems. We performed a broad and detailed set of experiments covering samples with different types of materials: synthetic data of glass beads and rock-like sample, real glass beads sample and CMC samples with fiber

beds. The impact of choosing the right segmentation algorithm and metric depending on the scientific goals is demonstrated throughout the experiments. Although **MSM** comes with a pre-defined set of segmentation algorithms and metrics, the pipeline can be easily extended with additional methods for comparison.

We show that the three unsupervised segmentation algorithms detect different phases of the materials and give comparable results for all the experiments. However, specimens with complex geometries and fine details may diverge considerably with regards to the segmentation results. The analysis of fiber beds require tailored segmentation algorithms, and a more specific set of metrics so that the necessary scientific questions can be answered. In this case, the experiments indicate that the **PMRF** algorithm is more suitable and more precise when segmenting the fiber beds.

Future directions of this work include studies of scalability of the segmentation methods in order to improve the efficiency of analytical process. This includes the use of an under development MPI-based version of the **PMRF** algorithm. In doing so, we intend to perform a detailed analysis of the fiber beds in CMC samples, modeling the fibers, and measuring fiber deformations and the matrix deformation evolution. Additionally, we will develop metrics that suggests if the input data needs enhancement or not. Currently, the image enhancement step in the proposed pipeline is optional and dependent on the user’s choice.

Acknowledgements

This work was supported by: the Office of Naval Research under grant N00014-13-1-0860, monitored by Dr. David A. Shifler; the grant “Towards Exascale: High Performance Visualization and Analytics” and the Early Career Research project, both under Advanced Scientific Computing Research (ASCR), project DE-AC02-05CH11231, under program manager Dr. Lucy Nowell; the Center for Applied Mathematics for Energy Related Applications (CAMERA), under management of ASCR

and Office of Basic Energy Sciences (BES) of the U.S. Department of Energy; an ALS Doctoral Fellowship in Residence (supporting N.M.L.) with funding provided by the U.S. Department of Energy; and a National Science Foundation Graduate Research Fellowship (N.M.L) under Grant No. 1144085. Any opinion, findings, and conclusions or recommendations expressed in this material are those of the authors and do not necessarily reflect the views of the National Science Foundation. The experimental work was performed at Beamline 8.3.2 at the Advanced Light Source (ALS), a Division of Lawrence Berkeley National Laboratory. The authors gratefully acknowledge Alastair MacDowell and Harold Barnard (ALS) for assistance with planning and executing the experiments. ALS is supported by the Director, Office of Science, Office of Basic Energy Sciences, of the U.S. Department of Energy under Contract No. DE-AC02-05CH11231.

References

- Aarle, W., Palenstijn, W. J., Beenhouwer, J. D., Altantzis, T., Bals, S., Batenburg, K. J. & Sijbers, J. (2015). *Ultramicroscopy*, **157**, 35 – 47.
- Arbelaez, P., Maire, M., Fowlkes, C. & Malik, J. (2011). *IEEE Transactions on Pattern Analysis and Machine Intelligence*, **33**(5), 898–916.
- Aurenhammer, F. (1991). *ACM Comput. Surv.* **23**(3), 345–405.
- Bale, H. A., Haboub, A., Macdowell, A. A., Nasiatka, J. R., Parkinson, D. Y., Cox, B. N., Marshall, D. B. & Ritchie, R. O. (2012). *Nat Mater*, **12**, 40–46.
- Bethel, E. W. (2012). *Exploration of Optimization Options for Increasing Performance of a GPU Implementation of a Three-Dimensional Bilateral Filter*. Tech. Rep. LBNL-5406E. Lawrence Berkeley National Laboratory, Berkeley, CA, USA, 94720.
- Bethel, W. *et al.* (2015). In *DOE ASCR Workshop*, pp. 2–30. DOE.
- Chen, R.-C., Dreossi, D., Mancini, L., Menk, R., Rigon, L., Xiao, T.-Q. & Longo, R. (2012). *Journal of Synchrotron Radiation*, **19**(5), 836–845.
- Chen, W., Ostrouchov, G., Pugmire, D., Prabhat & Wehner, M. (2013). *Technometrics*, **55**(4), 513–523.
- Ching, D. J. & Gürsoy, D. (2017). *Journal of Synchrotron Radiation*, **24**(2), 537–544.
URL: <https://doi.org/10.1107/S1600577517001928>
- Gonzalez, R. C. & Woods, R. E. (2006). *Digital Image Processing (3rd Edition)*. Upper Saddle River, NJ, USA: Prentice-Hall, Inc.
- Hintermüller, C., Marone, F., Isenegger, A. & Stampanoni, M. (2010). *Journal of Synchrotron Radiation*, **17**(4), 550–559.
- Inside Matters NV, (2016). Octopus imaging. <http://octopusimaging.eu/>.
- Kak, A. C. & Slaney, M. (2001). *Principles of Computerized Tomographic Imaging*. Philadelphia, PA: Society for Industrial and Applied Mathematics.
- Khanum, M., Mahboob, T., Imtiaz, W., Ghafoor, H. A. & Sehar, R. (2015). *International Journal of Computer Applications*, **119**(13), 34–39. Full text available.

- Li, S. Z. (2013). *Markov Random Field Modeling in Image Analysis*. Springer Publishing Company, Incorporated, 3rd ed.
- Macqueen, J. (1967). In *In 5-th Berkeley Symposium on Mathematical Statistics and Probability*, pp. 281–297.
- Mahapatra, D. & Sun, Y. (2012). *IEEE Transactions on Image Processing*, **21**(1), 170–183.
- Mizrahi, Y. D., Denil, M. & de Freitas, N. (2014). In *International Conference on Machine Learning (ICML)*.
- Münch, B., Trtik, P., Marone, F. & Stampanoni, M. (2009). *Opt. Express*, **17**(10), 8567–8591.
- Nock, R. & Nielsen, F. (2004). *IEEE Transactions on Pattern Analysis and Machine Intelligence*, **26**(11), 1452–1458.
- Perciano, T., Ushizima, D. M., Bethel, E. W., Mizrahi, Y. D., Parkinson, D. & Sethian, J. A. (2016). In *2016 IEEE International Conference on Image Processing (ICIP)*, pp. 1259–1263.
- Pinoli, J. C. & Debayle, J. (2012). *IEEE Journal of Selected Topics in Signal Processing*, **6**(7), 820–829.
- Polak, S. J., Candido, S., Levengood, S. K. L. & Johnson, A. J. W. (2012). *Computerized Medical Imaging and Graphics*, **36**(1), 54 – 65.
- Schindelin, J., Arganda-Carreras, I., Frise, E., Kaynig, V., Longair, M., Pietzsch, T., Preibisch, S., Rueden, C., Saalfeld, S., Schmid, B., Tinevez, J.-Y., White, D. J., Hartenstein, V., Eliceiri, K., Tomancak, P. & Cardona, A. (2012). *Nat Meth*, **9**(7), 676–682.
- Sheppard, A., Latham, S., Middleton, J., Kingston, A., Myers, G., Varslot, T., Fogden, A., Sawkins, T., Cruikshank, R., Saadatfar, M., Francois, N., Arns, C. & Senden, T. (2014). *Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms*, **324**, 49 – 56. 1st International Conference on Tomography of Materials and Structures.
- Shou, D., Ye, L. & Fan, J. (2014). *Journal of Composite Materials*, **49**(4), 1753–1763.
- Tassani, S., Korfiatis, V. & Matsopoulos, G. K. (2014). *Journal of Microscopy*, **256**(2), 75–81.
- Tomasi, C. & Manduchi, R. (1998a). In *Sixth International Conference on Computer Vision (IEEE Cat. No.98CH36271)*, pp. 839–846.
- Tomasi, C. & Manduchi, R. (1998b). In *Computer Vision, 1998. Sixth International Conference on*, pp. 839–846.
- Ushizima, D., Morozov, D., Weber, G. H., Bianchi, A. G. C., Sethian, J. A. & Bethel, E. W. (2012). *IEEE Transactions on Visualization and Computer Graphics*, **18**(12), 2041–2050.
- Ushizima, D., Parkinson, D., Nico, P., Ajo-Franklin, J., MacDowell, A., Kocar, B., Bethel, W. & Sethian, J. (2011). *Proc. SPIE*, **8135**, 813502–813502–14.
- Ushizima, D. M., Perciano, T., Krishnan, H., Loring, B., Bale, H., Parkinson, D. & Sethian, J. (2014). *IEEE International Conference on Big Data*.
- Van Droogenbroeck, M. & Talbot, H. (1996). *Pattern Recognition Letters*, **17**(14), 1451–1460.
- Yang, X., De Carlo, F., Phatak, C. & Gürsoy, D. (2017). *Journal of Synchrotron Radiation*, **24**(2), 469–475.
- Zok, F. W. (2016). *American Ceramic Society Bulletin*, **95**(5), 22–28.

Synopsis

The proposed Materials Segmentation and Metrics (MSM) dataflow provides protocols to systematically analyze and compare the results of unsupervised classification methods used for segmentation of synchrotron-based imaging. MSM offers different metrics to evaluate the performance of image segmentation algorithms in terms of quality, confidence and conformity with standards.