UC Berkeley

UC Berkeley Previously Published Works

Title

Origins of anisotropic transport in the electrically switchable antiferromagnet Fe_{1/3}NbS₂

Permalink

<https://escholarship.org/uc/item/5rm9d8z8>

Journal

Physical Review B, 103(21)

ISSN

2469-9950

Authors

Weber, SF

Neaton, JB

Publication Date

2021-06-01

DOI

10.1103/PhysRevB.103.214439

Peer reviewed

Origins of anisotropic transport in the electrically switchable antiferromagnet $\text{Fe}_{1/3}\text{NbS}_2$

Sophie F. Weber^{1,2} and Jeffrey B. Neaton^{1,2,3}

¹*Department of Physics, University of California, Berkeley, California 94720, USA*

²*Materials Science Division, Lawrence Berkeley National Laboratory, Berkeley, California 94720, USA*

³*Kavli Energy NanoScience Institute at Berkeley, Berkeley, California 94720, USA*

Recent experiments on the antiferromagnetic intercalated transition metal dichalcogenide $\text{Fe}_{1/3}\text{NbS}_2$ have demonstrated reversible resistivity switching by application of orthogonal current pulses below its magnetic ordering temperature, making $\text{Fe}_{1/3}\text{NbS}_2$ promising for spintronics applications. Here, we perform density functional theory calculations with Hubbard U corrections of the magnetic order, electronic structure, and transport properties of crystalline $\text{Fe}_{1/3}\text{NbS}_2$, clarifying the origin of the different resistance states. The two experimentally proposed antiferromagnetic ground states, corresponding to in-plane stripe and zigzag ordering, are computed to be nearly degenerate. In-plane cross sections of the calculated Fermi surfaces are anisotropic for both magnetic orderings, with the degree of anisotropy sensitive to the Hubbard U value. The in-plane resistance, computed within the Kubo linear response formalism using a constant relaxation time approximation, is also anisotropic, supporting a hypothesis that the current-induced resistance changes are due to a repopulating of antiferromagnetic domains. Our calculations indicate that the transport anisotropy of $\text{Fe}_{1/3}\text{NbS}_2$ in the zigzag phase is reduced relative to stripe, consistent with the relative magnitudes of resistivity changes in experiment. Finally, our calculations reveal the likely directionality of the current-domain response, specifically, which domains are energetically stabilized for a given current direction.

I. INTRODUCTION

Due to the bitlike nature of electronic spins, magnetic materials are natural candidates for storage and sensing devices. In particular, the scaling advantages of electrical current over magnetic fields makes spintronic materials whose magnetism can be controlled by current especially desirable [1]. The underlying mechanism for current-induced magnetic switching is generally thought to be spin-orbit torque; the applied electric current, in a manner dictated by crystal symmetries, induces a polarization in conduction electrons, thereby creating an effective magnetic field [2–7]. This effective field imparts a torque on the localized magnetic moments, enabling them to switch to different orientations.

There has been growing interest in electrically induced switching in antiferromagnetic (AFM) compounds. Antiferromagnets have been reported to switch (via a rotation of the Néel vector) at terahertz rates by electrical current compared to a nominal approximately gigahertz limit for ferromagnets (FMs) [8]. Moreover, their vanishing bulk magnetization makes them insensitive to stray magnetic fields, enhancing their stability for memory storage relative to FMs. In spite of their appeal, there are just a few reports of AFM materials which can be electronically manipulated; until very recently, the only known examples in single-crystal form were the collinear AFMs CuMnAs and Mn_2Au [9,10]. (Additionally, current-driven manipulation of AFMs has also been confirmed in heterostructure devices [11,12].)

Recently, an electrically switchable AFM was discovered among the magnetically intercalated transition metal dichalcogenides (TMDs), layered compounds in which the magnetic ions are intercalated between the layers. These materials have received attention in the past due to their high tunability; by simply varying the intercalated element, concentration of the intercalant, or base TMD, a wide variety of magnetic and electric ground states are induced [13,14]. Transport experiments by Nair *et al.* [15] demonstrated that one particular case, $\text{Fe}_{1/3}\text{NbS}_2$, can be switched between states of high and low resistance by applying orthogonal current pulses. The switching occurs below the Néel temperature of 49 K, indicating that the magnetic order is relevant to the changes in resistance.

However, the origin of the high- and low-resistance states has yet to be clarified. It has been hypothesized, based on the results of optical polarimetry measurements, that the resistance change is associated with a current-induced repopulation of three AFM domains [15,16], analogous to the current-induced switching observed in CuMnAs [17]. Little *et al.* [16] pointed out that this could occur in theory even if the Néel vector of $\text{Fe}_{1/3}\text{NbS}_2$ is fully out of plane. If domain repopulation leads to changes in resistance along a given direction, this will necessarily be reflected in the anisotropy of the electronic structure and transport for a single domain.

In what follows, we perform density functional theory (DFT) calculations of the electronic structure and the nature of the magnetic order in $\text{Fe}_{1/3}\text{NbS}_2$. We find an AFM ground state and two nearly degenerate in-plane magnetic orderings

corresponding to previously reported “stripe” and “zigzag” AFM states. We find that the Fermi surfaces for stripe and zigzag orders are both anisotropic in the k_x - k_y plane, although the in-plane anisotropy is larger for stripe order. Using our DFT electronic structure and a constant relaxation time approximation within the Kubo linear response formalism, we find that with stripe order the resistivity along the [120] crystallographic axis is roughly twice as large as that along the orthogonal [100] direction. On the other hand, the resistivity along [100]/ $\hat{x}$ is larger than [120]/ $\hat{y}$, and the relative anisotropy is reduced for zigzag order. Our computed resistivity tensors for stripe and zigzag orders, combined with the experimental switching data, suggest that for both magnetic states a current pulse depopulates the AFM domain whose principal axis is parallel to the current and increases the populations of the other domains. Our calculations support the domain repopulation hypothesis and provide insight into the specific current-domain dynamics in $\text{Fe}_{1/3}\text{NbS}_2$.

II. METHODS

For our first-principles DFT calculations on $\text{Fe}_{1/3}\text{NbS}_2$, we employ the Vienna *Ab initio* Simulation Package (VASP) [18] with a generalized gradient approximation using the Perdew-Burke-Ernzerhof functional [19] and projector augmented-wave method [20]. For all DFT calculations we include spin-orbit coupling and treat it self-consistently. We take $3d$ and $4s$; $4p$, $4d$, and $5s$; and $3s$ and $3p$ electrons explicitly as the valence for Fe, Nb, and S, respectively. We use an energy cutoff of 650 eV for our plane wave basis set. For our $\mathbf{k}$ -point grid we use a Γ -centered mesh of $12 \times 7 \times 6$ for the $1 \times \sqrt{3} \times 1$ orthorhombic supercell, consistent with stripe order, and a $6 \times 7 \times 6$ mesh for the $2 \times \sqrt{3} \times 1$ supercell, consistent with zigzag AFM order. We use the tetrahedron method [21] for Brillouin zone integrations. These parameters lead to total energy convergence of <1 meV/Fe ion. We use experimental lattice constants of $a = 5.76$ Å and $c = 12.20$ Å and experimental atomic coordinates [14], having checked that relaxation changes parameters and atomic positions negligibly. For calculations of two-dimensional Fermi surfaces and velocities, we use Wannier interpolation as implemented in the postprocessing utility POSTW90 for WANNIER90 [22–24]. We use 208 and 416 bands for stripe and zigzag orders, respectively, in our Wannierizations. We select Fe d , Nb d_{z^2} , and S p orbitals as our localized projections. Cross sections of the Fermi surfaces and Fermi velocities are evaluated on a $k_x \times k_y \times k_z$ grid of $251 \times 251 \times 1$. Fermi surface cross sections shown in the Supplemental Material [25] without band velocities were generated using WANNIERTOOLS [26]. The evaluation of the Kubo formula for conductivity is performed using the WANNIER LINEAR RESPONSE code [27]. The code calculates linear response properties within the Kubo formalism based on DFT-parameterized tight-binding Hamiltonians, taking the overlap of Wannier functions as input. We use a converged k -grid of $400 \times 400 \times 400$ for evaluation of the conductivities.

To approximately account for the localized nature of the Fe d electrons we add a Hubbard U correction [28], and we select the rotationally invariant implementation by Dudarev and Botton [29]. We note here that our quantitative results

FIG. 1. Left: hexagonal crystal structure of $\text{Fe}_{1/3}\text{NbS}_2$, with space group $P6_322$. The primitive cell contains two Fe atoms sandwiched between the layers of NbS_2 at $c = 1/4$ and $c = 3/4$. Right: c -oriented view of the two Fe layers with ions in layers $c = 1/4$ and $c = 3/4$ colored red and blue, respectively.

for energetics, Fermi surface cross sections, and transport tensors are highly sensitive to the specific value of Hubbard U chosen. The Hubbard U , an *ad hoc* parameter, acts here explicitly on the Fe d states, which have a very large weight near the Fermi energy in $\text{Fe}_{1/3}\text{NbS}_2$; therefore, small changes in U have a disproportionate effect on bands in an energy window relevant for transport properties (see the Supplemental Material for orbital-projected band structures [25]). Given the limitations of PBE+ U , to gain confidence in consistent qualitative features in transport anisotropy we perform and describe PBE+ U calculations using two different U values in the main text. We first use PBE+ U with $U = 0.3$ eV following previous work, which results in a magnetoanisotropy energy (MAE) consistent with experiment [30]. However, as we noted in Ref. [30], $U = 0.3$ eV overestimates Heisenberg exchange constants compared to experiment by several orders of magnitude. This motivates our consideration of a larger value $U = 0.9$ eV for comparison, which results in smaller (although still overestimated) Heisenberg exchange constants due to increased localization and also gives the correct sign for the MAE (easy axis along c) while the magnitude of the MAE is overestimated. We note here that, as shown in the Supplemental Material, even if we use a much larger $U = 4$ eV, which gives an incorrect sign for the MAE, the qualitative trends for transport with both zigzag and stripe magnetism are identical to those presented here using $U = 0.3$ eV and $U = 0.9$ eV, giving us further confidence in the robustness of our results. We refer the reader to the Supplemental Material for further details and discussion [25].

III. CRYSTAL STRUCTURE

$\text{Fe}_{1/3}\text{NbS}_2$ is a layered compound with Fe intercalated between $2H$ -type TMD NbS_2 layers [13]. The primitive non-magnetic unit cell is depicted in Fig. 1. We note that this structure with $\frac{1}{3}$ Fe intercalation is simply a $\sqrt{3} \times \sqrt{3}$ supercell of the unintercalated $2H$ - NbS_2 TMD (with a marginal ~ 0.03 Å expansion of the lattice upon addition of Fe). The Nb atoms are surrounded by the S atoms in a trigonal prismatic coordination. $\text{Fe}_{1/3}\text{NbS}_2$ takes up the space group $P6_322$ [182]. The Fe atoms are sandwiched between the NbS_2 layers at relative coordinates $(1/3, 2/3, 1/4)$ and $(2/3, 1/3, 3/4)$ (Wyckoff position 2d). There are two different Fe layers

FIG. 2. Experimentally proposed magnetic orderings, (a) $P_c2_12_12_1$ (a-stripe) and (b) $P_c2_12_12$ (a-zigzag), with only Fe spins shown. In our DFT calculations the Néel vector is purely out of plane; + and - symbols refer to up and down spins, respectively. Magnetic supercells are outlined in black. The orthohexagonal supercell for stripe order in terms of the primitive hexagonal lattice vectors a and c is $a \times \sqrt{3}a \times c$, and the supercell for zigzag order is $2a \times \sqrt{3}a \times c$. Dashed purple circles show the three interplanar nearest neighbors for a given ion, which determine whether the planes are “FM” coupled or “AFM” coupled; the coupling is AFM in both cases.

stacked along c , with each layer forming a triangular lattice in the a - b plane (note that the a - b plane is what we refer to as “in plane” in what follows).

IV. MAGNETIC ORDER

The magnetic ground state of $\text{Fe}_{1/3}\text{NbS}_2$ is known to be AFM below about 50 K [13], but the nature of the AFM order is highly sensitive to small changes in Fe concentration. Seminal work more than 40 years ago [14] indicated that Fe_xNbS_2 with $x = 0.323$ has an in-plane “zigzag” AFM order of the Fe spins, with the Néel vector oriented out of plane along [001] and the spins along one in-plane Fe bond direction alternating between up and down and between “up-up” and “down-down” along the other two bond directions [Fig. 2(b)]. However, another neutron scattering study by Suzuki *et al.* [31] with $x = 0.297$ found evidence for a stripe AFM ground state, with rows of spins along one Fe bond direction alternating between all up and all down [Fig. 2(a)].

We perform DFT calculations for both experimentally proposed collinear magnetic orderings, with the Néel vector taken along c , corresponding to magnetic space groups $P_c2_12_12_1$ (stripe) [31] and $P_c2_12_12$ (zigzag) [14] (see Fig. 2). In what follows, we will refer to them as a-stripe and a-zigzag, respectively, with the “a” indicating that adjacent planes of Fe ions are AFM coupled. From our PBE+ U calculations, these two magnetic orders at the stoichiometric Fe concentration of $x = \frac{1}{3}$ are nearly degenerate; the energy differences between the magnetic states are 0.9 and 2.5 meV per Fe atom for $U = 0.3$ and $U = 0.9$ eV, respectively. Additionally, the slightly preferred ground state switches from a-stripe for $U = 0.3$ eV to a-zigzag for $U = 0.9$ eV.

The near degeneracy of a-stripe and a-zigzag phases can be understood quantitatively from a Heisenberg Hamiltonian also discussed in Ref. [30] for PBE+ U calculations with $U = 0.3$ eV. We return to it here and discuss the exchange constants in the case of both $U = 0.3$ eV and $U = 0.9$ eV. Neglecting the antisymmetric spin exchange constants which could

lead to slight deviations from fully collinear order, magnetic contributions to the energy of $\text{Fe}_{1/3}\text{NbS}_2$ can be described approximately by the following Heisenberg Hamiltonian for the Fe lattice:

$$H = E_0 + \sum_{\langle ij \rangle} J_1 \mathbf{S}_i \cdot \mathbf{S}_j + \sum_{\langle\langle ij \rangle\rangle} J_2 \mathbf{S}_i \cdot \mathbf{S}_j + \sum_{\langle ij \rangle_c} J_{1c} \mathbf{S}_i \cdot \mathbf{S}_j + \sum_{\langle\langle ij \rangle\rangle_c} J_{2c} \mathbf{S}_i \cdot \mathbf{S}_j + \sum_{\langle\langle\langle ij \rangle\rangle\rangle_c} J_{3c} \mathbf{S}_i \cdot \mathbf{S}_j - \sum_i D(S_i^z)^2, \quad (1)$$

where $S = 2$ is the spin value of Fe^{2+} ; one, two, and three pairs of brackets distinguish Heisenberg exchange constants between equidistant nearest, next-nearest and third-nearest neighbors, respectively; and the c subscript refers to interplanar, rather than in-plane, couplings. The last term is the MAE, which, while relevant to our studies in Ref. [30], we neglect here as both a-stripe and a-zigzag phases have their Néel vectors fully along [001]. E_0 encompasses nonmagnetic contributions to the energy. Note that we neglected the third-nearest-neighbor exchange J_{3c} in Ref. [30] as it did not qualitatively alter our conclusions. To obtain the five coupling constants plus E_0 we fit our DFT total energies for six inequivalent collinear magnetic configurations (discussed in the Supplemental Material [25]), which include the a-stripe and a-zigzag phases, to Eq. (1) for each U value studied.

We find for both sets of PBE+ U calculations that the in-plane and interplanar nearest-neighbor exchange constants J_1 and J_{1c} are antiferromagnetic ($J > 0$) and significantly larger in magnitude than the other three exchange constants, J_2 , J_{2c} , and J_{3c} (which are all ferromagnetic, $J < 0$). We note that this is also qualitatively consistent with a previous DFT study of the exchange constants in $\text{Fe}_{1/3}\text{NbS}_2$ with no Hubbard U correction ($U = 0$ eV) [32]. Focusing on the experimentally relevant a-stripe and a-zigzag phases, the difference in energy between a-stripe and a-zigzag phases using the above equation is given by

$$E_{\text{a-stripe}} - E_{\text{a-zigzag}} = 4J_{2c}S^2 - 4J_2S^2 - 8J_{3c}S^2, \quad (2)$$

where again, the interplanar J_{2c} and J_{3c} and in-plane J_2 are all (FM; $J < 0$). We see then that the condition for the a-stripe phase to be favored is $|J_{2c}| > |J_2| + 2|J_{3c}|$, whereas the a-zigzag is energetically favored when $|J_{2c}| < |J_2| + 2|J_{3c}|$. Thus, the fact that the ground state changes from the a-stripe to a-zigzag phase as a function of U can be connected to a shift in calculated relative values of three very small exchange constants (a table with all Heisenberg exchange constants in Eq. (1) for both U values is provided in the Supplemental Material [25]). Specifically, while the magnitudes of most of the $U = 0.9$ eV exchange constants diminish fairly uniformly relative to those calculated with $U = 0.3$ eV (as expected due to increased electron localization with larger U), the in-plane next-nearest-neighbor exchange constant J_2 grows with U . This is likely due the enhanced hybridization between Nb d and Fe d states in the $k_z = 0$ plane for PBE+ U with $U = 0.9$ eV compared to $U = 0.3$ eV (see the orbital-projected band structures in the Supplemental Material [25]). Because the magnetism in $\text{Fe}_{1/3}\text{NbS}_2$ and other magnetically intercalated TMDs is likely mediated by Ruderman-Kittel-Kasuya-Yosida (RKKY) interactions [13], enhanced hybridization between Fe and Nb states in the

FIG. 3. Electronic structure in the $k_z = 0$ plane of $\text{Fe}_{1/3}\text{NbS}_2$, with a finite broadening for aesthetic purposes of 10 meV for a-stripe order with (a) and (b) $U = 0.3$ and (e) and (f) $U = 0.9$ eV and 2 and 5 meV for a-zigzag order with (c) and (d) $U = 0.3$ and (g) and (h) $U = 0.9$ eV, respectively. The plots are colored by either the x or y component of the band velocity, as indicated at the top.

$k_z = 0$ plane would be consistent with larger long-range in-plane couplings.

Direct conclusions regarding the magnetic ground state of $\text{Fe}_{1/3}\text{NbS}_2$ for intercalations slightly below or above $x = \frac{1}{3}$ cannot, strictly speaking, be made from our PBE+ U calculations using this stoichiometric intercalation. Nevertheless, our PBE+ U result of competing ground states at $x = \frac{1}{3}$ is consistent with the experimental sensitivity of the magnetic ground state to small deviations from $\frac{1}{3}$. Moreover, the change in our computed exchange constants, and, consequently, in the magnetic ground state, for small changes in the U parameter is consistent with the recent neutron scattering report [33] suggesting that a-stripe and a-zigzag phases may coexist at $x = \frac{1}{3}$. If the experimental ground state at $x = \frac{1}{3}$ is, in fact, a superposition of a-stripe and a-zigzag phases, the changes in magnetic energetics as a function of U could reflect the fact that this compound is incompletely described by a single set of Heisenberg exchange constants. In any case, the experimental relevance of the a-stripe and a-zigzag phases, in addition to our PBE+ U findings that they are energetically competitive, motivates us to study the transport anisotropy of both magnetic orders in what follows.

V. FERMI SURFACE CROSS SECTIONS

We now examine cross sections of the Fermi surfaces (FSs) for a-stripe and a-zigzag orders computed with our two sets of PBE+ U calculations. We focus on electronic structure parallel to the k_x - k_y plane, relevant to the switching experiments. We plot Fermi contours in the $k_z = 0$ plane of the Brillouin zone (BZ); cuts of the k_x - k_y FS at other values of k_z are given in the Supplemental Material [25]. We focus first on the a-stripe FS, depicted in Figs. 3(a) and 3(b) and 3(e) and

3(f) for $U = 0.3$ and $U = 0.9$ eV, respectively. We consider the two U values for the reasons discussed in Sec. II. For both choices of U , the a-stripe FS results from relatively flat bands extending along the entire k_y direction of the BZ (k_x is parallel to the [100] crystallographic direction in real space, and k_y is parallel to [120]); we use the hexagonal notation of the primitive cell for crystallographic directions throughout the text). We gain a more explicit picture of the corresponding anisotropy in carrier transport by examining the in-plane components of the band velocities. Figures 3(a) and 3(b) are color-coded according to $v_x(k_0) = \frac{1}{\hbar} \frac{\partial E}{\partial k_x} \big|_{\mathbf{k}=\mathbf{k}_0, E=E_F}$, where x is along [100], E_F is the Fermi energy, and k_0 is a point in the k_x - k_y plane. Figures 3(b) and 3(f) are colored by v_y , whose magnitude is greatly reduced compared to v_x . This reduction suggests that, for the stripe phase, the conductance σ_{xx} along the x direction of the sample (parallel to the magnetic stripes in real space) will be higher than σ_{yy} (perpendicular to the stripes), and equivalently, the resistance $R_{xx} < R_{yy}$ for a-stripe order.

While still anisotropic, the a-zigzag FS cuts, depicted in Figs. 3(c), 3(d), 3(g), and 3(h) for $U = 0.3$ and $U = 0.9$ eV, are more symmetric compared to a-stripe, which is also evident from examining the band velocities. For PBE+ U with $U = 0.3$ the v_x and v_y components at E_F appear to be isotropic [Figs. 3(c) and 3(d)], likely a coincidental result due to this choice of U . The a-zigzag weight of v_y relative to v_x increases significantly for $U = 0.9$ eV [Figs. 3(g) and 3(h)]. This implies that the transport anisotropy in a-zigzag, at least for $U = 0.9$ eV, switches compared to stripe (i.e., for a-zigzag, $\sigma_{xx} < \sigma_{yy}$ and $R_{xx} > R_{yy}$). We point out that the large qualitative changes in the FS cross section for a-zigzag order in going from $U = 0.3$ to $U = 0.9$ eV compared to a-stripe order are presumably linked to the large number of

low-dispersion bands near the Fermi level for a-zigzag which are highly sensitive to small changes in U (see the Supplemental Material for orbital-projected band structures [25]).

VI. RESISTIVITY TENSOR AND SWITCHING

In order to understand the specific current-domain response implied by the FS anisotropies above, we can compute the resistivity tensor for monodomain $\text{Fe}_{1/3}\text{NbS}_2$ with input from our DFT calculations within the Kubo linear response formalism [34]. Within this formalism, using the eigenstate representation, the static conductivity tensor σ in the zero-temperature limit may be written as [35,36]

$$\sigma_{ij} = -\frac{e\hbar}{\pi} \sum_{\mathbf{k}, n, m} [\Gamma^2 \text{Re}(\langle n\mathbf{k} | \hat{v}_i | m\mathbf{k} \rangle \langle m\mathbf{k} | \hat{v}_j | n\mathbf{k} \rangle)] \times \{[(E_F - \epsilon_{n\mathbf{k}})^2 + \Gamma^2][(E_F - \epsilon_{m\mathbf{k}})^2 + \Gamma^2]\}^{-1}, \quad (3)$$

with $\epsilon_{n\mathbf{k}}$ being the eigenenergy of the corresponding eigenstate $|n\mathbf{k}\rangle$ and $\hat{v}_i$ being the velocity operator in the i th direction. The indices n and m run over all bands (occupied and unoccupied). We use a constant band broadening Γ , where $\Gamma = \frac{\hbar}{2\tau}$ is inversely proportional to the electron relaxation time τ , assuming τ is band and $\mathbf{k}$ independent, sufficient for our purposes. The Bloch eigenstates, eigenvalues, and velocity operators in Eq. (3) are constructed using Wannier functions obtained from our PBE+ U calculations, and Eq. (3) is evaluated using the WANNIER LINEAR RESPONSE software [37]. In general, the linear response conductivity can also contain a term which is odd under time reversal, whereas Eq. (3) is even under this operation [36]. However, both a-stripe and a-zigzag magnetisms possess time reversal symmetry plus a translation according to their magnetic space groups, such that the part of the conductivity which is odd under time reversal is necessarily zero, leaving us with only Eq. (3) to evaluate.

Apart from the approximations inherent in our conductivity tensors computed using Eq. (3), additional deviations from experimental results may come from our use of the pristine $x = \frac{1}{3}$ Fe concentration in all PBE+ U calculations, as the recent transport and switching experiments [15,38] were performed on Fe_xNbS_2 samples with a range of Fe concentrations $x \sim 0.31$ – 0.35 . Although NMR data suggest that a spin-glass coexists with the AFM order above and below $x = \frac{1}{3}$ and may well be the underlying mechanism for the efficient switching of the ordered magnetic domains [38], we expect that the electronic structure and transport anisotropy of the stripe and zigzag phases, which we focus on in this paper, will not differ significantly between slightly off-stoichiometry structures and the $x = \frac{1}{3}$ structure we use in our DFT calculations. Moreover, the NMR measurements, as well as contemporary neutron experiments [33], find evidence of a slight in-plane magnetic moment, in contrast to the earlier neutron studies [14,31]. However, given the strong magnetic anisotropy which favors spins pointing along the c axis in $\text{Fe}_{1/3}\text{NbS}_2$ [13,30], we expect our focus on calculations of transport properties with collinear magnetic order along c to be an acceptable simplification.

Having obtained conductivity tensors within the constant relaxation time approximation, the resistance R is then the resistivity $\rho = \sigma^{-1}$ multiplied by the ratio of device length

TABLE I. In-plane transport anisotropy computed for $\text{Fe}_{1/3}\text{NbS}_2$, defined as $A = \frac{R_{yy}}{R_{xx}}$ with x along [100], for a-zigzag and a-stripe phases for both U values used in our PBE+ U calculations. Absolute values of R_{xx} and the values of Γ used in Eq. (3) are provided as well.

	$U = 0.3$ eV		$U = 0.9$ eV	
	a-stripe	a-zigzag	a-stripe	a-zigzag
Γ (meV)	10	5	30	10
R_{xx} (Ω)	0.26	0.28	0.28	0.25
A	2.15	0.97	2.00	0.77

to cross-sectional area ($\sim 3.7 \times 10^{-4}$ cm)⁻¹ [15]. In order to meaningfully compare the anisotropy of the resistance tensors with different magnetic orders and U values, we treat Γ as a parameter and adjust it for each U and magnetic order such that the R_{xx} component of the tensor (corresponding to the resistance along the [100] direction) is roughly equivalent to the experimentally measured resistance of $\text{Fe}_{1/3}\text{NbS}_2$ samples, between 0.25 and 0.3 Ω [39]. Since the samples associated with these values are not monodomain [15], this measured value does not, strictly speaking, correspond to R_{xx} of a single-domain crystal, but we use it nonetheless to normalize the computed resistance tensors. We present the quantitative dependence of the resistance, as well as the in-plane anisotropy, on Γ for each magnetic ordering and U value in the Supplemental Material [25].

The results of our calculations appear in Table I. The transport anisotropy we compute from our PBE+ U calculations, which we define quantitatively as $A = \frac{R_{yy}}{R_{xx}}$, is consistent with the calculated band velocities in Fig. 3. For a-stripe ordering, R_{yy} along [120] is higher than R_{xx} along [100] by roughly a factor of 2, for both U values considered. With a-zigzag ordering, however, R_{yy} becomes smaller than R_{xx} ($A < 1$). For both sets of PBE+ U calculations, the transport anisotropy for a-zigzag is significantly reduced compared with stripe ordering. Indeed, for $U = 0.3$ eV the transport anisotropy is nearly unity for zigzag ordering.

Having obtained approximate resistivity tensors for monodomain $\text{Fe}_{1/3}\text{NbS}_2$ with a-stripe and a-zigzag ordering based on our PBE+ U calculations, we can infer the current-domain response by making a comparison with experiment. In the following discussion we use our PBE+ U results with $U = 0.9$ eV. In Fig. 4(a) we show the a - b plane of the $\text{Fe}_{1/3}\text{NbS}_2$ crystal overlaid with the directions of applied currents and measured resistances for the experiments in Refs. [15,38]. In these experiments, DC pulses, $\mathbf{J}^{\text{write}}$ and $\mathbf{J}_2^{\text{write}}$, were applied in succession along the $-k_y/[120]$ and $k_x/[100]$ crystallographic directions. The low-frequency AC current $\mathbf{J}^{\text{probe}}$ used to measure the sample resistance after each writing pulse was applied at an angle of 45° with respect to DC pulses. The transverse resistance $\mathbf{R}_\perp$ was read out along the contact which is orthogonal to $\mathbf{J}^{\text{probe}}$. Note that it is equal to the $\mathbf{R}_{xy}$ component of the resistance tensor with the x axis along $\mathbf{J}^{\text{probe}}$; we obtain this tensor by a rotation of our computed resistance matrix with the x axis along [100] [40] (see the Supplemental Material for details [25]). The experimental changes in $\mathbf{R}_\perp$, normalized by the longitudinal resistance $\mathbf{R}_\parallel$

FIG. 4. Electrical switching. (a) $\text{Fe}_{1/3}\text{NbS}_2$ crystal structure overlaid with directions of applied currents and measured resistance in experiment. In the experiment, orthogonal pulses applied along the red and blue arrows switch $\text{Fe}_{1/3}\text{NbS}_2$ between two states with different domain populations, detected by changes in the transverse resistance $\mathbf{R}_\perp$. (b) and (c) Calculated $\frac{\Delta R_\perp}{R_\parallel}$ based on Eqs. (4) (red) and (5) (blue) as a function of f_3 for a fixed initial value of f_1 . f_1 (f_3) can be viewed as the resulting fractional population of the domain with the principal axis along [100] after $\mathbf{J}_1^{\text{write}}$ ($\mathbf{J}_2^{\text{write}}$). (b) corresponds to the a-stripe phase, and (c) corresponds to the a-zigzag phase. Dashed lines [same color coding as the (PBE+ U)-derived points] indicate the value of f_3 where the calculated $\frac{\Delta R_\perp}{R_\parallel}$ agrees with the experimental data in Ref. [38] for Fe intercalations likely corresponding to a-stripe and a-zigzag order.

along $\mathbf{J}^{\text{probe}}$, are shown in Ref. [38] to be $\sim 2.5\%$ and $\sim 1.3\%$ (when normalized to the same DC pulse current density) for Fe intercalations corresponding to $x = 0.31$ and $x = 0.35$, respectively; the smaller intercalation was used in Ref. [15] as well. In addition to the reduction in magnitude of $\frac{\Delta R_\perp}{R_\parallel}$ going from the underintercalated to overintercalated sample, the sign of resistance change also switches; specifically, for $x = 0.31$ a pulse along $\mathbf{J}_1^{\text{write}}$ causes a decrease in $\mathbf{R}_\perp$, whereas for $x = 0.35$, $\Delta R_\perp$ is positive after a pulse along $\mathbf{J}_1^{\text{write}}$. In interpreting the experimental results, we assume that $x = 0.31$ and $x = 0.35$ correspond to a-stripe and a-zigzag orders, respectively, as implied by neutron measurements (in addition to the results by Van Laar *et al.* and Suzuki *et al.* [14,31], a recent more systematic analysis of Fe concentration specifically indicated a stripe ground state for $x < \frac{1}{3}$ and a zigzag AFM ground state for $x > \frac{1}{3}$ [33].) We note also that both zigzag and stripe magnetic space groups are consistent with the threefold AFM domain structure observed by Little *et al.* (where the zigzags/stripe directions for each domain are related by 120° rotations about c [16].)

With these assumptions of the experimental magnetic order, we can explore the implications of our computed re-

sistance tensors for domain repopulation with a-stripe and a-zigzag magnetisms. We assume the total transverse resistance after each $\mathbf{J}_1^{\text{write}}$ or $\mathbf{J}_2^{\text{write}}$ pulse is proportional to the sum of resistances of the three domains, weighted by their fractional areas f , analogous to previous studies of domain-based anisotropic magnetoresistance [41]. Then, we have

$$[1\bar{2}0]/\mathbf{J}_1^{\text{write}} \rightarrow \mathbf{R}_\perp^{\mathbf{J}_1^{\text{write}}} = f_1 \mathbf{R}_\perp^{[100]} + f_2 (\mathbf{R}_\perp^{[010]} + \mathbf{R}_\perp^{[\bar{1}\bar{1}0]}) \quad (4)$$

and

$$[100]/\mathbf{J}_2^{\text{write}} \rightarrow \mathbf{R}_\perp^{\mathbf{J}_2^{\text{write}}} = f_3 \mathbf{R}_\perp^{[100]} + f_4 (\mathbf{R}_\perp^{[010]} + \mathbf{R}_\perp^{[\bar{1}\bar{1}0]}), \quad (5)$$

where $\mathbf{R}_\perp^{[010]}$, for example, is the transverse resistance for a single domain with the principal axis along [010]. f_1 and f_2 are fractional domain populations after a $\mathbf{J}_1^{\text{write}}$ pulse, f_3 and f_4 result from a $\mathbf{J}_2^{\text{write}}$ pulse, and we set $f_2 = (1 - f_1)/2$ and $f_4 = (1 - f_3)/2$ in Eqs. (4) and (5) to ensure the fractions add to unity. We assume in each case that $f([1010]) = f([\bar{1}\bar{1}0])$ because both writing pulses bisect these two axes; the resistance tensors for the three domains are connected by rotations of $2\pi/3$ (see the Supplemental Material [25]). The $\mathbf{R}_\perp$ values in Eqs. (4) and (5) are obtained from the off-diagonal components of these tensors.

We can calculate the relative fractional domain changes required to reproduce the experimental switching amplitudes for the pulses, defined as

$$\frac{\Delta \mathbf{R}_\perp^{\mathbf{J}_1^{\text{write}}/\mathbf{J}_2^{\text{write}}}}{\bar{\mathbf{R}}_\parallel} = \frac{\mathbf{R}_\perp^{\mathbf{J}_1^{\text{write}}/\mathbf{J}_2^{\text{write}}} - \bar{\mathbf{R}}_\perp}{\bar{\mathbf{R}}_\parallel}, \quad (6)$$

where

$$\bar{\mathbf{R}}_\perp = (\mathbf{R}_\perp^{\mathbf{J}_1^{\text{write}}} + \mathbf{R}_\perp^{\mathbf{J}_2^{\text{write}}})/2, \quad \bar{\mathbf{R}}_\parallel = (\mathbf{R}_\parallel^{\mathbf{J}_1^{\text{write}}} + \mathbf{R}_\parallel^{\mathbf{J}_2^{\text{write}}})/2 \quad (7)$$

are the averages of the two resistances. We do this by selecting constant values of f_1 (fraction of the [100] domain after $\mathbf{J}_1^{\text{write}}$) and plotting $\frac{\Delta \mathbf{R}_\perp}{R_\parallel}$ for both $\mathbf{J}_1^{\text{write}}$ and $\mathbf{J}_2^{\text{write}}$ as a function of f_3 (fraction of the [100] domain after $\mathbf{J}_2^{\text{write}}$). Note that $\Delta \mathbf{R}_\perp^{\mathbf{J}_1^{\text{write}}}/\bar{\mathbf{R}}_\parallel$ and $\Delta \mathbf{R}_\perp^{\mathbf{J}_2^{\text{write}}}/\bar{\mathbf{R}}_\parallel$ are each dependent on both f_1 and f_3 through $\bar{\mathbf{R}}_\perp$ and $\bar{\mathbf{R}}_\parallel$ defined in Eq. (7). Results based on our PBE+ U (with $U = 0.9$ eV) calculations are shown in Figs. 4(b) and 4(c). In both plots we have selected f_1 such that the values of f_1 and f_3 which yield the experimental resistance changes are symmetrically displaced about $f = \frac{1}{3}$, which is the equilibrium fraction we would expect for all three domains in the absence of external current. We emphasize, however, that for a given magnetic order, the qualitative results are identical regardless of the value of f_1 ; that is, the sign and magnitude of the fractional change $f_1 - f_3$ of domain [100] between the pulses remains constant. The dashed lines correspond to the experimental percentage values for the intercalation corresponding to the same magnetic order. We see that, as a consequence of the crossover in the computed anisotropy from $A > 1$ for a-stripe to $A < 1$ for a-zigzag, the current-domain response for both magnetic structures is the same assuming the experimental data with opposite $\Delta \mathbf{R}_\perp$ signs indeed corresponds to the two proposed magnetic orders. Specifically, to replicate the correct sign of switching from experiment, for *both* a-stripe and a-zigzag orders, $f_1 - f_3 > 0$. This means that the $\mathbf{J}_1^{\text{write}}$ pulse along $[1\bar{2}0]$

causes a fractional increase in the orthogonal [100] domain, whereas the $\mathbf{J}_2^{\text{write}}$ pulse parallel to [100] destabilizes the [100] domain and increases the fraction of domains along [010] and $[\bar{1}\bar{1}0]$. Moreover, we can see that experimental reduction in switching amplitude for a-zigzag order compared to a-stripe is consistent with the reduced in-plane anisotropy we find for a-zigzag order in our PBE+ U calculations. Indeed, using our $U = 0.9$ eV PBE+ U results, the computed fractional changes from the equilibrium distribution $\frac{1}{3} : \frac{1}{3} : \frac{1}{3}$ required to match the corresponding experimental resistance changes are very close, $f_1 = 0.38$ for a-stripe and $f_1 = 0.395$ for a-zigzag, as one would expect for a given current density.

VII. DISCUSSION AND CONCLUSION

We have used DFT calculations to understand the magnetism and origins of the electrical switching observed in $\text{Fe}_{1/3}\text{NbS}_2$. Our PBE+ U calculations indicate that the experimentally proposed a-stripe and a-zigzag magnetic phases are nearly degenerate, consistent with neutron data [14,31,33] indicating that the ground state switches for small changes in Fe concentration. We found that the in-plane Fermi surface and corresponding transport for a-stripe order is anisotropic, with $R_{yy} > R_{xx}$, for all values of U used in our PBE+ U calculations. The FS and transport for a-zigzag order is also anisotropic, but the degree of anisotropy is reduced relative to stripe, and the quantitative results are highly sensitive to small changes in the Hubbard U used. Our findings suggest that there are two important factors leading to the particularly high anisotropy in the electronic structure and transport for stripe order in $\text{Fe}_{1/3}\text{NbS}_2$. First, the reduction of sixfold symmetry in the high-temperature paramagnetic phase to twofold symmetry due to the in-plane stripe magnetic order is consistent with the high anisotropy of the FS. Isostructural $\text{Co}_{1/3}\text{NbS}_2$, also believed to have a stripe ground state, has been reported to have an anisotropic FS with quasiflat bands much like $\text{Fe}_{1/3}\text{NbS}_2$ from prior DFT calculations [42]. With a-zigzag ordering, however, the anisotropy in the electronic structure and transport for $\text{Fe}_{1/3}\text{NbS}_2$, while still present, is significantly reduced in spite of an identical reduction to twofold rotational symmetry due to the magnetic order. This suggests that the magnetic interactions between nearest Fe neighbors may play an even larger role than rotational symmetry reduction in determining the degree of anisotropy in transport.

Our calculations also revealed that, for both a-zigzag and a-stripe magnetic orders, a pulse along a given direction should disfavor domains whose principal axes (and stripes/zigzags) are parallel to the pulse and increase the populations of the other two domains. This directional dependence has implications for the microscopic details of the mechanism responsible for the current-induced domain repopulation. Further studies are required to understand the origins of the current-domain coupling which leads to domains parallel to the current pulse being disfavored and whether this is consistent with the spin-glass-mediated spin-orbit torque mechanism proposed in Ref. [38].

For example, if further neutron scattering studies show unambiguously that the Fe spins in $\text{Fe}_{1/3}\text{NbS}_2$ have zero in-plane component, the origin of current-induced switching must differ from traditional spin-orbit torque mechanisms, including the spin-glass-mediated case proposed in Ref. [38]. The reason is because the in-plane directionality of the spin-orbit torque in the experimental geometry could not result in a switching between domains with the Néel vector fully along [001] for all three domains. In this situation, knowledge of the directionality of domain stabilization could inform the search for a novel switching mechanism that results in 180° flips of the [001]-oriented spins comprising the AFM domains. Overall, our transport and electronic structure calculations support repopulation of magnetic domains being the underlying cause of electrical switching in $\text{Fe}_{1/3}\text{NbS}_2$ and provide a platform for future studies.

ACKNOWLEDGMENTS

The authors wish to thank E. Maniv and S. Wu for invaluable discussions regarding the experimental data. This work is supported by the Center for Novel Pathways to Quantum Coherence in Materials, an Energy Frontier Research Center funded by the US Department of Energy, Director, Office of Science, Office of Basic Energy Sciences, under Contract No. DE-AC02-05CH11231. Computational resources were provided by the National Energy Research Scientific Computing Center (NERSC) through the US Department of Energy under the same contract number. Calculations were also performed on the Lawrence Livermore cluster, operated by Lawrence Berkeley National Laboratory, and on Savio, operated by the University of California, Berkeley.

-
- [1] A. Manchon, J. Železný, I. M. Miron, T. Jungwirth, J. Sinova, A. Thiaville, K. Garello, and P. Gambardella, *Rev. Mod. Phys.* **91**, 035004 (2019).
 - [2] A. Manchon and S. Zhang, *Phys. Rev. B* **78**, 212405 (2008).
 - [3] A. Manchon and S. Zhang, *Phys. Rev. B* **79**, 094422 (2009).
 - [4] V. V. Bel'kov and S. D. Ganichev, *Semicond. Sci. Technol.* **23**, 114003 (2008).
 - [5] S. Fukami and H. Ohno, *Jpn. J. Appl. Phys.* **56**, 0802A1 (2017).
 - [6] J. Sinova, S. O. Valenzuela, J. Wunderlich, C. H. Back, and T. Jungwirth, *Rev. Mod. Phys.* **87**, 1213 (2015).
 - [7] J. Železný, H. Gao, A. Manchon, F. Freimuth, Y. Mokrousov, J. Zemen, J. Mašek, J. Sinova, and T. Jungwirth, *Phys. Rev. B* **95**, 014403 (2017).
 - [8] K. Olejník, T. Seifert, Z. Kašpar, V. Novák, P. Wadley, R. P. Campion, M. Baumgartner, P. Gambardella, P. Nemec, J. Wunderlich, J. Sinova, P. Kužel, M. Müller, T. Kampfrath, and T. Jungwirth, *Sci. Adv.* **4**, eaar3566 (2018).
 - [9] P. Wadley *et al.*, *Science* **351**, 587 (2016).
 - [10] S. Y. Bodnar, L. Šmejkal, I. Turek, T. Jungwirth, O. Gomonay, J. Sinova, A. A. Sapozhnik, H. J. Elmers, M. Kläui, and M. Jourdan, *Nat. Commun.* **9**, 348 (2018).

- [11] T. Moriyama, K. Oda, T. Ohkochi, M. Kimata, and T. Ono, *Sci. Rep.* **8**, 14167 (2018).
- [12] X. Z. Chen, R. Zarzuela, J. Zhang, C. Song, X. F. Zhou, G. Y. Shi, F. Li, H. A. Zhou, W. J. Jiang, F. Pan, and Y. Tserkovnyak, *Phys. Rev. Lett.* **120**, 207204 (2018).
- [13] R. H. Friend, A. R. Beal, and A. D. Yoffe, *Philos. Mag.* **35**, 1269 (1977).
- [14] B. Van Laar, H. M. Rietveld, and D. J. Ijdo, *J. Solid State Chem.* **3**, 154 (1971).
- [15] N. L. Nair, E. Maniv, C. John, S. Doyle, J. Orenstein, and J. G. Analytis, *Nat. Mater.* **19**, 153 (2019).
- [16] A. Little, C. Lee, C. John, S. Doyle, E. Maniv, N. L. Nair, W. Chen, D. Rees, J. W. Venderbos, R. M. Fernandes, J. G. Analytis, and J. Orenstein, *Nat. Mater.* **19**, 1062 (2020).
- [17] M. J. Grzybowski, P. Wadley, K. W. Edmonds, R. Beardsley, V. Hills, R. P. Campion, B. L. Gallagher, J. S. Chauhan, V. Novak, T. Jungwirth, F. Maccherozzi, and S. S. Dhesi, *Phys. Rev. Lett.* **118**, 057701 (2017).
- [18] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- [19] J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).
- [20] P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- [21] P. E. Blöchl, O. Jepsen, and O. K. Andersen, *Phys. Rev. B* **49**, 16223 (1994).
- [22] N. Marzari and D. Vanderbilt, *Phys. Rev. B* **56**, 12847 (1997).
- [23] A. A. Mostofi, J. R. Yates, G. Pizzi, Y. S. Lee, I. Souza, D. Vanderbilt, and N. Marzari, *Comput. Phys. Commun.* **185**, 2309 (2014).
- [24] J. R. Yates, X. Wang, D. Vanderbilt, and I. Souza, *Phys. Rev. B* **75**, 195121 (2007).
- [25] See Supplemental Material at <http://link.aps.org/supplemental/10.1103/PhysRevB.103.214439> for PBE+ U details, energetics, band structures, Γ dependence on transport anisotropy, additional FS cuts, transport for $U = 4$, and rotation of the coordinate system for domains.
- [26] Q. S. Wu, S. N. Zhang, H. F. Song, M. Troyer, and A. A. Soluyanov, *Comput. Phys. Commun.* **224**, 405 (2018).
- [27] J. Zelezny, Wannier linear response (2018), <https://bitbucket.org/zeleznyj/wannier-linear-response/wiki/Home>.
- [28] V. I. Anisimov, F. Aryasetiawan, and A. I. Lichtenstein, *J. Phys.: Condens. Matter* **9**, 767 (1997).
- [29] S. Dudarev and G. Botton, *Phys. Rev. B* **57**, 1505 (1998).
- [30] S. C. Haley, S. F. Weber, T. Cookmeyer, D. E. Parker, E. Maniv, N. Maksimovic, C. John, S. Doyle, A. Maniv, S. K. Ramakrishna, A. P. Reyes, J. Singleton, J. E. Moore, J. B. Neaton, and J. G. Analytis, *Phys. Rev. Research* **2**, 043020 (2020).
- [31] Y. Suzuki, T. Ikeda, S. Richardson, and J. W. Yamaguchi, in *Proceedings of the Fifth International Symposium on Advanced Nuclear Energy Research* (Japan Atomic Energy Research Institute, Tokyo, Japan, 1993), pp. 343–346.
- [32] S. Mankovsky, S. Polesya, H. Ebert, and W. Bensch, *Phys. Rev. B* **94**, 184430 (2016).
- [33] S. Wu, Z. Xu, S. C. Haley, S. F. Weber, A. Acharya, E. Maniv, Y. Qiu, A. A. Aczel, J. B. Neaton, J. G. Analytis, and R. J. Birgeneau, *arXiv:2106.01341*.
- [34] G. D. Mahan, *Many-Particle Physics*, 3rd ed. (Plenum Press, New York, 2000).
- [35] F. Freimuth, S. Blügel, and Y. Mokrousov, *Phys. Rev. B* **90**, 174423 (2014).
- [36] J. Železný, Y. Zhang, C. Felser, and B. Yan, *Phys. Rev. Lett.* **119**, 187204 (2017).
- [37] J. Zelezny, Linear response symmetry (2017), <https://bitbucket.org/zeleznyj/linear-response-symmetry/src/master/>.
- [38] E. Maniv, N. Nair, S. C. Haley, S. Doyle, C. John, S. Cabrini, A. Maniv, S. K. Ramakrishna, Y. L. Tang, P. Ercius, R. Ramesh, Y. Tserkovnyak, A. P. Reyes, and J. Analytis, *Sci. Adv.* **7**, eabd8452 (2021).
- [39] E. Maniv (private communication).
- [40] W. Zhang, W. Han, S. H. Yang, Y. Sun, Y. Zhang, B. Yan, and S. S. Parkin, *Sci. Adv.* **2**, e1600759 (2016).
- [41] D. Kriegner, K. Výborný, K. Olejník, H. Reichlová, V. Novák, X. Marti, J. Gazquez, V. Saidl, P. Němec, V. V. Volobuev, G. Springholz, V. Holý, and T. Jungwirth, *Nat. Commun.* **7**, 11623 (2016).
- [42] P. Popčević, I. Batistić, A. Smontara, K. Velebit, J. Jaćimović, E. Martino, I. Živković, N. Tsyrlin, J. Piatek, H. Berger, A. A. Sidorenko, H. M. Rønnow, N. Barišić, L. Forró, and E. Tutiš, *arXiv:2003.08127*.