Lawrence Berkeley National Laboratory

Recent Work

Title

Advances in soft X-ray RIXS for studying redox reaction states in batteries.

Permalink

<https://escholarship.org/uc/item/622754j7>

Journal

Dalton transactions (Cambridge, England : 2003), 49(39)

ISSN

1477-9226

Authors

Wu, Jue
Yang, Yong
Yang, Wanli

Publication Date

2020-10-01

DOI

10.1039/d0dt01782e

Peer reviewed

Advances of soft X-ray RIXS for studying redox reaction states in batteries

Jue Wu^{1,2}, Yong Yang^{1,3*}, Wanli Yang^{2*}

¹ State Key Laboratory for Physical Chemistry of Solid Surfaces, Department of Chemistry, College of Chemistry and Chemical Engineering, Xiamen University, Xiamen 361005, China.

² Advanced Light Source, Lawrence Berkeley National Laboratory, One Cyclotron Road, Berkeley, California 94720, USA.

³ School of Energy Research, Xiamen University, Xiamen 361005, China.

E-mail: yyang@xmu.edu.cn; wlyang@lbl.gov.

Abstract: Redox (reduction and oxidation) chemistry provides the fundamental basis for numerous energy-related electrochemical devices. Detecting the electrochemical redox chemistry is pivotal but challenging, because it requires independent probes of the cationic and anionic redox states at different electrochemical states. The synchrotron-based soft X-ray mapping of resonant inelastic X-ray scattering (mRIXS) has recently emerged as a powerful tool for exploring such states in electrochemical devices, especially batteries. High-efficiency and wide energy-window mRIXS covers the energy range of the absorption edge with the extra dimension of information on the emitted photon energies. In this Frontiers article, we review recent representative demonstrations on utilizing soft X-ray mRIXS for detecting the novel chemical state during electrochemical operation, and for quantifying the cationic redox reactions through inverse partial fluorescence yield analysis (mRIXS-iPFY). More importantly, the unusual oxidation states of oxygen in electrodes involving oxygen redox reactions could be reliably captured by mRIXS, with its reversibility quantified by the intensity variation of the characteristic mRIXS feature through a super-partial fluorescence yield analysis (mRIXS-sPFY). These recent establishments inspire future perspectives on using mRIXS for studying the complex phenomena in energy materials, with both technical and scientific challenges on RIXS theory, *in-situ/operando* experiments, and spatially resolved RIXS imaging.

Introduction

Figure 1. Schematic of the practical challenges and cationic-anionic redox reactions in batteries. The high energy density, cyclability and safety are three ~~of the most~~ important goals for battery system. These goals are closely related to the intrinsic redox reaction mechanism in battery materials and the interfaces between electrodes and electrolyte/electrode/electrolyte interface, however, the detailed relationship between them is yet to be clarified.

Electric energy storage devices based on electrochemical operations (batteries) are the key components for many modern sustainable energy applications, such as electric vehicles and green power grid. However, the demand of high-capacity high-energy batteries that could operate at high voltage under a safe and reversible condition is yet to be met¹. In batteries, the electron charge transfer is coupled with the alkali-ion diffusion in/out of the electrodes, leading to the so-called “redox” (reduction and oxidation) reactions in the electrode materials. The redox chemistry provides the fundamental basis of electrochemical devices. Redox reaction mechanism essentially defines the capacity and stability of a battery electrode, and it may involve multiple elements in battery electrodes, especially for battery cathode. Currently, cathode has been the bottleneck of the battery capacity and used cathode materials are typically transition metal (TM) oxides^{2,3}, which principally implies that both cationic TM redox and anionic oxygen redox reactions could be triggered depending on the electrochemical operation.

Naively, there are always two types of possible redox chemistry, the cationic redox and anionic redox reactions in battery electrodes and electrode/electrolyte interface. The different types of redox reactions with different properties in amount, potential, reversibility and stability of redox reactions fundamentally define the capacity, voltage, life time, and safety, respectively³. In addition to the desired reversible redox reactions in batteries, undesired redox reactions, e.g., irreversible oxygen release, parasitic surface reactions, etc., also take place and lead to various battery problems such as voltage fade, capacity decay, voltage hysteresis and safety issues (**Figure 1**)³. Therefore, the in-depth detecting of an elemental and chemical resolved redox reaction mechanism becomes one of the most valuable information for understanding the operation mechanism and for optimizing the device performance.

In the conventional or commercialized Li-ion battery system, it is believed that only cationic TM reaction takes place in the practical voltage range. This often leads to a relatively stable battery operation with a typical voltage range below 4.1 V. In principle, almost all TMs could be active in the battery cathode if the cycling voltage triggers the TM redox reactions. The most typical TM elements involved in today's Li-ion batteries are Mn, Fe, Co, Ni in the cathodes, and Ti in the anodes in addition to the dominating Carbon based materials^{3,4}. Experimentally, the redox states of these 3d TMs are more often probed by *K*-edge hard X-ray absorption spectroscopy (XAS). The *K*-edge XAS benefits from the deep penetration depth of hard X-rays, so provides true bulk probe with convenient *in-situ/operando* experiments that are almost standard these days^{5,6,7}. Although *K*-edge XAS has been very popular in the battery field for characterizing TM redox states, the analysis often relies on the main edge shifting, which is not a directly 3d valence state probe and may be confusing as the edge features could vary significantly even with exactly the same oxidation state⁸. On the contrary, TM *L*-edge soft X-ray absorption spectroscopy (sXAS) is based on excitations directly to the valence 3d states, thus providing a more sensitive and direct probe of the TM oxidation states⁵. Due to the high sensitivity of TM-*L* sXAS to the oxidation states, sXAS spectra could be quantified directly to get almost precise numbers of the charge transfer numbers of TM redox reactions during battery operations, e.g., Fe^{2+/3+}, Mn^{2+/3+/4+}, Ni^{2+/3+/4+}, Co^{3+/4+} and so on^{9, 10, 11, 12}. The

disadvantages of sXAS stem from its shallow probe depth of 10 nm or 100-200 nm in different detection modes¹². The limitation on the sXAS probe depth complicates the *in-situ/operando* experiments^{13, 14,15}. Additionally, the TM *L*-edge signals of the hundreds of nanometer probe depth through the so-called fluorescence yield mode suffer serious spectral lineshape distortion, hindering its quantification. Fortunately, such a technical challenge could be addressed through the iPFY analysis, first demonstrated through commercial silicon drift detectors (SDD)¹⁶, and recently became accessible through mRIXS with much higher energy resolution^{17,18}, a topic that will be elaborated later in this article.

In order to push the capacity and voltage beyond what conventional battery system could offer, recent battery researches have focused on anionic oxygen redox. The hope is to realize and utilize reversible oxygen redox reactions for accessing the high-voltage high-capacity range of the battery operation¹⁹. However, the oxygen redox activities often trigger detrimental effects on the battery operation, such as gas release, surface reactions, voltage drop, and sluggish kinetics. At this time, neither the fundamental mechanism nor the optimization direction of cathode materials that could enable stable and reversible oxygen redox reaction has been clarified²⁰. Experimentally, detecting the lattice oxygen redox states has been a nontrivial issue. The popular X-ray photoelectron spectroscopy (XPS) has been questioned due to its surface sensitivity²¹. Additionally, we have recently clarified that another popular technique of O-*K* sXAS is not a reliable probe of oxygen redox states due to their dominating characters from TM states in the so-called “pre-edge” range^{17,22}, evidenced by the significant variation in non-oxygen redox systems, such as the olivine LiFePO₄ and spinel Li(Ni_{0.5}Mn_{1.5})O₄^{10, 11, 23}. As elaborated later, such a technical challenge has been solved recently through the development of ultra-high efficiency mRIXS technique^{17,18}.

The purpose of this Frontier article is to highlight these recent developments pertaining to the mRIXS technique and its impacts on exploring both the cationic and anionic redox states in battery electrodes. We first introduce the basic principle and instrument requirement of mRIXS technique for studying battery materials. Next, we demonstrate the superior power offered by Mn-*L* and O-*K* mRIXS. At the end, we provide our perspectives to elaborate how mRIXS could further impact the development of next-generation batteries in different

technical and scientific aspects. It is important to note that this article by no means covers all the topics of battery researches that could be tackled by soft X-ray spectroscopy, e.g., **the crucial surface and interface issue²⁴ between the electrodes and electrolyte^{24,25,26}**. Readers should refer to other general reviews on synchrotron-based techniques for studying batteries, especially those through the conventional techniques⁵. Instead, this article focuses on the recent mRIXS developments, demonstrations, and perspectives. We also note that although mRIXS has been quickly evolving in the field of battery research, the full potential of mRIXS is yet to be explored for energy material studies; a task that is still ongoing and deserves attention of scientists in different fields of physics, chemistry and material sciences.

The mRIXS instrument

Figure 2. The schematic of principle and instrument for mRIXS. (a) The states involved in the RIXS process and the simplified atomic model of XES (left) and RIXS (right). Reprinted with permission from ref.¹⁷. (b) Schematic illustration of the optical design for a high efficiency RIXS system. Reprinted with permission from ref.¹⁸. (c) Controlled X-ray and itinerant samples during experiments to eliminate the radiation damage effect. (d) Sample temperature controlled through cryogenic liquids. (e) Zero-air exposure sample handling through home-made transfer suitcase from the Ar-filled glovebox to soft X-ray experimental chamber.

Technically, the experimental detection of redox states in battery material is a nontrivial issue. The chemical state after electrochemical activation could be unstable in the air, especially on the surface, which requires sample handling without any exposure to the air. Secondly, the effect of X-ray irradiation could change the chemical states of the samples under investigation. For example, it has been found that the oxidized oxygen species could be changed under X-ray irradiation, and the RIXS signals of oxidized oxygen in battery materials could decrease in intensity upon exposure to X-ray beam^{27,28}. Therefore, zero-air-exposure sample handling and controlled experiments are vital for reliable analysis.

While X-ray spectroscopy has long been considered as elemental sensitive probes of the chemistry of materials, conventional techniques often show their limitations on detecting the critical chemical states in today's battery research, as briefly mentioned above. Therefore, the synchrotron-based RIXS has recently been optimized for measuring energy materials¹⁸. The simplified physical process for RIXS is schematically shown in **Figure 2a**. RIXS is a photon-in-photon-out (PIPO) process triggered by a core electron excitation from ground state via a tunable incident X-ray, i.e., the X-ray absorption process. The electron in excited states will then decay to fill generated core hole, which leads to different types of features in the decay process.

RIXS is a photon-hungry technique (very low fluorescence yield information in the soft X-ray regime), which naturally triggers the technical challenges in both statistics and radiation damages due to the required high flux of X-ray photons²⁸. Experimental details also involve the concerns that electrode materials are often air sensitive too. Therefore, tremendous efforts have been taken into mRIXS instrumentation to address these concerns: i) reduce the necessary X-ray radiation dose through the high efficiency spectrometer (**Figure 2b**)^{18, 29} and itinerant sample manipulation during measurements (**Figure 2c**)³⁰; ii) liquid nitrogen cooling to provide a low-temperature environment for certain samples, especially organic materials, to further reduce the risk of radiation damage (**Figure 2d**)³¹; iii) for air sensitivity materials, during the sample installation and transfer process, the sample will be protected in an inert argon atmosphere throughout the sample handling process via glovebox, home-made portable suitcase and load lock to avoid any air exposure (**Figure 2e**)¹².

1 TM-L mRIXS

2

3 **Figure 3 Characterizations of cationic and anionic redox states through mRIXS.** (a) The
 4 Mn-L sXAS, (b) Mn-L mRIXS and (c) mRIXS-iPFY spectra of a Li_2MnO_3 electrode. The
 5 peak in mRIXS-iPFY spectra comes from the inverse signals of integrated O-K XES feature
 6 (white box) in (b). (d) The O-K sXAS, (e) (f) O-K mRIXS for fully charged Li-rich
 7 $\text{Li}_{1.2}\text{Ni}_{0.13}\text{Mn}_{0.54}\text{Co}_{0.13}\text{O}_2$ electrode. (g) The mRIXS-sPFY results are obtained by integrating
 8 the signals in the white box in (f), and the oxidized oxygen feature (black arrow) intensity
 9 could be quantified by mRIXS-sPFY peak upon electrochemical cycling. The oxidized oxygen
 10 peak area of the mRIXS-sPFY is plotted in (g) together with the electrochemical profile.

11 In battery cathode, cationic redox reactions dominate the electrochemical operation.
 12 While we have demonstrated that, due to the high sensitivity of TM *L*-edge to the valence $3d$
 13 states, *L*-edge sXAS could be utilized for quantitative analysis of TM states³², the sXAS for
 14 such an analysis is limited to surface signals due to the serious distortion of the lineshape of
 15 the PIPO channel with bulk signals (**Figure 3a**). By extracting iPFY from the mRIXS result, a
 16 direct oxidation state quantification of bulk Mn is realized by Mn-L mRIXS-iPFY¹⁸. **Figure**

3b presents a typical Mn-*L* mRIXS data of a battery cathode, Li-rich Li₂MnO₃. It is a **two-dimensional map** with information including excitation energy, emission energy and emission peak intensity. The Mn-*L* mRIXS-iPFY spectra could be gained in two steps: firstly, integrate the O-*K* XES emission energy area (white dashed square in **Figure 3b**) in Mn-*L* mRIXS data; secondly, inverse the integrated O-*K* XES signal into iPFY signals (**Figure 3c**). The extracted mRIXS-iPFY data enables the quantitative analysis of the bulk Mn oxidation state based on the established linear-combination fitting method with references and/or calculations³². [The reviewer asked a fair question, you need to explain the final results (Fig. 3c) here!]

In battery materials, Mn is one of the most important TM elements, owing to its low cost, high abundance, and low toxicity. However, quantifying the Mn oxidation states has been challenging with conventional spectroscopic techniques, including XPS and hard X-ray Mn-*K* spectroscopy⁸. The combined sXAS surface signals and mRIXS-iPFY bulk data characterizes quantitatively the Mn oxidation state evolution on both the electrode surface and in the bulk upon electrochemical states³³.

Additionally, mRIXS data provides a new dimension of information along the emission energy that is completely missing in conventional sXAS spectra. This leads to the improved chemical sensitivity to novel oxidation state that cannot be clearly probed through conventional spectroscopy. For example, recent investigation in prussian blue analogs, Na_{1.24}Mn[Mn(CN)₆]·2.1H₂O through Mn-*L* mRIXS directly reveals the unusual monovalent manganese in the charged anode (**Figure 4d**)³⁴. This is the first time that a low spin 3d⁶ system, Mn¹⁺, is directly fingerprinted based on the power of mRIXS. In general, mRIXS has been developed as a highly valuable tool for systematically exploring the low-energy charge, spin, orbital and lattice excitations, which could be further extended in energy material³⁵.

These demonstrations highlight the unique ability of TM-*L* mRIXS data in revealing TM redox contribution for electrochemistry process. The results derived from TM-*L* mRIXS could either provide a quantitative evaluation of the bulk TM chemical states or detect novel chemical states in the battery systems that are hard to be sensed through other characterizations.

O-*K* mRIXS

A more important application of mRIXS studies on battery materials is to characterize the oxygen redox reaction in oxide-based battery cathodes. The oxygen activity usually consists of different types of oxygen-involved reactions, such as gas release, radical oxygen evolution and surface reaction³⁶. The mRIXS under the ultra-high vacuum condition naturally rules out the signals of the gas species, and distinguishes lattice oxygen redox reactions from other released oxygen. Compared with conventional O-K sXAS spectra (**Figure 3d**), mRIXS further resolves the emission energy of the signals. It has been found that a striking feature at around 523.7 eV emission energy and around 531.0 excitation energy appears in mRIXS (black arrow in **Figure 3e, 3f**) that is buried in the “pre-edge” of sXAS spectra (**Figure 3d**). Indeed, we have clarified that the O-K sXAS pre-edge is dominated by the TM character through strong hybridization effects, thus is not a reliable probe of oxygen redox states in oxide based battery electrodes^{17,22}. Such a feature was observed through high-efficiency gas phase mRIXS experiments of various oxidized oxygen species, such as Li₂O₂ and O₂^{37, 38}. For battery materials, this fingerprint of the oxidized oxygen has been confirmed in Li-rich layered cathode (**Figure 4c**)³⁹⁻⁴², Li-rich disordered rocksalt electrodes⁴³⁻⁴⁶, conventional Li-ion battery electrode materials⁴⁷⁻⁵⁰, and Na-ion battery materials^{33,51,52}. However, it is important to note that the fundamental mechanism of the oxygen redox reaction is still under active debates, and these mRIXS results have yet to be fully understood. A recent comparison on the mRIXS data for O⁻(Li₂O₂), O⁰(O₂), O²⁻(CO₂) and battery cathode oxide reveals that the oxidized oxygen state in battery material is beyond a simple molecular configuration of either the peroxide or oxygen gas type, and may be even different among different cathode materials³⁷.

For practical applications of oxygen redox reactions, the kinetics and the reversibility are always the most serious concerns²⁰. By virtue of the high sensitivity of mRIXS, the reversibility of oxygen redox reactions could be detected by tracking the evolution of the corresponding mRIXS feature intensity upon electrochemical cycling, which could be quantified through mRIXS-sPFY³³. During electrochemical operation, the intensity of the oxidized oxygen feature evolves systematically with the electrochemical charge-discharge process, indicating the reversibility of the oxygen redox reaction³⁰. As shown in **Figure 3f**, the

one-dimension sPFY spectra is gained via extracting and integrating the 523.7 eV emission energy feature (range from 523.0 eV to 524.5 eV emission energy). The reversibility of oxygen redox could then be gained via intensity comparisons between the charge and discharge states (**Figure 3g**). For example, $\text{Na}_{2/3}\text{Mg}_{1/3}\text{Mn}_{2/3}\text{O}_2$ has been confirmed delivering 79% reversible lattice oxygen redox in the initial cycle and 87% sustained after 100 cycles via O-K mRIXS-sPFY analysis (**Figure 4f**)³³.

Additionally, the mRIXS presents its superior sensitivity for probing the subtle change in chemical environment. The oxygen redox reaction behavior has been proposed being sensitive to the chemical environment, such as the local structure, surrounding atoms and interatomic interaction^{53,54}. However, detecting such a subtle change of the chemical environment is extremely difficult because the critical signals are usually buried in the strong background. Recently, by employing mRIXS, an intriguing interaction between the protons and oxygen is revealed in battery materials³¹. As shown in **Figure 4e**, compared with the reference samples, not only a reversible oxygen redox feature, but also a moderate coupling between lattice oxygen and protons through a beneficial inductive effect is directly observed through O-K mRIXS. The interaction probe provides valuable information on the detailed configuration in cathode oxide, and such findings from mRIXS open up new opportunities for studying the electrochemical energy storage material with subtle chemical variations. As another example, the local electronic structure of aqueous potassium chloride solution can be studied by RIXS to monitor the effect of the ion solvation on the hydrogen-bond network of liquid water. The significant change in the O K-edge RIXS spectra are observed upon KCl concentration change, which can be attributed to the modifications in the proton dynamics, caused by a specific coordination structure around the salt ions⁵⁵. Detecting these subtle chemical variations in battery system, e.g., chemistry in electrodes and solvation shells in electrolyte, has been a grand challenge for understanding and improving a battery system, mRIXS has now been demonstrated as a powerful tool to provide unprecedented information on these hard topics.

Conclusions and outlook

Milestones of mRIXS applications for battery studies

Figure 4. Milestones in the establishment of high efficiency mRIXS as a unique tool in battery research. The mRIXS technique is initially applied in HOPG material (a). Representative examples are selected to cover different aspects of mRIXS applications in both TMs (b, d) and oxygen state (c, e, f) characterizations. mRIXS figures are reprinted with permission from ref.^{29, 18, 39, 34, 33, 31}.

A battery is a complex system that is yet to be comprehensively understood. The redox states involved in battery operation are one of the keys in chemistry of the fundamental

1 mechanism and practical optimizations. As illustrated above, mRIXS technique has become
2 pivotal to reveal and characterize the redox states in both the cations and anions, sometimes as
3 almost the only choice for detecting unconventional chemical states in batteries. **Figure 4**
4 presents the key milestones in the development of mRIXS in the past decades. Due to the
5 reviewer asked about a better figure explanation, put the missing parts of the Fig. 4 panels
6 here. Most of them are already explained in the text above and in this paragraph below, but
7 some are still missing. Here, we highlight that mRIXS enables the mRIXS-iPFY detection
8 channel with superior energy resolution for quantitative measurements of the TM redox
9 reactions³³. The TM-*L* mRIXS features also provide much more sensitive detection of
10 unconventional state, e.g., Mn¹⁺, that cannot be sensed through any conventional technique³⁴.
11 More importantly, the improved chemical sensitivity through the new dimension of
12 information along emission energy could differentiate the intrinsic oxygen redox state from
13 the dominating signals from TM-O hybridization.

14 We note that the power of mRIXS has not been explored and capitalized on to its full
15 potential, e.g., the recent mRIXS detection of the subtle chemical changes of oxygen affected
16 by only an inductive effect opens up new opportunities of using mRIXS to study polyanionic
17 frameworks such as phosphates, silicates, and sulfates³¹. With new capabilities of mRIXS
18 being continuously explored, the employment of mRIXS for energy material researches will
19 becomes more and more indispensable.

20 Other than the advances in mRIXS techniques and experimental findings, we have to
21 realize that fully understanding the striking mRIXS features in energy materials remains a
22 grand challenge for spectroscopy physics, especially in theory. For example, although the
23 oxygen redox feature has been found in no divalent oxygen references like peroxide and O₂³⁸,
24 detailed comparison between them shows that the features of TM oxide based electrodes are
25 different from those reference compounds³⁷, indicating the fundamental form of the oxidized
26 oxygen may not be simply a molecular configuration. It is obviously that theoretical
27 interpretation of the mRIXS feature of TM oxide electrode holds the promise to uncover the
28 mystery of the oxidized oxygen state in the oxygen redox system, which deserves further
29 collaborative works between theoretical physics, spectroscopy, and material sciences.

1 The battery research has also evolved into extensive studies of solid-state batteries in
2 recent years, due to the benefit of solid-state electrolyte for potentially working with high
3 capacity electrode, e.g., Li metal, under safe operations. However, many scientific and
4 technical challenges remain⁵⁶. The mRIXS technique, with its superior chemical sensitivity
5 beyond conventional spectroscopic tools in both TM and O, as demonstrated here, provides
6 unique opportunities for studying the interface and high capacity electrode materials. On the
7 other hand, the solid-state electrolyte is naturally compatible with the ultra-high vacuum that
8 is required for soft X-ray spectroscopy experiments. Typical *in-situ* soft X-ray experiments
9 require sophisticated model cell systems that could only mimic the electrochemical operation
10 with complicated signals especially for O and C^{13, 14}. The solid-state battery setups could
11 enable straightforward *in-situ* setups for truly real-world experiments^{14, 17}. This mutual benefit
12 will further advance both the mRIXS technical developments and its scientific impacts.

13 Last but not the least, RIXS is principally a photon-hungry experiment, which often
14 triggers the concern of radiation damage, especially for the unconventional chemical states
15 that are often unstable. We note this problem will become more serious when the light
16 sources evolve into the next generation of diffraction limited rings. Obviously, merely
17 improving the incident X-ray beam will not solve this problem. Enhancing the detecting
18 efficiency with relatively broadened beam size has been demonstrated to be an effective
19 solution⁵⁰, which requires continuous innovations in spectrometer designs that not only
20 focuses on resolution but also throughput. Unfortunately, the broadened beam size casts a
21 natural limitation on the spatial resolution of the mRIXS technique. Such a dilemma could
22 only be resolved if mRIXS could be performed in an imaging mode without the need of beam
23 focusing. This formidable challenge has recently been cracked through a spectrometer based
24 on Wolter-mirror designs with other technical advances, through which, a spatial resolution of
25 100 nm with a time resolution of 1 ns could be achieved⁵⁷. We expect that, coupled with the
26 new-generation diffraction-limited light sources, further developments of RIXS technique into
27 the spatial and temporal domains, coupled with its superior elemental and chemical
28 sensitivities, will further revolutionize the characterizations of energy materials in a vast field
29 beyond battery research.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This research was financially supported by National Natural Science Foundation of China (Grant No. 21935009, 21761132030). X-ray experiments were performed at the Advanced Light Source (ALS) at Lawrence Berkeley National Laboratory, a US DOE Office of Science User Facility. W.Y. acknowledges the supported from DOE EERE VTO under the Applied Battery Materials Program, both under contract No. DE-AC02-05CH11231. J.W. acknowledges the support from the Energy & Biosciences Institute through the EBI-Shell program, the ALS student fellowship program, graduate exchange program of Xiamen University and the College of Chemistry and Chemical Engineering of Xiamen University.

References

1. J.-M. Tarascon and M. Armand, *Nature*, 2011, **414**, 171-179.
2. M. S. Whittingham, *Chem. Rev.*, 2004, **104**, 4271-4302.
3. J. B. Goodenough and Y. Kim, *Chem. Mater.*, 2010, **22**, 587-603.
4. B. L. Ellis, K. T. Lee and L. F. Nazar, *Chem. Mater.*, 2010, **22**, 691-714.
5. F. Lin, Y. Liu, X. Yu, L. Cheng, A. Singer, O. G. Shpyrko, H. L. Xin, N. Tamura, C. Tian and T.-C. Weng, *Chem. Rev.*, 2017, **117**, 13123-13186.
6. X. Yu, Y. Lyu, L. Gu, H. Wu, S.-M. Bak, Y. Zhou, K. Amine, S. N. Ehrlich, H. Li, K.-W. Nam and X.-Q. Yang, *Adv. Energy Mater.*, 2014, **4**, 1300950.
7. Y.-N. Zhou, J.-L. Yue, E. Hu, H. Li, L. Gu, K.-W. Nam, S.-M. Bak, X. Yu, J. Liu, J. Bai, E. Dooryhee, Z.-W. Fu and X.-Q. Yang, *Adv. Energy Mater.*, 2016, **6**, 1600597.
8. A. Manceau, M. A. Marcus and S. Grangeon, *Am. Mineral.*, 2012, **97**, 816-827.
9. X. Liu, J. Liu, R. Qiao, Y. Yu, H. Li, L. Suo, Y. S. Hu, Y. D. Chuang, G. Shu, F. Chou, T. C. Weng, D. Nordlund, D. Sokaras, Y. J. Wang, H. Lin, B. Barbiellini, A. Bansil, X. Song, Z. Liu, S. Yan, G. Liu, S. Qiao, T. J. Richardson, D. Prendergast, Z. Hussain, F. M. de Groot and W. Yang, *J. Am. Chem. Soc.*, 2012, **134**, 13708-13715.
10. R. Qiao, Y. Wang, P. Olalde-Velasco, H. Li, Y.-S. Hu and W. Yang, *J. Power Sources*, 2015, **273**, 1120-1126.
11. R. Qiao, L. A. Wray, J.-H. Kim, N. P. W. Pieczonka, S. J. Harris and W. Yang, *J. Phys. Chem. C*, 2015, **119**, 27228-27233.
12. W. Yang, X. Liu, R. Qiao, P. Olalde-Velasco, J. D. Spear, L. Roseguo, J. X. Pepper, J. D. Denlinger and Z. Hussain, *J. Electron Spectrosc. Relat. Phenom.*, 2013, **190**, 64-74.
13. J. Guo, *J. Electron Spectrosc. Relat. Phenom.*, 2013, **188**, 71-78.
14. X. Liu, W. Yang and Z. Liu, *Adv. Mater.*, 2014, **26**, 7710-7729.
15. X. Liu, D. Wang, G. Liu, V. Srinivasan, Z. Liu, Z. Hussain and W. Yang, *Nat.*

- 1 *Commun.*, 2013, **4**, 2568.
- 2 16. A. J. Achkar, T. Z. Regier, H. Wadati, Y. J. Kim, H. Zhang and D. G. Hawthorn, *Phys.*
3 *Rev. B*, 2011, **83**, 081106.
- 4 17. W. Yang and T. P. Devereaux, *J. Power Sources*, 2018, **389**, 188-197.
- 5 18. R. Qiao, Q. Li, Z. Zhuo, S. Sallis, O. Fuchs, M. Blum, L. Weinhardt, C. Heske, J.
6 Pepper, M. Jones, A. Brown, A. Spucces, K. Chow, B. Smith, P. A. Glans, Y. Chen, S.
7 Yan, F. Pan, L. F. Piper, J. Denlinger, J. Guo, Z. Hussain, Y. D. Chuang and W. Yang,
8 *Rev. Sci. Instrum.*, 2017, **88**, 033106.
- 9 19. A. Grimaud, W. Hong, Y. Shao-Horn and J.-M. Tarascon, *Nat. Mater.*, 2016, **15**, 121-
10 126.
- 11 20. G. Assat and J.-M. Tarascon, *Nat. Energy*, 2018, **3**, 373-386.
- 12 21. Z. W. Lebens-Higgins, H. Chung, M. J. Zuba, J. Rana, Y. Li, N. V. Faenza, N. Pereira,
13 B. D. McCloskey, F. Rodolakis, W. Yang, M. S. Whittingham, G. G. Amatucci, Y. S.
14 Meng, T.-L. Lee and L. F. J. Piper, *J. Phys. Chem. Lett.*, 2020, **11**, 2106-2112.
- 15 22. Q. Ruimin, R. Subhayan, Z. Zengqing, L. Qinghao, L. Yingchun, K. Jung-Hyun, L.
16 Jun, L. Eungje, P. Bryant J, G. Jinghua, Y. Shishen, H. Yongsheng, L. Hong, P. David
17 and Y. Wanli, 2019, DOI: 10.26434/chemrxiv.11416374.v2.
- 18 23. X. Liu, Y. J. Wang, B. Barbiellini, H. Hafiz, S. Basak, J. Liu, T. Richardson, G. Shu, F.
19 Chou and T.-C. Weng, *Phys. Chem. Chem. Phys.*, 2015, **17**, 26369-26377.
- 20 24. Z. Q. Zhuo, P. Lu, C. Delacourt, R. M. Qiao, K. Xu, F. Pan, S. J. Harris and W. L. Yang,
21 *Chem. Commun.*, 2018, **54**, 814-817.
- 22 25. R. Qiao, I. T. Lucas, A. Karim, J. Syzdek, X. Liu, W. Chen, K. Persson, R. Kostecki and
23 W. Yang, *Adv. Mater. Interfaces*, 2014, **1**, 1300115.
- 24 26. Q. H. Li, S. S. Yan and W. L. Yang, *J. Chem. Phys.*, 2020, **152**, 140901.
- 25 27. R. Qiao, Y. D. Chuang, S. Yan and W. Yang, *PLoS ONE*, 2012, **7**, e49182.
- 26 28. Z. W. Lebens-Higgins, J. Vinckeviciute, J. Wu, N. V. Faenza, Y. Li, S. Sallis, N. Pereira,
27 Y. S. Meng, G. G. Amatucci and A. V. Der Ven, *J. Phys. Chem. C*, 2019, **123**, 13201-
28 13207.
- 29 29. O. Fuchs, L. Weinhardt, M. Blum, M. Weigand, E. Umbach, M. Baer, C. Heske, J.
30 Denlinger, Y. D. Chuang, W. McKinney, Z. Hussain, E. Gullikson, M. Jones, P. Batson,
31 B. Nelles and R. Follath, *Rev. Sci. Instrum.*, 2009, **80**, 063103.
- 32 30. J. Wu, Q. Li, S. Sallis, Z. Zhuo, W. E. Gent, W. C. Chueh, S. Yan, Y.-d. Chuang and W.
33 Yang, *Condens. Matter*, 2019, **4**, 5.
- 34 31. J. Wu, X. Zhang, S. Zheng, H. Liu, J. Wu, R. Fu, Y. Li, Y. Xiang, R. Liu, W. Zuo, Z. Cui,
35 Q. Wu, S. Wu, Z. Chen, P. Liu, W. Yang and Y. Yang, *ACS Appl. Mater. Interfaces*,
36 2020, **12**, 7277-7284.
- 37 32. Q. Li, R. Qiao, L. A. Wray, J. Chen, Z. Zhuo, Y. Chen, S. Yan, F. Pan, Z. Hussain and
38 W. Yang, *J. Phys. D: Appl. Phys.*, 2016, **49**, 413003.
- 39 33. K. Dai, J. Wu, Z. Zhuo, Q. Li, S. Sallis, J. Mao, G. Ai, C. Sun, Z. Li, W. E. Gent, W. C.
40 Chueh, Y.-d. Chuang, R. Zeng, Z.-x. Shen, F. Pan, S. Yan, L. F. J. Piper, Z. Hussain, G.
41 Liu and W. Yang, *Joule*, 2019, **3**, 518-541.
- 42 34. A. Firouzi, R. Qiao, S. Motallebi, C. W. Valencia, H. S. Israel, M. Fujimoto, L. A. Wray,
43 Y. D. Chuang, W. Yang and C. D. Wessells, *Nat. Commun.*, 2018, **9**, 861.
- 44 35. L. J. Ament, M. Van Veenendaal, T. P. Devereaux, J. P. Hill and J. Van Den Brink, *Rev.*

- 1 *Mod. Phys.*, 2011, **83**, 705.
- 2 36. W. Yang, *Nat. Energy*, 2018, **3**, 619-620.
- 3 37. Z. Zhuo, Y.-S. Liu, J. Guo, Y.-d. Chuang, F. Pan and W. Yang, *J. Phys. Chem. Lett.*,
4 2020, **11**, 2618-2623.
- 5 38. Z. Zhuo, C. D. Pemmaraju, J. Vinson, C. Jia, B. Moritz, I. Lee, S. Sallies, Q. Li, J. Wu,
6 K. Dai, Y. D. Chuang, Z. Hussain, F. Pan, T. P. Devereaux and W. Yang, *J. Phys.*
7 *Chem. Lett.*, 2018, **9**, 6378-6384.
- 8 39. W. E. Gent, K. Lim, Y. Liang, Q. Li, T. Barnes, S. J. Ahn, K. H. Stone, M. McIntire, J.
9 Hong, J. H. Song, Y. Li, A. Mehta, S. Ermon, T. Tyliczszak, D. Kilcoyne, D. Vine, J. H.
10 Park, S. K. Doo, M. F. Toney, W. Yang, D. Prendergast and W. C. Chueh, *Nat.*
11 *Commun.*, 2017, **8**, 2091.
- 12 40. J. Xu, M. Sun, R. Qiao, S. E. Renfrew, L. Ma, T. Wu, S. Hwang, D. Nordlund, D. Su, K.
13 Amine, J. Lu, B. D. McCloskey, W. Yang and W. Tong, *Nat. Commun.*, 2018, **9**, 947.
- 14 41. S. Ramakrishnan, B. Park, J. Wu, W. Yang and B. D. McCloskey, *J. Am. Chem. Soc.*,
15 2020, **142**, 8522-8531.
- 16 42. J. Wu, Q. Li, S. Sallis, Z. Zhuo, W. Gent, W. Chueh, S. Yan, Y.-d. Chuang and W. Yang,
17 *Condens. Matter*, 2019, **4**, 5.
- 18 43. E. Zhao, Q. Li, F. Meng, J. Liu, J. Wang, L. He, Z. Jiang, Q. Zhang, X. Yu, L. Gu, W.
19 Yang, H. Li, F. Wang and X. Huang, *Angew. Chem., Int. Ed.*, 2019, **58**, 4323-4327.
- 20 44. H. Ji, J. Wu, Z. Cai, J. Liu, D.-H. Kwon, H. Kim, A. Urban, J. K. Papp, E. Foley, Y. Tian,
21 M. Balasubramanian, H. Kim, R. J. Clement, B. D. McCloskey, W. Yang and G.
22 Ceder, *Nat. Energy*, 2020, **5**, 213-221.
- 23 45. D. Chen, J. Wu, J. K. Papp, B. D. McCloskey, W. Yang and G. Chen, *Small*, 2020, DOI:
24 10.1002/smll.202000656.
- 25 46. M. Luo, S. Zheng, J. Wu, K. Zhou, M. Feng, H. He, R. Liu, G. Zhao, S. Chen, W. Yang,
26 Z. Peng, Q. Wu and Y. Yang, *J. Mater. Chem. A*, 2020, **8**, 5115-5127.
- 27 47. J.-N. Zhang, Q. Li, C. Ouyang, X. Yu, M. Ge, X. Huang, E. Hu, C. Ma, S. Li, R. Xiao,
28 W. Yang, Y. Chu, Y. Liu, H. Yu, X.-Q. Yang, X. Huang, L. Chen and H. Li, *Nat. Energy*,
29 2019, **4**, 594-603.
- 30 48. G.-H. Lee, J. Wu, D. Kim, K. Cho, M. Cho, W. Yang and Y. Kang, *Angew. Chem., Int.*
31 *Ed.*, 2020, **59**, 8681-8688.
- 32 49. N. Li, S. Sallis, J. K. Papp, J. Wei, B. D. McCloskey, W. Yang and W. Tong, *ACS Energy*
33 *Lett.*, 2019, **4**, 2836-2842.
- 34 50. Z. W. Lebens-Higgins, N. V. Faenza, M. D. Radin, H. Liu, S. Sallis, J. Rana, J.
35 Vinckeviciute, P. J. Reeves, M. J. Zuba, F. Badway, N. Pereira, K. W. Chapman, T.-L.
36 Lee, T. Wu, C. P. Grey, B. C. Melot, A. Van Der Ven, G. G. Amatucci, W. Yang and L.
37 F. J. Piper, *Mater. Horiz.*, 2019, **6**, 2112-2123.
- 38 51. J. Wu, Z. Zhuo, X. Rong, K. Dai, Z. Lebens-Higgins, S. Sallis, F. Pan, L. F. J. Piper, G.
39 Liu, Y.-d. Chuang, Z. Hussain, Q. Li, R. Zeng, Z.-x. Shen and W. Yang, *Sci. Adv.*,
40 2020, **6**, eaaw3871.
- 41 52. K. Dai, J. Mao, Z. Zhuo, Y. Feng, W. Mao, G. Ai, F. Pan, Y.-d. Chuang, G. Liu and W.
42 Yang, *Nano Energy*, 2020, **74**, 104831.
- 43 53. D.-H. Seo, J. Lee, A. Urban, R. Malik, S. Kang and G. Ceder, *Nat. Chem.*, 2016, **8**,
44 692.

- 1 54. N. Yabuuchi, M. Nakayama, M. Takeuchi, S. Komaba, Y. Hashimoto, T. Mukai, H.
2 Shiiba, K. Sato, Y. Kobayashi and A. Nakao, *Nat. Commun.*, 2016, **7**, 1-10.
- 3 55. Y. L. Jeyachandran, F. Meyer, S. Nagarajan, A. Benkert, M. Baer, M. Blum, W. Yang,
4 F. Reinert, C. Heske, L. Weinhardt and M. Zharnikov, *J. Phys. Chem. Lett.*, 2014, **5**,
5 4143-4148.
- 6 56. Y. Xiang, X. Li, Y. Cheng, X. Sun and Y. Yang, *Mater. Today*, 2020.
- 7 57. Y.-D. Chuang, X. Feng, P.-A. Glans-Suzuki, W. Yang, H. Padmore and J. Guo, *J.*
8 *Synchrotron Rad.*, 2020, **27**, 695-707.
9