UC Berkeley

UC Berkeley Previously Published Works

Title

High Photoluminescence Quantum Yield in Band Gap Tunable Bromide Containing Mixed Halide Perovskites.

Permalink

<https://escholarship.org/uc/item/67k7r3w9>

Journal

Nano letters, 16(1)

ISSN

1530-6984

Authors

Sutter-Fella, Carolin M
Li, Yanbo
Amani, Martin
et al.

Publication Date

2016

DOI

10.1021/acs.nanolett.5b04884

Peer reviewed

This document is confidential and is proprietary to the American Chemical Society and its authors. Do not copy or disclose without written permission. If you have received this item in error, notify the sender and delete all copies.

High Photoluminescence Quantum Yield in Band Gap Tunable Bromide Containing Mixed Halide Perovskites

Journal:	<i>Nano Letters</i>
Manuscript ID	Draft
Manuscript Type:	Communication
Date Submitted by the Author:	n/a
Complete List of Authors:	Sutter-Fella, Carolin; UC Berkeley - EECS, EECS Li, Yanbo; Joint Center for Artificial Photosynthesis, Lawrence Berkeley National Laboratory Amani, Matin; UC Berkeley, Electrical Engineering and Computer Science Ager, Joel; Lawrence Berkeley National Laboratory, Materials Sciences Division Toma, Francesca; Joint Center for Artificial Photosynthesis, Lawrence Berkeley National Lab Yablonovitch, Eli; UC Berkeley, EECS Sharp, Ian; Lawrence Berkeley National Laboratory, Joint Center for Artificial Photosynthesis Javey, Ali; UC Berkeley, EECS

SCHOLARONE™
Manuscripts

High Photoluminescence Quantum Yield in Band Gap Tunable Bromide Containing Mixed Halide Perovskites

Carolyn M. Sutter-Fella^{†‡⊥}, Yanbo Li^{§⊥}, Martin Amani^{†‡}, Joel W. Ager III^{‡#}, Francesca M. Toma^{§⊥}, Eli Yablonovitch^{†‡}, Ian D. Sharp^{§⊥}, and Ali Javey^{†‡*}*

[†] Electrical Engineering and Computer Sciences, University of California, Berkeley, CA 94720, United States

[‡] Materials Sciences Division, Lawrence Berkeley National Laboratory, Berkeley, CA 94720, United States

[§] Joint Center for Artificial Photosynthesis, Lawrence Berkeley National Laboratory, CA 94720, United States

[⊥] Chemical Sciences Division, Lawrence Berkeley National Laboratory, Berkeley, CA 94720, United States

[#] Materials Science and Engineering, University of California, Berkeley, CA 94720, United States

KEYWORDS halide perovskite, wide band gap semiconductor, quantum yield, tandem device

1
2
3 ABSTRACT Hybrid organic-inorganic halide perovskite based semiconductor materials are
4
5 attractive for use in a wide range of optoelectronic devices because they combine the advantages
6
7 of suitable optoelectronic attributes and simultaneously low-cost solution processability. Here we
8
9 present a two-step low pressure vapor-assisted solution process to grow high quality
10
11 homogeneous $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ perovskite films over the full band gap range of 1.6 eV to 2.3
12
13 eV. Photoluminescence light-in versus light-out characterization techniques are used to provide
14
15 new insights into the optoelectronic properties of Br-containing hybrid organic-inorganic
16
17 perovskites as a function of optical carrier injection by employing pump-powers over a six order
18
19 of magnitude dynamic range. The internal luminescence quantum yield of wide band gap
20
21 perovskites reaches impressive values up to 30%. This high quantum yield translates into
22
23 substantial quasi-Fermi level splitting, and high “luminescence or optically implied” open-circuit
24
25 voltage. Most importantly, both attributes, high internal quantum yield and high optically
26
27 implied open-circuit voltage, are demonstrated over the entire band gap range ($1.6 \text{ eV} \leq E_g \leq 2.3$
28
29 eV). These results demonstrate the versatility of Br-containing perovskite semiconductors for a
30
31 variety of applications and especially for the use as high quality top cell in tandem photovoltaic
32
33 devices in combination with industry dominant Si bottom cells.
34
35
36
37
38
39
40
41
42
43
44

45 Hybrid organic-inorganic halide perovskites are a new class of semiconductors that have
46
47 attracted significant research attention in the last few years.¹ These materials offer several
48
49 advantages over conventional semiconductors such as low-cost solution processability^{2,3} at low
50
51 temperatures,⁴ high defect tolerance,^{5,6} and the tunability of the optical band gap over a large
52
53 range.⁷ Within this class of materials, methyl ammonium lead halides, $\text{CH}_3\text{NH}_3\text{PbX}_3$ ($\text{X} = \text{Cl}, \text{Br},$
54
55 I or combinations thereof) have been most extensively studied. Indeed, mixed I/Br halide
56
57
58
59
60

perovskites ($\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$) offer tunable band gaps in the visible and near-infrared range, from 1.57 – 2.29 eV.⁷ Considering the facile methods used to deposit organic-inorganic perovskites, they possess surprisingly good optoelectronic attributes. These include high absorption coefficient,⁸ low Urbach energy,⁸ long minority carrier lifetime and diffusion lengths,^{9–12} and high photoluminescence quantum yield.^{13,14} As a result, perovskites are not only attractive for the use in single junction solar cells, which have been demonstrated with certified efficiencies above 20%,^{15,16} but also promising candidates for application as the top cell in tandem devices, for example in combination with Si^{17–19} or $\text{Cu}(\text{In,Ga})\text{Se}_2$.^{19,20} Moreover, they offer desirable properties for use as light emitting devices such as LEDs^{21,22} and lasers gain media.^{13,23}

Specifically, for the case of tandem photovoltaic devices with a Si bottom cell ($E_g = 1.12$ eV), ideally a top cell with a band gap of $\sim 1.65 - 1.9$ eV should be employed to reach efficiencies close to $\sim 35\%$ under 1-sun AM1.5G illumination.^{24,25} So far, the material choice for the top cell was limited to InGaP,²⁵ AlGaAs²⁶ or (In)GaN.^{27,28} There are, however, practical constraints related to growth of these semiconductors on Si, arising from large lattice mismatch and high temperature processing requirements. Here, we show that mixed halide perovskites in the $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ composition space combine low temperature processability and high intrinsic material quality over the full band gap range from 1.6 – 2.3 eV, thus making them ideal candidates for tandem photovoltaic devices in combination with Si.

A universal metric to judge the intrinsic optoelectronic quality of a semiconductor is the internal radiative efficiency or internal photoluminescence (PL) quantum yield (iQY), which is defined as the number of photons radiatively emitted divided by the number of photons absorbed and corrected for the refractive index. This quantity is equivalent to the radiative recombination

rate over the sum of radiative and non-radiative recombination rates. In an ideal semiconductor material there is only radiative recombination due to the absence of trap states, thus the iQY is 100%. Defects in the semiconductor, as well as at its interface, lead to non-radiative recombination at trap sites, also known as Shockley-Read-Hall (SRH) recombination, and, as a result, reduce the iQY. High QY, however, is important for solar cells because it directly affects the open-circuit voltage (V_{oc}) and thus the conversion efficiency.²⁹ The optically implied V_{oc} is defined as $qV_{oc} = E_g - T\Delta S - kT|\ln QY|$,^{29,30} where q is the elementary charge, E_g the band gap, k the Boltzmann constant, T the absolute temperature, and S the entropy. The recombination as a function of optical carrier injection in these materials is studied by using pump-power dependent photoluminescence measurements. The pump-power corresponds to an effective carrier concentration in the material, as generated by light, and is referred to as optical carrier injection. From these results we are able to predict an optimum carrier concentration for the respective material compositions at which the intrinsic optoelectronic quality is the highest as reflected by the maximum iQY.

Most of the studies on optoelectronic properties of perovskites have been centered around the pure $\text{CH}_3\text{NH}_3\text{PbI}_3$ ^{9,11,23,31,32} and mixed $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Cl}_x$ ^{9,10,13,14,23,32,33} compositions. Only a few studies have reported on the optoelectronic properties of Br containing perovskites.^{7,34–36} While high iQY has been demonstrated only for the low band gap perovskites ($E_g \sim 1.6$ eV) without Br,^{13,14} this study addresses the full band gap range and investigates the mixed lead halide perovskites ($\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$), thereby significantly broadening the spectrum of possible applications in optoelectronic devices. We present a synthetic approach to fabricate high optoelectronic quality $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ over the entire composition range and demonstrate impressive iQY values up to 30% using in-depth photoluminescence based characterization as a

function of halide composition. Most notably, the iQY is high over the entire band gap range, which translates into high optically implied open-circuit voltage. Furthermore, halide perovskites synthesized using our approach exhibit significantly improved phase stability over an expanded composition range. This study thus establishes the potential of the band gap tunable $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ ($1.6 \text{ eV} \leq E_g \leq 2.3 \text{ eV}$) system as an efficient and low-cost building block for both solar cells and light emitting devices.

Perovskite thin films with varying Br concentration were fabricated by a two-step low pressure vapor-assisted solution process (LP-VASP) that is adapted to allow controllable synthetic access to the full $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ composition space, as depicted in Figure 1. First, mixed lead halide ($\text{PbI}_2/\text{PbBr}_2$) was spin-coated onto the glass substrate and dried at 110°C for 15 min. Second, the precursor film was annealed in $\text{CH}_3\text{NH}_3\text{I}/\text{CH}_3\text{NH}_3\text{Br}$ vapor at 120°C for 2 h under a pressure of ~ 0.4 Torr.³⁷ Br incorporation occurs via a dynamic exchange with the vapor and the equilibrium composition is defined by the partial pressures of the $\text{CH}_3\text{NH}_3\text{I}/\text{CH}_3\text{NH}_3\text{Br}$ precursors in the vapor phase (for more details, see Methods section in the Supporting Information). It is demonstrated that the full compositional range of $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ ($x = 0 - 3$) can be processed with very high spatial uniformity. Perovskite films were coated with a ~ 30 nm thick poly(methyl methacrylate) (PMMA) capping layer to prevent exposure to moisture, which is known to cause degradation in this material system.³⁸ Top view SEM images (Supporting Information, Figure 1) show that films are highly faceted, pin-hole free, and exhibit grain sizes up to ~ 500 nm. Figure 2a shows the optical absorption spectra obtained from transmittance (T%) and reflectance (R%) measurements taken for the full range of band gap tuned perovskite films. All samples exhibit sharp absorption onsets above the band edge, with absorption coefficients $\alpha > 10^4 \text{ cm}^{-1}$ (Supporting Information, Figure S2a). An increase in the Br concentration monotonically shifts

the absorption onset to higher energies. The non-linear dependence of the band gap on composition x can be fitted with the empirical equation: $E_g(x) = E_g(\text{CH}_3\text{NH}_3\text{PbBr}_3)^{\frac{x}{3}} + E_g(\text{CH}_3\text{NH}_3\text{PbI}_3)(1 - \frac{x}{3}) - \frac{x}{3}(1 - \frac{x}{3})b$ with the bowing parameter $b = 0.34$ and $0 \leq x \leq 3$ is the atomic Br fraction (Supporting Information, Figure S2b). The obtained bowing parameter is in good agreement with literature.⁷ Samples with composition $x \geq 2$ exhibit a peak at the absorption edge that is likely related to an excitonic transition that appears due to the higher exciton binding energy³⁹ at high Br concentration. The below band gap absorption artifact seen for all samples is caused by constructive thin-film interference effects due to multiple reflections at the air/PMMA and PMMA/perovskite interfaces. Steady state PL spectra are presented in Figure 2b. The PL spectra are slightly blue shifted (anti-Stokes shift of ~ 10 nm or 30 meV) with respect to the absorption onset. The precise position of the absorption edge, as well as the PL peak position, can change depending on the exciton binding energy and self-absorption in the perovskite film²³ or as a result of the lattice phonon-photon interaction.

The X-ray diffraction (XRD) patterns (Figure 2c) of the perovskite films reveal that there is no phase separation into I- and Br-rich domains. These data also indicate that the majority of the starting PbI_2 / PbBr_2 precursor is converted to the mixed halide $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ phase by incorporation of Br via the gas phase (compare Figure 1). The (110) peak gradually shifts to larger angles with increasing Br concentration (XRD zoom in Figure 2d) due to the decreasing lattice parameter with increasing x .

The optoelectronic uniformity of the perovskite films was characterized via PL imaging over large areas ($>100 \times 100 \mu\text{m}^2$) by analyzing the integrated luminescence peak. The PL images as well as the standard deviation of the measured luminescence are presented in Figure 3. The

spatial homogeneity exhibits a maximum standard deviation of $< 30\%$. The insets illustrate the point-to-point variation of the PL spectra, with invariant lineshapes, confirming the uniformity of the films. While we note that local intra- and inter-grain non-uniformities may exist at length scales below those probed here,¹⁰ our results indicate excellent homogeneity over large areas and are consistent with the reproducible iQY measurements presented in this work (Supporting Information, Figure S6c).

Next, the pump-power dependent steady state PL at room temperature was investigated to identify the recombination regimes occurring in the perovskite films as a function of optically injected carrier concentration. Figure 4a illustrates the pump-power dependence of the PL intensity over a six orders of magnitude dynamic range, with minimum power of $7 \times 10^{-4} \text{ W/cm}^2$ up to a maximum power of $5 \times 10^2 \text{ W/cm}^2$. The excitation intensity is divided by the film thickness to establish the generation rate $G \text{ (s}^{-1} \text{ cm}^{-3}\text{)}$. The Measurements were performed starting at the lowest pump-power and were terminated when sample degradation was observed as the pump-power was increased (for experimental details see Supporting Information).

It is important to note, that various illumination-induced effects were observed in the course of this work. Data points at the respective pump-power are only considered in this study if the spectral shape and position of the PL signal did not change during the measurement. By exceeding an illumination intensity threshold (that is specific to the Br concentration, Supporting Information Figure S3 and Figures S4c+d) a reversible shift in PL spectra by up to $\sim 20 \text{ nm}$ (or 45 meV) accompanied by a drop in intensity is observed (Supporting Information, Figure S4b). Samples with $x > 1.25$ (Supporting Information, Figure S3) are more prone to show a spectral red shift and slight peak broadening with increasing pump-power. At low pump-power, the PL intensity is constant over time (Supporting Information, Figure S5a). Illumination-induced phase

transformations of $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ have been previously reported. Films prepared by spin-coating of the precursor followed by hot plate annealing were previously shown to undergo light-induced reversible phase separation for $x \geq 0.6$ at 0.15 suns illumination intensity within less than a minute.⁴⁰ This was attributed to the formation of I-rich domains.⁴⁰ In comparison, for LP-VASP $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ samples with $x = 1.4$ only a small spectral red shift is observed within two minutes at 2 suns illumination intensity (Supporting Information, Figure S5b). The observed red shift is small compared to the previous report and might be explained by minor illumination-induced local compositional variation in the Br/I ratio. A reversible phase segregation under illumination (below 1 sun), similar to the previous report of solution processed thin films,⁴⁰ was only seen for $x \geq 2$ (Supporting Information, Figure S5c). We conclude that the material quality and stability of $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ grown from our LP-VASP exhibits superior light-stability.

The luminescence intensity versus generation rate G (Figure 4a and Supporting Information Figure S6a), is characterized by power law fits that indicate two regimes for the mixed halide samples. Up to a generation rate of $G \sim 3 \times 10^{22} \text{ s}^{-1} \text{ cm}^{-3}$ (~ 30 suns; 1-sun is used equivalent to the power density of 100 mW/cm^2) the curves follow a dependence $\propto G^{1.7}$, and for generation rates above $3 \times 10^{22} \text{ s}^{-1} \text{ cm}^{-3}$ the luminescence intensity is $\propto G^{0.9}$. Power law dependences larger than one are indicative of SRH like recombination, that is intra-gap trap assisted recombination instead of direct electron-hole recombination (bimolecular recombination). A PL intensity dependence with the generation rate $\propto G^{1.5}$ was observed by Saba *et al.*²³ At low intensities, traps are filled first, before bimolecular recombination starts to dominate as the pump-power increases. The pure Br sample ($x = 3$) exhibits a single trend line that is $\propto G^{1.8}$ indicating only monomolecular recombination over the investigated generation rate.

The QY is extracted from the pump-power dependent PL measurements. The measured external luminescence efficiency is corrected for the band-edge refractive index⁴¹ to determine the internal quantum yield (iQY). The details of the measurement set-up and calibration of the PL data are reported in our previous study.⁴² With increasing pump-power, the iQY rises for all samples, indicating that trap states lead to low iQY at low optical injection levels (see Figure 4b, Supporting Information Figure S6b). As seen in the pump-power dependent luminescence study (Figure 4a), bimolecular recombination dominates when reaching $G \geq 3 \times 10^{22} \text{ s}^{-1} \text{ cm}^{-3}$ (slope $\propto 1$), where the iQY is constant over almost two orders of magnitude of generation rate (observable for sample with $x = 0.1$). At higher optical injection, Auger recombination begins to dominate, leading to a drop in iQY when exceeding a generation rate $G \sim 5 \times 10^{24} \text{ s}^{-1} \text{ cm}^{-3}$ (~ 500 suns). The iQY of the pure Br sample ($x = 3$) shows a completely different behavior: first, the iQY in general is almost two orders of magnitude lower compared to mixed halide samples at the respective pump-power. Second, the iQY increases over the entire range of investigated generation rates, indicating a limitation by monomolecular trap assisted recombination. The iQY of the investigated samples reaches a maximum value of 30%. We would like to highlight, that all $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ samples over the full band gap range exhibit remarkably high iQY values, as summarized in Figure 4c (the upper x-axis as a function of the Br concentration is obtained by using the equation given in the Supporting Information, Figure S2b). It is noted that our reported iQY values for samples in which the Auger regime cannot be reached do not represent the maximum achievable values but are instead limited by material degradation under intense illumination (that strongly depends on the Br concentration). The spot-to-spot variation of the iQY on the same sample is minimal as shown in the Supporting Information, Figure S6c.

To elucidate the possible effect of laser illumination-induced heating of the perovskite thin films, PL is studied over a temperature range of 170 K to 410 K (Supporting Information, Figure S7). The lower bound of the temperature dependent measurements is set by a phase change, from a tetragonal to an orthorhombic crystal system at 150 K^{43,44} and the higher bound is limited by the PMMA glass transition temperature. Surprisingly, the sample shows extraordinary stability at elevated temperatures with a PL intensity drop to 65% of the room temperature value at 400 K. With decreasing temperature we see a small red shift in the PL spectra. This finding was observed earlier for CH₃NH₃PbI₃ as well as CH₃NH₃PbI_{3-x}Cl_x and is often seen for Pb containing semiconductors.⁴⁴ Moreover, the PL intensity increases by 40% at 210 K, relative to the room temperature value (Supporting Information, Figure S7). A 40% PL intensity increase directly translates to the same increase in the iQY. The rise of iQY with decreasing temperature can simply be explained by a reduced trap activity, which eventually diminishes to zero at sufficiently low temperatures.

Pulsed laser excitation of CH₃NH₃PbI_{3-x}Br_x samples was investigated to extract the minority carrier lifetimes. Results are discussed in the Supporting Information, along with the modeling of both the TRPL and steady-state iQY data (Figure S9).

In order to relate the above presented results to the V_{oc} , an important metric for solar cells, the optically implied V_{oc} is calculated and illustrated in Figure 5. The optically implied V_{oc} is calculated as $qV_{oc} = E_g - T\Delta S - kT \ln iQY$.^{29,30} That is, the V_{oc} (i.e. chemical potential difference) is treated as a thermodynamic variable, where the entropy due to non-ideality is equal to 260 meV in the band gap range of 1.0-1.8 eV.⁴⁵⁻⁴⁷ Here, the optically implied V_{oc} reflects the maximum V_{oc} that can be achieved purely based on the intrinsic material quality, assuming no optical losses nor losses caused by non-ideal contact architectures. Figure 5 illustrates the

1
2
3 evolution of the optically implied V_{oc} with increasing band gap at 1 sun (blue squares) as well as
4
5 under optimized carrier injection level (red circles) as calculated from the maximum iQY. The
6
7 V_{oc} deficit ($E_g/q - V_{oc}$) is about 400 mV at 1 sun up to a band gap of 1.97 eV and increases to 480
8
9 mV at 2.28 eV. The V_{oc} deficit can be reduced by ~60 mV for samples with Br concentration up
10
11 to $x = 2$ and by 150 mV for the pure Br sample at the respective optimized carrier injection level
12
13 (i.e. illumination intensity) for each composition. Please note that the optimized carrier injection
14
15 is extracted from the iQY versus pump-power analysis. Samples with $x > 0.8$ show 1 sun V_{oc}
16
17 very close to the optimized carrier injection conditions because the samples degrade under higher
18
19 pump-powers, thus higher generation rates cannot be accessed experimentally in this study. The
20
21 best state-of-the art perovskite solar cells, with band gaps of ~1.55 eV, exhibit electrical V_{oc}
22
23 deficits of about 450 mV.⁴⁸ As a comparison, the lowest reported V_{oc} deficit is 298 mV, which
24
25 has been achieved in high quality single crystalline GaAs solar cells.¹⁶ In literature on perovskite
26
27 solar cell devices, the electrical V_{oc} values drop significantly with increasing band gap (see
28
29 Supporting Information, Figure S10). This study points out that the reported electrical V_{oc} of
30
31 higher band gap perovskites is limited by the choice of the selective contact material but not the
32
33 perovskite material itself if Br-containing films using the described process are utilized.
34
35
36
37
38
39
40
41

42 In summary, we have established a low pressure vapor-assisted solution process that is adapted
43
44 to synthetically access the full set of band gap tunable $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ perovskites with phase
45
46 purity. Uniform and high quality films were obtained and studied by photoluminescence based
47
48 spectroscopy over the full compositional range of $x = 0 - 3$. The dependency of iQY on
49
50 generation rate (i.e., illumination intensity), which defines the optically injected carrier
51
52 concentration, was used to determine the optimal operation range for each perovskite
53
54 composition. Our results indicate that Br-containing perovskites exhibit high optoelectronic
55
56
57
58
59
60

quality over the entire compositional range ($1.6 \text{ eV} \leq E_g \leq 2.3 \text{ eV}$) with iQYs as high as 30%. Importantly, we observe improved photo-stability of $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ films formed by LP-VASP compared to previously reported solution processed material. Based on this study, we conclude that hybrid organic-inorganic mixed halide perovskites $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ possess suitable optical band gaps and high iQY, which makes them highly promising candidates as top cell materials in conjunction with industry dominated Si bottom cells. Future work should focus on building perovskite/Si tandem photovoltaic cells using the described Br-containing films.

FIGURES

Figure 1. Process scheme for the low pressure vapor-assisted solution process (LP-VASP). Mixed lead halide $\text{PbI}_2/\text{PbBr}_2$ is spin-coated onto the glass substrate, dried, and then annealed in $\text{CH}_3\text{NH}_3\text{I}/\text{CH}_3\text{NH}_3\text{Br}$ vapor at low pressure to yield the $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ films.

Figure 2. Br-containing perovskite film characterization. (a) UV-VIS absorption spectra of perovskite films on glass substrate with PMMA cap extracted from transmittance and reflectance measurements. (b) Photoluminescence spectra recorded at room temperature, excited with an Argon laser (with $\lambda = 514\text{ nm}$; and for $x=3$ with $\lambda = 488\text{ nm}$) and (c,d) X-ray diffraction patterns of the investigated set of samples.

Figure 3. Photoluminescence imaging of Br-containing perovskite films. (a-f) Photoluminescence imaging in counts per second and the corresponding standard deviation (given in %) taken over an area $> 100 \times 100\text{ }\mu\text{m}^2$. The insets show representative variation of PL spectra from spot-to-spot.

Figure 4. Steady-state photoluminescence. (a) Pump-power dependence of the integrated photoluminescence signal for three Br concentrations. (b) Pump-power dependence of the iQY. (c) Summary of iQY versus $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Br}_x$ composition and corresponding band gap.

Figure 5. Optically implied V_{oc} ($qV_{oc} = E_g - T\Delta S - kT|\ln iQY|$), representing the V_{oc} that can be obtained based on the intrinsic material quality as a function of band gap, at one sun equivalent (blue squares) and at optimized illumination (red points). Optimized illumination refers to the carrier injection level at which the iQY is at the maximum value. Blue and red solid lines show linear fits to the data, dashed line: band gap, solid line: band gap less $T\Delta S$.

ASSOCIATED CONTENT

Supporting Information. Detailed experimental procedures, Figures S1-10 and kinetic modeling of PL and TRPL data. This material is available free of charge via the Internet at <http://pubs.acs.org>.

AUTHOR INFORMATION

Corresponding Author

*E-mail Ian D. Sharp: idsharp@lbl.gov

*E-mail Ali Javey: ajavey@berkeley.edu

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript. [†]These authors contributed equally.

Acknowledgement

The optical characterization and quantum yield measurements were supported by the Electronic Materials program, funded by the Director, Office of Science, Office of Basic Energy Sciences, Materials Sciences and Engineering Division of the U.S. Department of Energy under Contract No. DE-AC02-05CH11231. Perovskite process development, thin film synthesis, and structural characterization were performed at the Joint Center for Artificial Photosynthesis, a DOE Energy Innovation Hub, supported through the Office of Science of the US Department of Energy under

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Award Number DE-SC0004993. SEM/EDX measurements were performed at the Molecular Foundry. C. M. S.-F. acknowledges financial support from the Swiss National Science Foundation (P2EZP2_155586).

REFERENCES

- (1) Stranks, S. D.; Snaith, H. J. *Nat. Nanotechnol.* **2015**, *10* (5), 391–402.
- (2) Nie, W.; Tsai, H.; Asadpour, R.; Blancon, J.-C.; Neukirch, A. J.; Gupta, G.; Crochet, J. J.; Chhowalla, M.; Tretiak, S.; Alam, M. A.; Wang, H.-L.; Mohite, A. D. *Science* **2015**, *347* (6221), 522–525.
- (3) Docampo, P.; Hanusch, F. C.; Stranks, S. D.; Döblinger, M.; Feckl, J. M.; Ehrensperger, M.; Minar, N. K.; Johnston, M. B.; Snaith, H. J.; Bein, T. *Adv. Energy Mater.* **2014**, *4* (14), n/a – n/a.
- (4) Ball, J. M.; Lee, M. M.; Hey, A.; Snaith, H. J. *Energy Environ. Sci.* **2013**, *6* (6), 1739–1743.
- (5) Yin, W.-J.; Shi, T.; Yan, Y. *Appl. Phys. Lett.* **2014**, *104* (6), 063903.
- (6) Kim, J.; Lee, S.-H.; Lee, J. H.; Hong, K.-H. *J. Phys. Chem. Lett.* **2014**, *5* (8), 1312–1317.
- (7) Noh, J. H.; Im, S. H.; Heo, J. H.; Mandal, T. N.; Seok, S. I. *Nano Lett.* **2013**, *13* (4), 1764–1769.
- (8) De Wolf, S.; Holovsky, J.; Moon, S.-J.; Löper, P.; Niesen, B.; Ledinsky, M.; Haug, F.-J.; Yum, J.-H.; Ballif, C. *J. Phys. Chem. Lett.* **2014**, *5* (6), 1035–1039.
- (9) Stranks, S. D.; Eperon, G. E.; Grancini, G.; Menelaou, C.; Alcocer, M. J. P.; Leijtens, T.; Herz, L. M.; Petrozza, A.; Snaith, H. J. *Science* **2013**, *342* (6156), 341–344.
- (10) Quillettes, D. W. de; Vorpahl, S. M.; Stranks, S. D.; Nagaoka, H.; Eperon, G. E.; Ziffer, M. E.; Snaith, H. J.; Ginger, D. S. *Science* **2015**, *348* (6235), 683–686.
- (11) Xing, G.; Mathews, N.; Sun, S.; Lim, S. S.; Lam, Y. M.; Grätzel, M.; Mhaisalkar, S.; Sum, T. C. *Science* **2013**, *342* (6156), 344–347.
- (12) Dong, Q.; Fang, Y.; Shao, Y.; Mulligan, P.; Qiu, J.; Cao, L.; Huang, J. *Science* **2015**, *347* (6225), 967–970.
- (13) Deschler, F.; Price, M.; Pathak, S.; Klintberg, L. E.; Jarausch, D.-D.; Higler, R.; Hüttner, S.; Leijtens, T.; Stranks, S. D.; Snaith, H. J.; Atatüre, M.; Phillips, R. T.; Friend, R. H. *J. Phys. Chem. Lett.* **2014**, *5* (8), 1421–1426.
- (14) Stranks, S. D.; Burlakov, V. M.; Leijtens, T.; Ball, J. M.; Goriely, A.; Snaith, H. J. *Phys. Rev. Appl.* **2014**, *2* (3), 034007.
- (15) Jeon, N. J.; Noh, J. H.; Yang, W. S.; Kim, Y. C.; Ryu, S.; Seo, J.; Seok, S. I. *Nature* **2015**, *517* (7535), 476–480.
- (16) Green, M. A.; Emery, K.; Hishikawa, Y.; Warta, W.; Dunlop, E. D. *Prog. Photovolt. Res. Appl.* **2015**, *23* (1), 1–9.
- (17) Löper, P.; Moon, S.-J.; Nicolas, S. M. de; Niesen, B.; Ledinsky, M.; Nicolay, S.; Bailat,

- J.; Yum, J.-H.; Wolf, S. D.; Ballif, C. *Phys. Chem. Chem. Phys.* **2014**, *17* (3), 1619–1629.
- (18) Mailoa, J. P.; Bailie, C. D.; Johlin, E. C.; Hoke, E. T.; Akey, A. J.; Nguyen, W. H.; McGehee, M. D.; Buonassisi, T. *Appl. Phys. Lett.* **2015**, *106* (12), 121105.
- (19) Bailie, C. D.; Christoforo, M. G.; Mailoa, J. P.; Bowring, A. R.; Unger, E. L.; Nguyen, W. H.; Burschka, J.; Pellet, N.; Lee, J. Z.; Grätzel, M.; Noufi, R.; Buonassisi, T.; Salleo, A.; McGehee, M. D. *Energy Environ. Sci.* **2015**, *8* (3), 956–963.
- (20) Kranz, L.; Abate, A.; Feurer, T.; Fu, F.; Avancini, E.; Löckinger, J.; Reinhard, P.; Zakeeruddin, S. M.; Grätzel, M.; Buecheler, S.; Tiwari, A. N. *J. Phys. Chem. Lett.* **2015**, *6* (14), 2676–2681.
- (21) Tan, Z.-K.; Moghaddam, R. S.; Lai, M. L.; Docampo, P.; Higler, R.; Deschler, F.; Price, M.; Sadhanala, A.; Pazos, L. M.; Credgington, D.; Hanusch, F.; Bein, T.; Snaith, H. J.; Friend, R. H. *Nat. Nanotechnol.* **2014**, *9* (9), 687–692.
- (22) Ning, Z.; Gong, X.; Comin, R.; Walters, G.; Fan, F.; Voznyy, O.; Yassitepe, E.; Buin, A.; Hoogland, S.; Sargent, E. H. *Nature* **2015**, *523* (7560), 324–328.
- (23) Saba, M.; Cadelano, M.; Marongiu, D.; Chen, F.; Sarritzu, V.; Sestu, N.; Figus, C.; Aresti, M.; Piras, R.; Geddo, A.; Lehmann, A.; Cannas, C.; Musinu, A.; Quochi, F.; Mura, A.; Bongiovanni, G. *Nat. Commun.* **2014**, *5*, 5049.
- (24) Bremner, S. P.; Levy, M. Y.; Honsberg, C. B. *Prog. Photovolt. Res. Appl.* **2008**, *16* (3), 225–233.
- (25) Essig, S.; Ward, S.; Steiner, M. A.; Friedman, D. J.; Geisz, J. F.; Stradins, P.; Young, D. L. *Energy Procedia* **2015**, *77*, 464–469.
- (26) Soga, T.; Baskar, K.; Kato, T.; Jimbo, T.; Umeno, M. *J. Cryst. Growth* **1997**, *174* (1–4), 579–584.
- (27) Hsu, L.; Walukiewicz, W. *J. Appl. Phys.* **2008**, *104* (2), 024507.
- (28) L. A. Reichertz; I. Gherasoiu; Yu, K. M.; Kao, V. M.; Walukiewicz, W.; Ager III, J. W. *Appl. Phys. Express* **2009**, *2*, 122202.
- (29) Miller, O. D.; Yablonovitch, E.; Kurtz, S. R. *IEEE J. Photovolt.* **2012**, *2* (3), 303–311.
- (30) Ross, R. T. *J. Chem. Phys.* **1967**, *46* (12), 4590–4593.
- (31) La-o-vorakiat, C.; Salim, T.; Kadro, J.; Khuc, M.-T.; Haselsberger, R.; Cheng, L.; Xia, H.; Gurzadyan, G. G.; Su, H.; Lam, Y. M.; Marcus, R. A.; Michel-Beyerle, M.-E.; Chia, E. E. M. *Nat. Commun.* **2015**, *6*, 7903.
- (32) D’Innocenzo, V.; Srimath Kandada, A. R.; De Bastiani, M.; Gandini, M.; Petrozza, A. *J. Am. Chem. Soc.* **2014**, *136* (51), 17730–17733.
- (33) Chen, Q.; Zhou, H.; Fang, Y.; Stieg, A. Z.; Song, T.-B.; Wang, H.-H.; Xu, X.; Liu, Y.; Lu, S.; You, J.; Sun, P.; McKay, J.; Goorsky, M. S.; Yang, Y. *Nat. Commun.* **2015**, *6*, 7269.

- (34) Liang, P.-W.; Chueh, C.-C.; Xin, X.-K.; Zuo, F.; Williams, S. T.; Liao, C.-Y.; Jen, A. K.-Y. *Adv. Energy Mater.* **2015**, 5 (1), n/a – n/a.
- (35) Eperon, G. E.; Stranks, S. D.; Menelaou, C.; Johnston, M. B.; Herz, L. M.; Snaith, H. J. *Energy Environ. Sci.* **2014**, 7 (3), 982–988.
- (36) Yang, Y.; Yan, Y.; Yang, M.; Choi, S.; Zhu, K.; Luther, J. M.; Beard, M. C. *Nat. Commun.* **2015**, 6, 7961.
- (37) Li, Y.; Cooper, J. K.; Buonsanti, R.; Giannini, C.; Liu, Y.; Toma, F. M.; Sharp, I. D. *J. Phys. Chem. Lett.* **2015**, 6 (3), 493–499.
- (38) Matsumoto, F.; Vorpahl, S. M.; Banks, J. Q.; Sengupta, E.; Ginger, D. S. *J. Phys. Chem. C* **2015**, 119 (36), 20810–20816.
- (39) Tanaka, K.; Takahashi, T.; Ban, T.; Kondo, T.; Uchida, K.; Miura, N. *Solid State Commun.* **2003**, 127 (9–10), 619–623.
- (40) Hoke, E. T.; Slotcavage, D. J.; Dohner, E. R.; Bowring, A. R.; Karunadasa, H. I.; McGehee, M. D. *Chem. Sci.* **2014**, 6 (1), 613–617.
- (41) Yablonovitch, E.; Cody, G. D. *IEEE Trans. Electron Devices* **1982**, 29 (2), 300–305.
- (42) Amani, M.; Lien, D.-H.; Kiriya, D.; Xiao, J.; Azcatl, A.; Noh, J.; Madhvapathy, S. R.; Addou, R.; Kc, S.; Dubey, M.; Cho, K.; Wallace, R. M.; Lee, S.-C.; He, J.-H.; Ager, J. W.; Zhang, X.; Yablonovitch, E.; Javey, A. *Science* **2015**, 350 (6264), 1065–1068.
- (43) Mashiyama, H.; Kurihara, Y.; Azetsu, T. *J. Korean Phys. Soc.* **1998**, 32, 156–158.
- (44) D’Innocenzo, V.; Grancini, G.; Alcocer, M. J. P.; Kandada, A. R. S.; Stranks, S. D.; Lee, M. M.; Lanzani, G.; Snaith, H. J.; Petrozza, A. *Nat. Commun.* **2014**, 5, 3586.
- (45) Markvart, T. *Phys. Status Solidi A* **2008**, 205 (12), 2752–2756.
- (46) Hirst, L. C.; Ekins-Daukes, N. J. *Prog. Photovolt. Res. Appl.* **2011**, 19 (3), 286–293.
- (47) Miller, O. D. *Photonic Design: From Fundamental Solar Cell Physics to Computational Inverse Design*, University of California: Berkeley, 2012.
- (48) Snaith, H. J. *J. Phys. Chem. Lett.* **2013**, 4 (21), 3623–3630.

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

TOC Figure

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19

a

b

c

d

a **b** **c**