Lawrence Berkeley National Laboratory

Recent Work

Title

FORMATION AND CHARACTERIZATION OF DIVALENT EINSTEINIUM IN A CaF CRYSTAL

Permalink

<https://escholarship.org/uc/item/6bc1m6v6>

Authors

Edelstein, N.
Conway, John G.
Fujita, D.
et al.

Publication Date

1970-03-01

c.2

RECEIVED
LAWRENCE
RADIATION LABORATORY

APR 20 1970

LIBRARY AND
DOCUMENTS SECTION

FORMATION AND CHARACTERIZATION OF DIVALENT
EINSTEINIUM IN A CaF_2 CRYSTAL

N. Edelstein, John G. Conway, D. Fujita,
W. Kolbe and R. McLaughlin

March 1970

AEC Contract No. W-7405-eng-48

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545*

LAWRENCE RADIATION LABORATORY
UNIVERSITY of CALIFORNIA BERKELEY

UCRL-19568

DISCLAIMER -

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

FORMATION AND CHARACTERIZATION OF DIVALENT EINSTEINIUM IN A CaF_2 CRYSTAL*

N. Edelstein, John G. Conway, D. Fujita, W. Kolbe and R. McLaughlin

Lawrence Radiation Laboratory
University of California
Berkeley, California 94720

March 1970

Although no compounds of divalent actinides have been isolated, tracer chemistry experiments¹ and interpretation of charge transfer bands in the visible and UV spectral range² indicate that actinide elements with $Z > 97$ might form a chemically stable dipositive oxidation state. Dipositive states of the entire lanthanide series have been stabilized in crystals of CaF_2 .³ However, the only dipositive actinide ion positively identified as being stabilized in CaF_2 has been Am^{2+} .⁴ We now report the identification by electron paramagnetic resonance of Es^{2+} ($Z = 99$) in CaF_2 .

Powdered CaF_2 ($\sim 3\text{mg}$) to which had been added 2 wt. % PbF_2 was placed in the center of a spectroscopic grade carbon rod in which a small hole had been drilled. Approximately 6 μg of purified $^{253}\text{Es}^{3+}$ ($t_{1/2} = 20.5$ days) in a volume of $\sim 1 \lambda$ HCl ⁵ was pipeted onto the powder. The carbon rod was attached to two electrodes, the apparatus was evacuated, and current was passed through the rod until the CaF_2 powder was seen visually to coalesce. The current was immediately turned off, and after cooling for approximately ten minutes the CaF_2 crystal, now ~ 1 mm diameter sphere was removed. The amount of Es actually incorporated in the crystal is unknown. Initially the crystal was colorless, after one hour it turned medium red, and in about 3-4 hours was dark red or black due to radiation damage.

The EPR spectrum of this crystal ($f \sim 35$ Ghz, $T = 4.2^\circ\text{K}$) consisted of an isotropic eight line spectrum which was fitted to the parameters of a spin Hamiltonian

$$\mathcal{H} = g\beta\vec{H} \cdot \vec{S}' + A \vec{I} \cdot \vec{S}'$$

with $I = 7/2$ and $S' = 1/2$. Because of the large hyperfine interaction the energy expression given by the Breit-Rabi formula was used to determine the parameters; the values obtained were $|g| = 5.809 \pm 0.005$ and $|A| = (0.1216 \pm 0.002) \text{ cm}^{-1}$. The line widths were initially about 20 gauss peak to peak (the first spectrum was obtained about 1 hour after annealing) but continually broadened due to radiation damage of the crystal, and 8 hours after annealing the spectrum was too broad to observe. The crystal could be reannealed and the spectrum regenerated.

Dipositive Es has the electronic configuration outside closed shells of $5f^{11}$ with the ground state being primarily $^4I_{15/2}$. A cubic crystalline field will split the $J = 15/2$ state into three Γ_8 quartets and two doublets, a Γ_6 and Γ_7 .⁶ For the likely values of the crystalline field parameters, either the Γ_6 or Γ_7 doublet should be the ground crystalline field state. The calculated g-value for the Γ_6 doublet (assuming a pure $^4I_{15/2}$ state) is -6.0 which is in reasonable agreement with the experimental value when effects of the crystalline field, spin orbit coupling, and covalency are considered.

The crystal was radioluminescent and more reddish in appearance at 77°K than at room temperature. Spectra were recorded using a Jarrell-Ash 3/4 meter model 75-000 spectrograph. At 77°K the emission spectrum consisted of a few

relatively sharp lines superimposed upon a continuum which extended from 590 to 670 nm. At room temperature the sharp lines disappeared and the continuum extended from 560 to 700 nm. The sharpening of the broad band continuum was responsible for the color change observed at 77°K. Intense continuous absorption was observed at 77°K which started at 410 nm and probably represents a transition to a f^{10} d or charge transfer state of dipositive Es. The broad band emission could result from a transition from this state to an excited state of the f^{11} configuration. Because of the short half life of ^{253}Es the emission spectrum changed noticeably after a few half lives. Figure 1 compares the spectrum taken at two different times. Since ^{253}Es decays by α emission to ^{249}Bk ($t_{1/2} = 314$ d) the new features which appear at 680 nm at a later time represent transitions associated with Bk ions.

The results of this investigation show that dipositive Es is more readily stabilized in CaF_2 than the earlier actinides (expecting Am). This evidence supports earlier work^{1,2} which predicted that the heavier actinides should have chemically stable dipositive oxidation states.

We wish to thank Professor B. B. Cunningham for many valuable comments and suggestions.

FOOTNOTES AND REFERENCES

* Work performed under the auspices of the U. S. Atomic Energy Commission.

1. J. Maly, J. Inorg. Nucl. Chem. 31, 1007 (1969).
2. L. Nugent, R. Baybarz and J. Burnett, J. Phys. Chem. 73, 1177 (1969).
3. D. S. McClure and Z. J. Kiss, J. Chem. Phys. 39, 325 (1963).
4. N. Edelstein, W. Easley and R. McLaughlin, J. Chem. Phys. 44, 3130 (1966).
5. B. B. Cunningham, J. R. Peterson, R. D. Baybarz and T. C. Parsons, Inorg. Nucl. Chem. Letters 3, 519 (1969).
6. H. R. Lewis and E. S. Sabisky, Phys. Rev. 130, 1370 (1963). E. S. Sabisky, Phys. Rev. 141, 352 (1966).
7. N. F. Ramsey, "Molecular Beams," (Oxford University Press, London, 1956), p. 80.

FIGURE CAPTION

Fig. 1. Radioluminescence of $\text{CaF}_2:\text{Es}$. Upper curve, emission spectrum 73 days after purification of Es; lower curve, spectrum 10 days after purification.

XBL70I-2250

Fig. 1.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or*
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.*

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

TECHNICAL INFORMATION DIVISION
LAWRENCE RADIATION LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720