Lawrence Berkeley National Laboratory

Recent Work

Title

SOME CONSIDERATIONS ON FATIGUE CRACK CLOSURE AT NEAR-THRESHOLD STRESS INTENSITIES DUE TO FRACTURE SURFACE MORPHOLOGY

Permalink

<https://escholarship.org/uc/item/6vv5z94v>

Authors

Ritchie, R.O.
Suresh, S.

Publication Date

1981-07-01

Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

RECEIVED

LAWRENCE
BERKELEY LABORATORY

FEB 1 1982

LIBRARY AND
DOCUMENTS SECTION

Materials & Molecular Research Division

To be published in Metallurgical Transactions A,
Vol. 13A, 1982

SOME CONSIDERATIONS ON FATIGUE CRACK CLOSURE AT
NEAR-THRESHOLD STRESS INTENSITIES DUE TO FRACTURE
SURFACE MORPHOLOGY

R.O. Ritchie and S. Suresh

July 1981

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 6782*

LBL-13836
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

SOME CONSIDERATIONS ON FATIGUE CRACK CLOSURE AT
NEAR-THRESHOLD STRESS INTENSITIES DUE TO
FRACTURE SURFACE MORPHOLOGY

by

R. O. Ritchie and S. Suresh

July 1981

Accepted for publication in Metallurgical
Transactions A, Vol. 13A, 1982

R. O. Ritchie is Associate Professor of Metallurgy and S. Suresh is Research Associate/Metallurgist, Materials and Molecular Research Division, Lawrence Berkeley Laboratory, and Department of Materials Science and Mineral Engineering, University of California, Berkeley, CA 94720. Both authors were formerly of the Department of Mechanical Engineering, Massachusetts Institute of Technology, Cambridge, MA 02139.

This work was supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Science Division of the U.S. Department of Energy, under Contract Nos. W-7405-ENG-48 and DE-AC02-79-ER10389-A000.

COMMUNICATION

SOME CONSIDERATIONS ON FATIGUE CRACK CLOSURE AT NEAR-THRESHOLD STRESS INTENSITIES DUE TO FRACTURE SURFACE MORPHOLOGY

R. O. Ritchie and S. Suresh

1. *Introduction:* Recently there has been considerable interest in mechanisms of fatigue crack closure, particularly at very low stress intensities approaching the threshold stress intensity range ΔK_0 , below which cracks remain dormant or grow at experimentally undetectable rates¹⁻¹³. Crack closure, as first popularized by Elber¹⁴, was considered to arise from the fact that during fatigue crack growth, material is plastically strained at the crack tip and due to the restraint of surrounding elastic material on this residual stretch, some closure of the crack surfaces occurs at positive loads during the fatigue cycle. This concept, which we term *plasticity-induced crack closure*⁴, has proved to be extremely effective in explaining, at least qualitatively, many aspects of fatigue crack propagation behavior, including the influence of load ratio^{*} ¹⁴, the role of variable amplitude loading¹⁵, and so forth. It has become clear, however, that such plasticity-induced closure is most prevalent under essentially plane stress conditions,^{16,17} and yet, at the ultralow growth rates ($<10^{-6}$ mm/cycle) associated with near-threshold fatigue where plane strain conditions invariably exist, very significant effects of crack closure have been observed¹⁻¹³. To account for such large closure effects in plane

* Load ratio R is defined as K_{min}/K_{max} , where K_{min} and K_{max} are the minimum and maximum stress intensities of the loading cycle.

R. O. Ritchie and S. Suresh, both formerly of Department of Mechanical Engineering, Massachusetts Institute of Technology, are Associate Professor and Postdoctoral Research Associate, respectively, Department of Materials Science and Mineral Engineering, and Lawrence Berkeley Laboratory, University of California, Berkeley, CA 94720.

strain, several "microscopic" mechanisms have recently been proposed, based on the role of crack flank corrosion deposits⁴⁻⁶ and fracture surface roughness or morphology^{2,6,10,12,13} (Fig. 1). The former effect, termed *oxide-induced crack closure*⁴, follows from the fact that during near-threshold crack growth at low load ratios in moist environments, corrosion products of a thickness comparable with the size of crack tip opening displacements can build up near the crack tip, thus providing a mechanism for enhanced closure such that the crack is wedged-closed at stress intensities above K_{min} .⁴⁻⁶ For lower strength steels, tested in moist air (30% relative humidity) at $R = 0.05$, oxide films have been observed on near-threshold fracture surfaces with a maximum thickness some twenty times larger than films naturally formed on metallographically-polished samples exposed to the same environment for similar time periods⁶. The closure effect promoted by such deposits, which are considered to arise via a mechanism of fretting oxidation¹⁸, aided by plasticity-induced closure and significant Mode II displacements¹⁹, has been substantiated by Auger measurements of oxide thicknesses⁶⁻⁸ and direct experimental closure measurements using ultrasonics techniques⁸. As discussed in detail elsewhere⁴⁻⁸, this model has provided a very plausible explanation for many of the somewhat surprising observations on the role of environment (i.e., hydrogen, water vapor, inert gas, vacuum, etc.) in influencing near-threshold fatigue behavior in steels.

In analogous fashion, significant effects of crack closure can arise from an irregular or rough fracture surface morphology^{2,6,10,12,13}. As first reported by Walker and Beevers² and subsequently modelled by McEvily and others^{10,13,7}, where the

size-scale of the fracture surface roughness is comparable with crack tip opening displacements and where significant Mode II displacements exist (a situation found at near-threshold levels at low load ratios), crack closure can again be promoted since the crack may be wedged open at discrete contact points along the crack faces⁶ (Fig. 1). This latter effect, termed *roughness-induced crack closure*⁷, can provide an important contribution to the role of microstructure in influencing near-threshold crack growth^{3,6,7,11,12} and further may have wider significance to a larger range of engineering materials¹³.

The purpose of the current note is to discuss the origin and significance of this latter mechanism of roughness-induced crack closure in the light of recently published data^{2,6-8,10-13}.

2. *Mechanistic Aspects:* Initial attempts to quantify the effect of fracture surface roughness on fatigue crack closure were reported by Purushothaman and Tien²¹, who simply suggested that the closure stress intensity K_{cl} could be estimated by equating the change in fracture surface asperity height (taken as a function of true fracture ductility) to the crack tip opening displacement. However, the model did not incorporate the role of crack tip Mode II displacements which are clearly very relevant to the extent of fracture surface interference at near-threshold levels. This can be appreciated from the replica studies on fatigue cracks in titanium² and mild steels¹³ which show the mismatch (arising from crack tip shear displacements) of the serrated fracture surface profile at near-threshold levels (c.f. Fig. 1), compared to a much more planar profile at higher growth rates.

This distinction between behavior at near-threshold levels and at higher growth rates is consistent with the different modes of crack advance in these two regimes¹³. As pointed out by Tomkins²², fatigue crack propagation can be considered in terms of intense localized shear deformation in flow bands near the crack tip which results in the creation of new crack surface by shear decohesion at the tip (Fig. 2). However, when the crack and its associated local plasticity is contained within a few grain diameters, growth is confined to one shear direction, with one primary slip system in the direction of growth and a tensile component normal to this (Fig. 2a). Such crack propagation, called Stage I in Forsyth's original terminology²³, proceeds under a combination of Mode II plus Mode I displacements. Support for such Stage I growth at near-threshold levels is evident from work on low carbon steel²⁴ which showed a marked transition from a tensile mode striation growth above $\sim 10^{-6}$ mm/cycle to an intense shear mode of fracture close to ΔK_0 . Further, stereoimaging studies¹⁹ have clearly confirmed a strong Mode II component to crack growth at near-threshold levels. Conversely, at higher stress intensities where the extent of crack tip plasticity encompasses many grains, crack advance proceeds by the operation of two slip systems, either simultaneously or alternately²⁵⁻²⁷, resulting in the formation of ductile striations (Fig. 2b). Such crack growth, termed Stage II²³, is more planar in nature, and occurs in pure Mode I perpendicular to the principal tensile stresses.

Thus, at near-threshold stress intensities where the maximum plastic zone size (r_y) is typically smaller than the grain size (d), fatigue crack growth takes place by the Stage I mechanism (Fig. 2a), and the resulting serrated or faceted fracture surface morphology coupled with crack tip

Mode II displacements would be expected to generate high closure loads via the mechanism depicted in Fig. 1. At higher growth rates, on the other hand, as the plastic zone size increases, the transition to Stage II propagation in Mode I results in a more planar fracture surface morphology such that closure loads would be expected to diminish.

Such notions are in agreement with experimental closure measurements on steels, aluminum and titanium alloys which in general show a decrease in closure stress intensity K_{cl} with increasing ΔK ^{13,20,28}. In particular, the recent closure measurements on 2048 aluminum by Asaro et al²⁰ show a distinct transition from a region of high closure ($K_{cl}/K_{max} \sim 0.5$) to one of low closure ($K_{cl}/K_{max} \sim 0.2$) with increasing growth rates. By examining several coarse and fine-grained microstructures, these authors concluded that the transition could not be fully accounted for by changes in specimen compliance but rather occurred when the computed maximum plastic zone size (r_y) was fully extended over at least one grain (Fig. 3). This is entirely consistent with the roughness-induced closure concepts presented above since it is to be expected that high closure loads would be observed when the plastic zone is small compared to the grain size as a consequence of faceted Stage I crack growth. Furthermore, at larger plastic zone sizes, the transition to a Stage II striation growth mechanism would be expected to result in a corresponding reduction in closure.

The distinction between crack growth behavior at near-threshold levels and higher stress intensities is further supported by extensive fractographic evidence in the literature. In fact, near-threshold crack growth has been termed "microstructurally-sensitive"²⁹ owing to the

presence of planar facets on fracture surfaces which are intergranular in ferritic steels and transgranular in austenitic stainless steels and alloys of titanium, aluminum, copper and nickel^{*}. However, the proportion of facets is found to diminish with increasing growth rates and to be largely absent once the maximum plastic zone roughly exceeds the grain size³³. Correspondingly, at higher growth rates, crack propagation mechanisms have been termed "microstructurally-insensitive". The salient features associated with these modes of fatigue crack growth are summarized in Fig. 4.

3. *Implications:* The implications of the Stage I mechanism of near-threshold crack advance with its associated large roughness-induced closure contributions are particularly relevant to the effects of grain size on fatigue crack growth behavior⁶. Whereas refining grain size can be beneficial in raising the fatigue limit or endurance strength of (planar slip) materials³⁴, the effect of grain size on crack propagation has in general been found to be negligible in most studies at intermediate growth rates^{31,34,35}. However, at lower near-threshold growth rates, most reported observations show decreasing growth rates (and higher thresholds) in coarse-grained materials³¹. Although several microstructural mechanisms have been proposed for this effect (see ref. 31 for a review), it is significant that where behavior has been examined at both low and high load ratios, the beneficial effect of coarse grain sizes is absent at the higher load ratios (Fig. 5)^{11,36}. This is strong evidence for a prominent role of crack closure, and is analogous to the absence of environmental effects at

* Such faceted fractures have been described by a number of terms including "crystallographic fatigue" in nickel alloys and "cyclic cleavage" in titanium and stainless steels. For a more complete description see, for example, refs. 30-32.

high load ratios during near-threshold corrosion fatigue where oxide-induced crack closure is important⁶. In terms of the current roughness-induced closure mechanism, such behavior is to be expected, since at near-threshold levels coarser-grained microstructures will promote rougher (more serrated) fracture surfaces. Further, such microstructures delay the transition to the more planar Stage II growth until higher ΔK levels, where the plastic zone size exceeds the grain size. At high load ratios, on the other hand, where closure effects in general are minimal, this mechanism would be insignificant and accordingly no influence of grain size would be expected. Recent studies¹¹ in pearlitic rail steels have demonstrated this phenomenon particularly clearly in that coarser microstructures tested in room air displayed markedly lower growth rates at $R = 0.1$, yet at $R = 0.7$, behavior was virtually identical for both coarse and fine structures (Fig. 5). Moreover, an increase in fracture surface roughness, together with a corresponding increase in corrosion debris, was observed in the coarse-grained material suggesting that rougher fracture surfaces may additionally promote oxide-induced crack closure (in moist environments), presumably by enhancing abrasion (fretting oxidation) between mating crack faces.

4. *Summary:* It is noted that at near-threshold levels, in addition to the role of plasticity- and oxide-induced crack closure, fracture surface roughness or morphology may promote significant closure effects in plane strain, as similarly noted by Minakawa and McEvily^{10,13}. This is considered to result from the fact that, where maximum plastic zones sizes are small compared to the grain size, fatigue crack growth proceeds by a single shear decohesion mechanism (Stage I) with associated Mode II + I displacements. The resulting serrated or faceted fracture surfaces

("microstructurally-sensitive growth") coupled with Mode II crack tip displacements thus induce high closure loads (i.e., $K_{cl}/K_{max} \sim 0.5$) by wedging the crack open at discrete contact points. At higher growth rates where the plastic zone encompasses many grains, striation growth via alternating or simultaneous shear mechanisms (Stage II) produces a more planar fracture surface, with pure Mode I displacements, and a corresponding reduction in closure loads. Such concepts of roughness-induced closure are shown to be consistent with observations of the role of coarse grain sizes in reducing near-threshold crack growth rates at low load ratios and of the absence of this effect at high load ratios.

This work was supported by the Director, Office of Energy Research, Office of Basic Energy Science, Materials Science Division of the U.S. Department of Energy under Contract Nos. DE-AC02-79ER10389.A000 and W-7405-ENG-48. Helpful discussions with Professors R. J. Asaro, F. A. McClintock and D. M. Parks are gratefully acknowledged.

1. A. J. McEvily: Metal Sci., 1977, vol. 11, p. 274.
2. N. Walker and C. J. Beevers: Fat. Eng. Mat. Struct., 1979, vol. 1, p. 135.
3. C. J. Beevers: Metal Sci., 1980, vol. 14, p. 418.
4. R. O. Ritchie, S. Suresh, and C. M. Moss: J. Eng. Mat. Tech., Trans. ASME Series H, 1980, vol. 102, p. 293.
5. A. T. Stewart: Eng. Fract. Mech., 1980, vol. 13, p. 463.
6. S. Suresh, G. F. Zamiski, and R. O. Ritchie: Met. Trans. A, 1981, vol. 12A, p. 1435.
7. R. O. Ritchie: in Fatigue Thresholds, Proceedings 1st Intl. Conf., Stockholm, J. Bäcklund, A. Blom and C. J. Beevers, eds., EMAS Publ. Ltd., Warley, U.K., 1981.
8. S. Suresh, D. M. Parks, and R. O. Ritchie: ibid.
9. B. L. Freeman, P. Smith, and A. T. Stewart: ibid.
10. K. Minakawa and A. J. McEvily: ibid.
11. G. T. Gray, A. W. Thompson, J. C. Williams, and D. H. Stone: ibid.

12. I. C. Mayes and T. J. Baker: Fat. Eng. Mat. Tech., 1981, vol. 4, p. 79.
13. K. Minakawa and A. J. McEvily: Scripta Met., 1981, vol. 15, p. 633.
14. W. Elber: in Damage Tolerance in Aircraft Structures, ASTM STP 486, p. 280, 1971.
15. E. F. J. von Euw, R. W. Hertzberg, and R. Roberts, in Stress Analysis and Growth of Cracks, ASTM STP 513, p. 230, 1972.
16. T. C. Lindley and C. E. Richards: Mater. Sci. Eng., 1974, vol. 14, p. 281.
17. B. Budiansky and J. W. Hutchinson: J. Appl. Mech., Trans. ASME Series E, 1978, vol. 45, p. 267.
18. D. Benoit, R. Namdar-Tixier, and R. Tixier: Mater. Sci. Eng., 1981, vol. 45, p. 1.
19. D. L. Davidson: Fat. Eng. Mat. Tech., 1981, vol. 3, p. 229.
20. R. J. Asaro, L. Hermann, and J. M. Baik: Met. Trans. A, 1981, vol. 12A, p. 1135.
21. S. Purushothaman and J. K. Tien: in Strength of Metals and Alloys, Proc. ICSMA5 Conf., Pergamon Press, New York, vol. 2, p. 1267, 1979.
22. B. Tomkins: Metal Sci., 1979, vol. 13, p. 387.
23. P. J. E. Forsyth: in Crack Propagation, Proc. Symp., Cranfield, College of Aeronautics, Cranfield Press, 1962, p. 76.
24. A. Ohtsuka, K. Mori, and T. Miyata: Eng. Fract. Mech., 1975, vol. 7, p. 429.
25. B. Tomkins and W. D. Biggs: J. Mater. Sci., 1969, vol. 4, p. 544.

26. R.M.N. Pelloux: Eng. Fract. Mech., 1970, vol. 1, p. 697.
27. P. Neumann: Zeitschrift f. Metallkunde, 1967, vol. 11, p. 780.
28. P. C. Paris and L. Hermann: Proc. Intl. Cong. Theor. Appl. Mech.,
Delft, W. T. Koiter, ed., North-Holland, Amsterdam, 1977.
29. R. J. Cooke and C. J. Beevers: Mater. Sci. Eng., 1974, vol. 13, p. 201.
30. C. J. Beevers: Metal Sci., 1977, vol. 11, p. 362.
31. R. O. Ritchie: Int. Metals Rev., 1979, vol. 20, p. 205.
32. G. R. Yoder, L. A. Cooley, and T. W. Crooker: Met. Trans. A , 1978,
vol. 9A, p. 1413.
33. J. D. Frandsen and H. L. Marcus: Scripta Met., 1975, vol. 9, p. 1089.
34. R.M.N. Pelloux: in Ultrafine-Grain Metals, Syracuse Univ. Press,
p. 231, 1970.
35. A. W. Thompson and R. J. Bucci: Met. Trans., 1973, vol. 4, p. 1173.
36. E. K. Priddle: Scripta Met., 1977, vol. 11, p. 49.

LIST OF FIGURES

- Fig. 1. Schematic illustration of possible mechanisms of fatigue crack closure at near-threshold stress intensities. ΔK_{eff} is the effective stress intensity range, given by $K_{\text{max}} - K_{\text{cl}}$, where K_{max} is the maximum stress intensity and K_{cl} is the stress intensity to close the crack ($K_{\text{cl}} \geq K_{\text{min}}$, the minimum stress intensity) (after ref. 7).
- Fig. 2. Crack opening profiles corresponding to a) near-threshold (Stage I) and b) higher growth rate (Stage II) fatigue crack propagation (after ref. 22).
- Fig. 3. Measurements of fatigue crack closure in coarse and fine grain 2048-T851 aluminum alloy, represented in terms of the ratio of closure stress intensity to maximum stress intensity ($K_{\text{cl}}/K_{\text{max}}$). Note transition from high closure to low closure once the maximum plastic zone size (r_y) exceeds roughly the grain size (d) (after ref. 20).
- Fig. 4. Schematic illustration of the three regimes of fatigue crack propagation behavior and their corresponding mechanisms and characteristics.
- Fig. 5. Fatigue crack propagation in fully pearlitic hot-rolled rail steel ($R = 0.1$ and 0.7), showing lower growth rates and higher threshold values in the coarse-grained microstructure ($d = 130 \mu\text{m}$) compared to the fine-grained structure ($d = 25 \mu\text{m}$), at low load ratios only (after ref. 11).

Fig. 1. Schematic illustration of possible mechanisms of fatigue crack closure at near-threshold stress intensities. ΔK_{eff} is the effective stress intensity range, given by $K_{max} - K_{cl}$, where K_{max} is the maximum stress intensity and K_{cl} is the stress intensity to close the crack ($K_{cl} \geq K_{min}$, the minimum stress intensity)..

- a) Near-Threshold : $r_y < d$
(Stage I, Modes II + I)

- b) Higher Growth Rates : $r_y > d$
(Stage II, Mode I)

Fig. 2. Crack opening profiles corresponding to a) near-threshold (Stage I) and b) higher growth rate (Stage II) fatigue crack propagation (after ref. 22).

Fig. 3. Measurements of fatigue crack closure in coarse and fine grain 2048-T851 aluminum alloy, represented in terms of the ratio of closure stress intensity to maximum stress intensity (K_{Cp}/K_{max}). Note transition from high closure to low closure once the maximum plastic zone size (r_y) exceeds roughly the grain size (d) (after ref. 20).

Fig. 4. Schematic illustration of the three regimes of fatigue crack propagation behavior and their corresponding mechanisms and characteristics.

Fig. 5. Fatigue crack propagation in fully pearlitic hot-rolled rail steel ($R = 0.1$ and 0.7), showing lower growth rates and higher threshold values in the coarse-grained microstructure ($d = 130\mu m$) compared to the fine-grained structure ($d = 25\mu m$), at low load ratios only (after ref. 11).

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720