Lawrence Berkeley National Laboratory

Recent Work

Title

DIFFERENTIAL THERMAL CALORIMETRIC ESTIMATION OF THE KAOLINITE-METAKAOLINITE
ENDOTHERMIC ENTHALPY

Permalink

<https://escholarship.org/uc/item/70t9g73t>

Authors

Nicholson, Patrick S.
Fulrath, Richard M.

Publication Date

1969-06-01

Submitted as a Note to J. Am. Ceram. Soc.

UCRL-19025
Preprint

cy. 2

DIFFERENTIAL THERMAL CALORIMETRIC ESTIMATION
OF THE KAOLINITE-METAKAOLINITE
ENDOTHERMIC ENTHALPY

RECEIVED
LAWRENCE
RADIATION LABORATORY

Patrick S. Nicholson and Richard M. Fulrath

JUL 14 1969

June 1969

LIBRARY AND
DOCUMENTS SECTION

AEC Contract No. W-7405-eng-48

TWO-WEEK LOAN COPY

This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545

LAWRENCE RADIATION LABORATORY
UNIVERSITY of CALIFORNIA BERKELEY

UCRL-19025

cy. 2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

DIFFERENTIAL THERMAL CALORIMETRIC ESTIMATION OF
THE KAOLINITE-METAKAOLINITE ENDOTHERMIC ENTHALPY

Patrick S. Nicholson* and Richard M. Fulrath

Inorganic Materials Research Division, Lawrence Radiation Laboratory,
and Department of Materials Science and Engineering,
College of Engineering, University of California,
Berkeley, California

June 1969

The 550°C endothermic reaction of kaolinite has received much attention. Many studies of the kinetics of the reaction have been made and activation energies obtained.¹⁻⁵ In 1952 Stone⁶ studied the effect of varying the partial pressure of water vapor on the decomposition temperature of kaolinite. Utilizing the Van'tHoff equation

$$d \ln K = \frac{\Delta H}{RT^2} dT$$

* Presently visiting assistant professor, Division of Materials Science and Engineering, College of Engineering, University of Utah, Salt Lake City, Utah.

Based in part on a thesis submitted by Patrick S. Nicholson for the Ph.D. degree in ceramic engineering at the University of California, Berkeley, September 1967.

Supported by the United States Atomic Energy Commission under Contract W-7405-eng-48.

At the time this work was done the writers were, respectively, research assistant and professor of ceramic engineering, Department of Materials Science and Engineering, College of Engineering, and Inorganic Materials Research Division, Lawrence Radiation Laboratory, University of California, Berkeley.

where K = the reaction equilibrium constant,

ΔH = the reaction enthalpy and

T = the absolute temperature ($^{\circ}\text{K}$),

he arrived at an endothermic enthalpy value for the reaction. Stone utilized a differential thermal analysis technique in these studies. The presence of a product-gas phase in the system greatly complicates the mechanisms of heat transfer in a D.T.A. experiment, however, and this tends to introduce errors into the D.T.A. measurements.

Differential thermal calorimetric (D.T.C.) techniques do not suffer from this drawback. The basic principle of D.T.C. is to supply or subtract heat to or from a reacting system so as to maintain the temperature at some point in the system the same as that of a similar point in a physically inert system. By carefully monitoring and controlling the temperature gradients in the D.T.C. system, the detrimental effect of the product-gas phases on the heat transfer characteristics of the system can be avoided. The D.T.C. system design utilized in the investigations reported here is discussed elsewhere.⁷

When a reaction starts in the sample system, the power supplied to the inert system must be altered to maintain the two-system differential temperature at zero. The integrated area under the power-time trace obtained gives the enthalpy of the reaction being measured according to the equation

$$H_T = H_{298} + \int_{298}^T C_p dT$$

where H_T = the heat content/mole at temperature T ,
 H_{298} = the heat content at room temperature,
 C_p = the heat capacity at constant pressure, and
 T = the temperature ($^{\circ}\text{K}$).

The apparatus was demonstrated to have a $\pm 2\%$ accuracy in heat content estimations conducted on quartz and α -alumina.

The dehydration of kaolinite is not strictly a reversible reaction. The enthalpy involved can be measured with a differential thermal calorimeter. Such measurements were carried out on four kaolinites from different geographical areas of the United States. These kaolins were chosen on the basis of their high purity. The chemical analyses of these clays are given in Table I. The measured enthalpy values associated with the 550°C endotherm are given in Table II. The values obtained are in fairly close agreement.

The demonstrated accuracy of the DTC system when used for thermodynamic estimations on known systems lends weight to the endothermic enthalpy values measured for the four kaolins and these values fall within the range predicted by Vaughan.²

REFERENCES

1. P. Murray and J. White, "Kinetics of the Thermal Dehydration of Clays. II. Isothermal Decomposition of Clay Minerals," Trans. Brit. Ceram. Soc. 54, 151 (1955).
2. F. Vaughan, "Energy Changes when Kaolin Minerals Are Heated," Clay Min. Bull. 2, 265 (1955).
3. G. W. Brindley and M. Nakahira, "Kinetics of Dehydroxylation of Kaolinite and Halloysite," J. Am. Ceram. Soc. 40, 346 (1957).
4. J. L. Evans and J. White, "Further Studies on the Thermal Decomposition of Clays," Trans. Brit. Ceram. Soc. 57, 289 (1958).
5. J. B. Holt, I. B. Cutler, and M. E. Wadsworth, "Thermal Dehydration of Kaolinite in Vacuum," J. Am. Ceram. Soc. 45, 133 (1962).
6. R. L. Stone, "DTA of Kaolin Group Minerals Under Controlled Partial Pressures of H_2O ," J. Am. Ceram. Soc. 35, 90 (1952).
7. P. S. Nicholson and R. M. Fulrath, "Heat Transfer Consideration in Differential Calorimeter Design," (submitted to J. Am. Ceram. Soc.)
8. American Petroleum Institute Project 49, Clay Mineral Standards. Columbia University 1949-1950.

TABLE I

Chemical Analyses of the Kaolinite Samples

(only major components shown)

	API 4 ⁸	API 9 ⁸	API 17 ⁸	DRG
SiO ₂	44.8%	46.07%	45.72%	47.24%
Al ₂ O ₃	37.20	38.07	39.82	35.72
Fe ₂ O ₃	0.41	0.33	0.10	0.27
MgO	0.23	0.01	trace	0.47
CaO	0.58	0.38	trace	0.52
Na ₂ O	0.40	0.27	0.16	0.36
K ₂ O	0.43	0.43	0.36	0.49
H ₂ O	14.68	13.90	14.22	14.82
Location of deposit	Macon, Georgia	Mesa Alta, New Mexico	Montana	Georgia

TABLE II

Differential Thermal Calorimetric Enthalpy Values for the

550° Endotherm of Kaolinite

ΔH in Kcals/mol

API 4	API 9	API 17	DRG	Stone
38	39	39	48	37
44	41	39	47	
			45	

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or*
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.*

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

TECHNICAL INFORMATION DIVISION
LAWRENCE RADIATION LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720