Lawrence Berkeley National Laboratory

Lawrence Berkeley National Laboratory

Title

Ultrasonic Spray Pyrolysis of Hierarchically Structured Cathode Materials

Permalink

<https://escholarship.org/uc/item/75g7m739>

Author

Kam, Kinson

Publication Date

2011-10-10

Ultrasonic Spray Pyrolysis of Hierarchically Structured Cathode Materials

Kinson C. Kam, Anthony Chern, and Marca M. Doeff

Lawrence Berkeley National Laboratory
Environmental Energy Technologies Division,
University of California,
Berkeley, CA, 94720. U.S.A.

Aerosol processing is widely used in industry to manufacture advanced materials such as pigments and oxide ceramics.¹ Simple and low cost continuous processing methods such as ultrasonic spray pyrolysis generate fine particles by decomposing atomized droplets containing metal precursors, and can be easily scaled up. Product particles with high purity are readily separated from the gas stream, without any liquid by-products unlike wet chemistry processes. In addition, multicomponent materials are also easily prepared by this route.

We have recently used a solution combustion technique to prepare layered mixed-metal oxide nanoparticles,² and are now exploring the possibility of making related battery materials using ultrasonic spray pyrolysis. Our initial work has successfully demonstrated that spherical LiFePO_4/C ³ and LiCoPO_4/C ⁴ particles can be prepared with good electrochemical performance. The particles are approximately $10\text{ }\mu\text{m}$ in diameter, but consist of nano-scale primary particles coated with carbon and have an interconnected network of nanopores that allow rapid transport of ions and electrons. The spherical morphology and relatively large size of the secondary particles allow easy processing of the materials into composite electrodes, and alleviate the energy density penalty often associated with nanostructuring. This illustrates the advantages of hierarchical structuring for battery materials.

The ultrasonic spray pyrolysis technique is now being extended to the preparation of other oxides and polyanionic based cathode materials with high voltage or capacity characteristics. By modifying spray pyrolysis conditions, the sizes of the secondary particles, made up of nanometric primary particles, can be varied from $1\text{ }\mu\text{m}$ to $\sim 10\text{ }\mu\text{m}$ (Figure 1). Figure 2 shows an SEM image of spray-pyrolyzed $\text{LiFe}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{PO}_4/\text{C}$ particles,⁵ indicating that multicomponent materials are easily prepared using this method. For this talk, we will discuss the microstructure of these materials and their relevance to the electrochemical properties.

Figure 1. Scanning electron micrographs (SEMs) of $\text{LiNi}_{0.5}\text{Mn}_{1.5}\text{O}_4$ particles made by spray pyrolysis: a) as-made from 1M metal nitrate solution using a 120 kHz nozzle, b) particle from a, heated at 900° for 15 minutes c) as-made from 1M metal nitrate solution using a 2.4 MHz nozzle, d) as-made from 1M nitrate solution with glycine added, 120 kHz, e) sample d heated to 900°C for one hour, f) as-made 3M metal nitrate solution and 120 kHz.

Figure 2. SEM image of $\text{LiFe}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{PO}_4/\text{C}$ composite particle and EDX elemental mapping for P, Mn, Fe, and Co.

ACKNOWLEDGMENTS

This work was supported by the Assistant Secretary of Energy for Energy Efficiency and Renewable Energy, Office of Vehicle Technologies of the United States Department of Energy under Contract No. DE-AC02-05CH11231.

REFERENCES

1. T. T. Kodas and M. J. Hampden-Smith, *Aerosol Processing of Materials*, p. 680, Wiley-VCH, New York, (1999).
2. K.C. Kam and M. M. Doeff, *J. Mater. Chem.*, DOI: 10.1039/C0JM04193A (2011).
3. J. Liu, T. E. Conry, X. Song, M. M. Doeff and T. J. Richardson, *Energy Environ. Sci.*, **4**, 885 (2011).
4. J. Liu, T. E. Conry, X. Song, L. Yang, M. M. Doeff and T. J. Richardson, *J. Mater. Chem.*, DOI: 10.1039/C1JM10793C (2011).
5. Y. U. Park, J. Kim, H. Gwon, D. H. Seo, S. W. Kim and K. Kang, *Chem. Mater.*, **22**, 2573 (2010).

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.