Lawrence Berkeley National Laboratory

Recent Work

Title

SINTERING OF Sc MODIFIED LEAD ZIRCONATE-TITANATE

Permalink

<https://escholarship.org/uc/item/79g5m5z8>

Author

Dih, J.J.

Publication Date

1976-04-01

0 0 0 0 4 5 0 0 0 0 0

Submitted to Journal of the American
Ceramic Society

LBL-5100
Preprint c.1

SINTERING OF Sc MODIFIED LEAD ZIRCONATE-TITANATE

J. J. Dih and R. M. Fulrath

April 1976

Prepared for the U. S. Energy Research and
Development Administration under Contract W-7405-ENG-48

For Reference

Not to be taken from this room

LBL-5100
c.1

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

SINTERING OF Sc MODIFIED LEAD ZIRCONATE-TITANATE

J. J. Dih and R. M. Fulrath

Materials and Molecular Research Division, Lawrence Berkeley Laboratory
and Department of Materials Science and Engineering,
University of California, Berkeley, California 94720

ABSTRACT

Lead zirconate-titanate (PZT) is an important ceramic material widely used for piezoelectric devices.^{1,2} Defect structures in PZT have been reported to affect the electrical properties, sintering kinetics, and grain growth.³⁻⁵ It is apparent that understanding the behavior of defects in PZT is important in understanding the electrical properties. Many investigators tried to develop a desired defect structure extrinsically in PZT by intentionally doping. Scandium oxide is one of the materials that has received some attention as a dopant. Holman and Fulrath^{6,7} determined that Sc^{3+} substitutes for (Ti, Zr) and creates oxygen vacancies in the perovskite structure. Lee and Fulrath⁸ reported that Sc can convert the ferroelectric characteristics of PZT to an anti-ferroelectric-like behavior. The major problem in analyzing the Sc doped material is that the suppression of the rate of densification by the incorporation of Sc ions into PZT is so great that only very low density samples can be fabricated. The purpose of this study was to investigate the effect of PbO activity established by a packing powder during sintering on the densification of Sc doped PZT. A high density Sc doped sample was achieved.

A PZT composition of $\text{Pb}(\text{Zr}_{0.5}\text{Ti}_{0.5})\text{O}_3$ was prepared from lead oxide powder, zirconium tetra-butoxide liquid and titanium tetra-butoxide liquid. 1 mole % scandium oxide (Sc_2O_3) powder were used as a dopant.

Proper proportion of raw materials were mixed in a blender and then reacted and co-precipitated from solution when distilled water was added. The blended slurry was dried and calcined at 500°C for 24 hours. After calcining, the powder was milled for 4 hours in isopropyl alcohol and using ZrO_2 as a grinding media. The powder was calcined again at 500°C for 8 hours. After the second calcination, 2.5 wt% or 5 wt% PbO was added to the powder. The PbO rich powder was milled again and then passed through a 325 mesh screen to complete the powder preparation process.

The powder was cold pressed at 10,000 psi in a 1 inch diameter steel die. The pressed pellets with green density about 2.6 gm/cc were sintered in a Pt crucible. The samples were always buried deeply into a packing powder with known PbO activity. The two compositions of the packing powder were lead zirconate-titanate plus 5 wt% PbO (PZT+P) and lead zirconate plus 5 wt% ZrO_2 (PZ+Z). Either 1 atm oxygen or 1 atm helium was used as the sintering atmosphere. All sintering runs would begin by heating the furnace at constant rate of 300°C/hr to the sintering temperature 1200°C. The samples were held at temperatures for 16 hours and then allowed to cool at natural cooling rate of the furnace. Density of the sintered samples were measured by water displacement and also by geometric measurements. Theoretical density for PZT was taken as 8 gm/cc. X-ray diffraction was used to identify crystal phases present. The results are shown in Table I.

For a sample without excess PbO and using PZ+Z as the packing powder while sintering in 1 atm oxygen, the sintered density only reached 65% of the theoretical density. The density of a sample with

excess PbO can achieve 81% theoretical density. This is due to the excess PbO giving a liquid phase at high temperature to enhance sintering. If the PZT+P instead of PZ+Z is used as the packing powder, a completely dense sample is obtained. The X-ray diffraction pattern indicated that there was a trace of PbO in the sample. Recently, Holman and Fulrath⁹ established the PbO activity above the PbTiO_3 - PbZrO_3 system and determined the single phase width of the compounds in the system. It has been shown that PZT+P will provide a higher PbO activity than PZ+Z during firing. The PbO activity of PZ+Z is lower than that of the green compact. Therefore, the excess PbO in the sample is eventually lost to reach local atmospheric equilibrium with the PZ+Z packing powder. A high density sample can not be obtained. The high PbO activity established by PZT+P packing powder can suppress the PbO loss from the sample and lead to high density. The effect of environmental PbO activity on the sintered density is shown in Fig. 1. When 1 atm helium instead of oxygen was used during firing, the sintered density reached 95% theoretical density and no trace of a PbO phase was found in the sample. This shows that the lower the oxygen partial pressure in the sintering atmosphere the greater the PbO loss from the sample and the less effective is the liquid phase sintering process.

ACKNOWLEDGMENT

This work was done under the auspices of the U.S. Energy Research and Development Administration.

TABLE I

SINTERING PARAMETERS

Sample Compositions	Temperature (°C)	Time (Hour)	Atmosphere (1 atm)	Composition of Packing Powder	% Theoretical Density	X-ray Pattern
$\text{PZ}_{0.5}\text{T}_{0.5} + 2 \text{ mole\% Sc}_2\text{O}_3$	1200	16	O_2	PZ+Z	65%	PZT
$\text{PZ}_{0.5}\text{T}_{0.5} + 2 \text{ mole\% Sc}_2\text{O}_3$ + 2.5 wt%PbO	1200	16	O_2	PZ+Z	81%	PZT
$\text{PZ}_{0.5}\text{T}_{0.5} + 2 \text{ mole\% Sc}_2\text{O}_3$ + 5 wt%PbO	1200	16	O_2	PZ+Z	85%	PZT
$\text{PZ}_{0.5}\text{T}_{0.5} + 2 \text{ mole\% Sc}_2\text{O}_3$ + 2.5 wt%PbO	1200	16	O_2	PZT+P	99.9%	PZT+P
$\text{PZ}_{0.5}\text{T}_{0.5} + 2 \text{ mole\% Sc}_2\text{O}_3$ + 2.5 wt%PbO	1200	16	He	PZT+P	95%	PZT
$\text{PZ}_{0.5}\text{T}_{0.5} + 2 \text{ mole\% Sc}_2\text{O}_3$ + 5 wt%PbO	1200	16	He	PZT+P	96%	PZT

0 0 0 0 4 5 0 3 3 6 3

-5-

FIGURE CAPTION

Fig. 1. Effect of environmental PbO activity provided by a packing powder during sintering on the sintered density.

BL 762-6520

Fig. 1

REFERENCES

1. B. Jaffe, R. S. Roth and S. Marzullo, "Properties of Piezoelectric Ceramics in the Solid Solution Series Lead Titanate-Lead Zirconate-Lead Oxide, Tin Oxide and Lead Titanate-Lead Hafnate", J. of Research of the National Bureau of Standards, 55 [5] 239-253 (1953).
2. D. A. Berlincourt, C. Cmolic and B. Jaffe, "Piezoelectric Properties of Polycrystalline Lead Titanate Zirconate Compositions", Proc. IRD 48 [2] 220-229 (1960).
3. R. B. Atkin and R. M. Fulrath, "Point Defects and Sintering of Lead Zirconate-Titanate", J. Am. Ceram. Soc., 54 [5] 265-270 (1971).
4. A. H. Webster, T. B. Weston and N. F. H. Brickt, "Effect of PbO Deficiency on the Piezoelectric Properties of Lead Zirconate-Titanate Ceramics", J. Am. Ceram. Soc., 50 [9] 490-491 (1967).
5. J. J. Dih and R. M. Fulrath, "Electrical Conductivity in Lead Zirconate-Titanate Ceramics", Ph.D. Thesis, University of California, Berkeley (1976).
6. R. L. Holman, "Intrinsic and Extrinsic Non-stoichiometry in the Lead Zirconate-Titanate System", Ph.D. Thesis, University of California, Berkeley (1972).
7. R. B. Atkin, R. L. Holman and R. M. Fulrath, "Substitution of Bi and Nb Ions in Lead Zirconate-Titanate", J. Am. Ceram. Soc. 54 [2] 113 (1971).
8. D. C. Lee, "Sintering Sc and Nb Modified Lead Zirconate-Titanate" M.S. Thesis, University of California, Berkeley (1970).

9. R. L. Holman and R. M. Fulrath, "Intrinsic Non-stoichiometry in the Lead Zirconate-Titanate System Determined by Knudsen Effusion", J. Appl. Phys., 44 [12] 5227-5236 (1973).

LEGAL NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

TECHNICAL INFORMATION DIVISION
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720