UC Irvine

UC Irvine Previously Published Works

Title

Strong electronic correlations in a new class of Yb-based compounds: YbXCu₄ (X=Ag,Au,Pd).

Permalink

<https://escholarship.org/uc/item/7c07h3r5>

Journal

Physical review. B, Condensed matter, 35(4)

ISSN

0163-1829

Authors

Rossel, C
Yang, KN
Maple, MB
et al.

Publication Date

1987-02-01

DOI

10.1103/physrevb.35.1914

Copyright Information

This work is made available under the terms of a Creative Commons Attribution License, available at <https://creativecommons.org/licenses/by/4.0/>

Peer reviewed

Strong electronic correlations in a new class of Yb-based compounds: YbXCu_4 ($X = \text{Ag}, \text{Au}, \text{Pd}$)

C. Rossel, K. N. Yang, and M. B. Maple

*Department of Physics and Institute for Pure and Applied Physical Sciences,
University of California, San Diego, La Jolla, California 92093*

Z. Fisk, E. Zirngiebl, and J. D. Thompson

Los Alamos National Laboratory, Los Alamos, New Mexico 87545

(Received 4 August 1986)

A new series of heavy-electron Yb compounds YbXCu_4 with $X = \text{Ag}, \text{Au},$ or Pd are reported which have electron effective masses as high as $\sim 60m_e$, where m_e is the mass of the free electron. Whereas the compounds with $X = \text{Au}$ and Pd order magnetically below 1 K, the compound with $X = \text{Ag}$ is nonmagnetic. The magnetic susceptibility and specific heat of YbAgCu_4 can be accounted for by the Bethe-ansatz solution of the Coqblin-Schrieffer impurity model without any adjustable parameters.

The remarkable physical properties of compounds of rare earth and actinide elements which are associated with the hybridization between conduction-electron and localized f -electron states continue to attract the attention of experimentalists and theoreticians alike. A significant amount of effort has been expended in characterizing exemplary f -electron materials and developing theoretical models with which their extraordinary properties can be compared.^{1,2} Compounds of the rare-earth elements Ce and Yb are especially well suited for this purpose, since the $4f$ shell of Ce and Yb can accommodate at most one electron or hole, respectively, which considerably simplifies relevant theoretical models.

In this paper we report transport, thermal, and magnetic measurements on a new series of Yb compounds with the formula YbXCu_4 , where $X = \text{Ag}, \text{Au},$ or Pd . These compounds appear to be nearly ideal materials for testing theoretical models since their crystal structure has cubic symmetry, the Yb $4f$ shell contains approximately one hole, and interactions between the Yb magnetic moments are relatively weak. Our results reveal that the compounds with $X = \text{Au}$ and Pd order magnetically below 1 K, whereas YbAgCu_4 has a nonmagnetic ground state. Moreover, the magnetic ground state in YbAuCu_4 and the nonmagnetic groundstate in YbAgCu_4 both develop out of a heavy Fermi liquid characterized by an effective mass of $\sim 50m_e$, where m_e is the mass of the free electron. We have found that the magnetic susceptibility χ as a function of temperature T and the value of the coefficient γ of the specific heat $C = \gamma T$ of the nonmagnetic compound YbAgCu_4 can be described by the Bethe-ansatz solution of the Coqblin-Schrieffer Hamiltonian³ for angular momentum $J = \frac{7}{2}$, which is appropriate for the Hund's rule groundstate multiplet of trivalent Yb, without any adjustable parameters.

The polycrystalline YbXCu_4 samples were prepared in three ways: by melting the pure elements in (1) an argon arc furnace on a Cu hearth, (2) a BeO crucible, or (3) a

sealed Ta tube, in order to minimize losses of the volatile Yb. The physical properties of the samples were not influenced by the different cooling rates involved in these three techniques. X-ray powder diffraction and metallographic analyses yielded no evidence of impurity phases. In contrast to YbCu_5 , which has the hexagonal CaCu_5 -type crystal structure and in which Yb is divalent,⁴ the three YbXCu_4 compounds with $X = \text{Ag}, \text{Au},$ and Pd have the cubic AuBe_5 structure (space group $C15b$ or $F-43m$) and Yb appears to be trivalent, or nearly so. The values of the lattice parameters are 7.0696, 7.0519, and 7.0396 Å for $X = \text{Ag}, \text{Au},$ and Pd , respectively. The Yb-Yb distance in these materials is of the order of 5 Å, a relatively large value which seems to favor a magnetic and/or heavy-electron ground state as proposed for the actinides by Hill.⁵ Electrical resistivity ρ measurements were made with a self-balancing four-wire impedance bridge operating at a frequency of 16 Hz between 80 mK and 295 K. The data below 1.2 K were taken in a conventional ^3He - ^4He dilution refrigerator. The magnetic susceptibility χ was measured with an SHE superconducting quantum-interference device (SQUID) magnetometer in a magnetic field of 1 T between ~ 2 and 300 K. Heat-capacity C measurements were carried out in a semiadiabatic ^3He calorimeter between 0.45 and 16 K.

Normalized electrical resistivity $\rho(T)/\rho(295 \text{ K})$ versus T data between 80 mK and 295 K for the three YbXCu_4 compounds, displayed in Fig. 1, exhibit different types of behavior for each of the three substituent X elements. Little temperature dependence is observed for all three samples down to ~ 80 K. However, below ~ 60 K, the resistivity of YbAgCu_4 falls rapidly and follows a T^2 power-law dependence between ~ 1 and 28 K which is characteristic of Fermi-liquid behavior or spin fluctuations. In contrast, the resistivity of YbAuCu_4 increases with decreasing temperature below ~ 100 K and displays two maxima, one at ~ 20 K and a second one at ~ 1.1 K (see inset of Fig. 1). The drop in $\rho(T)$ below this second

FIG. 1. Normalized electrical resistivity $\rho(T)/\rho(295 \text{ K})$ vs temperature T for YbXCu_4 compounds with $X=\text{Ag}$, Au , and Pd . Shown in the inset are the curves below 6 K. The presence of a maximum at 1.1 K for $X=\text{Au}$ and at 0.7 K for $X=\text{Pd}$ is associated with freezing out of magnetic scattering due to the onset of magnetic order.

peak is due to the onset of magnetic ordering (probably antiferromagnetic) as verified by specific-heat measurements which are discussed below. The drop in $\rho(T)$ below $\sim 0.7 \text{ K}$ for the compound YbPdCu_4 is also associated with magnetic order. In these latter two compounds $\rho(T)$ seems to exhibit Kondo-like behavior with a typical minimum located around 85 K for the Au-based sample and $\sim 60 \text{ K}$ for the Pd-based material. At room temperature, the electrical resistivity of these compounds ranged between 30 and $100 \mu\Omega \text{ cm}$.

The types of ρ versus T curves displayed by the YbXCu_4 compounds could be associated with a temporal admixture of divalent and trivalent Yb (valence fluctuations) which are thought to be appropriate for compounds like YbAl_3 , YbCu_2Si_2 , YbInAu_2 , and YbCuAl ,⁶ or to the transition from a single-impurity Kondo regime at high temperature into a coherent Kondo lattice at low temperature. It is interesting to note that the presence of a Kondo-like resistivity maximum in Yb systems such as YbAuCu_4 , discussed here, or in YbCuAl , which passes from a high-temperature localized to a low-temperature Fermi-liquid regime in the vicinity of 30 K [with $\gamma(0) \sim 255 \text{ mJ/mol K}^2$], is less common than in Ce systems. The origin of this asymmetry of behavior at the two ends of the lanthanide series is not understood.⁶

The inverse magnetic susceptibility χ^{-1} versus T for the YbXCu_4 compounds is shown in Fig. 2. For YbAuCu_4 and YbPdCu_4 , the χ^{-1} versus T plots are linear between room temperature and about 30 K [i.e., $\chi(T)$ follows a Curie-Weiss law $\chi(T) = N\mu_{\text{eff}}^2/3k_B(T - \Theta)$, where N is the number of ions which carry magnetic moments] and show a slight deviation from linearity below $\sim 30 \text{ K}$. The values of the respective Curie-Weiss temperatures Θ and effective magnetic moments μ_{eff} , which are close to the $4.54\mu_B$ value expected for a free Yb^{3+} ($J = \frac{7}{2}$) ion, are summarized in Table I together with the extrapolated values of $\chi(T)$ at 0 K.

FIG. 2. Inverse magnetic susceptibility χ^{-1} vs T for YbXCu_4 compounds with $X=\text{Ag}$, Au , and Pd , measured in a magnetic field $\mu_0 H = 1 \text{ T}$.

Shown in Fig. 3 are $\chi(T)$ data for YbAgCu_4 which follow a Curie-Weiss law between room temperature and $\sim 100 \text{ K}$ (see Fig. 2) and then pass through a maximum at $\sim 35 \text{ K}$ before reaching a constant value at low temperature. This behavior of $\chi(T)$ is rather interesting and similar to that reported for YbCuAl .⁷ Rajan⁸ has calculated $\chi(T)$ and the specific heat $C(T)$ in zero magnetic field for angular momentum values from $J = \frac{1}{2}$ to $\frac{7}{2}$ by solving the exact thermodynamic equations of the Coqblin-Schrieffer impurity model with the Bethe-ansatz. Calculations based on the Coqblin-Schrieffer model^{8,9} have been applied successfully by Hewson *et al.*¹⁰ to YbCuAl which suggests that this compound is a good example of a Kondo lattice. Kondo-lattice behavior is expected for compounds containing rare-earth ions with integral valence such as Ce^{3+} (e.g., CeAl_3), Sm^{3+} (e.g., SmB_6), or Yb^{3+} which have a ground-state multiplet and tendency towards mixed valence, and where the antiferromagnetic exchange coupling between the rare-earth ion and the conduction electron spins dominates over the Ruderman-Kittel-Kasuya-Yosida (RKKY) interaction. Such compounds are usually paramagnetic at $T = 0 \text{ K}$ or have very low ordering temperatures which appears to be the case for the new YbXCu_4 compounds discussed herein.

As shown in Fig. 3 the numerical results of Ref. 8 (solid line in the figure) provide an excellent description of the $\chi(T)$ data for YbAgCu_4 . The theoretical curve is based on only one parameter, the characteristic temperature T_0 which is given by $T_0 = \nu(\nu^2 - 1)g_J^2\mu_B^2/24\pi k_B\chi(0)$, where ν is the degeneracy of the ground state, g_J is the Landé g factor of the Hund's-rule ground-state multiplet with angular momentum J , and $\chi(0)$ is the experimental value of the susceptibility at zero temperature. The value $T_0 = 167.5 \text{ K}$ used to generate the theoretical curve in Fig. 3 was calculated from this relation using $\chi(0) = 1.96 \times 10^{-2} \text{ cm}^3/\text{mol}$ for YbAgCu_4 and $\nu = 2J + 1 = 8$ for Yb^{3+} .

Specific heat C versus T data are displayed in Fig. 4 for the three compounds with $X=\text{Ag}$, Au , and Pd . The large peak in $C(T)$ at the respective temperatures of $\sim 0.8 \text{ K}$

TABLE I. Summary of magnetic susceptibility and specific-heat data for YbXCu_4 ($X=\text{Ag,Au,Pd}$).

Material	μ_{eff} (μ_B)	Θ (K)	$\chi(T)$		T_{max} (K)	$\gamma(0)$ (mJ/mol K ²)	Θ_D (K)	$C(T)$	
			$\chi(0)$ (cm ³ /mol)					T_N (K)	m^* (m_e)
YbAgCu ₄	4.28	−31	1.96×10^{-2}		34	245 ± 6	129 ± 1		60
YbAuCu ₄	4.39	−8.8	2.75×10^{-1}					0.6	5.6
YbPdCu ₄	4.33	−13.5	1.74×10^{-1}			200	138	0.8	48

and ~ 0.6 K for the specimens with $X=\text{Au}$ and Pd is presumably associated with the anticipated long-range antiferromagnetic order. The absence of an anomaly in $C(T)$ for YbAgCu_4 confirms that this compound does not exhibit any magnetic order, at least down to 0.45 K. The plots of C/T versus T^2 presented in Fig. 5 reveal large $\gamma(0)$ values of ~ 245 mJ/mol K² for YbAgCu_4 and ~ 200 mJ/mol K² for YbPdCu_4 . For this latter compound, a linear extrapolation of the C/T versus T^2 data to $T=0$ to estimate $\gamma(0)$ seems reasonable in spite of the magnetic contribution at low T . In the case of YbAuCu_4 , there does not seem to be a reliable way of determining $\gamma(0)$ even if a fairly large value were to be expected. The values of $\gamma(0)$, the Debye temperature Θ_D , the Néel temperature T_N , the effective mass m^* and the temperature at which the entropy S reaches $R \ln 2$ are summarized in Table I. The effective mass was estimated from the relation $m^* = \hbar^2 k_F^2 \gamma(0) / \pi k_B (Z/\Omega)$ where $k_F = (3\pi^2 Z/\Omega)^{1/3}$, with $Z=4$ the number of $4f$ holes per unit cell (assuming Yb to have a valence 3+) and Ω the volume of the cubic unit cell.

According to Ref. 8, the zero-temperature, zero-field limit of the specific heat is given by $C(T \rightarrow 0)/T = \gamma = (\nu - 1)\pi k_B / 6T_0$. Using the value $T_0 = 167.5$ K determined above from the zero-temperature limit of the magnetic susceptibility $\chi(0)$, we obtain a value of 182 mJ/mol K² for γ which is in reason-

able agreement with the experimental value of ~ 245 mJ/mol K².

The reason that the Coqblin-Schrieffer model for Yb^{3+} impurities provides such a good description of $\chi(T)$ and γ for YbAgCu_4 seems to be that the intersite Yb-Yb interaction (presumably Néel) temperatures of the YbXCu_4 compounds with $X=\text{Au}$ and Pd . A general trend which seems to emerge is that the Néel temperatures T_N of Yb compounds are, on the average, smaller than those of Ce compounds, which, in turn, appear to be smaller than those of U materials [i.e., $T_N(\text{Yb}) < T_N(\text{Ce}) < T_N(\text{U})$]. In fact, all of the Yb-based systems which are known to order antiferromagnetically have $T_N < 1$ K [e.g., YbIr_2 ,¹¹ YbPd ,¹² YbX ($X=\text{N,P,As}$) (Ref. 13) and YbXCu_4 ($X=\text{Au,Pd}$)] with the exceptions of YbBe_{13} ($T_N = 1.28$ K) (Ref. 14) and Yb_3Pd_4 ($T_N = 3$ K).¹⁵ In the Ce and U compounds, T_N is usually closer to 10 K [e.g., CeAl_2 ($T_N = 3.5$ K), UCd_{11} ($T_N = 5$ K) or U_2Zn_{17} ($T_N = 9.7$ K)].

FIG. 3. Magnetic susceptibility χ vs temperature for YbAgCu_4 . The solid line is the calculated susceptibility $\chi(T)$ scaled to the zero temperature value, using the results of Ref. 8 for the $J = \frac{7}{2}$ Coqblin-Schrieffer model.

FIG. 4. Specific heat C vs temperature for YbXCu_4 compounds with $X=\text{Ag, Au, and Pd}$.

FIG. 5. Specific heat C divided by temperature T vs T^2 for YbXCu_4 compounds with $X = \text{Ag, Au, and Pd}$.

Another reason which makes the present family of Yb compounds interesting is the rather low entropy associated with the ground state which is expected to be a magnetic Γ_6 or Γ_7 doublet. It is apparent from Table I that for both YbAuCu_4 and YbPdCu_4 an entropy of $S = R \ln 2$ is not recovered until the temperature is raised from 0 K to about 10 times T_N , or in other words, only about 30–40 % of $R \ln 2$ is released by the magnetic transition. Similar behavior has been reported for YbX compounds with $X = \text{N, P, and As}$ (Ref. 13). It seems to be a general observation in magnetically ordered heavy-electron systems that the highly correlated electronic ground state removes a sizable amount of the entropy over a scale of the order of the Kondo temperature T_K . Since T_K is usually larger than T_N , only a small fraction of the expected magnetic entropy $R \ln 2$ is recovered at T_N . The competition between the magnetic ground state and the nonmagnetic heavy-electron ground state has been addressed by several authors,¹⁶ but the criteria for the occurrence of magnetic order in a heavy-electron system remains an unresolved problem for all Ce, U, and Yb materials.

In conclusion, we have shown that the hexagonal YbCu_5 compound, which is a nonmagnetic normal metal, can be transformed into a face-centered-cubic structure by

replacing one of the Cu atoms with an X atom of Ag, Au, or Pd, yielding dramatic changes in its electronic properties. In particular, the three YbXCu_4 compounds exhibit strong electronic correlations at low temperature with high γ values and large effective masses m^* . Whereas YbAuCu_4 and YbPdCu_4 order magnetically below 1 K, YbAgCu_4 does not display any cooperative phase transition. The excellent description of the temperature dependence of the magnetic susceptibility $\chi(T)$ and the electronic specific-heat coefficient γ of YbAgCu_4 by the Bethe-ansatz solution of the Coqblin-Schrieffer model seems to prove that the conduction electron-impurity spin-exchange interaction is much larger in this compound than the intersite interaction and any possible crystalline electric field terms in the effective Hamiltonian.

Finally, it is interesting to note that the original motivation for this study was based on some previous work performed in the Ce-Cu and U-Cu phase diagrams. For example, the hexagonal compound CeCu_5 orders magnetically at low temperature and has a rather low electronic specific-heat coefficient,¹⁷ whereas, in contrast, the two neighboring compounds CeCu_4 (Ref. 17) and CeCu_6 exhibit heavy-electron behavior.¹⁸ Another interesting case consists of the magnetically ordered UCu_5 and UAgCu_4 systems in which the formation of a heavy-electron state has also been reported.¹⁹ The present study clearly demonstrates that new efforts should be made to include Yb-based compounds in the fascinating and rapidly growing family of heavy fermion systems.

This work was supported by the U.S. National Science Foundation, Low Temperature Physics, Grant DMR-8411839 (C.R., M.B.M.), the U.S. Department of Energy under Grant No. DE-FG03-86ER45230 at University of California, San Diego (UCSD) (K.N.Y.), and under the auspices of the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Science, at Los Alamos (Z.F., E.Z., J.D.T.). The support of the Swiss National Science Foundation is gratefully acknowledged (C.R.). The authors would like to thank J. W. Chen for his assistance in making the low-temperature electrical-resistivity measurements in the dilution refrigerator.

¹See, for example, *Valence Fluctuations in Solids*, edited by L. M. Falicov, W. Hanke and M. B. Maple (North-Holland, Amsterdam, 1981); *Valence Instabilities*, edited by P. Wachter and H. Boppart (North-Holland, Amsterdam, 1982); *Valence Fluctuations*, edited by E. Müller-Hartmann, B. Roden, and D. Wohlleben (North-Holland, Amsterdam, 1984).

²For example, D. L. Cox, N. E. Bickers, and J. W. Wilkins, *J. Magn. Magn. Mater.* **54-57**, 333 (1986); P. Schlottmann, *J. Magn. Magn. Mater.* **47&48**, 367 (1985).

³B. Coqblin and J. R. Schrieffer, *Phys. Rev.* **185**, 847 (1969).

⁴A. Iandelli and A. Palenzona, *J. Less Common Met.* **25**, 333 (1971).

⁵H. H. Hill, in *Plutonium 1970 and Other Actinides*, edited by

W. H. Miner (AIME, New York, 1970), p. 2.

⁶D. Wohlleben and B. Wittershagen, *Adv. Phys.* **34**, 403 (1985).

⁷W. C. M. Mattens, R. A. Elenbaas, and F. R. de Boer, *Commun. Phys.* **2**, 147 (1977); W. C. M. Mattens, Ph.D. thesis, University of Amsterdam (1980).

⁸V. T. Rajan, *Phys. Rev. Lett.* **51**, 308 (1983).

⁹A. C. Hewson, D. M. Newns, J. W. Rasul, and N. Read, *J. Magn. Magn. Mater.* **47&48**, 354 (1985).

¹⁰A. C. Hewson and J. W. Rasul, *J. Phys. C* **16**, 6799 (1983).

¹¹J. O. Willis, Z. Fisk, and J. L. Smith, *J. Magn. Magn. Mater.* **47&48**, 581 (1985).

¹²R. Pott *et al.*, *Phys. Rev. Lett.* **54**, 481 (1985).

¹³H. R. Ott, H. Rudiger, and F. Hulliger, *Solid State Commun.*

- 55, 113 (1985).
- ¹⁴U. Walter, Z. Fisk, and E. Holland-Moritz, *J. Magn. Magn. Mater.* **47&48**, 159 (1985).
- ¹⁵B. Politt, J. Röhler, and P. Weidner, *J. Magn. Magn. Mater.* **47&48**, 583 (1985).
- ¹⁶S. Doniach, *Physica* **91B**, 231 (1977); in *Valence Instabilities and Related Narrow Band Phenomena*, edited by R. D. Parks (Plenum, New York, 1977), p. 2977; R. Jullien, in *Valence Instabilities*, edited by P. Wachter and H. Boppert (North-Holland, Amsterdam, 1982), p. 11, and references cited therein.
- ¹⁷B. Batlogg, Z. Fisk, and J. O. Willis (unpublished).
- ¹⁸G. R. Stewart, Z. Fisk, and M. S. Wire, *Phys. Rev. B* **30**, 482 (1984).
- ¹⁹H. R. Ott, H. Rudigier, E. Felder, Z. Fisk, and B. Batlogg, *Phys. Rev. Lett.* **55**, 1595 (1985).