UC Berkeley

UC Berkeley Previously Published Works

Title

Integrated catalytic sequences for catalytic upgrading of bio-derived carboxylic acids to fuels, lubricants and chemical feedstocks

Permalink

<https://escholarship.org/uc/item/7cz3139q>

Journal

Sustainable Energy and Fuels, 1(8)

ISSN

2398-4902

Authors

Shylesh, S
Gokhale, AA
Sun, K
et al.

Publication Date

2017

DOI

10.1039/c7se00359e

Peer reviewed

Cite this: *Sustainable Energy Fuels*,
2017, 1, 1805

Integrated catalytic sequences for catalytic upgrading of bio-derived carboxylic acids to fuels, lubricants and chemical feedstocks†

Sankaranarayananpillai Shylesh,^{ab} Amit A. Gokhale,^{id ac} Keyang Sun,^b
Adam M. Grippo,^a Deepak Jadhav,^a Alice Yeh,^a Christopher R. Ho^b
and Alexis T. Bell^{id *ab}

In the late 1850s, Charles Friedel's dry distillation of calcium acetate gave the world a novel route to the commercial production of acetone, a process that would later be referred to as decarboxylative dehydration (ketonization). While the subsequent development of the petrochemical industry made this route to acetone uncompetitive, today there is considerable interest in ketonization as means for converting biomass-derived fatty acids to produce longer-chained ketones, which could serve as precursors to fuels and lubricants. However, the lack of strategies beyond direct hydrogenation of the ketones into hydrocarbons has limited the practical application of ketonization for producing biofuels. We describe here integrated catalytic sequences for converting a range of biomass-derived carboxylic acids, sourced through fermentation of sugars, hydrolysis of lipids, or biomass pyrolysis, to compounds that are fully compatible with the existing energy infrastructure and require minimal hydrogen input.

Received 27th July 2017
Accepted 29th August 2017

DOI: 10.1039/c7se00359e

rsc.li/sustainable-energy

Growing public concern with climate change caused by the combustion of petroleum-based fuels combined with the rising worldwide demand for such fuels has created an urgent need to develop sustainable alternatives to fossil fuels.^{1–3} Nearly 86% of all energy used globally comes from fossil reserves (petroleum, natural gas, and coal) of which nearly 28% is used by the transportation sector; consequently, replacing even a part of the petroleum barrel with biomass could have a positive effect on climate change.⁴ Of the various bio-derived intermediates, carboxylic acids, especially light carboxylic acids (C₂–C₆) obtained by biomass fermentation or pyrolysis and mid- (C₈–C₁₄) and long-chained fatty acids (C₁₆–C₂₀) produced by hydrolysis of plant, animal, and algal oils (Scheme S1, ESI†) are of particular interest.^{3,5–8} We note that light carboxylic acids (C₂–C₃) are present in bio-oils in high concentration. Butyric acid, for example, can be generated in high titer (>60 g L^{−1}) from *Clostridium tyrobutyricum* by the anaerobic fermentation of glucose.⁹ Valeric acid (pentanoic acid) can be derived by the reduction of levulinic acid, which in turn is produced from γ -valerolactone (GVL) through hydrolysis of 5-hydroxy-

methylfurfural (HMF).¹⁰ Because of their low energy density, poor low-temperature properties, high water solubility, relatively high oxygen content, and acidity fatty acids cannot be used as fuels and need to be upgraded to remove oxygen.^{11–15} Though decarboxylation/decarbonylation is an attractive means for removing oxygen, these reactions do not enlarge the carbon chain length, promote C–C cleavage and usually requires large amounts of hydrogen obtained by steam reforming of methane, which coproduce CO₂. Here, we outline upgrading catalytic sequences based on self- and cross-ketonic decarboxylation (ketonization), a process that condenses two molecules of carboxylic acid to produce linear ketones together with CO₂, and H₂O.¹² The product ketones have an acidic CH group at the α position and possess both electrophilic and nucleophilic functionality, allowing them to be used as building blocks for producing petrol, jet, diesel, and lubricants.^{16–22} This approach utilizes the reactivity of biomass-derived molecules to deoxygenate them *via* intermolecular dehydration or decarboxylation and enables the production of longer chained hydrocarbons suitable as drop-in fuels and lubricants, while also using reducing the overall hydrogen demand for the process.

Our strategies for processing biomass-derived C₂–C₅ carboxylic acids and C₈–C₁₆ fatty acids to produce linear and branched alkanes and alkylated aromatic-cycloalkane compounds that can function as blending stocks for liquid fuels and as lubricants is summarized in Fig. 1. Step 2 in this scheme involves ketonic decarboxylation. While others have suggested hydrogenating such linear ketones to give fuels,^{8,17} we

^aEnergy Biosciences Institute, University of California, 2151 Berkeley Way, Berkeley, CA 94720, USA. E-mail: alexbell@berkeley.edu

^bDepartment of Chemical and Biomolecular Engineering, University of California, Berkeley, CA 94720, USA

^cBASF Corporation, 33 Wood Avenue South, Iselin, NJ, 07076, USA

† Electronic supplementary information (ESI) available: Experimental details, characterization of catalysts and reaction study details of ketonization, aldol condensation and hydrodeoxygenation catalysts. See DOI: 10.1039/c7se00359e

Fig. 1 Various reaction pathways for converting biomass-derived, short-chain carboxylic acids and fatty acids to liquid alkanes suitable for use as fuels and lubricants. Step (1): alcohols produced via fermentation of mixtures of sugars and/or by the hydrogenation of carboxylic acids. Step (2): self- and cross-ketonic decarboxylation of various carboxylic acids to the respective internal and methyl ketones. Step (3): formation of ketones by mono/dialkylation of alcohols with acetone. Step (4): aldol-type condensation of ketones to form respective dimer/trimer enones and alkylated aromatics. Step (5): hydrodeoxygenation of acyclic/cyclic enones, ketones, and alkylated aromatics to produce linear, branched and cyclic alkanes suitable for use as fuels and lubricants.

choose the dimerization of these ketones over acidic Nb_2O_5 followed by hydrodeoxygenation (HDO) over NbOPO_4 -supported Pt. This approach gives access to C_{10} – C_{18} acyclic alkanes. By controlling the relative proportions of the various acids, it is easy to match the typical product profile for diesel and jet fuels starting with relatively cheap carboxylic acids. In the past, ketonic decarboxylation followed by hydrodeoxygenation has been carried out with relatively expensive, vegetable-oil sourced, longer chained fatty acids (C_8 – C_{16}) to produce linear alkanes for diesel blends.¹¹ While the C_{15} – C_{17} hydrocarbons are ideal diesel components, the lack of branching on some of the higher molecular weight compounds makes them undesirable in fuels due to their poor cold flow properties. A more value-added strategy, therefore, is to dimerize the ketone intermediates to produce C_{30+} branched compounds, suitable for use as industrial lubricants and greases, since the price of these products is significantly higher than that of diesel (~ 1700 per mt for group III base oils vs. $\$950$ per mt for ULSD).²⁰ Similarly, cross-ketonic decarboxylation of acetic acid with carboxylic acids of various chain-lengths offers a route for producing alkyl methyl ketones.²³ Subsequent condensation of these ketones over acidic silica-supported tantalum oxide produces alkylated aromatic compounds, while reaction over an acid–base Mg/Al mixed oxide produces cyclic enones, compounds that upon hydrodeoxygenation give cycloalkane derivatives ideally suited as fuels or lubricants depending on their molecular weight.

Since ketonic decarboxylation is the gateway reaction for all of our catalytic schemes, self- and cross-ketonic decarboxylation of C_2 – C_5 carboxylic acids were carried out over calcined zirconia at 573 K to produce a distribution of symmetric and asymmetric

C_3 – C_9 ketones (Fig. 2 and S1–S2, ESI†). The calcination temperature was found to have a strong effect on the catalyst activity. Calcination at 823 K produced $t\text{-ZrO}_2$ which was about twice as active (per gram) as $m\text{-ZrO}_2$, produced by pre-treating zirconia sample at 1073 K. The higher activity of $\text{ZrO}_2@823$ K vs. $\text{ZrO}_2@1073$ K is ascribable to the higher concentration of basic sites for $m\text{-ZrO}_2$ compared to $t\text{-ZrO}_2$, $5.09 \mu\text{mol CO}_2$ per m^2 vs. $2.72 \mu\text{mol CO}_2$ per m^2 , as determined from IR spectra of adsorbed CO_2 .

The C_3 – C_9 internal ketones produced by ketonic decarboxylation are useful building blocks for further C–C bond forming reactions. To this end, various acid, base, and acid–base catalysts were investigated to establish their effectiveness for the selective dimerization of heptan-4-one. While calcined hydro-talcite ($\text{Mg}(\text{Al})\text{O}$) is an ideal catalyst for the trimerization of methyl ketones,²⁰ this catalyst and other basic and acid–base condensation catalysts such as MgO and hydroxyapatite (Ca-HAP , $\text{Ca}/\text{P} = 1.6$) exhibited low activity ($<5\%$ yield) for self-condensation of heptan-4-one at 453 K (Fig. S3, ESI†). By contrast, acidic Nb_2O_5 pre-treated at 523 K, was found to be highly active and selective because Lewis acidic on Nb_2O_5 are effective in stabilizing negatively charged enolate intermediates of central ketones. Using this catalyst, we obtained nearly 75% yield to the C_{14} acyclic enone dimers even under neat conditions (Table 1).

Pre-treatment of Nb_2O_5 was found to be crucial for obtaining high dimer yield. For example, Nb_2O_5 calcined at 573 K ($\text{Nb}_2\text{O}_5@573$ K), resulted in a nearly two-fold higher conversion of heptan-4-one and a higher selectivity to the dimer product than Nb_2O_5 pre-treated at 773 K ($\text{Nb}_2\text{O}_5@773$ K). The lower activity of $\text{Nb}_2\text{O}_5@773$ K is attributed to the formation of the crystalline orthorhombic (T) phase, a decrease in acid site

Fig. 2 Distribution of C_5 – C_9 ketones produced by cross-ketonic decarboxylation of C_3 – C_5 carboxylic acids over a calcined ZrO_2 catalyst. Feed composition: (A) $\text{C}_3 : \text{C}_4 : \text{C}_5 = 1 : 1 : 1$, (B) $\text{C}_3 : \text{C}_4 : \text{C}_5 = 0.5 : 0.5 : 2$, (C) $\text{C}_3 : \text{C}_4 : \text{C}_5 = 2 : 0.5 : 0.5$, (D) cross-ketonization scheme of C_3 – C_5 carboxylic acids to C_5 – C_9 ketones. Reaction conditions: $T = 573$ K, carboxylic acids = 3 mmol, solvent = 7 mL, $t = 6$ h, $M_{\text{cat}} = 0.2$ g. All reactions were carried out in a stirred autoclave.

Table 1 Condensation of ketones derived from self- and cross-ketonic decarboxylation of carboxylic acids to the respective dimer acyclic enones, cyclic enones and aromatic trimers^a

Entry	Ketone (1)			Catalyst	Conv. 1 (%)	Yield of condensates (%) [*]		
	C _n	R	R ¹			2	3	4
1	C ₇	Et	Et	Nb ₂ O ₅	88	73	0	0
2	C ₆	Et	Me	Nb ₂ O ₅	93 (91)	83	5	0
3 ⁺	C ₅	Me	Me	Nb ₂ O ₅	89	79	1	0
4	C ₉	<i>n</i> Pr	<i>n</i> Pr	Nb ₂ O ₅	80	81	3	0
5	C ₉	<i>n</i> Bu	Et	Nb ₂ O ₅	81	70	0	0
6	C ₅	<i>n</i> Pr	H	Mg(Al)O	98 (96)	0	93	0
7	C ₆	<i>n</i> Pr	H	Ta/SiO ₂	96 (93)	0	4	71

^a Ketone (1, 2 mmol), catalyst (200 mg), *T* (453 K), *t* (6 h for Mg(Al)O and 24 h for Nb₂O₅ and Ta/SiO₂ catalyst) and toluene (3 mL) were heated in a sealed Q-tube reactor. ^{*}Mixture of positional and stereoisomers. ⁺Produced as a mixture of dimer and trimer isomers in a 3 : 1 ratio. Values in parenthesis show the reusability of the catalysts after third reuse. Cyclic enone trimers and aromatic compounds constitute major side products. (Mg/Al)O represents Mg–Al oxides with an Mg/Al molar ratio of 3, and Ta/SiO₂ represent silica-supported Ta₂O₅ with a Ta/Si molar ratio of 0.2.

concentration (ASC), as well as a decrease in surface area (Fig. S4, ESI†).²⁴ Similarly, nonan-5-one, produced by ketonic decarboxylation of pentanoic acid, could be dimerized very selectively to a C₁₈ acyclic enone, whereas pentan-3-one, obtained by the ketonic decarboxylation of propionic acid, produced a mixture of dimer and trimer acyclic enones in a nearly 3 : 1 ratio. The C₅–C₉ ketones produced by the cross-ketonic decarboxylation of C₃–C₅ carboxylic acids were subsequently cross-condensed over Nb₂O₅ to produce a distribution of C₁₀–C₁₈ acyclic ketones with varying degrees of branching. Finally, hydrodeoxygenation of the acyclic enone dimers over a Pt supported on niobium phosphate (2 wt% Pt/NbOPO₄) produced C₁₀–C₁₈ acyclic alkanes with varying degrees of branching, products that are ideal drop-in replacements for fossil-derived jet and diesel (Fig. S5, ESI†).²² The hydrogen required for these upgrading deoxygenation reactions can be obtained by aqueous reforming of biomass, as reported by Dumesic and co-workers.²⁵ The Nb₂O₅ and the Pt/NbOPO₄ catalysts could be recycled three times without any loss in activity (Table 1).

Ketonic decarboxylation of carboxylic acids can also be used to produce fuels and lubricants from renewable sources. For example, it is possible to produce the high-octane gasoline additive 2,4-dimethyl pentane *via* ketonic decarboxylation of isobutyric acid followed by hydrodeoxygenation over Pt/NbOPO₄ (Fig. S2, ESI†). Similarly, C₈–C₁₆ fatty acids obtained from vegetable oils can be converted to their respective ketones with yields >80% at 593 K, using *t*-ZrO₂ as the catalyst. Decarboxylation of fatty acids, a side reaction, reduces the yield but

gives linear alkanes, which are still useable for blending into diesel.¹⁵ Linear alkanes suitable as diesel and lubricants can also be obtained by hydrodeoxygenation of the C₁₅–C₃₁ internal ketones obtained by ketonic decarboxylation of fatty acids over Pt/NbOPO₄ catalysts (Fig. 3A). The C₁₅–C₂₃ linear alkanes produced by this sequence are drop-in diesel fuels having high cetane numbers (CN > 90) while, the corresponding C₂₇–C₃₅ linear alkanes are excellent lubricants that have high viscosity indices and thermal stability.²⁶ It is noted, though, that straight chain alkanes tend to increase the cloud point to between –20 °C and 5 °C; consequently, isomerization of straight chain alkanes is necessary to avoid wax formation for low-temperature applications.¹⁴ On the other hand, high quality base-oils containing >30 carbons can be synthesized by dimerization and hydrodeoxygenation of ketones produced by ketonic decarboxylation of fatty acids in yields >50% (Fig. 3B, Scheme S3, ESI†).

We investigated avenues for replacing cyclic alkanes and aromatics derived from petroleum.^{27,28} Such compounds are present in petrol, which contains 5–10% cycloalkanes and 20–50% aromatics, and jet, which contains 10–30% cycloalkanes and aromatics.²⁹ The hydroprocessing of linear alkanes over zeolites has been proposed to produce aromatics and cyclics; however this approach requires relatively large amounts of hydrogen and frequent catalyst regeneration to counteract high coking rates.²⁸ We have found that alkylated cyclic alkanes and aromatics can be produced from alkyl methyl ketones (C₄–C₁₁) (Table 1), obtained by the cross-ketonic decarboxylation of carboxylic acid with acetic acid (Fig. S6†) or by monoalkylation of acetone with various alcohols (Scheme S2, ESI†). Screening studies revealed that a γ-Al₂O₃-supported MgO or a calcined

Fig. 3 (A) Yield of C₁₅–C₃₁ alkanes after ketonic decarboxylation and hydrodeoxygenation of C₈–C₁₆ fatty acids over a ZrO₂ and 2 wt% Pt/NbOPO₄, respectively. (B) Production of diesel range C₁₅ linear alkanes and synthetic lubricant-type C₃₀ alkanes by ketonic decarboxylation of C₈ carboxylic acid and subsequent condensation-hydrodeoxygenation. The small amount of <C₁₀ products are lower molecular weight alkanes produced during hydrodeoxygenation. (C) Catalytic trimerization of C₄–C₁₁ methyl ketones to their respective C₁₂–C₃₃ cycloalkane compounds over Mg/Al oxides and hydrodeoxygenation over a 2 wt% Pt/NbOPO₄. (D) Catalytic trimerization of C₄–C₁₀ methyl ketones to the respective C₁₂–C₃₀ alkylated aromatics over a Lewis-acidic Ta/SiO₂ at 453 K.

hydrotalcite ($\text{Mg}/\text{Al} = 3$) is a very selective catalysts for trimerizing $\text{C}_4\text{--C}_{11}$ alkyl methyl ketones to their respective cyclic enones. Hydrodeoxygenation of these compounds over Pt/NbOPO_4 produced cycloalkane derivatives in >95% yields (Fig. 3C, Table 1). Cycloalkane derivatives made by trimerization of $\text{C}_4\text{--C}_6$ ketones are suitable for jet/diesel, whereas condensates made from $\text{C}_9\text{--C}_{11}$ ketones are suitable as lubricants.^{20,22}

For instance, the derived cetane number (DCN) of $\text{C}_{12}\text{--C}_{18}$ cycloalkanes was found to be 48 while the C_{33} cycloalkane derivatives have an excellent pour point ($\text{PP} = -69^\circ\text{C}$), viscosity index ($\text{VI} = 123$) and volatility ($\text{TGA Noack} = 2.58\%$), properties that are comparable to those of PAOs ($\text{PP} = -72^\circ\text{C}$, $\text{VI} = 124$ and $\text{TGA Noack} = 9.64\%$) and significantly better than those of mineral base oils ($\text{PP} = -10$ to -20°C and $\text{VI} = 80\text{--}120$).²⁰ We have extended this approach in order to identify heterogeneous catalysts and appropriate reaction conditions for the self-condensation of $\text{C}_4\text{--C}_{10}$ methyl ketones to their respective alkylated aromatic compounds (Fig. S7, ESI†). Of the various acidic catalysts screened, we found that silica-supported Ta_2O_5 ($\text{Ta}_2\text{O}_5/\text{SiO}_2$) to be ideal for catalyzing the trimerization of alkyl methyl ketones to chemical feedstocks and fuel-lubricant range alkylated aromatic compounds in high overall yields (Fig. 3D, Table 1). Presumably, this catalyst has the appropriate Lewis acidity to effectively convert the methyl ketones to the alkylated aromatics and during this transformation oxygen is removed in the form of water without utilizing hydrogen (Fig. S8, ESI†). However, the $\text{Ta}_2\text{O}_5/\text{SiO}_2$ catalysts needs to be calcined at 823 K before they are reused due to the adsorption of cyclic enones on the acidic sites, as suggested by IR studies (Fig. S9, ESI†).

The integrated catalytic approaches reported here allow the processing of carboxylic acids of various chain length to linear and branched alkanes as well as aromatics and cycloalkane derivatives that are compatible with existing transportation fuels. Producing fuels, chemicals and lubricants from renewable sources is mainly controlled by the availability of synthons and processing costs, which is closely linked to the number of reaction steps associated with the transformation of highly oxygenated molecules to the oxygen-free liquid alkanes. The integrated catalytic sequences illustrated in this study, which are based on relatively inexpensive carboxylic acids as feedstocks; the use of highly selective, hydrothermally stable catalysts; and the minimal demand for hydrogen make the whole process economically attractive and ideal for commercialization. Interestingly, both ketonic decarboxylation and the ketone condensation can increase the carbon chain length and lower the oxygen content relative to that in the reactant without the need for a hydrogen assisted deoxygenation reaction pathway. For example, utilizing a ketonic decarboxylation-aldol condensation pathway, butyric acid with a C/O ratio of 2 can be enhanced significantly to a C/O ratio of 14 by the removal of CO_2 and H_2O , without utilizing hydrogen. From a process perspective, it may be theoretically possible to structure a reaction sequence involving the conversion of carboxylic acids into ketones *via* ketonization followed by ketone condensation and hydrodeoxygenation to alkanes of the desired molecular range without introducing intermediate separation steps. In such a scheme, complete conversion of carboxylic acids to ketones or

alkanes would be crucial since the base catalyst used for ketone condensation is highly susceptible to poisoning by the acids. Nevertheless, a cascade of the liquid phase reactions described here could be integrated into a process to convert bio-derived carboxylic acids to renewable fuels and other chemical feedstocks.

Conclusions

In summary, we have shown that a sequence of catalyzed reactions can be envisioned for converting carboxylic acids to linear and branched alkanes as well as aromatics and cycloalkane derivatives that are compatible with the existing transportation fuels. This synthetic strategy is also applicable to the production of high-quality lubricants. We also note that both ketonic decarboxylation and ketone condensation increase the carbon chain length and lower the oxygen content relative to that in the reactant without the need for extensive hydrodeoxygenation. Contrary to previously reported methods for producing jet-diesel range linear alkanes,^{1,18,30} the processes presented here consumes a maximum of three moles of hydrogen per mole of product for the production of branched alkanes from carboxylic acids, and alkylated aromatics can be produced without any hydrogen input. Therefore, we conclude that the integrated catalytic sequences discussed in this article hold promise because they use relatively inexpensive carboxylic acids and catalysts, and require minimal consumption of hydrogen to produce a broad range of fuels, fuel additives, and lubricants in high overall yields.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the Energy Bioscience Institute funded by BP. We gratefully acknowledge the contributions of Lipeng Wu, and Lin Louie to the experimental section of the manuscript.

References

- 1 G. W. Huber, J. N. Chheda, C. J. Barrett and J. A. Dumesic, *Science*, 2005, **308**, 1446–1450.
- 2 Y. Roman-Leshkov, J. N. Chheda and J. A. Dumesic, *Science*, 2006, **312**, 1933–1937.
- 3 M. J. Climent, A. Corma and S. Iborra, *Green Chem.*, 2014, **16**, 516–547.
- 4 S. Chu and A. Majumdar, *Nature*, 2012, **488**, 294–303.
- 5 G. W. Huber, S. Iborra and A. Corma, *Chem. Rev.*, 2006, **106**, 4044–4098.
- 6 A. Pulido, B. Oliver-Thomas, M. Renz, M. Boronat and A. Corma, *ChemSusChem*, 2013, **6**, 141–151.
- 7 D. M. Alonso, S. G. Wettstein and J. A. Dumesic, *Chem. Soc. Rev.*, 2012, **41**, 8075–8098.

- 8 C. Aiello-Mazzarri, F. K. Agbogbo and M. T. Holtzapple, *Bioresour. Technol.*, 2006, **97**, 47–56.
- 9 J.-M. Lee, P. P. Upare, J.-S. Chang, Y. K. Hwang, J. H. Lee, D. W. Hwang, D.-Y. Hong, S. H. Lee, M.-G. Jeong, Y. D. Kim and Y.-U. Kwon, *ChemSusChem*, 2014, **7**, 2998–3001.
- 10 E. L. Kunkes, D. A. Simonetti, R. M. West, J. C. Serrano-Ruiz, C. A. Gartner and J. A. Dumesic, *Science*, 2008, **322**, 417–421.
- 11 A. Corma, M. Renz and C. Schaverien, *ChemSusChem*, 2008, **1**, 739–741.
- 12 T. N. Pham, T. Sooknoi, S. P. Crossley and D. E. Resasco, *ACS Catal.*, 2013, **3**, 2456–2473.
- 13 B. Peng, Y. Yao, C. Zhao and J. A. Lercher, *Angew. Chem., Int. Ed.*, 2012, **51**, 2072–2075.
- 14 G. W. Huber, P. O'Connor and A. Corma, *Appl. Catal., A*, 2007, **329**, 120–129.
- 15 E. Santillan-Jimenez and M. Crocker, *J. Chem. Technol. Biotechnol.*, 2012, **87**, 1041–1050.
- 16 J. C. Serrano-Ruiz and J. A. Dumesic, *Energy Environ. Sci.*, 2011, **4**, 83–99.
- 17 A. Corma, B. Oliver-Thomas, M. Renz and I. L. Simakova, *J. Mol. Catal. A: Chem.*, 2014, **388–389**, 116–122.
- 18 A. Corma, O. de la Torre and M. Renz, *Energy Environ. Sci.*, 2012, **5**, 6328–6344.
- 19 P. Anbarasan, Z. C. Baer, S. Sreekumar, E. Gross, J. Binder, H. W. Blanch, D. S. Clark and F. D. Toste, *Nature*, 2012, **491**, 235–239.
- 20 M. Balakrishnan, E. R. Sacia, S. Sreekumar, G. Gunbas, A. A. Gokhale, C. D. Scown, F. D. Toste and A. T. Bell, *Proc. Natl. Acad. Sci. U. S. A.*, 2015, **112**, 7645–7649.
- 21 M. T. Holtzapple, R. R. Davison, M. K. Ross, S. Aldrett-Lee, M. Nagwani, C.-M. Lee, S. Adelson, W. Kaar, D. Gaskim, H. Shirage, N.-S. Chang, V. S. Chang and M. E. Loescher, *Appl. Biochem. Biotechnol.*, 1999, **77–79**, 609–631.
- 22 E. R. Sacia, M. Balakrishnan, M. H. Deaner, K. Goulas, F. D. Toste and A. T. Bell, *ChemSusChem*, 2015, **8**, 1726–1736.
- 23 C. A. Gaertner, J. C. Serrano Ruiz, D. J. Braden and J. A. Dumesic, *Ind. Eng. Chem. Res.*, 2010, **49**, 6027–6033.
- 24 G. S. Nair, A. A. Alsalme, I. V. Kozhevnikov, D. J. Cooke, D. R. Brown and N. R. Shiju, *Catal. Sci. Technol.*, 2012, **2**, 1173–1179.
- 25 R. D. Cotright, R. R. Davda and J. A. Dumesic, *Nature*, 2002, **418**, 964–967.
- 26 T. G. Smagala, E. Christensen, K. M. Christison, R. E. Mohler, E. Gjersing and R. L. McCormick, *Energy Fuels*, 2013, **27**, 237–246.
- 27 T. P. Vispute, H. Zhang, A. Sanna, R. Xiao and G. W. Huber, *Science*, 2010, **330**, 1222–1227.
- 28 J. D. Adjaye and N. N. Bakhshi, *Fuel Process. Technol.*, 1995, **45**, 185–202.
- 29 R. W. Jenkins, C. M. Moore, T. A. Semelsberger, C. J. Chuck, J. C. Gordon and A. D. Sutton, *ChemSusChem*, 2016, **9**, 922–931.
- 30 L. X. Li, E. Coppola, J. Rine, J. L. Miller and D. Walker, *Energy Fuels*, 2010, **24**, 1305–1315.