Lawrence Berkeley National Laboratory

Recent Work

Title

PRESSURE DEPENDENCE OF SCHOTTKY BARRIER HEIGHT AT PT/GAAS INTERFACE

Permalink

<https://escholarship.org/uc/item/7n65j0q3>

Authors

Shan, W.

Li, M.F.

Yu, P.Y.

Publication Date

1988-08-01

RECEIVED
LAWRENCE
BERKELEY LABORATORY

LBL-25691

OCT 4 1988

LIBRARY AND
DOCUMENTS SECTION

Center for Advanced Materials

CAM

Presented at the Fifteenth International
Conference on Defects in Semiconductors,
Budapest, Hungary, August 22-26, 1988

Pressure Dependence of Schottky Barrier Height at Pt/GaAs Interface

W. Shan, M.F. Li, P.Y. Yu,
W. Walukiewicz, and W.L. Hansen

August 1988

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks.*

Materials and Chemical Sciences Division
Lawrence Berkeley Laboratory • University of California
ONE CYCLOTRON ROAD, BERKELEY, CA 94720 • (415) 486-4755

Prepared for the U.S. Department of Energy under Contract DE-AC03-76SF00098

LBL-25691
c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

PRESSURE DEPENDENCE OF SCHOTTKY BARRIER HEIGHT AT Pt/GaAs INTERFACE

W. Shan^{1,2}, M.F. Li^{1,3}, P.Y. Yu¹, W. Walukiewicz⁴ and W.L. Hansen⁴

1. Department of Physics, University of California, and Materials and Chemical Sciences Division, Lawrence Berkeley Laboratory, Berkeley, CA 94720, U.S.A
2. On leave from Shanghai Institute of Technical Physics, Academia Sinica, Shanghai, China
3. Present address: Graduate School, University of Science and Technology of China, Beijing, China
4. Center for Advanced Materials, Lawrence Berkeley Laboratory, Berkeley, CA 94720, U.S.A

ABSTRACT

The pressure dependence of Schottky barrier height at the Pt/GaAs interface has been studied using a diamond anvil cell. The pressure coefficient of the Schottky barrier height suggests that whatever states responsible for the Fermi level pinning follow the valence band edge under pressure. Within models that simple intrinsic defects are responsible for the formation of Schottky barriers in GaAs, our results suggest that these intrinsic defects may involve vacancies.

INTRODUCTION

The basic mechanisms of the formation of Schottky barrier(SB) on the surface of semiconductors such as GaAs by deposition of metal overlayers are still not well understood. Detailed studies of the chemical, electronic, and spatial structure of metal-semiconductor interfaces have indicated very weak dependence of the Schottky barrier height on metal work function and electronegativity. Also a large density of states at metal-semiconductor interfaces[1-3] have been proposed to be responsible for pinning the Fermi level. So far the microscopic nature of those states is not clear, although some theories attributed these states to defects while others attributed them to metal-induced gap states. In this paper we present a measurement of the pressure coefficient of Schottky barrier heights at Pt/GaAs(n-type) interface and compare it with pressure coefficients of different types of deep levels introduced by native defects. We found that the SB height under pressure shifts to higher energy with a linear pressure coefficient of 11 meV/kbar and with a nonlinear coefficient of -0.26 meV/kbar^2 . Our results are found to be consistent with

level in heavily irradiated group III-V and IV semiconductors. In particular it was suggested that simple defects, such as V_{Ga} (acceptor) and $As_{Ga}+V_{As}$ (donor), together could stabilize the Fermi level position in the forbidden gap.

So far there is no way to prove or disprove these models since there has been no direct evidence of the existence of such defects at the interface. Pressure dependence offers one way to test these models since the pressure dependence of SB height should be determined by the pressure dependence of the defect levels responsible for the pinning of the Fermi level. For example, the pressure dependence of the EL2 has been determined by Dobaczewski *et al.* [14]. The linear and nonlinear pressure coefficient are 4.4 meV/kbar and -0.11 meV/kbar² respectively. These pressure coefficients are significantly different from that of the SB determined by this work that one has to exclude the EL2 as responsible for pinning the Fermi level at the Pt/GaAs interface. It is more difficult to test the model of Walukiewicz since the pressure coefficients of the intrinsic defects V_{Ga} and $As_{Ga}+V_{As}$ have not been reported. To explore further the idea of stabilization of the Fermi level by defects, we compare the pressure coefficients of the SB with the pressure coefficients of deep centers in GaAs compiled by Kumagai *et al.* [15] and Wallis *et al.* [16]. From Table 1 in Ref. 15, we conclude that only two deep levels, E_3 and E_4 have pressure coefficients consistent with our result. Their pressure dependences are shown in Fig. 2 for comparison with those of the SB. Unfortunately the identification of these deep levels are still uncertain. The level E_3 has been associated with V_{Ga} mainly because it has been found to track with the valence band edge as a function of pressure and of the Al concentration in $Ga_{1-x}Al_xAs$ alloys [17]. It was argued that, since the wavefunctions of Ga vacancies were derived predominantly from valence band states, they should follow the valence band edge. This identification has been questioned for example by Ren *et al.* [18]. Based on their theoretical calculations of the pressure coefficients of deep defect levels, these authors have concluded that both E_3 and E_4 were probably complexes, possibly an interstitial $As-V_{As}$ pair. Thus our results are consistent with the model of Walukiewicz provided the intrinsic defects, responsible for pinning the Fermi level at metal/GaAs interfaces, are complexes containing vacancies of As or Ga.

CONCLUSIONS AND ACKNOWLEDGEMENTS

We have shown that the native defect EL2 is not responsible for the Fermi level pinning at metal-GaAs interfaces. The pressure dependence of the SB height is consistent with the amphoteric native defect model of the Schottky barrier formation provided these intrinsic defects involve complexes of Ga and As vacancies.

This work is supported by the Director, Office of Basic Energy Sciences, Materials Sciences Division of the U.S. Department of Energy under contract no. DE-AC03-76SF00098.

REFERENCES

1. Newman, N., Schilfgaard, M. Van, Kendelewicz, T., Williams, M.D., and Spicer, W.E.: Phys. Rev., 1986, B33, 1146.
2. Zussman, A.: J. Appl. Phys. Lett., 1986, 59, 3894.
3. Waldrop, J.R.: Appl. Phys. Lett., 1985, 46, 864.
4. Erskine, D., Yu, P.Y. and Martinez, G.: Rev. Sci. Instruments, 1987, 58, 406.
5. Sze, S.M.: in PHYSICS OF SEMICONDUCTOR DEVICES, Wiley, New York, 1969, Chapter 8.
6. Welber, B., Cardona, M., Kim, C.K. and Rodriguez, S.: Phys. Rev., 1975, B12, 5729.
7. Hanfland, M., Syassen, K. and Christensen, N.E.: J. de Physique, 1984, C8, Suppl. 11, C8-57.
8. Spicer, W.E., Lindau, I., Skeath, P., Su, C.Y., and Chye, P.: Phys. Rev., Lett., 1980, 44, 420; J. Vac. Sci. Technol., 1980, 17, 1019.
9. Spicer, W.E., Eglash, S., Lindau, I., Su, C.Y., and Skeath, P.: Thin Solid Films, 1982, 89, 447.
10. Daw, M.S. and Smith, D.L.: Solid State Commun., 1981, 37, 205.
11. Allen R.E. and Dow, J.D.: Phys. Rev., 1982, B25, 1423.
12. Lagowski, J., Lin, D.G. Chen, J.P., Skowronski, M. and Gatos, H.C.: Appl. Phys. Lett., 1985, 47, 929.
13. Walukiewicz, W.: J. Vac. Sci. Technol., 1987, B5, 1062; Phys. Rev., 1988, B37, 4760.
14. Dobaczewski, L. and Sienkiewicz, A.: Act. Phys. Polon., 1987, A71, 341.
15. Kumagai, O., Wunstel, K. and Jantsch, W.: Solid State Comm., 1982, 41, 89.
16. Wallis, R.H., Zylbersztejn, A. and Besson, J.M.: Appl. Phys. Lett., 1981, 38, 698.
17. Long, D.V., Logan, R.A. and Kimerling, L.C.: Phys. Rev., 1977, B15, 4874.
18. Ren, S.Y., Dow, J.D. and Wolford, D.J.: Phys. Rev., 1982, B25, 7661.

*LAWRENCE BERKELEY LABORATORY
TECHNICAL INFORMATION DEPARTMENT
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720*