Lawrence Berkeley National Laboratory

Recent Work

Title

THE PREPARATION OF ACCELERATOR TARGETS BY THE EVAPORATION OF ACETATE-ORGANIC SOLUTIONS IN THE PRESENCE OF NH₃ GAS

Permalink

<https://escholarship.org/uc/item/8246s1fb>

Authors

Cai, S.Y.

Ghiorso, A.

Hoffman, D.C.

Publication Date

1987-03-01

Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

RECEIVED
LIBRARY
BERKELEY LABORATORY

JUN 9 1987

LIBRARY
DOCUMENTS SECTION

**THE PREPARATION OF ACCELERATOR TARGETS
BY THE EVAPORATION OF ACETATE-ORGANIC
SOLUTIONS IN THE PRESENCE OF NH_3 GAS**

S.-Y. Cai, A. Ghiorso, and D.C. Hoffman

March 1987

TWO-WEEK LOAN COPY

*This is a Library Circulating Copy
which may be borrowed for two weeks*

LBL-23409 c.2

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

The Preparation of Accelerator Targets by the Evaporation of
Acetate-Organic Solutions in the Presence of NH_3 Gas

Shan-Yu Cai*, A. Ghiorso, Darleane C. Hoffman

*On leave from the Radioisotope Division, Institute of Atomic Energy, P. O. Box 275(66), Beijing, China

Nuclear Science Division, Lawrence Berkeley Laboratory, University of California, Berkeley, California 94720

This work was supported by the Director, Office of Energy Research, Division of Nuclear Physics of the Office of High Energy and Nuclear Physics of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098.

The Preparation of Accelerator Targets by the Evaporation of Acetate-Organic Solutions in the Presence of NH_3 Gas

Shan-Yu Cai*, A. Ghiorso, Darleane C. Hoffman

*On leave from the Radioisotope Division, Institute of Atomic Energy, P. O. Box 275(66), Beijing, China

Nuclear Science Division, Lawrence Berkeley Laboratory, University of California, Berkeley, California 94720

The chemical methods described in this paper have been developed for preparation of isotopic targets for bombardment by accelerator-produced ions. Three systems are compared: nitrate-, chloride-, and acetate-organic solutions. The best method was found to be the metallic acetate-organic solution system, evaporated onto the substrate in the presence of ammonia gas. A detailed procedure is given for this method.

The targets obtained by the acetate-organic solution system are uniform and adherent. The hydroxide forms fine crystals of good quality for target thicknesses from a few $\mu\text{g}/\text{cm}^2$ to several mg/cm^2 . Thicknesses up to $5 \text{ mg}/\text{cm}^2$ of Eu as the oxide were obtained by this method. The process is simple and fast.

I. Introduction

Many techniques have been employed to make targets for accelerator bombardments. Among them are evaporation,^{1,2} vacuum sublimation,^{3,4} electrospraying,^{5,6,7} ion implantation,⁸ powder pressing,⁹ and electrodeposition or molecular plating,¹⁰⁻¹⁸ etc. Each has its own merits and drawbacks.

For vacuum sublimation (using resistance or electron bombardment heating), electrospraying or ion implantation techniques, the drawbacks are either the complexity of equipment or the difficulty of the procedure. With regard to powder pressing, a number of materials are needed to make the targets.

Molecular plating has long been used for the preparation of targets and radioactive sources. The deposits are in most cases uniform and adherent. However, each layer cannot be more than $100 \mu\text{g}/\text{cm}^2$ thick. In order to obtain thicker layers, the deposit on the backing material is calcined in a muffle furnace, and then the plating procedure is repeated. However, the overall time for this procedure for preparing thicker targets is very long. In addition, the deposits can be partially dissolved while the electrolyte solution is added to or removed from the cell and this can affect the quality of the target. In general, target thicknesses up to about $1 \text{ mg}/\text{cm}^2$ can be obtained. The yield of deposition is usually from 70 to 90%.

The method of evaporating a solution is very simple, but the trouble is that each drop which is evaporated can be dissolved by the addition of the next. For this reason, it is difficult to get uniform and adherent targets.

One way to solve this main problem is to change the chemical form after each drop is deposited. For example, it is possible to continuously convert the metallic salt into the hydroxide. This hydroxide can subsequently be converted to the oxide which is insoluble. The following sections are devoted to a detailed description of the experiments that were undertaken to determine the optimum chemical conditions for taking advantage of this idea.

II. Experimental

2.1 Preparation of the feed solutions

Most of the experiments were done with lanthanum and europium compounds; however, samples prepared with samarium, neodymium and praseodymium were of equal quality.

Lanthanum nitrate, $\text{La}(\text{NO})_3 \cdot 6 \text{H}_2\text{O}$, was dissolved in dilute nitric acid. Europium oxide (purity 99%) was dissolved in dilute hydrochloric or acetic acid. In order to increase the solubility of Eu_2O_3 in acetic acid, heating was necessary.

The above acidic solutions were pipetted into centrifuge tubes and dried. The dry material was then dissolved in a mixture of water and ethanol. The resulting solutions were dried again.

Finally, the dry material was dissolved in the different mixtures of organic solutions, forming stock solutions with concentrations of less than 0.2 mg/ml.

2.2 Backing material

The following thin metal foils were used as backing materials, aluminum (5×10^{-2} mm thick), beryllium (1.3×10^{-2} mm thick), platinum (2×10^{-3} mm thick).

Prior to preparing the target, it was necessary to clean the backing material. Each foil was washed with HNO_3 , H_2O , or acetone depending on which foil was used, by means of an ultrasonic cleaner. Subsequently, the foils were rinsed with alcohol or acetone and dried. The quality of the layers was excellent on the above substrates because the organic solution does not attack Al, Be, or Pt foils.

2.3 Ammonia gas

Concentrated ammonium hydroxide was poured into a plastic wash-bottle which could be squeezed to produce hydrous NH_3 gas. An ammonia cylinder (anhydrous) was also used in the experiments, but it was found that for good targets the ammonia should be hydrated.

2.4 Other equipment

A hot plate was used for heating the substrate. The temperature of the substrate could be controlled automatically, and was measured by an iron-constantan thermocouple. A muffle furnace was used to convert the hydroxide to the oxide at 450-550⁰. The quality of targets was observed by means of a microscope (x5).

2.5 Defining the area of each target

In order to define the area of a target, a circular paper disk (6 or 8 mm) was wet with water and stuck to the Al or Be foil. Orr-Lac (spray lacquer) was sprayed onto the substrate. After the lacquer had dried, the paper was removed from the substrate and the circular area was cleaned with ethanol. The advantage of lacquer is that it cannot be decomposed at 130⁰C, but it can be carbonized at 450-550⁰C.

2.6 The method of preparing targets

The substrate is heated at constant temperature by a hot plate. The organic solution containing the metallic salt is dropped onto the substrate in 20 μ l or 25 μ l aliquots. In order to get a uniform and circular deposit, it is important to control the evaporation of the original drops (1-3 drops). Because of the low surface tension of the organic solution, the best way to do this is to keep the tip of the pipette in touch with the drop until it dries.

As the drops of solution are being evaporated, ammonia gas is continuously blown over the surface to convert the salt into its hydroxide form. After each drop is dried, the next drop can be pipetted onto the surface without dissolving the previous material. In this way, the process is repeated until the target reaches the desired thickness. The target is then placed in an oven at

450-550°C for 15 minutes to convert the hydroxide to the oxide form. This procedure works well for targets up to 500 $\mu\text{g}/\text{cm}^2$, but for thicker targets, more than 0.5 mg/cm^2 , it is best to build them up in layers of $\sim 200 \mu\text{g}/\text{cm}^2$ each, with conversion to the oxide after each layer is completed.

II Results

3.1 Choosing the solvent

To prevent introduction of undesirable impurities, all reagents used should be of the highest possible purity.

Experiments indicate that using acidic solution as a solvent in preparing the targets is inadvisable, because each drop will dissolve the previously deposited drop, even after the deposit has been converted to the hydroxide form by NH_3 gas.

Pure water also does not work well as a solvent, although it easily dissolves the acetate. The main problem with water as a solvent is that the surface tension of the solution is too high and the evaporation of the solution is too slow. Furthermore, the target material cracks easily because the ammonium salt which is formed in the reaction of ammonia and metallic salts dissolves in water.

It was found that an organic solvent system is more suitable than an aqueous solution. As a result of comparing several organic solvents, such as acetone, ethyl ether, ethanol, isopropanol (2-propanol), isobutyl alcohol, butyl alcohol, ethylene glycol, toluene, and TTA-MIBK, isopropanol was found to be superior to the others.

3.2 Nitrate-organic solution system

Rare earth or other metallic nitrates react with ammonia gas to form the hydroxides when the solution contains water or OH^- . The chemical reaction is as follows:

The influence of the water content in the nitrate-isopropanol system has been studied for water concentrations in isopropanol of 2%, 5%, 10%, 15% and 20%. These experiments indicate that water causes nonuniform layers which tend to crack and peel off the substrate.

When using ethanol-isopropanol as a mixed solvent, it was found that several grooves were usually observed and circular cracking still took place with solutions in which the amount of ethanol was 2%, 4%, 6% and 8%, because a small quantity of water present in the ethanol can dissolve NH_4NO_3 which cannot be decomposed at lower temperatures.

Pure isopropanol also does not work well. Crystals of NH_4NO_3 are formed and the NH_4NO_3 layers become thicker and thicker. A lot of small holes were left in the target after calcining at $450\text{--}550^\circ\text{C}$.

The temperature of the substrate can be increased to more than 210°C during the pipetting of the solution. However, there are problems with the drop of solution sputtering off the substrate when the temperature is higher than 180°C . Furthermore, the higher the temperature, the less favorable is the chemical reaction for producing the rare earth hydroxide.

3.3 Chloride-organic solution system

Rare earth or other metallic chlorides can also react with ammonia gas to form hydroxides when the solution contains H_2O or OH^- . The chemical reaction is as follows:

Based on the same consideration as for the others, the influence of water concentration in the EuCl_3 -isopropanol solution of 2%, 5%, 10% and 20% was investigated. Experiments showed that the main problem is a buildup of NH_4Cl on the target because not all of it is removed by heating while the target is being deposited. Subsequent drops readily dissolve this NH_4Cl and cause its redistribution on the target face. The edge of the target was found to be thicker than the center and a lot of small holes were left after the calcining operation.

The ethanol-isopropanol with chloride system has also been studied. Experiments were carried out with the amount of ethanol in isopropanol at 4%, 6%, 8% and 10%. These experiments indicate that the NH_4Cl layer became thicker and thicker as the drops were added and the deposits partially dissolved in the next drop. Also, many small holes were produced after calcining.

In the case of pure isopropanol as a solvent for EuCl_3 , the next drop cannot dissolve the previously deposited drop. The crystals of hydroxide obtained in this case are much finer than those from the nitrate-isopropanol system. However, when the thickness of the targets is more than $500 \mu\text{g}/\text{cm}^2$, many tiny holes are formed after calcining at $550^\circ\text{--}600^\circ\text{C}$ because of the decomposition of NH_4Cl . If the targets are calcined after each $200 \mu\text{g}/\text{cm}^2$ layer, and the process of evaporating and calcining is repeated, the uniformity and adherence can be improved.

3.4 Acetate-organic solution system.

Rare earth or other metallic acetates are similar to the nitrate and chloride systems and make use of the following reaction:

Obviously, the decomposition of ammonium acetate is much easier than that of ammonium nitrate and ammonium chloride.

The $\text{EuAc}_3\text{-H}_2\text{O}$ -isopropanol system has been investigated. Even if the isopropanol contains only 0.2% or 0.4% water, channels are formed as each drop is dried and cracking gradually occurs.

The influence of different compositions of organic solvents on the quality of the targets has been investigated carefully. The results are listed in table 1.

Experiments showed that the mixture of ethanol and isopropanol is better than pure isopropanol for the uniform dispersion of the target material. A good quality target was obtained by using the optimum composition: from 4% ethanol and 6% isopropanol to 6% ethanol and 4% isopropanol. More than 8% ethanol in isopropanol will produce small channels. In addition, the surface tension of the solution increases and evaporation is slower.

The solubility of acetate in isopropanol is rather small, but ethanol (proof 190, water concentration 5%) increases the solubility of the acetate. Furthermore, it is beneficial in dispersing the target material.

In order to obtain good quality targets, the temperature of the substrate should be strictly controlled at 125 to 130°C. If the temperature is too high, it is unfavorable for converting the acetate to the hydroxide because the organic solvent is vaporized too fast. If the temperature is lower than 120°C, the vaporization of the water is slower, and tiny channels will form on the surface of the layers.

Using the optimum composition of organic solutions, a number of Eu_2O_3 and other rare earth oxide targets were prepared, most of them with thicknesses of more than 1 mg/cm^2 . The crystals of the hydroxide or oxide forms are rather fine. If a drop of water is put on the surface of the target that is just finished, the deposits do not dissolve. This shows that the hydroxide has been formed and the ammonium acetate has been decomposed.

By careful heating at 450-550°C, oxides were formed which were extremely resistant against scrubbing and were not washed away by water, alcohol or acetone.

Table 1. The effects on target quality of ethanol concentration in the acetate-isopropanol system

Backing material: Al foil

Evaporating temperature: 125 - 130°C

Diameter of target: 8 mm

Calcining temperature: 450 - 550°C

Sample No.	Concentration of Ethanol in Isopropanol (vol. %)	Target Thickness (mg/cm ²)	Visual Observations
1	100% isopropanol* (no ethanol)	1.00 1.59 3.37	Next drop cannot dissolve the previously deposited material. Dispersion is not good.
2	2% ethanol** (contains 0.1% H ₂ O)	1.00	Dispersion is not too uniform.
3	4% ethanol (contains 0.2% H ₂ O)	1.00 1.20	Quality of each layer is excellent, very uniform and adherent, no cracking after calcining. Crystals of hydroxide are very fine.
4	5% ethanol (contains 0.25% H ₂ O)	1.00 1.20 5.00	Very uniform and adherent. No cracking after calcining. Hydroxide crystals are very fine.
5	6% ethanol (contains 0.3% H ₂ O)	1.00 2.50	Very uniform and adherent. No cracking after calcining. Hydroxide crystals are fine.
6	8% ethanol (contains 0.4% H ₂ O)	1.00	There are several small grooves at the center of target.
7	10% ethanol (contains 0.5% H ₂ O)	1.00	Grooves appeared as each drop dried. Evaporation of drop becomes slower. Surface tension is higher.
8	20% ethanol (contains 1% H ₂ O)	1.00	Many channels produced. Deposit flaky after calcining. Surface tension even higher.

*Isopropanol contains 0.02% H₂O

**Ethanol concentration is 95%

IV. Conclusion

Experiments show that the aqueous systems and water-organic solution systems do not work well. Comparison of the rare earth nitrate, chloride and acetate-organic solution systems demonstrate that the acetate system is the most satisfactory for the preparation of targets. This method solves the main problem - that each drop should not dissolve those previously deposited. The following procedures and conditions are recommended:

1. The rare earth compound is dissolved in glacial acetic acid at 80-90°C to convert it to the acetate form.
2. The feed solution is pipetted into a centrifuge tube and dried. Water and ethanol are then added to the tube and dried again to remove the acid.
3. The dried material is dissolved in a mixture of ethanol (95% concn.) and isopropanol (the optimum composition is 4 - 6% ethanol in isopropanol).
4. Prior to the preparation of the target, the backing material is washed and rinsed with suitable solvent by means of an ultrasonic cleaner.
5. Lacquer is sprayed onto the backing material around a mask which defines the area of deposit.
6. 20 μ l or 25 μ l stock solution is then pipetted onto the substrate by hand at 125 - 130°C at the same time NH_3 gas is gently blown over the surface.
7. Repeating the process, the deposits are increased until the desired thickness is obtained.
8. The target is placed in an oven and calcined at 450 - 550°C to convert the hydroxide to oxide and burn off the masking lacquer.
9. Thicker layers of target ($>500 \mu\text{g}/\text{cm}^2$) can be produced by repeating the deposition in 200 $\mu\text{g}/\text{cm}^2$ layers and calcining at 450 - 550°C after each layer is deposited.

This method is suitable for making targets at least as thick as several mg/cm^2 . It is simple, fast, and convenient. There is no loss of material during the evaporation of the solution. The uniformity and adhesiveness of the targets is comparable to that of molecular plating.

We have designed this technique for the preparation of uniform and adherent targets, but it should also be admirably suited to the preparation of certain radioactive sources (such as α , β or γ sources).

This method is also well suited to the preparation of targets or sources in which tiny droplets are sprayed onto the substrate in the presence of NH_3 gas. Some preliminary work has been started which demonstrates that such a technique will be very valuable.

Besides the lanthanides, it should be possible to use this method for other elements, such as the actinides and those elements that form alcohol soluble acetates and form insoluble hydroxides with NH_3 gas.

Acknowledgement: This work was supported by the Director, Office of Energy Research, Division of Nuclear Physics of the Office of High Energy and Nuclear Physics of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098.

We are grateful to Professor Glenn T. Seaborg for his support, concern, and help. We wish to thank Dr. M. Nurmi and H. L. Hall for their good suggestions. We also thank Diana Lee, Dr. K. E. Gregorich, R. M. Chasteler and Dr. H. A. O'Brian for their beneficial discussions.

References:

1. K. Glover, P. Robinson; In Proceedings of the Seminar on the Preparation and Standardization of Isotope Targets and Foils, AERE-R 5097 (1965).
2. L. Yaffe, Ann. Rev. Nucl. Sci. 12, 153 (1962).
3. R. Lougheed, E. Hulet; Nucl. Inst. Meth. 166, 329 (1979).
4. S. H. Maxmann; Nucl. Inst. Meth. 50, 53 (1967).
5. D. Corswell, J. Milstead; J. Nucl. Eng. 4, 5 (1967).
6. K.F. Lauer, V. Verdingh; Nucl. Inst. Meth. 21, 161 (1963).
7. V. Verdingh, K.F. Lauer; Nucl. Inst. Meth. 49, 179 (1967).
8. W. Cole, G. W. Grime; Preparation of Nuclear Targets for Particle Accelerators, p. 109 (1979).
9. J. Van. Audenhove, J. Pauwels; ibid, p. 79 (1979).
10. W. Porter, H. Bildstein, N. Getaff; Nucl. Inst. Meth. 26, 55 (1964).
11. W. Porter, H. Bildstein, N. Getaff; Nucl. Inst. Meth. 26, 61 (1964).
12. N. Getaff, H. Bildstein; Nucl. Inst. Meth. 36, 173 (1965).
13. N. Getaff, H. Bildstein; Nucl. Inst. Meth. 70, 352 (1969).
14. J.E. Evans, R.W. Lougheed, M.S. Coops, R.W. Hoff and E.K. Hulet; Nucl. Inst. Meth. 102, 389 (1972).
15. D.C. Aumann, G. Müllen; Nucl. Inst. Meth. 115, 75 (1974).
16. G. Müllen, D.C. Aumann; Nucl. Inst. Meth. 128, 425 (1975).
17. K.J. Moody, LBL-16249 (1983).
18. K.E. Gregorich, LBL-20192 (1985).

*LAWRENCE BERKELEY LABORATORY
TECHNICAL INFORMATION DEPARTMENT
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720*