UC Santa Barbara

UC Santa Barbara Previously Published Works

Title

Synthesis and Characterization of "Atlas-Sphere" Copper Nanoclusters: New Insights into the Reaction of Cu^{2+} with Thiols.

Permalink

<https://escholarship.org/uc/item/88k8n2xh>

Journal

Inorganic chemistry, 58(13)

ISSN

0020-1669

Authors

Cook, Andrew W
Jones, Zachary R
Wu, Guang
et al.

Publication Date

2019-07-01

DOI

10.1021/acs.inorgchem.9b01140

Peer reviewed

Synthesis and Characterization of “Atlas-sphere” Copper Nanoclusters: New Insights into the Reaction of Cu²⁺ with Thiols

Andrew W. Cook[†], Zachary R. Jones[^], Guang Wu[†], Simon J. Teat[‡], Susannah L. Scott^{^*}, and Trevor W. Hayton^{†*}

[†] Department of Chemistry and Biochemistry, University of California, Santa Barbara, California 93106, United States

[^] Department of Chemical Engineering, University of California, Santa Barbara, California 93106, United States

[‡] Advanced Light Source, Lawrence Berkeley National Laboratory, Berkeley, California 94720, United States

Supporting Information Placeholder

ABSTRACT: Thiolates are a widely used ligand class for the stabilization of M(0)-containing gold and silver nanoclusters. Curiously, though, very few thiolate-stabilized Cu nanoclusters are known. Herein, we report an examination of the reactivity of RSH (R = CH₂CH₂Ph, *n*-Bu, *n*-C₁₂H₂₅) with Cu²⁺ under anhydrous conditions. These reactions result in formation of fluorescent “Atlas-sphere”-type copper-thiolate nanoclusters, including [Cu₁₂(SR')₆Cl₁₂][(Cu(R'SH))₆] (**2**, R' = ⁿBu) and [H(THF)₂]₂[Cu₁₇(SR'')₆Cl₁₃(THF)₂(R'SH)₃] (**3**, R'' = CH₂CH₂Ph), which were characterized by X-ray crystallography, ESI-MS, NMR spectroscopy, as well as XANES and EXAFS. Consistent with our X-ray crystallographic results, the edge energies of **2** and **3** suggest they are constructed exclusively with Cu(I) ions. Similarly, EXAFS of **2** and **3** reveal long Cu-Cu pathlengths, which is also consistent with their X-ray crystal structures. Given these results, as well as past work on Cu²⁺/thiol reactivity, we suggest that Cu(0) is unlikely to be formed by reaction of Cu²⁺ with a thiol, and that previous reports of Cu(0)-containing nanoclusters synthesized by reaction of Cu²⁺ with thiols are likely erroneous.

Introduction

The past decade has seen a dramatic increase in the number of reported atomically precise nanoclusters (APNCs) of gold and silver.¹ Many of these APNCs have been characterized by X-ray crystallography, giving researchers a level of structural detail that is not available for traditional nanoparticles. For Ag and Au, the most common capping ligands are thiolates (RS⁻) (R = alkyl, aryl). For example, one of the first structurally characterized Au APNCs, [Au₂₅(SCH₂CH₂Ph)₁₈]⁻, features phenylethylthiolate capping ligands.²⁻³ Other notable thiolate-stabilized Au APNCs include [Au₃₈(SCH₂CH₂Ph)₂₄], [Au₁₄₄(SCH₂CH₂Ph)₆₀], [Au₂₄₆(SC₆H₄-*p*-Me)₈₀], and Au₂₇₉(SC₆H₄-*p*-Bu)₈₄.⁴⁻⁷ Similarly, many of the first structurally characterized Ag APNCs also featured thiolate ligands, including [Ag₄₄(*p*-MBA)₃₀]⁴⁺ (*p*-MBA = *para*-mercaptobenzoic acid) and [Ag₂₅(SCH₂CH₂Ph)₁₈]⁻.⁸⁻¹⁰ As seen in these aforementioned examples, both alkyl- and aryl thiolates are effective at stabilizing Ag and Au APNCs. The ubiquitous use of thiolates for this purpose is likely related to the strength of the M-S bond,¹¹

which protects the APNCs against agglomeration and unwanted reactivity. As a result, these materials have been proposed for a variety of applications for which high stability is desired, including *in vivo* chemical sensing and drug delivery.¹

Given this context, it is surprising that Cu(0)-containing, thiolate-stabilized Cu APNCs are essentially unknown, and of the few Cu APNCs that have been reported, most have only been partially characterized.¹²⁻¹⁴ For example, Mukherjee and co-workers synthesized a glutathione-stabilized Cu APNC with the formula [Cu₁₅(GSH)₄].¹⁵ This material was characterized by TEM, MALDI-TOF mass spectrometry, and UV-vis spectroscopy, but a single-crystal X-ray structure was not forthcoming. Similarly, Chang and co-workers reported the synthesis of a mixture of mercaptobenzoic acid-stabilized Cu nanoclusters, but these materials were not structurally characterized.¹⁶ In contrast, structurally-characterized mercaptobenzoic acid-stabilized APNCs of both Ag and Au are well known.¹ Cu APNCs of aryl thiolates have also been reported, such as [Cu₉(SC₆H₄-*p*-F)₇] and [Cu₉(SC₆H₄-*p*-Br)₆], but again structural characterization by X-ray crystallography has remained elusive.¹⁷ Finally, it is worth noting that a 2011 report of a thiolate-stabilized Cu₈ nanocluster, [Cu₈(MPP)₄] (HMPP = 2-mercapto-5-*n*-propylpyrimidine), was recently found to be erroneous.¹⁸⁻¹⁹

In 2015, Zhang and co-workers reported the synthesis of a mixed-valent Cu-thiolate APNC Cu₁₄(SR)₁₀ (R = C₁₂H₂₅), which was formed by reaction of CuCl₂ with excess RSH in dibenzyl ether.²⁰ Under these conditions, the thiol acts as both the capping ligand and the reductant. Cu₁₄(SR)₁₀ was characterized by UV-vis and fluorescence spectroscopies, TGA, and TEM, amongst other techniques. While its exact structure could not be verified by single-crystal X-ray diffraction, the authors use mass spectrometry and DFT analysis to support their proposed formulation. Significantly, this Cu APNC was reported to have attractive photo-physical properties,²¹⁻²³ prompting speculation that it could be incorporated into light emitting diodes and displays.¹⁷

Cu₁₄(SR)₁₀ is especially intriguing to us, given our longstanding interest in Cu nanocluster chemistry,^{19, 24-27} and because it represents a rare example of a Cu nanocluster with partial Cu(0) character. Only a handful of low-valent, Cu(0)-containing nanoclusters have been reported, including [Cu₂₅H₂₂(PPh₃)₁₂]₂Cl, [Cu₂₉Cl₄H₂₂(Ph₂phen)₁₂]₂Cl,

$[\text{Cu}_{13}\{\text{S}_2\text{CN}^n\text{Bu}_2\}_6(\text{CCR})_4][\text{PF}_6]$ ($\text{R} = \text{C}(\text{O})\text{OMe}, \text{C}_6\text{H}_4\text{F}$), $[\text{Cu}_{20}(\text{CCPh})_{12}(\text{OAc})_6]$, $[\text{Cp}^*\text{Cu}_3\text{Al}_{12}]$, and $[\text{Cu}_{53}(\text{CF}_3\text{CO}_2)_{10}(\text{C}\equiv\text{C}^i\text{Bu})_{20}\text{Cl}_2\text{H}_{18}]^{+24, 26-30}$. $\text{Cu}_{14}(\text{SR})_{10}$ would also be an exceptionally rare example of a copper superatom with $N^* = 4$, which is not a magic number.²⁰ While non-magic number copper superatoms are known, such as $[\text{Cp}^*\text{Cu}_3\text{Al}_{12}]$, their anticipated lower stability makes them unusual.^{1, 19, 29}

Consequently, we attempted to remake $\text{Cu}_{14}(\text{SR})_{10}$ in an effort to further investigate its structure. Surprisingly, we found that the reaction of CuCl_2 with RSH ($\text{R} = \text{C}_{12}\text{H}_{25}$) does not result in a Cu APNC with Cu(0) character. Instead, the product is most likely a Cu(I)-containing “Atlas-sphere”-type thiolate nanocluster. Our conclusion is supported by a comparative synthetic and spectroscopic study, which includes analysis by X-ray absorption near-edge spectroscopy (XANES) and extended X-ray absorption fine structure (EXAFS). During the course of this work, we also synthesized and structurally characterized two other Cu(I) thiolate-containing clusters, $[\text{Cu}_{12}(\text{SR}')_6\text{Cl}_{12}][(\text{Cu}(\text{R}'\text{SH}))_6]$ ($\text{R}' = {}^i\text{Bu}$) and $[\text{H}(\text{THF})_2]_2[\text{Cu}_{17}(\text{SR}'')_6\text{Cl}_{13}(\text{THF})_2(\text{R}''\text{SH})_3]$ ($\text{R}'' = \text{CH}_2\text{CH}_2\text{Ph}$) using similar conditions to those reported by Zhang and co-workers.²⁰

Results and Discussion

Attempted Synthesis of $\text{Cu}_{14}(\text{SR})_{10}$ ($\text{R} = \text{C}_{12}\text{H}_{25}$). $\text{Cu}_{14}(\text{SR})_{10}$ was reportedly formed by reaction of $\text{CuCl}_2 \cdot 2\text{H}_2\text{O}$ (1 equiv) with 1-dodecanethiol (22 equiv) in dibenzyl ether (6 mL) (Scheme 1). A yield was not reported and the color of the material was not described, but photographs provided in the Supporting Information show that the solid is a pale-yellow powder.²⁰⁻²¹ The solubility of this material was also not explicitly discussed, but on the basis of the experimental description it appears to be insoluble in both CHCl_3 and acetone.

Zhang and co-workers characterized their material using a variety of methods, including UV-vis and emission spectroscopies, as well as mass spectrometry. The $\text{Cu}_{14}(\text{SR})_{10}$ formulation was proposed primarily on the basis of the MS data, however neither an exact mass match nor an analysis of the isotope pattern was provided.²⁰⁻²¹ The UV-vis data of the isolated material revealed the presence of two absorption bands at 275 and 358 nm. The fluorescence spectrum ($\lambda_{\text{ex}} = 365$ nm) showed a weak emission at approximately 380 nm.

Scheme 1. Synthetic Procedure Used to Prepare $\text{Cu}_{14}(\text{SR})_{10}$

We attempted to repeat the synthesis of $\text{Cu}_{14}(\text{SR})_{10}$, using the originally reported procedure with a few minor modifications. In particular, we used anhydrous CuCl_2 in place of $\text{CuCl}_2 \cdot 2\text{H}_2\text{O}$,³¹ we did not sonicate our CuCl_2 suspension, and we performed the reaction at room temperature. We believe that these minor changes should not affect the product speciation; however, they could affect the rate of reaction by modifying the solubility and grain size of the CuCl_2 starting material. The reaction generally proceeded as originally described (Scheme 1). Thus, addition of CuCl_2 (1 equiv) to dibenzyl ether (2 mL) at room temperature resulted in formation of a pale

brown slurry. Addition of 1-dodecanethiol (4 equiv) to this suspension resulted in dissolution of the brown solid over the course of 20 min, concomitant with the deposition of a very pale gray solid, which is similar in appearance to the material reported by Zhang and co-workers.²⁰ The solid was then collected on a fritted glass filter, and rinsed with hexanes to give **1** as an off-white solid (Figure S29). We also performed the reaction in THF. In this solvent, addition of 1-dodecanethiol to the slurry of CuCl_2 in THF initially resulted in dissolution of all the solid over the course of 2 min, concomitant with formation of a clear, pale-yellow solution. However, upon further stirring, a very pale-yellow powder began to precipitate from the solution (Figure S30). After 20 min of stirring, this solid was collected on a fritted glass filter and rinsed with several portions of hexanes to give **1** as a very pale yellow powder. Whether prepared from dibenzyl ether or THF, complex **1** is insoluble in alkanes, diethyl ether, benzene, toluene, THF, CH_2Cl_2 , chloroform, MeCN, DMSO, DMF, MeOH, EtOH, and water. While complex **1** is also insoluble in pyridine, it does appear to very slowly react with this solvent.

To better ascertain the reaction stoichiometry, we collected the colorless filtrate from the THF reaction mixture and removed the volatiles *in vacuo* to yield a colorless oil. A ^1H NMR spectrum of this colorless oil, recorded in CD_2Cl_2 (Figure S8), reveals the presence of unreacted 1-dodecanethiol, as well as di(1-dodecane)disulfide.³² These observations are consistent with the proposed reaction stoichiometry of Zhang and co-workers, who also noted the reduction of the Cu(II) ions via thiol oxidation.

A diffuse reflectance spectrum of solid **1** features the onset of an absorption band at ca. 425 nm (Figure 1, black trace). A fluorescence spectrum of the same material excited at 365 nm reveals a very broad emission centered at 510 nm (Figure 1, red trace). These data are broadly consistent with the spectra reported by Zhang and co-workers. For example, $\text{Cu}_{14}(\text{SR})_{10}$ was reported to have an absorption band centered at 368 nm,²⁰ along with emission peaks centered at 490 or 550 nm (depending on the method of sample preparation). Overall, the similarity of our spectroscopic results with those previously reported by Zhang, along with the similar physical descriptions of the two materials, leads us to believe that we are making the same material. The TGA trace recorded for **1** is also a close match with that reported previously for $\text{Cu}_{14}(\text{SR})_{10}$ (Figure S31).²⁰

Figure 1. Solid-state absorbance (black) and emission (red, $\lambda_{\text{ex}} = 365$ nm) spectra for complex **1**, synthesized from THF.

Finally, we recorded an X-ray photoelectron spectrum of cluster **1** to confirm the Cu oxidation state and determine its elemental composition. Specifically, the spectrum features two

prominent peaks at 932.70 and 952.70 eV, which are attributable to the Cu $2p_{3/2}$ and Cu $2p_{1/2}$ binding energies, respectively. These values are similar to the binding energies reported for other Cu(I)-containing materials.^{24, 33} Unfortunately, the similarity of Cu(I) and Cu(0) binding energies³⁴ generally makes it difficult to discriminate between these two states, and so we cannot rule out the presence or absence of Cu(0) in this sample. Nonetheless, the absence of satellite peaks in this region of the spectrum is consistent with absence of Cu(II). Moreover, the Cu LMM transitions for **1** appear at 918.3, 915.5, and 911.6 eV. These values are also consistent with the presence of Cu(I), in multiple chemical environments. As with the Cu $2p$ binding energies, it is difficult to use the Cu LMM data to discriminate between the Cu(0) and Cu(I) states. That said, our Cu LMM data closely match that originally reported for Cu₁₄(SR)₁₀, which exhibits transitions at ca. 918 and 915 eV.²⁰ Curiously, our XPS spectrum also reveals the presence of Cl, as revealed by the Cl 2s and Cl $2p_{3/2}$ peaks at 269.7 and 199.2 eV (Figure S21 and S25).³⁴ According to XPS data, the Cu:S:Cl ratio is approx. 2:2:1. Significantly, these data are not consistent with the original Cu₁₄(SR)₁₀ formulation, which should not contain Cl⁻, but are in-line with our findings from a comparative synthetic study using different thiols (see below). To be fair, though, Zhang and co-workers may not have tested their material for the presence of Cl⁻. Nonetheless, on the basis of these results, we believe that complex **1** is not a partially-metallic, mixed-valent Cu nanocluster. Instead, we believe that this material is likely an “Atlas-sphere” [Cu₁₂(SR)₆]⁶⁺-type cluster. That is, it does not have any Cu(0) character but instead contains exclusively Cu(I). Our evidence to support this conclusion is outlined in the next sections.

Synthesis of [Cu₁₂(SR')₆Cl₁₂][(Cu(R'SH))₆] (R' = "Bu). The insolubility of **1** greatly limited our ability to confirm its formulation. Therefore, we attempted to generate a more tractable material by substituting the 1-dodecanethiol ligand for an aliphatic thiol that was more amenable to crystallization, yet similar in structure and reducing ability (Scheme 2).³⁵ Thus, reaction of a slurry of CuCl₂ (1 equiv) in THF (2 mL) with *n*-butylthiol (5 equiv) at room temperature immediately results in dissolution of the CuCl₂, concomitant with the generation of a bright yellow solution. Work-up of the reaction mixture after 20 min resulted in the isolation of pale yellow crystals of the Cu(I) nanocluster, [Cu₁₂(SR')₆Cl₁₂][(Cu(R'SH))₆] (**2**, R' = "Bu), in 90% yield.

Scheme 2. Synthesis of **2**.

Complex **2** crystallizes in the triclinic space group $P\bar{1}$ (Figure 2). It features a [Cu₁₂(SR')₆]⁶⁺ “Atlas-sphere” core (Figure 2a), which has been observed for several other Cu(I) thiolate clusters.^{12, 36–39} Within the Cu₁₂S₆ core, each Cu occupies the vertex of a regular cuboctahedron, while each thiolate ligand is bound in a μ_4 fashion and occupies one of the six square faces of the cuboctahedron. The Cu–Cu distances range from 2.6524(7) to 3.7110(8) Å, while the Cu–SR' distances range from 2.225(2) to 2.276(1) Å. Both of these ranges are comparable to those seen in other [Cu₁₂(SR)₆]⁶⁺-containing clusters.^{12, 36–39} Each of the 12 Cu atoms in the “Atlas-sphere” core is also coordinated to a Cl⁻ ligand. Six additional Cu⁺ ions are bound to the outer surface of the cluster, via bridging interactions with the Cl⁻ ions. Two of these outer Cu⁺ ions are each coordinated to a single thiol ligand, while the remaining four Cu⁺ ions are each coordinated to two thiol ligands, four of which originate from an adjacent cluster. These bridging interactions give rise to a ladder-type coordination polymer bridging through two μ_2 -HSR linkages (Figure 2c).³⁸ The average Cu–S_{thiol} distance is 2.30 Å (range: 2.257(1) – 2.346(2) Å), which is slightly longer than the Cu–thiolate distance, as expected.

The ¹H NMR spectrum of **2** in THF-*d*₈ (Figure S2) features resonances at 3.26 and 2.53 ppm, assigned to the α -CH₂ resonances of the six μ_4 -SⁿBu ligands and the six ⁿBuSH ligands, respectively. These resonances are present in a 1:1 ratio, consistent with the solid-state structure. Also present in this spectrum is a broad singlet at 1.85 ppm, assigned to the SH proton of the six ⁿBuSH ligands. The ESI-MS of **2**, recorded in THF in negative ion mode, features a major peak at $m/z = 2039.9023$, which corresponds to the fragment [Cu₁₇(SR')₆Cl₁₂]⁻ (calcd $m/z = 2039.6666$) (Figure 3). Several other peaks are also present in this spectrum. Each of these peaks is related to the parent ion by loss/gain of CuCl ($m/z = 99$). These data suggest that the [Cu₁₂(SR')₆Cl₁₂]⁶⁺ core is relatively stable, but that the six outer Cu⁺ ions and coordinated thiol ligands are quite labile. Interestingly, an ESI-MS signal for **2** was only observed upon addition of [NEt₄][Cl] to the ESI-MS sample. It was observed previously that addition of salts to a nanocluster sample can facilitate transfer of material into the gas phase during the MS analysis.⁴⁰ Finally, a UV-vis spectrum of **2** in THF (Figure S16) reveals the presence of an absorption band at 370 nm. The spectrum is qualitatively similar to the spectrum recorded for Cu₁₄(SR)₁₀,²⁰ providing further support for the structural similarity of that material and **2**. The fluorescence spectrum of solid **2** ($\lambda_{\text{ex}} = 365$ nm) reveals a broad emission peak at 585 nm (Figure S19).

Figure 2. Ball-and-stick diagram showing a) the $[\text{Cu}_{12}(\text{SR}')_6\text{Cl}_{12}]^{6-}$ core, b) the structure of the monomeric unit, and c) the polymeric structure of **2** (hydrogen atoms omitted for clarity). Color legend: orange, Cu; yellow, S; green, Cl; gray, C.

Figure 3. Partial ESI-MS of complex **2** in negative ion mode. Assignments: $m/z = 2039.9023$ $[\text{Cu}_{17}(\text{SR}')_6\text{Cl}_{12}]^-$ (calcd $m/z =$

2039.6666), $m/z = 2139.7942$ $[\text{Cu}_{18}(\text{SR}')_6\text{Cl}_{13}]^-$ (calcd $m/z = 2139.5649$), $m/z = 1940.9977$ $[\text{Cu}_{16}(\text{SR}')_6\text{Cl}_{11}]^-$ (calcd $m/z = 1940.7682$), $m/z = 1842.0930$ $[\text{Cu}_{15}(\text{SR}')_6\text{Cl}_{10}]^-$ (calcd $m/z = 1841.8719$), $m/z = 1744.175$ $[\text{Cu}_{14}(\text{SR}')_6\text{Cl}_9]^-$ (calcd $m/z = 1743.9734$).

To better understand the stoichiometry of the transformation, the reaction of CuCl_2 with $n\text{BuSH}$ (5 equiv) was monitored by ^1H NMR spectroscopy (Figure S4). Addition of thiol to a THF- d_8 slurry of CuCl_2 results in the rapid dissolution of all solids and the formation of a bright yellow solution. After 20 min, the ^1H NMR spectrum of this solution revealed a resonance at 3.24 ppm, assigned to the $\alpha\text{-CH}_2$ resonance of the six $\mu_4\text{-S}^n\text{Bu}$ ligands in **2**, a resonance at 2.68 ppm, assigned to the $\alpha\text{-CH}_2$ resonance of di- n -butyl disulfide, and a broad resonance at 8.56 ppm, assigned to HCl. Integration of the methylene resonances against an internal standard (hexamethyldisiloxane) indicates that **2** was formed in 99% yield, while only 0.5 equiv of di- n -butyl disulfide was generated per CuCl_2 . Similarly, integration of the HCl resonance indicates that 1.3 equiv of HCl is formed relative to the initial amount of CuCl_2 . Importantly, these amounts of disulfide and HCl are consistent only with reduction of Cu(II) to Cu(I) and formation of **2**. If $\text{Cu}_{14}(\text{SR})_{10}$ were to be formed in this transformation, we would expect 0.64 equiv of di- n -butyl disulfide and 2.0 equiv of HCl to be formed instead.

We also briefly examined the chemical properties of complex **2**. Complex **2** is insoluble in alkanes, Et_2O , benzene, toluene, CH_2Cl_2 , and MeCN. It is soluble in THF, although it partially decomposes if left in solution at room temperature, as evidenced by the gradual bleaching of the pale-yellow color in conjunction with the deposition of a copious amount of white

powder, presumably CuCl. This process occurs over the course of 24 h. Finally, complex **2** reacts immediately upon dissolution in pyridine, to form $[\text{CuCl}(\text{pyridine})_3]$ (**4**) as the only isolable product. This complex can be isolated in 68% yield (based on Cl⁻) after work-up.⁴¹ The isolation of **4** from the reaction mixture demonstrates that, under the appropriate conditions, the “Atlas-sphere” core is susceptible to disassembly.

Synthesis of $[\text{H}(\text{THF})_2]_2[\text{Cu}_{17}(\text{SR}')_6\text{Cl}_{13}(\text{THF})_2(\text{R}'\text{SH})_3]$ ($\text{R}' = \text{CH}_2\text{CH}_2\text{Ph}$). To further understand the reactivity of Cu(II) with thiols, we explored the reaction of CuCl_2 with 2-phenylethanethiol. This specific thiol was chosen because it is widely used in the synthesis of Ag and Au APNCs,¹ yet an isolable 2-phenylethylthiolate-containing Cu APNC has so far remained elusive. Thus, reaction of a slurry of CuCl_2 (1 equiv) in THF with 2-phenylethanethiol (4 equiv) at room temperature immediately generates a bright yellow solution concomitant

with dissolution of the CuCl_2 (Scheme 3). Work-up of the reaction mixture after 20 min resulted in pale yellow crystals of the Cu(I) nanocluster $[\text{H}(\text{THF})_2]_2[\text{Cu}_{17}(\text{SR}')_6\text{Cl}_{13}(\text{THF})_2(\text{R}'\text{SH})_3]$ ($\text{R}' = \text{CH}_2\text{CH}_2\text{Ph}$, **3**), which can be isolated in 93% yield.

Scheme 3. Synthesis of **3.**

Figure 4. Ball-and-stick diagram showing a) the $[\text{Cu}_{16}(\text{SR})_6\text{Cl}_{12}]^{2-}$ core, b) the full structure of **3**·1.5THF, including one $[\text{H}(\text{THF})_2]^+$ cation (hydrogen atoms, THF ligands, and THF solvate molecules omitted for clarity). Color legend: orange, Cu; yellow, S; green, Cl; red, O; gray, C.

Complex **3** crystallizes in the triclinic space group $P\bar{1}$ as a THF solvate, **3**·1.5THF (Figure 4). Like **2**, complex **3** features a $[\text{Cu}_{12}(\text{SR}')_6]^{6+}$ “Atlas-sphere” core (Figure 4a). Within the core, the Cu–Cu distances range from 2.685(3) to 3.678(4) Å, while the average Cu–SR distance is 2.28 Å. These values are similar to those observed for **2**. Each of the 12 Cu atoms in the $[\text{Cu}_{12}(\text{SR}')_6]^{6+}$ core is coordinated to one Cl⁻ ligand. These Cl⁻ ions are grouped into four groups of three. Each group of Cl⁻ ions forms a trigonal planar bonding pocket, which is filled with a Cu⁺ ion. A thirteenth Cl⁻ ligand (Cl13) is also bound to the $[\text{Cu}_{12}(\text{SR}')_6]^{6+}$ core, in a μ_2 interaction with Cu6 and Cu7. One of the outer Cu⁺ ions (Cu11) is bound by an R'SH ligand, while another (Cu5) is bound by a THF ligand. One of the “core” Cu atoms (Cu10) is also bound by a THF ligand. Additionally, complex **3** features a $[\text{Cu}(\text{HSR}')_2]$ fragment appended to its outer surface via dative interactions with two Cl⁻ ligands

(Cl12 and Cl13). It is likely that this peripheral fragment, along with the peripheral THF and R'SH ligands, is extremely labile. Not surprisingly, the ¹H NMR spectrum (*vide infra*) in THF-*d*₈ reveals a highly symmetric cluster, with only one magnetically unique thiolate ligand. Finally, the overall cluster charge is balanced by the presence of two $[\text{H}(\text{THF})_2]^+$ cations. While the H-bonded protons in these cations were not located in the difference Fourier map, their presence is supported by the close approach of two sets of THF molecules. Specifically, the distances between O3 and O4 (2.47(2) Å) and O8 and O8* (2.36(1) Å) are similar to the O–O distances in other $[\text{H}(\text{THF})_2]^+$ and $[\text{H}(\text{Et}_2\text{O})_2]^+$ cations.^{42–49}

The ¹H NMR spectrum of **3** in THF-*d*₈ reveals resonances at 3.47 and 3.37 ppm, assigned to CH₂ resonances of the six μ_4 -SCH₂CH₂Ph ligands. Likewise, resonances at 2.88 and 2.77 ppm are assigned to the CH₂ resonances of the thiol ligands. The

thiol SH proton resonance at 1.95 ppm is also present. A very broad resonance at 8.82 ppm is assigned to the O-H-O proton of the $[\text{H}(\text{THF})_2]^+$ counterion.^{45, 48-49} For comparison, the O-H-O proton of the $[\text{H}(\text{THF})_2]^+$ counterion in $[\text{H}(\text{THF})_2][\text{Al}\{\text{OC}(\text{CF}_3)_3\}_4]$ is reported to appear at ca. 8 ppm.⁴⁵ The presence of thiolate and thiol environments in a 6:4 ratio, instead of the expected 6:3 ratio, suggests that a small amount of excess of thiol is present in the final product, which we have been unable to remove.

ESI-MS data were collected in negative ion mode for a THF solution of **3**. The major feature of the spectrum at $m/z = 2129.8726$ corresponds to the fragment $[\text{Cu}_{15}(\text{SR}')_6\text{Cl}_{10}]^-$ (calcd $m/z = 2129.8718$) (Figure 5). Several other peaks are also observed. They are related to the parent ion by loss/gain of CuCl ($m/z = 99$). These data suggest that the $[\text{Cu}_{12}(\text{SR}')_6]^{6-}$ core of **3** is relatively stable, but that the outer Cl^- anions, Cu^+ cations, and thiol ligands are more labile. Once again, we observed a signal only after addition of $[\text{NEt}_4][\text{Cl}]$ to the ESI-MS sample. A UV-vis spectrum of **3** in THF and features a broad absorption band at 355 nm (Figure S17), in good agreement with the spectrum observed for **2**. The fluorescence spectrum of **3**, recorded for the solid and excited at 365 nm, reveals a broad peak at 650 nm (Figure S20). We also briefly examined the chemical properties of complex **3**. Similar to complex **2**, it is insoluble in alkanes, Et_2O , benzene, toluene, CH_2Cl_2 , and MeCN. It is soluble in THF, although the cluster appears to partially decompose in that solvent upon standing at room temperature for 5 h, as evidenced by the deposition of a white powder and a bleaching of the yellow color. Complex **3** also reacts with pyridine to form **4**, which was isolated in 95% yield after work-up.⁴¹

Figure 5. Partial ESI-MS of **3** in negative ion mode. Assignments: $m/z = 2129.8726$ $[\text{Cu}_{15}(\text{SR}')_6\text{Cl}_{10}]^-$ (calcd $m/z = 2129.8718$), $m/z = 2527.6428$ $[\text{Cu}_{19}(\text{SR}')_6\text{Cl}_{14}]^-$ (calcd $m/z =$

2527.4636), $m/z = 2431.7378$ $[\text{Cu}_{18}(\text{SR}')_6\text{Cl}_{13}]^-$ (calcd $m/z = 2431.5574$), $m/z = 2327.6748$ $[\text{Cu}_{17}(\text{SR}')_6\text{Cl}_{12}]^-$ (calcd $m/z = 2327.6667$), $m/z = 2229.7747$ $[\text{Cu}_{16}(\text{SR}')_6\text{Cl}_{11}]^-$ (calcd $m/z = 2229.7683$), $m/z = 2031.9645$ $[\text{Cu}_{14}(\text{SR}')_6\text{Cl}_9]$ (calcd $m/z = 2031.9734$), $m/z = 1932.0714$ $[\text{Cu}_{13}(\text{SR}')_6\text{Cl}_8]$ (calcd $m/z = 1932.0750$), $m/z = 1831.0859$ $[\text{Cu}_{12}(\text{SR}')_6\text{Cl}_7]$ (calcd $m/z = 1831.1843$).

X-ray Absorption Spectroscopy Characterization. Previously, we demonstrated that X-ray absorption spectroscopy is a valuable tool for the structural characterization of copper nanoclusters.^{24, 26-27} In particular, we showed that the XANES edge energy is highly sensitive to the average Cu oxidation state in Cu nanoclusters.^{24, 26-27} Building on this past work, we measured the Cu K-edge XANES and EXAFS of nanoclusters **1** (synthesized using dibenzyl ether as the solvent), **2**, and **3**. The XANES spectra of nanoclusters **1**, **2**, and **3** feature edge positions at 8980.7, 8981.1, and 8980.5 eV (Figure S27), respectively. These values are essentially identical to those measured for the Cu(I) coordination complexes $[\text{CuCl}(\text{PPh}_3)_4]$ (8080.9 eV) and CuCl (8981.9 eV),^{24, 26} and corroborate our assignment of **1**, **2**, and **3** as Cu(I)-containing nanoclusters with no Cu(0) character. If **1**, **2**, and **3** did have some Cu(0) character, we would expect to observe edge positions at lower energies (comparable to 8979.6 eV for $[\text{Cu}_{25}\text{H}_{22}(\text{PPh}_3)_{12}][\text{Cl}]$ or 8979.0 eV for Cu foil, for example).^{24, 26-27}

The EXAFS spectra for nanoclusters **1**, **2**, and **3** show similar features (Table 1 and Figure 6). Specifically, there are two major peaks at ca. 1.8 and 2.3 Å in *R*-space. The first peak represents scattering from the light atoms (Cl and S) coordinated directly to Cu, while the second peak represents Cu-Cu scattering. Both features are more intense for **1**, whose EXAFS also contains a prominent long-range path at ca. 3.8 Å. For all three nanoclusters, scattering involving nearest-neighbor Cu-Cl, Cu-S and Cu-Cu paths was simulated using the “Atlas-sphere” $[\text{Cu}_{12}(\text{SR})_6\text{Cl}_{12}]^{6-}$ core present in clusters **2** and **3**. For the ligand-based paths, the expected coordination numbers are $N(\text{Cu-Cl}) = 1.0$ and $N(\text{Cu-S}) = 0.5$, which have nearly identical average distances of 2.27 and 2.28 Å, respectively. These similar path-lengths led us to combine the scattering paths for all ligands into a single Cu-L path in the EXAFS fit. The expected nearest-neighbor coordination number $N(\text{Cu-Cu})$ is 2.0, at an average distance of 2.76 Å; however, there is a large range in the crystallographically-determined Cu-Cu distances (see above). To account for this variation, EXAFS data were fitted with two different Cu-Cu paths, following a previous successful approach.²⁶⁻²⁷ The FEFF model⁵⁰ also predicts significant contributions from a variety of single-scattering paths at ca. 4.0 Å, which we modeled using a long Cu-Cu path.

Table 1. Comparison of average FEFF-predicted paths for the “Atlas-sphere” core $[\text{Cu}_{12}(\text{SR})_6\text{Cl}_{12}]^{6-}$, with EXAFS curvefit parameters for nanoclusters **1**, **2**, and **3**.

Cluster	Path	N	R (Å)	$10^3 \sigma^2$ (Å ²)
$[\text{Cu}_{12}(\text{SR})_6\text{Cl}_{12}]^{6-}$	Cu-L1	1.5	2.278	n.a.
	Cu-Cu1	1.33	2.718	
	Cu-Cu2	0.67	2.944	
	Cu-Cu3	2.87	4.03	
1 ^a	Cu-L	1.8(3)	2.249(6)	3.9(3)

	Cu-Cu1	1.6(3)	2.796(9)	4.6(2) ^b
	Cu-Cu2	0.4(2)	2.983(9)	4.6(2) ^b
	Cu-Cu3	2.4(4)	4.047(2)	8.9(5)
2 ^c	Cu-L	1.2(2)	2.240(2)	3.0(9)
	Cu-Cu1	1.5(4)	2.77(4)	11(4) ^d
	Cu-Cu2	0.4(2)	2.982(1)	11(4) ^d
3 ^e	Cu-L	1.5(3)	2.298(6)	4.1(3)
	Cu-Cu1	1.6(5)	2.71(1)	12(4) ^f
	Cu-Cu2	0.7(3)	2.92(2)	12(4) ^f

^a $N_{\text{idp}} = 23$, $\Delta R = 1.0 - 4.5 \text{ \AA}$, $\Delta k = 3.0 - 13.5 \text{ \AA}^{-1}$, $\Delta E_0 = 5.7(5)$.

^b Constrained to the same value. ^c $N_{\text{idp}} = 15$, $\Delta R = 1.0 - 3.0 \text{ \AA}$, $\Delta k = 3.0 - 14.5 \text{ \AA}^{-1}$, $\Delta E_0 = 5.7(2)$. ^d Constrained to the same value.

^e $N_{\text{idp}} = 13$, $\Delta R = 1.0 - 3.0 \text{ \AA}$, $\Delta k = 3.0 - 13.3 \text{ \AA}^{-1}$, $\Delta E_0 = 4.7(5)$.

^f Constrained to the same value. In all fits, the value of S_0^2 was fixed at 0.8, in accordance with our previous analyses of Cu(I) standards and Cu-based clusters,²⁶⁻²⁷ and ΔE_0 was refined as a global fit parameter. Uncertainties are shown in parentheses; values without uncertainties were fixed during curvefitting.

Satisfactory fits were achieved for all three nanoclusters. For example, for nanocluster **2**, the curve fit gives a Cu-L pathlength of 2.240(2) Å ($N = 1.2(2)$), and the combined value of $N(\text{Cu-Cu})$ is 1.9(6). These parameters are in good agreement with the FEFF-predicted paths for the “Atlas-sphere” core, $[\text{Cu}_{12}(\text{SR})_6\text{Cl}_{12}]^{6-}$. A similarly good fit was achieved for nanocluster **3**. For nanocluster **1**, the curve fit gives a Cu-L pathlength of 2.246(6) Å ($N = 1.8(3)$), while the combined value of $N(\text{Cu-Cu})$ is 2.0(5). Most significantly, these parameters agree well with those determined for **2** and **3**, and demonstrate that a single “Atlas-sphere” structural model can be used to describe the EXAFS of all three nanoclusters, albeit with slight differences in EXAFS intensity (which likely arises from perturbations of the core due to the different outer surface environments). These findings further reinforcement our hypothesis that nanocluster **1** is an “Atlas-sphere”-type cluster, and not a low-valent, Cu(0)-containing nanocluster as originally surmised.

For further comparison, we also recorded EXAFS data for an authentic Cu_{14} cluster, $[\text{Cu}_{14}\text{H}_{12}(\text{phen})_6(\text{PPh}_3)_4][\text{Cl}]_2$, which we synthesized and structurally characterized in 2015.⁵¹ In the solid state, $[\text{Cu}_{14}\text{H}_{12}(\text{phen})_6(\text{PPh}_3)_4][\text{Cl}]_2$ features a significantly shorter average Cu-Cu distance than is found in either **2** or **3**, making it a reasonable model for the $\text{Cu}_{14}(\text{SR})_{10}$ structure proposed by Zhang and co-workers. Its EXAFS spectrum contains a broad signal with multiple, overlapping components centered at ca. 2 Å (Figure 6a). The fit was conducted using contributions from Cu-L (L = N, P) scattering, as well as three distinct Cu-Cu single-scattering paths (Table S4). In particular, the curve fit gives Cu-N and Cu-P pathlengths of 2.07(1) and 2.30(1) Å, respectively, while the combined value of $N(\text{Cu-Cu})$ is 4.1(5). These parameters are in good agreement with those extracted from the X-ray crystallographic analysis. More importantly, though, the N -weighted average Cu-Cu EXAFS pathlength is 2.60 Å, which is close to the value of 2.55 Å found for bulk Cu metal,²⁴ and much different from the Cu-Cu pathlengths measured for nanocluster **1**. Finally, the prominent feature at ca. 4 Å in the EXAFS of $[\text{Cu}_{14}\text{H}_{12}(\text{phen})_6(\text{PPh}_3)_4][\text{Cl}]_2$ is reproduced well by a near-collinear multiple-scattering path (Cu-Cu-Cu, N

= 6, $\angle 160.1^\circ$). Overall, the spectrum of Cu_{14} exemplifies the EXAFS expected for a Cu_{14} nanocluster with strong Cu-Cu bonding, and is very different from the EXAFS of **1**, **2**, and **3**, supporting our conclusion about the structure of **1**.

Comparison to Other Reported Copper Thiolate Nanoclusters. As mentioned in the Introduction, several thiolate-protected Cu APNCs with partial Cu(0) character have been reported in the past few years, including $[\text{Cu}_{15}(\text{GSH})_4]$, $[\text{Cu}_9(\text{SC}_6\text{H}_4\text{-}p\text{-F})_7]$, and $[\text{Cu}_9(\text{SC}_6\text{H}_4\text{-}p\text{-Br})_6]$.^{15, 17} Many of these low-valent nanoclusters were reportedly formed by direct reaction of a Cu(II) salt with an alkyl or aryl thiol, which acts as both reducing agent and capping ligand. On the basis of the reactivity we report here, we now believe that these previous reactions do not result in the formation of low-valent Cu APNCs. Instead, we suspect that they lead to formation of Cu(I)-containing thiolate clusters, similar in formulation and structure to complexes **1**, **2**, and **3**. Given the apparent thermodynamic stability of the “Atlas-sphere” structure type, as revealed by the structures of **2** and **3**, as well as the structures of $[\text{Cu}_{12}(\text{SR})_6\text{X}_{12}][\text{CuX}]$ (X = Cl, Br; R = $\text{CH}_2\text{CH}_2\text{NH}_3$), $[\text{Cu}_{12}(\text{SR})_6\text{Cl}_{12}][\text{CuCl}]_5$, $[\text{Cu}_{12}(\text{SMe})_6(\text{CN})_6]$, and $[\text{Cu}_{12}\text{E}_6\text{L}_8]$ (E = S, Se; L = phosphine),^{37-38, 52-55} it is likely that many of these complexes also feature a $[\text{Cu}_{12}(\text{SR})_6]^{6+}$ core. That being said, other core structures are also possible, including $[\text{Cu}_4(\text{SR})_4]$ (R = 2,6-(Me₃Si)₂C₆H₃, 2,4,6-ⁱPr₃-C₆H₂),⁵⁶⁻⁵⁷ $[\text{Cu}_4(\text{SR})_6]^{2-}$ (R = Me, Et, ⁱPr, Ph, *p*-Cl-C₆H₄, *o*-^tBu-C₆H₄),⁵⁸⁻⁶⁵ $[\text{Cu}_5(\text{SR})_6]^-$ (R = ^tBu, 2,6-Me₂-C₆H₃, 1-adamantyl),^{64, 66-68} $[\text{Cu}_5(\text{SR})_7]^{2-}$ (R = Me, Ph),^{62, 69-70} $[\text{Cu}_6(\text{SR})_6(\mu_6\text{-Br})]$ (R = 1-(thiolato)tritycene),⁷¹ $[\text{Cu}_8(\text{SR})_8]$ (R = 2,4,6-ⁱPr₃-C₆H₂),^{57, 72} $[\text{Cu}_8(\text{SR})_6\text{Cl}_6]^{2+}$ (R = $\text{CH}_2\text{CH}_2\text{NH}_3$),⁵⁵ and $[\text{Cu}_{12}(\text{SR})_{12}]$ (R = 2-(Me₃Si)C₆H₄).⁷³

Figure 6. Comparison of Cu K-edge EXAFS for (a) $[\text{Cu}_{14}\text{H}_{12}(\text{phen})_6(\text{PPh}_3)_4][\text{Cl}]_2$ and **1**; and (b) **2** and **3**. All spectra are shown as FT magnitudes in non-phase corrected R -space (points). Parameters for the curvefits (solid lines) are shown in Tables 1 and S4. Spectra are offset vertically for clarity.

The reactivity of Cu(I) and Cu(II) salts with thiols and thiolates is actually well explored.⁷⁴ Despite this long history, there is no crystallographically authenticated example of this reaction resulting in formation of a Cu(0)-containing product. For example, Kroneck and co-workers monitored the reaction of $[\text{Cu}(\text{MeCN})_4][\text{ClO}_4]$ with a variety of thiols in MeCN/ H_2O . These reactions produce thiolate-containing Cu(I) coordination polymers exclusively.⁷⁵ In no case did they observe reduction of Cu(I) to Cu(0). Similarly, reaction of $[\text{Cu}(\text{MeCN})_4][\text{PF}_6]$ with $\text{HSC}_6\text{H}_4\text{-}o\text{-SiMe}_3$ results in formation of the Cu(I) nanocluster, $[\text{Cu}(\text{SC}_6\text{H}_4\text{-}o\text{-SiMe}_3)_{12}]$.⁷³ More recently, Donahue and co-workers found that reaction of CuCl with $[n\text{-Bu}_4\text{N}][\text{Cl}]$ and NaSR ($R = 1\text{-(thiolato)tritypycene}$) results in formation of the monometallic Cu(I) “ate” complex, $[\text{Cu}(\text{SR})_2]$.⁷¹ It is also useful to survey the reactivity of Ag and Au salts with thiols. For instance, reaction of AgNO_3 with RSH/ NEt_3 in MeCN resulted in formation of $[\text{Ag}(\text{SR})_n]$ oligomers.⁷⁶⁻⁷⁷ The reaction conditions are similar to those used in our study, yet no reduction to Ag(0) was observed, despite the fact that Ag(I) is a much stronger oxidant than Cu(I).⁷⁸ Similarly, reaction of AgNO_3

with $\text{PhSH}/[\text{NMe}_4][\text{Cl}]$ in MeOH/MeCN yields a series of $\text{Ag}^1(\text{SPh})$ “ate” complexes.⁷⁹ Again, no reduction to Ag(0) is observed. With respect to Au(I), which is a stronger oxidant than either Ag(I) or Cu(I),⁷⁸ reaction of $\text{H}[\text{AuCl}_4]$ with excess RSH in water results in formation of $[\text{Au}^1(\text{SR})_n]$ in excellent yields,⁸⁰ although in this case, reduction to metallic gold can be observed if the reaction mixture gets too hot. Similarly, reaction of $\text{Na}[\text{AuCl}_4]$ with 3 equiv of RSH in EtOH also results in formation of $[\text{Au}^1(\text{SR})_n]$.⁸¹ This procedure is compatible with a wide variety of R groups, including $n\text{Bu}$ and $\text{C}_{12}\text{H}_{25}$ (which were employed in the current study).

The well-known photochemical properties of Cu(I) clusters further buttresses our argument that the material isolated by Zhang and co-workers is a Cu(I)-containing “Atlas-sphere” nanocluster, and not the mixed valent nanocluster, $\text{Cu}_{14}(\text{SR})_{10}$, that was originally proposed. For example, the “Atlas-sphere” clusters, $[\text{Cu}_{12}\text{E}_6\text{L}_8]$ ($E = \text{S, Se}$; $L = \text{phosphine}$), are strongly luminescent, with measured PL quantum yields of up to 90%.⁵²⁻⁵⁴ In fact, many Cu(I)-containing clusters are known to be photoluminescent,^{13, 82-89} including many Cu(I)-thiolate and Cu(I)-thiolate/halide clusters.^{13, 83, 87-89} For example, $[\text{Cu}(\text{SR})_n]$ ($n = 2, 4, 7$; $R = p\text{-S-C}_6\text{H}_4\text{-NMe}_2$)¹³ features an emission peak between 480 and 560 nm, depending on its nuclearity, while $[(\text{Cu}(\text{S}^i\text{Bu})_4(\text{dppe}))_n]$ ($\text{dppe} = \text{bis(diphenylphosphino)ethane}$) and $[(\text{Cu}(\text{S}^i\text{Bu})_6(\text{bix}))_n]$ ($\text{bix} = 1,4\text{-bis(imidazole-1-ylmethyl)benzene}$) emit at 603 and 629 nm, respectively.⁸⁸

Conclusion

We have examined the reactions of CuCl_2 with a variety of thiols (RSH) under anhydrous conditions. In the cases where $R = n\text{-Bu}$ and $R = \text{CH}_2\text{CH}_2\text{Ph}$, we isolated “Atlas-sphere”-type nanoclusters in good yields. Both nanoclusters are built around identical $[\text{Cu}_{12}(\text{SR})_6]^{6+}$ core structures and both contain Cu(I) ions exclusively. Neither cluster features any Cu(0) character. In the case where $R = n\text{-C}_{12}\text{H}_{25}$, we generated an insoluble Cu(I)-containing thiolate nanocluster. The insolubility of this material prevented us from growing X-ray quality crystals. However, we believe this cluster also features an “Atlas-sphere” core on the basis of a comparative XANES and EXAFS analysis. Our conclusion concerning the nature of this material is further strengthened by our XPS characterization data, as well as the observation that the “Atlas-sphere” structure type is a conserved across a variety of thiolate ligands. Contrary to previous reports, we do not believe that this material is a mixed valent, Cu(0)-containing nanocluster.

Our conclusions concerning the nature of this material are also better aligned with previously reported group 11 thiolate chemistry, which has been extensively studied. In particular, this past work suggests that the M(0) state is not accessible without addition of stronger reducing agents, such as NaBH_4 . To the best of our knowledge, all previously reported reactions of Cu(II) salts with thiols have resulted only in formation of Cu(I)-containing products. Stated differently, thiols alone cannot reduce Cu^{2+} or Cu^+ to Cu(0). Perhaps most importantly, it is apparent that the synthesis of thiolate-stabilized, Cu(0)-containing APNCs is an unsolved synthetic problem. Their isolation would represent an important synthetic advance, but these materials remain elusive, in contrast with the plethora of known thiolate-stabilized Au(0)- and Ag(0)-containing APNCs. Going forward, we will continue to pursue the synthesis of Cu(0)-containing, thiolate-stabilized APNCs. However, their successful

isolation will likely require the development of new ligands and new synthetic procedures.

ASSOCIATED CONTENT

The Supporting Information is available free of charge on the ACS Publications website.

X-ray data for compound **2** and **3**·1.5THF (CIF)

Experimental procedures, crystallographic details, and spectral data (PDF)

AUTHOR INFORMATION

Corresponding Author

*hayton@chem.ucsb.edu

*sscott@engineering.ucsb.edu

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

T. W. H. and A. W. C. thank the National Science Foundation (CHE 1764345) for financial support. Z. J. and S. L. S. thank the U.S. Department of Energy, Office of Science, Office of Basic Energy Sciences, under the Catalysis Science Initiative (DE-FG-02-03ER15467). NMR spectra were collected on an instrument supported by an NIH Shared Instrumentation Grant (SIG, 1S10OD012077-01A1). ESI mass spectra, diffuse reflectance spectra, X-ray photoelectron spectra, and fluorescence spectra were acquired at the Materials Research Laboratory (MRL) Shared Experimental Facilities, supported by the MRSEC Program of the NSF under Award No. DMR 1720256 and a member of the NSF-funded Materials Research Facilities Network. X-ray absorption spectra were acquired at the Stanford Synchrotron Radiation Lightsource, a Directorate of SLAC National Accelerator Laboratory and an Office of Science User Facility operated for the U.S. Department of Energy Office of Science by Stanford University. We thank the support staff at the MRL and California NanoSystems Institute (CNSI) for their assistance. This research used resources of the Advanced Light Source, which is a DOE Office of Science User Facility under the contact no. DE-AC02-05CH11231. A. W. C. thanks the Mellichamp Academic Initiative in Sustainability at UCSB for a summer fellowship. We thank Alexander Touchton for assistance with the TGA measurement.

REFERENCES

- Jin, R.; Zeng, C.; Zhou, M.; Chen, Y., Atomically Precise Colloidal Metal Nanoclusters and Nanoparticles: Fundamentals and Opportunities. *Chem. Rev.* **2016**, *116*, 10346-10413.
- Heaven, M. W.; Dass, A.; White, P. S.; Holt, K. M.; Murray, R. W., Crystal structure of the gold nanoparticle $[\text{N}(\text{C}_8\text{H}_{17})_4][\text{Au}_{25}(\text{SCH}_2\text{CH}_2\text{Ph})_{18}]$. *J. Am. Chem. Soc.* **2008**, *130*, 3754-5.
- Zhu, M.; Aikens, C. M.; Hollander, F. J.; Schatz, G. C.; Jin, R., Correlating the crystal structure of a thiol-protected Au_{25} cluster and optical properties. *J. Am. Chem. Soc.* **2008**, *130*, 5883-5.
- Qian, H.; Eckenhoff, W. T.; Zhu, Y.; Pintauer, T.; Jin, R., Total Structure Determination of Thiolate-Protected Au_{38} Nanoparticles. *J. Am. Chem. Soc.* **2010**, *132*, 8280-8281.
- Qian, H.; Jin, R., Ambient Synthesis of $\text{Au}_{144}(\text{SR})_{60}$ Nanoclusters in Methanol. *Chem. Mater.* **2011**, *23*, 2209-2217.
- Zeng, C.; Chen, Y.; Kirschbaum, K.; Lambright, K. J.; Jin, R., Emergence of hierarchical structural complexities in nanoparticles and their assembly. *Science* **2016**, *354*, 1580-1584.
- Sakthivel, N. A.; Theivendran, S.; Ganeshraj, V.; Oliver, A. G.; Dass, A., Crystal Structure of Faradaurate-279: $\text{Au}_{279}(\text{SPh-tBu})_{84}$ Plasmonic Nanocrystal Molecules. *J. Am. Chem. Soc.* **2017**, *139*, 15450-15459.
- Joshi, C. P.; Bootharaju, M. S.; Alhilaly, M. J.; Bakr, O. M., $[\text{Ag}_{25}(\text{SR})_{18}]^-$: The "Golden" Silver Nanoparticle. *J. Am. Chem. Soc.* **2015**, *137*, 11578-11581.
- Desireddy, A.; Conn, B. E.; Guo, J.; Yoon, B.; Barnett, R. N.; Monahan, B. M.; Kirschbaum, K.; Griffith, W. P.; Whetten, R. L.; Landman, U.; Bigioni, T. P., Ultrastable silver nanoparticles. *Nature* **2013**, *501*, 399-402.
- Yang, H.; Wang, Y.; Huang, H.; Gell, L.; Lehtovaara, L.; Malola, S.; Hakkinen, H.; Zheng, N., All-thiol-stabilized Ag_{44} and $\text{Au}_{12}\text{Ag}_{32}$ nanoparticles with single-crystal structures. *Nat. Commun.* **2013**, *4*, 2422.
- Luo, Y.-R., Bond Dissociation Energies. In *CRC Handbook of Chemistry and Physics*, 89th ed.; Lide, D. R., Ed. CRC Press/Taylor and Francis: Boca Raton, FL, 2009.
- Fuhr, O.; Fernandez-Recio, L.; Fenske, D., New Copper Chalcogenide Clusters with a Selenide Core and a Sulfide Shell. *Eur. J. Inorg. Chem.* **2005**, *2005*, 2306-2314.
- Langer, R.; Yadav, M.; Weinert, B.; Fenske, D.; Fuhr, O., Luminescence in Functionalized Copper Thiolate Clusters – Synthesis and Structural Effects. *Eur. J. Inorg. Chem.* **2013**, *2013*, 3623-3631.
- Wang, Z.; Chen, B.; Rogach, A. L., Synthesis, optical properties and applications of light-emitting copper nanoclusters. *Nanoscale Horiz.* **2017**, *2*, 135-146.
- Das, N. K.; Ghosh, S.; Priya, A.; Datta, S.; Mukherjee, S., Luminescent Copper Nanoclusters as a Specific Cell-Imaging Probe and a Selective Metal Ion Sensor. *J. Phys. Chem. C* **2015**, *119*, 24657-24664.
- Lin, Y.-J.; Chen, P.-C.; Yuan, Z.; Ma, J.-Y.; Chang, H.-T., The isomeric effect of mercaptobenzoic acids on the preparation and fluorescence properties of copper nanoclusters. *Chem. Commun.* **2015**, *51*, 11983-11986.
- Ai, L.; Jiang, W.; Liu, Z.; Liu, J.; Gao, Y.; Zou, H.; Wu, Z.; Wang, Z.; Liu, Y.; Zhang, H.; Yang, B., Engineering a red emission of copper nanocluster self-assembly architectures by employing aromatic thiols as capping ligands. *Nanoscale* **2017**, *9*, 12618-12627.
- Wei, W.; Lu, Y.; Chen, W.; Chen, S., One-Pot Synthesis, Photoluminescence, and Electrocatalytic Properties of Subnanometer-Sized Copper Clusters. *J. Am. Chem. Soc.* **2011**, *133*, 2060-2063.
- Nguyen, T.-A. D.; Cook, A. W.; Wu, G.; Hayton, T. W., Subnanometer-Sized Copper Clusters: A Critical Re-evaluation of the Synthesis and Characterization of $\text{Cu}_8(\text{MPP})_4$ ($\text{HMPP} = 2\text{-Mercapto-5-}n\text{-propylpyrimidine}$). *Inorg. Chem.* **2017**, *56*, 8390-8396.
- Wu, Z.; Liu, J.; Gao, Y.; Liu, H.; Li, T.; Zou, H.; Wang, Z.; Zhang, K.; Wang, Y.; Zhang, H.; Yang, B., Assembly-Induced Enhancement of Cu Nanoclusters Luminescence with Mechanochromic Property. *J. Am. Chem. Soc.* **2015**, *137*, 12906-12913.
- Wu, Z.; Liu, H.; Li, T.; Liu, J.; Yin, J.; Mohammed, O. F.; Bakr, O. M.; Liu, Y.; Yang, B.; Zhang, H., Contribution of Metal Defects in the Assembly Induced Emission of Cu Nanoclusters. *J. Am. Chem. Soc.* **2017**, *139*, 4318-4321.
- Liu, Y.; Yao, D.; Zhang, H., Self-Assembly Driven Aggregation-Induced Emission of Copper Nanoclusters: A Novel Technology for Lighting. *ACS Appl. Mater. Interfaces* **2018**, *10*, 12071-12080.
- Wang, Z.; Chen, B.; Rogach, A. L., Synthesis, optical properties and applications of light-emitting copper nanoclusters. *Nanoscale Horiz.* **2017**, *2*, 135-146.
- Nguyen, T.-A. D.; Jones, Z. R.; Goldsmith, B. R.; Buratto, W. R.; Wu, G.; Scott, S. L.; Hayton, T. W., A Cu_{25} Nanocluster with Partial Cu(0) Character. *J. Am. Chem. Soc.* **2015**, *137*, 13319-13324.
- Cook, A. W.; Nguyen, T.-A. D.; Buratto, W. R.; Wu, G.; Hayton, T. W., Synthesis, Characterization, and Reactivity of the Group 11 Hydrido Clusters $[\text{Ag}_6\text{H}_4(\text{dppm})_4(\text{OAc})_2]$ and $[\text{Cu}_3\text{H}(\text{dppm})_3(\text{OAc})_2]$. *Inorg. Chem.* **2016**, *55*, 12435-12440.
- Nguyen, T.-A. D.; Jones, Z. R.; Leto, D. F.; Wu, G.; Scott, S. L.; Hayton, T. W., Ligand-Exchange-Induced Growth of an Atomically

Precise Cu₂₉ Nanocluster from a Smaller Cluster. *Chem. Mater.* **2016**, 28, 8385-8390.

27. Cook, A. W.; Jones, Z. R.; Wu, G.; Scott, S. L.; Hayton, T. W., An Organometallic Cu₂₀ Nanocluster: Synthesis, Characterization, Immobilization on Silica, and "Click" Chemistry. *J. Am. Chem. Soc.* **2018**, 140, 394-400.

28. Chakrahari, K. K.; Liao, J.-H.; Kahlal, S.; Liu, Y.-C.; Chiang, M.-H.; Saillard, J.-Y.; Liu, C. W., [Cu₁₃{S₂CN^oBu₂}₆(acetylide)]⁺: A Two-Electron Superatom. *Angew. Chem., Int. Ed.* **2016**, 55, 14704-14708.

29. WeBing, J.; Ganesamoorthy, C.; Kahlal, S.; Marchal, R.; Gemel, C.; Cador, O.; Da Silva, A. C. H.; Da Silva, J. L. F.; Saillard, J.-Y.; Fischer, R. A., The Mackay-Type Cluster [Cu₄₃Al₁₂](Cp*)₁₂: Open-Shell 67-Electron Superatom with Emerging Metal-Like Electronic Structure. *Angew. Chem., Int. Ed.* **2018**, 57, 14630-14634.

30. Yuan, P.; Chen, R.; Zhang, X.; Chen, F.; Yan, J.; Sun, C.; Ou, D.; Peng, J.; Lin, S.; Tang, Z.; Teo, B. K. K.; Zheng, L.-S.; Zheng, N., Ether-soluble Cu₅₃ Nanoclusters as an Effective Precursor of High-quality CuI Films for Optoelectronic Applications. *Angew. Chem., Int. Ed.* **2019**, 58, 835-839.

31. This change was made, in part, because we performed our syntheses in an inert atmosphere glove box.

32. Hasan, M.; Bethell, D.; Brust, M., The Fate of Sulfur-Bound Hydrogen on Formation of Self-Assembled Thiol Monolayers on Gold: ¹H NMR Spectroscopic Evidence from Solutions of Gold Clusters. *J. Am. Chem. Soc.* **2002**, 124, 1132-1133.

33. Biesinger, M. C., Advanced analysis of copper X-ray photoelectron spectra. *Surf. Interface Anal.* **2017**, 49, 1325-1334.

34. C. D. Wagner, A. V. N., A. Kraut-Vass, J. W. Allison, C. J. Powell, J. R. Rumble Jr., *NIST Standard Reference Database 20, Version 3.4 (web version)* (<http://srdata.nist.gov/xps/>) **2003**.

35. The redox potentials of organothiols are essentially independent of the substituent. See: Whitesides *et al.* *J. Org. Chem.* **1993**, 58, 642-647.

36. Janssen, M. D.; Spek, A. L.; Grove, D. M.; van Koten, G., A Mixed (Arenethiolato)copper(I)/Copper Bromide Aggregate: X-ray Structure of Octanuclear [Cu₈{SC₆H₃(CH₂NMe₂)₂-2,6,3}Br₅]. *Inorg. Chem.* **1996**, 35, 4078-4081.

37. Parish, R. V.; Salehi, Z.; Pritchard, R. G., Five-Coordinate Sulfur in a Polymeric Copper(I) Thiolate Complex. *Angew. Chem., Int. Ed. Engl.* **1997**, 36, 251-253.

38. G. Prichard, R.; V. Parish, R.; Salehi, Z., Self-assembling copper(I) clusters involving electron-deficient, quadruply bridging thiolate ligands. *J. Chem. Soc., Dalton Trans.* **1999**, 243-250.

39. Li, D.; Wu, T.; Zhou, X.-P.; Zhou, R.; Huang, X.-C., Twelve-Connected Net with Face-Centered Cubic Topology: A Coordination Polymer Based on [Cu₁₂(μ₄-SCH₃)₆]¹⁶⁺ Clusters and CN⁻ Linkers. *Angew. Chem., Int. Ed.* **2005**, 44, 4175-4178.

40. Qian, H.; Zhu, Y.; Jin, R., Atomically precise gold nanocrystal molecules with surface plasmon resonance. *Proc. Natl. Acad. Sci. U.S.A.* **2012**, 109, 696-700.

41. Scholz, S.; Lerner, H.-W.; Bolte, M., Chlorotripyridinecopper(I). *Acta Cryst. E.* **2002**, 58, m72-m73.

42. Brookhart, M.; Grant, B.; Volpe, A. F., [(3,5-(CF₃)₂C₆H₃)₄B]⁻ [H(OEt₂)₂]⁺: A Convenient Reagent for Generation and Stabilization of Cationic, Highly Electrophilic Organometallic Complexes. *Organometallics* **1992**, 11, 3920-3922.

43. Jutzi, P.; Müller, C.; Stämmler, A.; Stämmler, H.-G., Synthesis, Crystal Structure, and Application of the Oxonium Acid [H(OEt₂)₂]⁺[B(C₆F₅)₄]. *Organometallics* **2000**, 19, 1442-1444.

44. Pietikäinen, J.; Maaninen, A.; Laitinen, R. S.; Oilunkaniemi, R.; Valkonen, J., Halogenation of tellurium by SO₂Cl₂. Formation and crystal structures of (H₃O)[Te₃Cl₃]₂·1/2SO₂, [(C₄H₈O)₂H][TeCl₅](C₄H₈O), [(Me₂SO)₂H]₂[TeCl₆], and [Ni(NCCCH₃)₆][Te₂Cl₁₀]. *Polyhedron* **2002**, 21, 1089-1095.

45. Krossing, I.; Reisinger, A., Perfluorinated Alkoxyaluminate Salts of Cationic Brønsted Acids: Synthesis, Structure, and Characterization of [H(OEt₂)₂][Al{OC(CF₃)₃}]₄ and [H(THF)₂][Al{OC(CF₃)₃}]₄. *Eur. J. Inorg. Chem.* **2005**, 2005, 1979-1989.

46. Schnaars, D. D.; Wu, G.; Hayton, T. W., Reactivity of UI₄(OEt₂)₂ with phenols: probing the chemistry of the U-I bond. *Dalton Trans.* **2009**, 3681-3687.

47. Nachtigall, O.; Pataki, A.; Molski, M.; Lentz, D.; Spandl, J., Solvates of Manganese Trichloride Revisited - Synthesis, Isolation, and Crystal Structure of MnCl₃(THF)₃. *Z. Anorg. Allg. Chem.* **2015**, 641, 1164-1168.

48. Stasko, D.; Hoffmann, S. P.; Kim, K.-C.; Fackler, N. L. P.; Larsen, A. S.; Drovetskaya, T.; Tham, F. S.; Reed, C. A.; Rickard, C. E. F.; Boyd, P. D. W.; Stoyanov, E. S., Molecular Structure of the Solvated Proton in Isolated Salts. Short, Strong, Low Barrier (SSLB) H-bonds. *J. Am. Chem. Soc.* **2002**, 124, 13869-13876.

49. Hazin, K.; Serin, S. C.; Patrick, B. O.; Ezhova, M. B.; Gates, D. P., [HL₂][P(1,2-O₂C₆Cl₄)₃] (L = THF, DMF): Brønsted acid initiators for the polymerization of n-butyl vinyl ether and p-methoxystyrene. *Dalton Trans.* **2017**, 46, 5901-5910.

50. Ankudinov, A. L.; Ravel, B.; Rehr, J. J.; Conradson, S. D., Real-space multiple-scattering calculation and interpretation of x-ray-absorption near-edge structure. *Phys. Rev. B* **1998**, 58, 7565-7576.

51. Nguyen, T.-A. D.; Goldsmith, B. R.; Zaman, H. T.; Wu, G.; Peters, B.; Hayton, T. W., Synthesis and Characterization of a Cu₁₄ Hydride Cluster Supported by Neutral Donor Ligands. *Chem. – Eur. J.* **2015**, 21, 5341-5344.

52. Dehnen, S.; Fenske, D.; Deveson, A. C., [Cu₁₂S₆(P^oPr₃)₈] and [Cu₂₀S₁₀(P^oBu₁Bu₂)₈]: Two sulfur bridged copper clusters with Cu-s cluster cores of known compositions but new structures. *J. Cluster Sci.* **1996**, 7, 351-369.

53. Yang, X.-X.; Issac, I.; Lebedkin, S.; Kühn, M.; Weigend, F.; Fenske, D.; Fuhr, O.; Eichhöfer, A., Red-luminescent biphosphine stabilized 'Cu₁₂S₆' cluster molecules. *Chem. Commun.* **2014**, 50, 11043-11045.

54. Eichhöfer, A.; Buth, G.; Lebedkin, S.; Kühn, M.; Weigend, F., Luminescence in Phosphine-Stabilized Copper Chalcogenide Cluster Molecules—A Comparative Study. *Inorg. Chem.* **2015**, 54, 9413-9422.

55. Salehi, Z.; V. Parish, R.; G. Pritchard, R., A polymeric cationic copper(I) complex involving a quadruply bridging, zwitterionic thiolate ligand: {[Cu₈Cl₆(SCH₂CH₂NH₃)₆][Cl₂]}_n. *J. Chem. Soc., Dalton Trans.* **1997**, 4241-4246.

56. Block, E.; Kang, H.; Ofori-Okai, G.; Zubieta, J., The crystal and molecular structure of a tetranuclear copper thiolate cluster, [Cu{SC₆H₃-2,6-(SiMe₃)₂}]₄. *Inorg. Chim. Acta* **1990**, 167, 147-148.

57. Schröter-Schmid, I. S., J., Synthese und Struktur von Thiolatokomplexen des einwertigen Kupfers: Tetrameres und Octameres [CuSC₆H₂(ⁱPr)₃]₄. *Z. Naturforsch.* **1990**, 45b, 1537 - 1542.

58. Dance, I. G.; Calabrese, J. C., The crystal and molecular structure of the hexa-(μ₂-benzenethiolato)tetracuprate(I) dianion. *Inorg. Chim. Acta* **1976**, 19, L41-L42.

59. Coucouvanis, D.; Murphy, C. N.; Kanodia, S. K., Metal-mercaptide chemistry. The synthesis and structural characterization of the [Cu(SC₆H₃)₃]²⁻ anion. A rational synthesis and the structure of the [Cu₄(SC₆H₃)₆]²⁻ cluster. *Inorg. Chem.* **1980**, 19, 2993-2998.

60. Dance, I. G.; Bowmaker, G. A.; Clark, G. R.; Seadon, J. K., The formation and crystal and molecular structures of hexa(μ-organothiolato)tetracuprate(I) cage dianions: bis-(tetramethylammonium)hexa-(μ-methanethiolato)tetracuprate(I) and two polymorphs of bis(tetramethylammonium)hexa-(μ-benzenethiolato)-tetracuprate(I). *Polyhedron* **1983**, 2, 1031-1043.

61. Baumgartner, M.; Schmalte, H.; Dubler, E., Synthesis, characterization and crystal structure of copper(I) thiolates: [(C₆H₅)₄P⁺][Cu₄(C₂H₅S⁻)₆]·0.5C₂H₆O₂ and [(C₆H₅)₄P⁺][Cu₇(C₂H₅S⁻)₈]. *Polyhedron* **1990**, 9, 1155-1164.

62. Baumgartner, M.; Schmalte, H.; Baerlocher, C., Synthesis, Characterization, and Crystal Structure of Three Homoleptic Copper(I) Thiolates: (Cu(CH₃S))_∞, [(C₆H₅)₄P⁺][Cu₅(CH₃S⁻)₇]·C₂H₆O₂, and [(C₃H₇)₄N⁺][Cu₄(CH₃S⁻)₆]·CH₄O. *J. Solid State Chem.* **1993**, 107, 63-75.

63. Fujisawa, K.; Imai, S.; Suzuki, S.; Moro-oka, Y.; Miyashita, Y.; Yamada, Y.; Okamoto, K.-i., M-S vibrational study in three-coordinate thiolate compounds (NEt₄)₂[M(SC₆H₄-p-X)₃] and (NEt₄)₂[M₄(μ-SC₆H₄-p-Cl)₆]: M=Cu(I) and Ag(I), X=Cl and Br. *J. Inorg. Biochem.* **2000**, 82, 229-238.

64. Zeevi, S.; Tshuva, E. Y., Synthesis and X-ray Characterization of Mono- and Polynuclear Thiolatocopper(I) Complexes: The Effect of Steric Bulk on Coordination Number and Nuclearity. *Eur. J. Inorg. Chem.* **2007**, 2007, 5369-5376.
65. Kohner-Kerten, A.; Tshuva, E. Y., Preparation and X-ray characterization of two-coordinate Cu(I) complex of aliphatic thiolato ligand: Effect of steric bulk on coordination features. *J. Organomet. Chem.* **2008**, 693, 2065-2068.
66. Dance, I. G., Formation and X-ray structure of the hexa(*t*-butylthiolato)pentacuprate(I) monoanion. *J. Chem. Soc., Chem. Commun.* **1976**, 68-69.
67. Bowmaker, G. A.; Clark, G. R.; Seadon, J. K.; Dance, I. G., The formation and structural chemistry of the hexa(μ -*t*-butylthiolato)pentacuprate(I) cage anion with triethylammonium and tetraethylammonium cations. *Polyhedron* **1984**, 3, 535-544.
68. Fujisawa, K.; Imai, S.; Kitajima, N.; Moro-oka, Y., Preparation, Spectroscopic Characterization, and Molecular Structure of Copper(I) Aliphatic Thiolate Complexes. *Inorg. Chem.* **1998**, 37, 168-169.
69. Dance, I. G., The hepta(μ -benzenethiolato)pentacuprate(I) dianion; X-ray crystal and molecular structure. *J. Chem. Soc., Chem. Commun.* **1976**, 103b-104.
70. Dance, I., The Hepta(μ -benzenethiolato)pentametallate(I) dianions of copper and silver: Formation and crystal structures. *Aust. J. Chem.* **1978**, 31, 2195-2206.
71. Ferrara, S. J.; Mague, J. T.; Donahue, J. P., Synthesis and Structures of Cuprous Triptycylthiolate Complexes. *Inorg. Chem.* **2012**, 51, 6567-6576.
72. Yang, Q.; Tang, K.; Liao, H.; Han, Y.; Chen, Z.; Tang, Y., Synthesis and X-ray crystal structure of $[\text{Cu}(\text{SC}_6\text{H}_2\text{Pr}_3)]_8$. *J. Chem. Soc., Chem. Commun.* **1987**, 1076-1077.
73. Block, E.; Gernon, M.; Kang, H.; Ofori-Okai, G.; Zubieta, J., Coordination chemistry of sterically hindered thiolate ligands. Preparation and structural characterization of the oligomeric homoleptic complexes $[\text{Cu}(\text{S}_6\text{H}_4\text{-}o\text{-SiMe}_3)]_{12}$ and $[\{\text{Ag}(\text{SC}_6\text{H}_4\text{-}o\text{-SiMe}_3)\}_4]_2$ and a comparison to the structure of the cadmium mononuclear species $(\text{Et}_4\text{N})_2[\text{Cd}(\text{SC}_6\text{H}_4\text{-}o\text{-SiMe}_3)_4]$. *Inorg. Chem.* **1989**, 28, 1263-1271.
74. Blower, P. J.; Dilworth, J. R., Thiolato-complexes of the transition metals. *Coord. Chem. Rev.* **1987**, 76, 121-185.
75. Vortisch, V.; Kroneck, P.; Hemmerich, P., Model studies on the coordination of copper in enzymes. IV. Structure and stability of cuprous complexes with sulfur-containing ligands. *J. Am. Chem. Soc.* **1976**, 98, 2821-2826.
76. Tang, K.; Aslam, M.; Block, E.; Nicholson, T.; Zubieta, J., Steric control of aggregation in neutral silver(I) thiolates, $[\text{AgSR}]_n$. Crystal and molecular structures of $[\text{AgSCH}(\text{SiMe}_3)_2]_8$, a discrete molecular bicyclic of weakly interacting $[\text{AgSCH}(\text{SiMe}_3)_2]_4$ units, and of $[\text{AgSC}(\text{SiPhMe}_2)_3]_3$ and $[\text{AgSC}(\text{SiMe}_3)_3]_4$, discrete molecular monocycles containing linearly coordinated silver(I) and doubly bridging mercapto sulfur donors from novel sterically hindered thiolate ligands. A comparison with the nonmolecular structure of $[\text{Ag}_4\{\text{SCH}_2(\text{SiMe}_3)\}_3]_4^{1-}$. *Inorg. Chem.* **1987**, 26, 1488-1497.
77. Dance, I. G.; Fisher, K. J.; Banda, R. M. H.; Scudder, M. L., Layered structure of crystalline compounds silver thiolates (AgSR). *Inorg. Chem.* **1991**, 30, 183-187.
78. Bratsch, S. G., Standard Electrode Potentials and Temperature Coefficients in Water at 298.15 K. *J. Phys. Chem. Ref. Data* **1989**, 18, 1-21.
79. Dance, I. G., Crystallization and structure of bis(tetramethylammonium) octakis(benzenethiolato)hexaargentate(I), extending the series of cages $[\text{M}_4(\text{SPh})_6]^{2-}$, $[\text{M}_5(\text{SPh})_7]^{2-}$, $[\text{M}_6(\text{SPh})_8]^{2-}$, and $[\text{M}_{12}(\text{SPh})_{16}]^{4-}$. *Inorg. Chem.* **1981**, 20, 1487-1492.
80. Battisti, A.; Bellina, O.; Diversi, P.; Losi, S.; Marchetti, F.; Zanello, P., Preparation, Structure and Reactivity of Polynuclear Gold(I) Phosphanyl Alkanethiolates. *Eur. J. Inorg. Chem.* **2007**, 2007, 865-875.
81. Al-Sa'ady, A. K. H.; Moss, K.; McAuliffe, C. A.; Parish, R. V., Mössbauer and nuclear magnetic resonance spectroscopic studies on 'Myocrisin', 'Solganol', 'Auranofin', and related gold(I) thiolates. *J. Chem. Soc., Dalton Trans.* **1984**, 1609-1616.
82. Kyle, K. R.; Palke, W. E.; Ford, P. C., The photoluminescence properties of the copper(I) clusters $\text{Cu}_4\text{L}_4\text{A}_4$ (A = aromatic amine) in solution. *Coord. Chem. Rev.* **1990**, 97, 35-46.
83. Knotter, D. M.; Blasse, G.; Van Vliet, J. P. M.; Van Koten, G., Luminescence of copper(I) arenethiolates and its relation to copper(I) luminescence in other complexes. *Inorg. Chem.* **1992**, 31, 2196-2201.
84. Ford, P. C.; Vogler, A., Photochemical and Photophysical Properties of Tetranuclear and Hexanuclear Clusters of Metals with d^{10} and s^2 Electronic Configurations. *Acc. Chem. Res.* **1993**, 26, 220-226.
85. Ford, P. C.; Cariati, E.; Bourassa, J., Photoluminescence Properties of Multinuclear Copper(I) Compounds. *Chem. Rev.* **1999**, 99, 3625-3648.
86. Wang, X.-L.; Qin, C.; Wang, E.-B.; Su, Z.-M.; Li, Y.-G.; Xu, L., Self-Assembly of Nanometer-Scale $[\text{Cu}_{24}\text{L}_{10}\text{L}_{12}]^{14+}$ Cages and Ball-Shaped Keggin Clusters into a (4,12)-Connected 3D Framework with Photoluminescent and Electrochemical Properties. *Angew. Chem., Int. Ed.* **2006**, 45, 7411-7414.
87. Maiti, B. K.; Pal, K.; Sarkar, S., Flexible CuI-Thiolate Clusters with Relevance to Metallothioneins. *Eur. J. Inorg. Chem.* **2007**, 2007, 5548-5555.
88. Li, Z.; Li, X.; Lin, P.; Du, S., Self-assembly of 1D Coordination Polymers Containing Copper(I) *tert*-butylthiolato Clusters: Structural Characterization and Properties. *J. Cluster Sci.* **2008**, 19, 357-366.
89. Troyano, J.; Perles, J.; Amo-Ochoa, P.; Martínez, J. I.; Concepción Gimeno, M.; Fernández-Moreira, V.; Zamora, F.; Delgado, S., Luminescent Thermochromism of 2D Coordination Polymers Based on Copper(I) Halides with 4-Hydroxythiophenol. *Chem. – Eur. J.* **2016**, 22, 18027-18035.

Fluorescent, “Atlas-sphere”-type copper(I)-containing nanoclusters were prepared by reaction of CuCl_2 with a variety of thiols. In contrast to past reports, we find no evidence for reduction to $\text{Cu}(0)$ under the reaction conditions.