Lawrence Berkeley National Laboratory

Recent Work

Title

THERMAL EXPANSION COEFFICIENTS OF THE ANHYDROUS TRICHLORIDES OF CERIUM, PLUTONIUM AND AMERICIUM

Permalink

<https://escholarship.org/uc/item/8n3118d2>

Author

Fuger, Jena.

Publication Date

1965-08-01

University of California
Ernest O. Lawrence
Radiation Laboratory

**THERMAL EXPANSION COEFFICIENTS OF THE
ANHYDROUS TRICHLORIDES OF CERIUM
PLUTONIUM AND AMERICIUM**

TWO-WEEK LOAN COPY

**This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5545**

Berkeley, California

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

UNIVERSITY OF CALIFORNIA

Lawrence Radiation Laboratory
Berkeley, California

AEC Contract No. W-7405-eng-48

THERMAL EXPANSION COEFFICIENTS OF THE
ANHYDROUS TRICHLORIDES OF CERIUM,
PLUTONIUM AND AMERICIUM

Jean Fuger

August 1965

THERMAL EXPANSION COEFFICIENTS OF THE
ANHYDROUS TRICHLORIDES OF CERIUM,
PLUTONIUM AND AMERICIUM

Jean Fuger^{*}

Lawrence Radiation Laboratory
University of California
Berkeley, California

August 1965

ABSTRACT

As shown by Zachariasen⁽¹⁾ anhydrous trichlorides of the lighter lanthanide elements and of the first members of the actinides series exhibit a hexagonal structure, space group $C6_3/m - C_{6h}^2$, with two molecules per unit cell. We report here the thermal expansion coefficients of the trichlorides of cerium, plutonium and americium calculated from powder diffraction patterns, between room temperature and a temperature close to the melting point of the compounds.

^{*}Present address: Laboratoire de Chimie Nucléaire, Université de Liège, Belgium.

EXPERIMENTAL

Sample preparation

PuCl_3 was prepared from high purity* Pu^{239} metal in two steps:

- a) formation of the hydride by reaction of dry hydrogen on the metal at 400°C ;
- b) hydrochlorination of the hydride at 500°C .

CeCl_3 and AmCl_3 (Am^{241}) were prepared by hydrochlorination of the oxide at 500°C . The oxides were obtained from high purity* solutions. Preparations were carried out in quartz capillaries connected to a vacuum line. After evacuation ($\leq 10^{-6}$ mm Hg), the samples were sublimed to the tips of the capillaries which were then sealed off. A sharp temperature gradient was required to obtain the sublimate in a narrow band. X ray samples from a few micrograms to a few tens of micrograms were used. None of them showed extraneous diffraction lines.

* By the copper spark method the only impurities detected, expressed in micrograms per 50 micrograms of the element studied were, for plutonium: Ca $\leq$ 0.01, Mg, 0.01; for americium: Ca, 0.01; Mg, 0.01; for cerium: Mg, 0.02. The limits of detection of various elements by this method are indicated elsewhere.⁽²⁾ In the case of cerium analysis limits of detection for Al and Ca were 0.1 and 0.05 micrograms respectively.

X ray equipment

The present study has been initiated with a standard Norelco X ray unit type No. 12045 (35 kV-20 mA) and continued with a Jarrell-Ash microfocus X ray unit (45 kV-3.5 mA). Copper K α radiation was used.

The high temperature 9 cm diameter camera has been described by McWhan, Cunningham, and Wallmann.⁽³⁾ The thermocouple used to measure the sample temperature was calibrated against the melting point of various standard substances which were sealed in quartz capillaries of dimensions similar to those used in the study of the trichlorides. The calibration was checked several times during its period of use. Observation of the melting point was made by means of a microscope through the collimator and catcher holes. Temperature accuracy is believed to be $\pm 2^\circ\text{C}$ at 350°C , $\pm 2^\circ\text{C}$ at 600°C and $\pm 5^\circ\text{C}$ at 800°C . Lattice parameters for CeO_2 at various temperatures have been reported by Braver and Gingerich.⁽⁴⁾ From their data we calculate

$$\frac{\text{lattice param at } t' - \text{lattice param at } t}{(t' - t) \times \text{lattice param at } 20^\circ\text{C}} = 1.17 \times 10^{-6} \text{ in the range } \sim 25-900^\circ\text{C}.$$

We also measured the lattice parameter of CeO_2 as a function of temperature from room temperature to 800°C , and find the thermal expansion coefficient to be $(1.15 \pm 0.05) \times 10^{-6}$. Recording of the thermocouple output during the exposures insures a check on the temperature stability.

Ilford Industrial G films were used for the X ray measurements.

Exposure time ranged between 8 and 15 hours.

Lattice parameter calculations

To minimize random errors line position on the films were read two or three times. After indexing the various reflections, lattice parameters were calculated by the least squares method using a suitable correction function to minimize errors due to excentricity of the sample or divergence and absorption of the X ray beam. We have used a program written by Mueller and Heaton⁽⁵⁾ for an IBM 704 computer. The correction function chosen is $\sin^2 2\theta \left(\frac{1}{\sin \theta} + \frac{1}{\theta} \right)$. Unit weight has been given to each reflection. However when one observed line could be attributed to several planes, fractional weights were given proportionally to their relative intensity. To insure the proper indexing a program written by Smith⁽⁶⁾ for calculating the intensity of the various reflections, has been used.

Diffraction lines up to at least 75° (80° for CeCl_3) were usable even for high temperature results. The least squares fit of the various reflections leads to an error in the calculated value of the lattice parameter which is smaller than the error arising from the uncertainty in the effective camera radius ($\sim 0.02\%$). In general the relative error in c is larger than in a owing to a smaller number of diffracting planes having high l Miller indices. We estimate the uncertainty in the absolute value of the lattice parameters to be about $\pm 0.004 \text{ \AA}$.

Results

Table I summarizes the lattice parameters of the trichlorides as a function of temperature. Room temperature data for CeCl_3 and PuCl_3 agree reasonably well with literature results. Our value for the c axis of AmCl_3 differs notably from Zachariasen's results⁽¹⁾ but it is in reasonable agreement with recent data of Wallmann and Cunningham.⁽⁷⁾ Unresolved differences exist between the lattice parameters for AmCl_3 reported here and those found recently by Asprey, Keenan and Kruse,⁽⁸⁾ but are not important in the calculation of the expansion coefficients.

Table II summarizes the various room temperature results. Room temperature measurements of the samples after their thermal treatment showed no change in lattice parameters, within the experimental error.

Plots of the lattice parameters versus temperature are linear within our accuracy. Table III shows the thermal expansion coefficients calculated for 20°C. The anisotropy of the expansions is especially large with the actinide compounds. Experiments with other isomorphous halides should be of interest.

ACKNOWLEDGMENTS

The author wishes to thank Professor B. B. Cunningham and the late Dr. J. C. Wallmann of the Lawrence Radiation Laboratory and also Dr. L. B. Asprey and Dr. F. K. Keenan of Los Alamos Scientific Laboratory for fruitful discussions. Dr. J. C. Wallmann is also thanked for an AmCl_3 sample. Thanks are due to Mr. G. V. Shalimoff for performing spectrographic analyses and to Mrs. G. Bolz for providing assistance in handling radioactive materials.

The experimental part of this work was performed under the auspices of the U. S. Atomic Energy Commission at the Lawrence Radiation Laboratory of the University of California, Berkeley. Calculations have been concluded at the Centre de Calcul, University of Liege, Belgium.

REFERENCES

1. W. H. Zachariasen, Acta Cryst. 1, 265 (1948).
2. J. Fuger and B. B. Cunningham, J. Inorg. Nucl. Chem. 25, 1423 (1963).
3. D. B. McWhan, B. B. Cunningham and J. C. Wallmann, J. Inorg. Nucl. Chem. 24, 1025 (1962).
4. G. Braver and K. A. Gingerich, J. Inorg. Nucl. Chem. 16, 90 (1960).
5. M. H. Mueller and L. Heaton, Report ANL 6176 (1961); M. H. Mueller, L. Heaton and K. T. Miller, Acta Cryst. 13, 828 (1960).
6. D. K. Smith, Report UCRL-7196 (1963).
7. J. C. Wallmann and B. B. Cunningham, unpublished results.
8. L. B. Asprey, T. Keenan and H. Kruse, unpublished results.
9. D. H. Templeton and C. H. Dauben, J. Am. Chem. Soc. 76, 5237 (1954).

Table I. Lattice parameters of the trichlorides.

	$t^{\circ}\text{C}$	a ($\text{\AA}$, ± 0.004)	c ($\text{\AA}$, ± 0.004)
CeCl_3	23.5 ± 0.5	7.445	4.316
	110 ± 1.5	7.456	4.322
	230 ± 2	7.473	4.330
	307.5 ± 2	7.486	4.336
	424 ± 3	7.505	4.345
	519 ± 3	7.518	4.353
	723 ± 4	7.549	4.367
PuCl_3	23.5 ± 0.5	7.392	4.244
	124 ± 1.5	7.410	4.253
	240 ± 2	7.426	4.258
	376 ± 3	7.451	4.265
	485 ± 3	7.470	4.274
	590 ± 3	7.486	4.277
	700 ± 4	7.509	4.286
AmCl_3	23.5 ± 0.5	7.384	4.225
	116.5 ± 1.5	7.397	4.231
	228 ± 2	7.415	4.235
	312 ± 2	7.429	4.242
	425 ± 2	7.452	4.250
	516.5 ± 3	7.469	4.256
	607.5 ± 3	7.483	4.262

Table II. Comparison of various data for the room temperature lattice parameters.

	a (Å)	c (Å)	Authors
CeCl ₃	7.451 ± 0.004	4.313 ± 0.004	Zachariasen ⁽¹⁾
	7.450 ± 0.004	4.315 ± 0.002	Templeton and Dauben ⁽⁸⁾
	7.445 ± 0.004	4.316 ± 0.004	this work
PuCl ₃	7.395 ± 0.001	4.247 ± 0.001	Zachariasen ⁽¹⁾
			Wallmann and Cunningham ⁽⁷⁾
	7.392 ± 0.004	4.244 ± 0.004	this work
AmCl ₃	7.385 ± 0.01	4.249 ± 0.01	Zachariasen ⁽¹⁾
			Wallmann and Cunningham ⁽⁷⁾
	7.384 ± 0.004	4.225 ± 0.004	this work

Table III. Coefficients of thermal expansion (20°C) in °C⁻¹.

	α_a	α_c
CeCl ₃	2.13 ± 0.1 × 10 ⁻⁵	1.74 ± 0.1 × 10 ⁻⁵
PuCl ₃	2.40 ± 0.1 × 10 ⁻⁵	1.37 ± 0.1 × 10 ⁻⁵
AmCl ₃	2.40 ± 0.1 × 10 ⁻⁵	1.38 ± 0.1 × 10 ⁻⁵

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.